



Standard Specification for Electric-Resistance-Welded Carbon Steel Heat-Exchanger and Condenser Tubes¹

This standard is issued under the fixed designation A 214/A 214M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification² covers minimum-wall-thickness, electric-resistance-welded, carbon steel tubes to be used for heat exchangers, condensers, and similar heat-transfer apparatus.

1.2 The tubing sizes usually furnished to this specification are to 3 in. [76.2 mm] in outside diameter, inclusive. Tubing having other dimensions may be furnished, provided such tubes comply with all other requirements of this specification.

1.3 Mechanical property requirements do not apply to tubing smaller than 1/8 in. [3.2 mm] in inside diameter or 0.015 in. [0.4 mm] in thickness.

1.4 The purchaser shall specify in the order the outside diameter and minimum wall thickness. The inside diameter shall not be specified.

1.5 The values stated in either inch-pound units or SI units are to be regarded separately as standard. Within the text, the SI units are shown in brackets. The values stated in each system are not exact equivalents; therefore, each system must be used independently of the other. Combining values from the two systems may result in nonconformance with the specification. The inch-pound units shall apply unless the “M” designation of this specification is specified in the order.

2. Referenced Documents

2.1 ASTM Standards:

A 450/A 450M Specification for General Requirements for Carbon, Ferritic Alloy, and Austenitic Alloy Steel Tubes³

3. Ordering Information

3.1 Orders for material under this specification should include the following, as required, to describe the desired material adequately:

3.1.1 Quantity (feet, metres, or number of lengths),

- 3.1.2 Name of material (electric-resistance-welded tubes),
- 3.1.3 Size (outside diameter and minimum wall thickness),
- 3.1.4 Length (specific or random),
- 3.1.5 Optional requirements (Section 8 and 10.5),
- 3.1.6 Test report required (see Certification Section of Specification A 450/A 450M),
- 3.1.7 Specification designation, and
- 3.1.8 Special requirements.

4. General Requirements

4.1 Material furnished under this specification shall conform to the applicable requirements of the current edition of Specification A 450/A 450M, unless otherwise provided herein.

5. Manufacture

5.1 Tubes shall be made by electric-resistance welding.

6. Heat Treatment

6.1 After welding, all tubes shall be heat treated at a temperature of 1650°F [900°C] or higher and followed by cooling in air or in the cooling chamber of a controlled atmosphere furnace. Cold drawn tubes shall be heat treated after the final cold-draw pass at a temperature of 1200°F [650°C] or higher.

7. Chemical Composition

7.1 The steel shall conform to the following requirements as to chemical composition:

Carbon, max %	0.18
Manganese, %	0.27 to 0.63
Phosphorus, max, %	0.035
Sulfur, max, %	0.035

7.2 Supplying an alloy grade of steel that specifically requires the addition of any element other than those listed in 8.1 is not permitted.

8. Product Analysis

8.1 When requested on the purchase order, a product analysis shall be made by the supplier from one tube per 250 pieces; or when tubes are identified by heat, one tube per heat shall be

¹ This specification is under the jurisdiction of ASTM Committee A01 on Steel, Stainless Steel, and Related Alloys, and is the direct responsibility of Subcommittee A01.09 on Carbon Steel Tubular Products.

Current edition approved Oct. 10, 1996. Published November 1997. Originally published as A 214–39 T. Last previous edition A 214/A 214M – 90a.

² For ASME Boiler and Pressure Vessel Code applications see related Specification SA-214 in Section II of that Code.

³ *Annual Book of ASTM Standards*, Vol 01.01.

analyzed. The chemical composition thus determined shall conform to the requirements specified.

8.2 If the original test for product analysis fails, retests of two additional lengths of flat-rolled stock, or tubes shall be made. Both retests, for the elements in question, shall meet the requirements of the specification; otherwise all remaining material in the heat or lot (Note 1) shall be rejected or, at the option of the producer, each length of flat-rolled stock or tube may be individually tested for acceptance. Lengths of flat-rolled stock or tubes which do not meet the requirements of the specification shall be rejected.

NOTE 1—A lot consists of 250 tubes.

9. Hardness Requirements

9.1 The tubes shall have a hardness number not exceeding 72 HRB.

10. Mechanical Tests Required

10.1 *Flattening Test*—One flattening test shall be made on specimens from each of two tubes from each lot (Note 1) or fraction thereof.

10.2 *Flange Test*—One flange test shall be made on specimens from each of two tubes from each lot (Note 1) or fraction thereof.

10.3 *Reverse Flattening Test*—One reverse flattening test shall be made on a specimen from each 1500 ft [450 m] of finished tubing.

10.4 *Hardness Test*—Brinell or Rockwell hardness tests shall be made on specimens from two tubes from each lot. The term *lot* applies to all tubes prior to cutting, of the same nominal diameter and wall thickness which are produced from

the same heat of steel. When final heat treatment is in a batch-type furnace, a lot shall include only those tubes of the same size and the same heat which are heat treated in the same furnace charge. When final heat treatment is in a continuous furnace, a lot shall include all tubes of the same size and heat, heat treated in the same furnace at the same temperature, time at heat, and furnace speed.

10.5 *Hydrostatic or Nondestructive Electric Test*—Each tube shall be subjected to either the hydrostatic or the nondestructive electric test. The purchaser may specify which test is to be used.

11. Surface Condition

11.1 The finished tubes shall be free of scale. A slight amount of oxidation shall not be considered as scale.

12. Product Marking

12.1 In addition to the marking prescribed in Specification A 450/A 450M, the letters “ERW” shall be legibly stenciled on each tube, or marked on a tag attached to the bundle or box in which the tubes are shipped.

12.2 The manufacturer’s name or symbol may be placed permanently on each tube by rolling or light stamping before normalizing. If a single stamp is placed on the tube by hand, this mark should not be less than 8 in. [200 mm] from one end of the tube.

12.3 *Bar Coding*—In addition to the requirements in 12.1 and 12.2 bar coding is acceptable as a supplemental identification method. The purchaser may specify in the order a specific bar coding system to be used.

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).