



## Standard Specification for Seamless and Electric-Welded Low-Alloy Steel Tubes<sup>1</sup>

This standard is issued under the fixed designation A 423/A 423M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

*This standard has been approved for use by agencies of the Department of Defense.*

### 1. Scope

1.1 This specification<sup>2</sup> covers minimum-wall-thickness, seamless and electric-resistance welded, low-alloy steel tubes for pressure containing parts such as economizers or other applications where corrosion resistance is important.

1.2 The tubing sizes and thicknesses usually furnished to this specification are  $\frac{1}{2}$  to 5 in. [12.7 to 127 mm] in outside diameter and 0.035 to 0.500 in. [0.9 to 12.7 mm] inclusive, in minimum wall thickness. Tubing having other dimensions may be furnished, provided such tubes comply with all other requirements of this specification.

1.3 Mechanical property requirements do not apply to tubing smaller than  $\frac{1}{4}$  in. [3.2 mm] in inside diameter or 0.015 in. [0.4 mm] in thickness.

1.4 An optional supplementary requirement is provided and, when desired, shall be so stated in the order.

1.5 The values stated in either inch-pound units or SI units are to be regarded separately as standard. Within the text, the SI units are shown in brackets. The values stated in each system are not exact equivalents; therefore, each system must be used independently of the other. Combining values from the two systems may result in nonconformance with the specification. The inch-pound units shall apply unless the “M” designation of this specification is specified in the order.

### 2. Referenced Documents

#### 2.1 ASTM Standards:

E 213 Practice for Ultrasonic Examination of Metal Pipe and Tubing<sup>3</sup>

E 273 Practice for Ultrasonic Examination of Longitudinal Welded Pipe and Tubing<sup>3</sup>

A 450/A 450M Specification for General Requirements for Carbon, Ferritic Alloy, and Austenitic Alloy Steel Tubes<sup>3</sup>

### 3. Ordering Information

3.1 Orders for material under this specification shall include the following, as required, to describe the desired material adequately:

3.1.1 Quantity (feet, metres, or number of lengths),

3.1.2 Name of material (seamless or electric-resistance-welded tubes),

3.1.3 Grade (Table 1),

3.1.4 Manufacture (hot finished or cold finished),

3.1.5 Size (outside diameter and minimum wall thickness),

3.1.6 Length (specific or random),

3.1.7 Optional requirements (hydrostatic or electric test, 13.7),

3.1.8 Test report required (see Certification Section of Specification A 450/A 450M),

3.1.9 Specification designation, and

3.1.10 Special requirements and any supplementary requirements selected.

### 4. Manufacture

4.1 Tubes made by the seamless process may be hot finished or cold finished.

### 5. Heat Treatment

5.1 All tubes shall be normalized or given such heat treatment as may be necessary to conform to the requirements of this specification.

### 6. Chemical Composition

6.1 The steel shall conform to the requirements as to chemical composition prescribed in Table 1.

### 7. Product Analysis

7.1 An analysis of either one billet, one length of flat-rolled stock or one tube shall be made from each heat. The chemical composition thus determined shall conform to the requirements specified.

7.2 If the original test for product analysis fails, retests of two additional billets, lengths of flat-rolled stock, or tubes shall be made. Both retests, for the elements in question shall meet the requirements of the specification; otherwise all remaining material in the heat or lot (Note 1) shall be rejected or, at the

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee A01 on Steel, Stainless Steel, and Related Alloys, and is the direct responsibility of Subcommittee A01.09 on Carbon Steel Tubular Products.

Current edition approved Sept. 10, 1995. Published March 1996. Originally published as A 423 – 58 T. Last previous edition A 423/A 423M-91.

<sup>2</sup> For ASME Boiler and Pressure Vessel Code applications see related Specification SA-423 in Section II of that Code.

<sup>3</sup> Annual Book of ASTM Standards, Vol 03.03.

**TABLE 1 Chemical Requirements**

	Composition, %	
	Grade 1	Grade 2
Carbon, max	0.15	0.15
Manganese, max	0.55	0.50–1.00
Phosphorus	0.06–0.16	0.04 max
Sulfur, max	0.060	0.05
Silicon, min	0.10	...
Copper	0.20–0.60	0.30–1.00
Chromium	0.24–1.31	...
Nickel	0.20–0.70	0.40–1.10
Molybdenum, min	...	0.10

option of the producer, each billet, length of flat-rolled stock or tube may be individually tested for acceptance. Billets, lengths of flat-rolled stock or tubes which do not meet the requirements of the specification shall be rejected.

NOTE 1—For flattening, flaring, and flange requirements, the term *lot* applies to all tubes prior to cutting of the same nominal size and wall thickness that are produced from the same heat of steel. When final heat treatment is in a batch-type furnace, a lot shall include only those tubes of the same size and from the same heat which are heat treated in the same furnace charge. When the final heat treatment is in a continuous furnace the number of tubes of the same size and from the same heat in a lot shall be determined from the size of the tubes as prescribed in Table 2.

NOTE 2—For tensile and hardness test requirements, the term *lot* applies to all tubes prior to cutting, of the same nominal diameter and wall thickness that are produced from the same heat of steel. When final heat treatment is in a batch-type furnace, a lot shall include only those tubes of the same size and the same heat which are heat treated in the same furnace charge. When the final heat treatment is in a continuous furnace, a lot shall include all tubes of the same size and heat, heat treated in the same furnace at the same temperature, time at heat, and furnace speed.

**8. Tensile Requirements**

8.1 The material shall conform to the requirements as to tensile properties prescribed in Table 3.

**9. Hardness Requirements**

9.1 The tubes shall have a hardness number not exceeding 170 HB or 87 HRB.

**TABLE 2 Number of Tubes in a Lot Heat Treated by the Continuous Process**

Size of Tube	Size of Lot
2 in. [50.8 mm] and over in outside diameter and 0.200 in. [5.1 mm] and over in wall thickness	not more than 50 tubes
Less than 2 in. [50.8 mm] but over 1 in. [25.4 mm] in outside diameter or over 1 in. [25.4 mm] in outside diameter and under 0.200 in. [5.1 mm] in wall thickness	not more than 75 tubes
1 in. [25.4 mm] or less in outside diameter	not more than 125 tubes

**TABLE 3 Tensile Requirements**

Tensile strength, min, ksi [MPa],	60 [415]
Yield strength, min, or 50 mm, ksi [MPa]	37 [255]
Elongation in 2 in. or 50 mm, min, %	25
For longitudinal strip tests a deduction for each 1/2 in. [0.8 mm] decrease in wall thickness below 5/16 in. [8 mm] from the basic minimum elongation of the following percentage points shall be made	1.25 <sup>A</sup>

<sup>A</sup> Calculated elongation requirements shall be rounded to the nearest whole number.

**10. Forming Operations**

10.1 Tubes when inserted in the boiler shall stand expanding and beading without showing cracks or flaws.

**11. Mechanical Tests Required**

11.1 *Tension Test*—One tension test shall be made on a specimen for lots of not more than 50 tubes. Tension tests shall be made on specimens from two tubes for lots of more than 50 tubes (Note 2).

11.2 *Flattening Test*—One flattening test shall be made on specimens from each end of one finished tube, not the one used for the flaring or flanging test, from each lot (Note 1).

11.3 *Flaring Test (Seamless Tubes)*—One flaring test shall be made on specimens from each end of one finished tube, not the one used for the flattening test, from each lot (Note 1).

11.4 *Flange Test (Welded Tubes)*—One flange test shall be made on specimens from each end of one finished tube, not the one used for the flattening test, from each lot (Note 1).

11.5 *Hardness Test*—Brinell or Rockwell hardness tests shall be made on specimens from two tubes from each lot (Note 2).

11.6 *Reverse Flattening Test*—For welded tubes, one reverse flattening test shall be made on a specimen from each 1500 ft [460 m] of finished tubing.

11.7 *Hydrostatic or Nondestructive Electric Test*—Each tube shall be subjected to the hydrostatic test, or, instead of this test, a nondestructive electric test may be used when specified by the purchaser.

**12. General Requirements**

12.1 Material furnished under this specification should conform to the applicable requirements of the current edition of Specification A 450/A 450M, unless otherwise provided herein.

**13. Product Marking**

13.1 In addition to the marking prescribed in Specification A 450/A 450M, the marking shall include whether hot finished or cold finished, and whether seamless or welded.

**14. Keywords**

14.1 seamless steel tube; steel tube; alloy; welded steel tube

**SUPPLEMENTARY REQUIREMENTS**

The following supplementary requirement shall apply only when specified by the purchaser in the inquiry, contract, or order. Details of this supplemental requirement shall be agreed upon by the manufacturer and the purchaser.

**S1. Surface Condition**

S1.1 If pickling or shot blasting, or both, are required, this shall be specifically stated in the order and shall be done at the purchaser's expense.

**ADDITIONAL SUPPLEMENTARY REQUIREMENTS**

The following supplementary requirements may become a part of the specification when specified in the inquiry or invitation to bid, and purchase order or contract. These requirements shall not be considered unless specified in the order and the necessary tests shall be made at the mill.

**S2. Additional Testing of Welded Tubing per ASME Request**

S2.1 Each tube shall be subjected to an ultrasonic inspection employing Practices E 273 or E 213 with the rejection criteria referenced in Specification A 450/A 450M.

S2.2 If Practice E 273 is employed, a 100 % volumetric inspection of the entire length of each tube shall also be performed using one of the non-destructive electric tests permitted by Specification A 450/A 450M.

S2.3 The test methods described in the supplement may not be capable of inspecting the end portions of tubes. This condition is referred to as end effect. This portion, as determined by the manufacturer, shall be removed and discarded.

S2.4 In addition to the marking prescribed in Specification A 450/A 450M, "S2" shall be added after the grade designation.

*ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.*

*This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.*

*This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).*