



Standard Specification for Centrifugally Cast Ferritic/Austenitic Stainless Steel Pipe for Corrosive Environments¹

This standard is issued under the fixed designation A 872; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification covers centrifugally cast ferritic/austenitic steel pipe intended for general corrosive service. These steels are susceptible to embrittlement if used for prolonged periods at elevated temperatures.

1.2 Optional supplementary requirements are provided when additional testing may be required.

1.3 The values stated in inch-pound units are to be regarded as the standard.

2. Referenced Documents

2.1 ASTM Standards:

A 370 Test Methods and Definitions for Mechanical Testing of Steel Products²

A 488/A 488M Practice for Steel Castings, Welding, Qualification of Procedures and Personnel³

A 530/A 530M Specification for General Requirements for Specialized Carbon and Alloy Steel Pipe⁴

E 29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications⁵

E 94 Guide for Radiographic Examination⁶

E 165 Test Method for Liquid Penetrant Examination⁶

E 186 Reference Radiographs for Heavy-Walled (2 to 4½-in. (51 to 114-mm)) Steel Castings⁶

E 280 Reference Radiographs for Heavy-Walled (4½ to 12-in. (114 to 305-mm)) Steel Castings⁶

E 340 Test Method for Macroetching Metals and Alloys⁷

E 426 Practice for Electromagnetic (Eddy-Current) Examination of Seamless and Welded Tubular Products, Austenitic Stainless Steel and Similar Alloys⁶

E 446 Reference Radiographs for Steel Castings up to 2 in. (51 mm) in Thickness⁶

2.2 ASME Boiler and Pressure Vessel Code:

¹ This specification is under the jurisdiction of ASTM Committee A01 on Steel, Stainless Steel, and Related Alloys and is the direct responsibility of Subcommittee A01.18 on Castings.

Current edition approved July 15, 1991. Published September 1991. Originally published as A 872 – 77. Last previous edition A 872 – 87.

² *Annual Book of ASTM Standards*, Vol 01.03.

³ *Annual Book of ASTM Standards*, Vol 01.02.

⁴ *Annual Book of ASTM Standards*, Vol 01.01.

⁵ *Annual Book of ASTM Standards*, Vol 14.02.

⁶ *Annual Book of ASTM Standards*, Vol 03.03.

⁷ *Annual Book of ASTM Standards*, Vol 03.01.

Section IX Welding Qualifications⁸

2.3 ASTM Adjuncts:

Adjunct E 186 Reference Radiographs—Transparencies in Ringbinders, 3 Volumes⁹

Adjunct E 280 Reference Radiographs—Transparencies in Ringbinders, 2 Volumes¹⁰

Adjunct E 446 Reference Radiographs—Transparencies in Ringbinders, 3 Volumes¹¹

3. Ordering Information

3.1 Orders for material to this specification shall include the following, as required, to describe the desired material adequately.

3.1.1 Quantity (feet (metres) or number of lengths),

3.1.2 Name of material (centrifugally cast ferritic/austenitic steel pipe),

3.1.3 Grade (Table 1),

3.1.4 Size (outside or inside diameter and minimum wall thickness in inches (millimetres)),

3.1.5 Length (specific or random, Specification A 530/A 530M),

3.1.6 End finish of Specification A 530/A 530M,

3.1.7 Optional Requirements (S1 through S6),

3.1.8 Test report required (Section 12), and

3.1.9 Special requirements or additions to the specification.

4. General Requirements

4.1 Material furnished under this specification shall conform to the applicable requirements of the current edition of Specification A 530/A 530M, unless otherwise provided herein.

5. Materials and Manufacture

5.1 Manufacture:

5.1.1 The pipe shall be made by the centrifugal casting process.

⁸ Available from American Society of Mechanical Engineers (ASME International), Three Park Ave., New York, NY 10016-5990.

⁹ Available from ASTM International Headquarters. Request RRE018601 for Vol I, RRE018602 for Vol II, and RRE018603 for Vol III.

¹⁰ Available from ASTM International Headquarters. Request for RRE028001 Vol I and RRE028002 for Vol II.

¹¹ Available from ASTM International Headquarters. Request for RRE044601 Vol I, RRE044602 for Vol II, and RRE044603 for Vol III.

TABLE 1 Chemical Requirements

Element	UNS No.	
	J93183	J93550
C	0.030 max	0.030 max
Mn	2.0 max	2.0 max
P	0.040 max	0.040 max
S	0.030 max	0.030 max
Si	2.0 max	2.0 max
Ni	4.00–6.00	5.00–8.00
Cr	20.0–23.0	23.0–26.0
Mo	2.00–4.00	2.00–4.00
N	0.08–0.25	0.08–0.25
Cu	1.00 max	1.00 max
Co	0.50–1.50	0.50–1.50

5.1.2 All pipes shall be furnished in the heat-treated condition as shown in Table 2.

5.1.3 *Machining*—The pipe shall be machined on the inner surface and may be supplied either machined or unmachined in the outer surface. All machining shall be to a roughness value agreed upon between the manufacturer and purchaser.

6. Chemical Composition

6.1 *Heat Analysis*—An analysis of each heat shall be made by the manufacturer to determine the percentages of elements specified in Table 1. The analysis shall be made on a test sample taken preferably during the pouring of the heat. The chemical composition thus determined shall conform to the requirements specified in Table 1.

6.2 *Product Analysis*—A product analysis may be made by the purchaser. The sample for analysis shall be selected so as to be thoroughly representative of the pipe being analyzed. The chemical composition thus determined shall conform to the requirements specified in Table 1.

6.3 To determine conformance with the chemical analysis requirements, an observed value or calculated value shall be rounded in accordance with Practice E 29 to the nearest unit in the last right-hand place of values listed in Table 1.

7. Tensile Requirements

7.1 *Testing*—Steel used for the castings shall conform to the tensile and hardness requirements specified in Table 3.

7.2 Test Specimens:

7.2.1 Test bars shall be taken from heat-treated castings.

7.2.2 Tension test specimens shall be machined to the form and dimensions shown in Figs. 5 or 6 of Test Methods and Definitions A 370.

7.3 Number of Tests:

7.3.1 One tension test shall be made from each heat.

7.3.2 If a specimen is machined improperly or flaws are revealed by machining or during testing, the specimen may be discarded and another substituted from the same heat.

TABLE 2 Heat Treatment Requirements

UNS No.	Condition	
	Temperature, °F [°C]	Quenching
J93183	1920–2100	Water quench or rapid cooling by other means
J93550	[1050–1150] Do	Do

Requirement	UNS No.	
	J93183	J93550
Tensile strength, min, ksi (MPa)	90 [620]	90 [620]
Yield strength, min, ksi (MPa)	65 [450]	65 [450]
Elongation in 2 in. or 50 mm, min, %	25	20
Hardness, max:		
Brinell	290	297
Rockwell C	30.5	31.5

7.4 *Retests*—If the results of the mechanical test for any heat do not conform to the requirements specified, the casting may be reheat treated and retested, but this may not be solution treated more than twice.

8. Quality

8.1 The surface of the casting shall be examined visually and shall be free of cracks and hot tears. Other surface defects shall be judged in accordance with visual acceptance criteria that may be specified in the order.

9. Rework and Retreatment

9.1 Defects as defined in Section 9 shall be removed and their removal verified by visual inspection of the resultant cavities. Defects that are located by inspection using Supplementary Requirement S4, S5, or S6 shall be removed or reduced to an acceptable size.

9.2 If removal of the defect does not infringe upon the minimum wall thickness, the depression shall be blended uniformly into the surrounding surface.

9.3 If the cavity resulting from defect removal infringes upon the minimum wall thickness, weld repair is permitted subject to the purchaser's approval. The composition of the weld rod used shall be suitable for the composition of the metal being welded.

9.3.1 Practice A 488/A 488M or ASME Boiler and Pressure Vessel Code, Section IX shall be used as a guide for welder and procedure qualification and shall be by agreement between the purchaser and the manufacturer. All repair welds shall be inspected to the same quality standard used to inspect the casting.

10. Permissible Variations in Dimensions

10.1 *Thickness*—The wall thickness shall not vary over that specified by more than 1/8 in. (3 mm). There shall be no variation under the specified wall thickness.

11. Rejection

11.1 Each length of pipe received from the manufacturer may be inspected by the purchaser and if it does not meet the requirements of the specification based on the inspection and test method as outlined in the specification, the pipe may be rejected and the manufacturer shall be notified. Disposition of rejected pipe shall be a matter of agreement between the manufacturer and the purchaser.

12. Certification

12.1 Upon request of the purchaser in the contract or order, a manufacturer's certification that the material was manufactured, sampled, tested, and inspected in accordance with this



specification, together with a report of the test results, shall be furnished at the time of shipment.

13. Product Marking

13.1 Each length of pipe shall be legibly marked with the manufacturer's name or brand, the specification number, and

the grade. In addition, heat numbers or special numbers that are traceable to heat numbers, shall be marked on each length of pipe.

SUPPLEMENTARY REQUIREMENTS

Supplementary requirements shall be applied only when specified by the purchaser. Details of the supplementary requirements shall be agreed upon between the manufacturer and the purchaser. The specified tests shall be performed by the manufacturer prior to shipment of the castings.

S1. Additional Tension Tests

S1.1 Additional tension tests shall be made at a temperature to be specified by the customer, and the properties to be met are a matter of agreement between purchaser and manufacturer.

S2. Flattening Test

S2.1 The flattening test shall be made on specimens from one or both ends of each length of pipe. If the specimen from any end of any length fails to conform to the requirements of Specification A 530/A 530M, that length shall be rejected.

S3. Etching Test

S3.1 The steel shall be homogeneous as shown by etching tests conducted in accordance with the appropriate portions of Method E 340. Etching tests shall be made on a cross section from one end or both ends of each pipe and shall show sound and reasonably uniform material, free of injurious laminations, cracks, and similar objectionable defects. If this supplementary requirement is specified, the number of required tests per pipe shall also be specified. If a specimen from any length shows objectionable defects, the length shall be rejected, subject to removal of the defective end and subsequent retests indicating the remainder of the length to be sound and reasonably uniform material.

S4. Radiographic Examination

S4.1 The castings shall be examined for internal defects by means of X rays or gamma rays. The inspection procedure shall

be in accordance with Guide E 94 and the types and degrees of discontinuities considered shall be judged by Reference Radiographs E 186, E 280, or E 446. The extent of examination and the basis for acceptance shall be subject to agreement between the manufacturer and the purchaser.

S5. Liquid Penetrant Examination

S5.1 The castings shall be examined for surface discontinuities by means of liquid penetrant inspection. The method of performing the liquid penetrant test shall be in accordance with Practice E 165. The areas to be inspected, the methods, and types of liquid penetrants to be used, the developing procedure, and the basis for acceptance shall be as specified on the inquiry or contract or both, or as agreed upon between the manufacturer and the purchaser.

S6. Hydrostatic Test

S6.1 Each length of pipe shall be hydrostatically tested in accordance with Specification A 530/A 530M. Test pressure may be mutually agreed upon between the manufacturer and the purchaser.

S6.2 It is realized that the foundry may be unable to perform the hydrostatic test prior to shipment, or that the purchaser may wish to defer testing until additional work has been performed on the casting. In such cases, the foundry is responsible for the satisfactory performance of the casting when it is so tested.

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).