



Standard Specification for Seamless Carbon Steel Pipe for Atmospheric and Lower Temperatures¹

This standard is issued under the fixed designation A 524; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification² covers seamless carbon steel pipe intended primarily for service at atmospheric and lower temperatures, NPS 1/8 to 26 inclusive, with nominal (average) wall thickness as given in ANSI B 36.10. Pipe having other dimensions may be furnished, provided such pipe complies with all other requirements of this specification. Pipe ordered to this specification shall be suitable both for welding, and for bending, flanging, and similar forming operations.

1.2 The values stated in inch-pound units are to be regarded as the standard.

NOTE 1—The dimensionless designator NPS (nominal pipe size) has been substituted in this standard for such traditional terms as “nominal diameter,” “size,” and “nominal size”.

1.3 The following hazard caveat applies to the test methods portion, Section 16, only. *This standard does not purport to address all of the safety problems, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:

A 530/A530M Specification for General Requirements for Specialized Carbon and Alloy Steel Pipe³

E 29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications⁴

2.2 American National Standards Institute Standard:

B 36.10 Welded and Seamless Wrought Steel Pipe⁵

3. Ordering Information

3.1 Orders for material under this specification should include the following, as required, to describe the desired material adequately:

- 3.1.1 Quantity (feet or number of lengths),
- 3.1.2 Name of material (seamless carbon steel pipe),
- 3.1.3 Grade (Table 1 and Table 2),
- 3.1.4 Manufacture (hot finished or cold drawn),
- 3.1.5 Size (either nominal wall thickness and weight class or schedule number, or both, or outside diameter and nominal wall thickness, ANSI B 36.10),
- 3.1.6 Length (17),
- 3.1.7 Optional requirements (Section 8, and Section 11 of Specification A 530/A 530M),
- 3.1.8 Test report required (Certification Section of Specification A 530/A 530M),
- 3.1.9 Specification designation,
- 3.1.10 End use of material, and
- 3.1.11 Special requirements.

4. General Requirements

4.1 Material furnished to this specification shall conform to the applicable requirements of the current edition of Specification A 530/A 530M unless otherwise provided herein.

5. Materials and Manufacture

5.1 Process:

5.1.1 The steel shall be killed steel made by one or more of the following processes: open-hearth, electric-furnace, or basic-oxygen.

5.1.2 The steel shall be made to fine grain practice.

5.1.3 Steel may be cast in ingots or may be strand cast. When steel of different grades are sequentially strand cast, identification of the resultant transition material is required. The producer shall remove the transition material by any established procedure that positively separates the grades.

5.1.4 Pipe NPS 1½ and under may be either hot finished or cold drawn.

5.1.5 Unless otherwise specified, pipe NPS 2 and over shall be furnished hot finished. When agreed upon between the manufacturer and purchaser, cold-drawn pipe may be furnished.

5.2 Heat Treatment:

5.2.1 All hot-finished and cold-drawn pipe shall be reheated to a temperature above 1550 °F (845°C) and followed by cooling in air or in the cooling chamber of a controlled atmosphere furnace.

¹ This specification is under the jurisdiction of ASTM Committee A-1 on Steel, Stainless Steel, and Related Alloys, and is the direct responsibility of Subcommittee A01.09 on Steel Pipe.

Current edition approved Oct. 10, 1996. Published November 1997. Originally published as A 524 – 65. Last previous edition A 524 – 93.

² For ASME Boiler and Pressure Vessel Code Applications see related Specification SA-524 in Section II of that Code.

³ Annual Book of ASTM Standards, Vol 01.01.

⁴ Annual Book of ASTM Standards, Vol 14.02.

⁵ Available from American National Standards Institute, 11 West 42nd St., 13th Floor, New York, NY 10036.

TABLE 1 Chemical Requirements

Element	Grades I and II, Composition, %
Carbon, max	0.21
Manganese	0.90–1.35
Phosphorus, max	0.035
Sulfur, max	0.035
Silicon	0.10–0.40

6. Chemical Composition

6.1 The steel shall conform to the chemical requirements prescribed in Table 1.

7. Heat Analysis

7.1 An analysis of each heat of steel shall be made by the steel manufacturer to determine the percentages of the elements specified in Section 6. The chemical composition thus determined, or that determined from a product analysis made by the manufacturer, if the latter has not manufactured the steel, shall be reported to the purchaser or the purchaser's representative, and shall conform to the requirements specified in Section 6.

8. Product Analysis

8.1 At the request of the purchaser, analyses of two pipes from each lot (Note 2) shall be made by the manufacturer from the finished pipe. The chemical composition thus determined shall conform to the requirements specified in Section 6.

NOTE 2—A lot shall consist of 400 lengths, or fraction thereof, for each size NPS 2 up to but not including NPS 6, and of 200 lengths, or fraction thereof, for each size NPS 6 and over.

8.2 If the analysis of one of the tests specified in 8.1 does not conform to the requirements specified in 6, analyses shall be made on additional pipe of double the original number from the same lot, each of which shall conform to requirements specified.

9. Physical Properties

9.1 *Tensile Properties*—The material shall conform to the requirements as to tensile properties prescribed in Table 2.

9.2 *Bending Properties*:

9.2.1 For pipe NPS 2 and under, a sufficient length of pipe shall stand being bent cold through 90° around a cylindrical mandrel, the diameter of which is twelve times the nominal diameter of the pipe, without developing cracks. When ordered for close coiling, the pipe shall stand being bent cold through 180° around a cylindrical mandrel, the diameter of which is eight times the nominal diameter of the pipe, without failure.

9.2.2 For pipe whose diameter exceeds 25 in. (635 mm) and whose diameter to wall thickness ratio is 7.0 or less, bend test specimens shall be bent at room temperature through 180° without cracking on the outside of the bent portion. The inside diameter of the bend shall be 1 in. (25.4 mm). This test shall be in place of Section 10.

NOTE 3—Diameter to wall thickness ratio = specified outside diameter/nominal wall thickness.

Example: For 28 in. diameter 5.000 in. thick pipe the diameter to wall thickness ratio = $28/5 = 5.6$.

10. Flattening Test Requirements

10.1 For pipe over NPS 2, a section of pipe not less than 2½ in. (63.5 mm) in length shall be flattened cold between parallel plates until the opposite walls of the pipe meet. Flattening tests shall be in accordance with Specification A 530, except that in the equation used to calculate the H value, the following e constants shall be used:

0.07 for Grade I

0.08 for Grade II

10.2 When low D -to- t ratio tubulars are tested, because the strain imposed due to geometry is unreasonably high on the inside surface at the 6 and 12 o'clock locations, cracks at these locations shall not be cause for rejection if the D -to- t ratio is less than 10.

11. Hydrostatic Test Requirements

11.1 Each length of pipe shall be subjected to the hydrostatic pressure, except as provided in 11.2.

11.2 When specified in the order, pipe may be furnished without hydrostatic testing and each length so furnished shall include with the mandatory marking the letters "NH."

11.3 When certification is required by the purchaser and the hydrostatic test has been omitted, the certification shall clearly state "Not Hydrostatically Tested," and the specification number and grade designation, as shown on the certification, shall be followed by the letters "NH."

12. Dimensions and Weights

12.1 The dimensions and weights of plain-end pipe are included in ANSI B 36.10. Sizes and wall thicknesses most generally available are listed in Appendix X1.

13. Dimensions, Weight, and Permissible Variations

13.1 *Weight*—The weight of any length of pipe shall not vary more than 6.5 % over and 3.5 % under that specified for pipe of Schedule 120 and lighter nor more than 10 % over and 3.5 % under that specified for pipe heavier than Schedule 120. Unless otherwise agreed upon between the manufacturer and purchaser, pipe in sizes NPS 4 and smaller may be weighed in convenient lots; pipe in sizes larger than NPS 4 shall be weighed separately.

13.2 *Diameter*—Variations in outside diameter shall not exceed those specified in Table 3.

13.3 *Thickness*—The minimum wall thickness at any point shall not be more than 12.5 % under the nominal wall thickness specified.

NOTE 4—The minimum wall thickness on inspection is shown in Appendix X1.

14. Workmanship, Finish, and Appearance

14.1 The pipe manufacturer shall explore a sufficient number of visual surface imperfections to provide reasonable assurance that they have been properly evaluated with respect to depth. Exploration of all surface imperfections is not required but may be necessary to assure compliance with 14.2.

14.2 Surface imperfections that penetrate more than 12½ % of the nominal wall thickness or encroach on the minimum wall thickness shall be considered defects. Pipe with such defects shall be given one of the following dispositions:

TABLE 2 Tensile Requirements

	Wall Thicknesses			
	Grade I, 0.375 in. (9.52 mm) and under		Grade II, greater than 0.375 in. (9.52 mm)	
Tensile strength, psi (MPa)	60 000–85 000 (414–586)		55 000–80 000 (380–550)	
Yield strength, min, psi (MPa)	35 000 (240)		30 000 (205)	
	Longitudinal	Transverse	Longitudinal	Transverse
Elongation in 2 in. or 50 mm, min %:				
Basic minimum elongation for walls $\frac{5}{16}$ in. (7.9 mm) and over in thickness, strip tests, and for all small sizes tested in full section	30	16.5	35	25
When standard round 2 in. or 50 mm gage length test specimen is used for strip tests, a deduction for each $\frac{1}{32}$ in. (0.8 mm) decrease in wall thickness below $\frac{5}{16}$ in. (7.9 mm) from the basic minimum elongation of the following percentage	22 1.50 ^A	12 1.00 ^A	28 ...	20 ...

^AThe following table gives the computed minimum values:

Wall Thickness	Elongation in 2 in. or 50 mm, min, %		
		Grade I	
		Longitudinal	Transverse
in.	mm		
$\frac{5}{16}$ (0.312)	7.94	30.0	16.5
$\frac{3}{32}$ (0.281)	7.14	28.5	15.5
$\frac{1}{4}$ (0.250)	6.35	27.0	14.5
$\frac{7}{32}$ (0.219)	5.56	25.5	...
$\frac{3}{16}$ (0.188)	4.76	24.0	...
$\frac{5}{32}$ (0.156)	3.97	22.5	...
$\frac{1}{8}$ (0.125)	3.18	21.0	...
$\frac{3}{32}$ (0.094)	2.38	19.5	...
$\frac{1}{16}$ (0.062)	1.59	18.0	...

Note—The above table gives the computed minimum elongation values for each $\frac{1}{32}$ -in. (0.79 mm) decrease in wall thickness. Where the wall thickness lies between two values shown above, the minimum elongation value is determined by the following equation:

Grade	Direction of Test	Equation
I	transverse	$E = 32t + 6.50$
I	longitudinal	$E = 48t + 15.00$

where:

E = elongation in 2 in. or 50 mm in % and
 t = actual thickness of specimen, in. (mm).

TABLE 3 Variations in Outside Diameter

NPS Designator	Permissible Variations in Outside Diameter, in. (mm)	
	Over	Under
$\frac{1}{8}$ to $1\frac{1}{2}$, incl	$\frac{1}{64}$ (0.4)	$\frac{1}{32}$ (0.8)
Over $1\frac{1}{2}$ to 4, incl	$\frac{1}{32}$ (0.8)	$\frac{1}{32}$ (0.8)
Over 4 to 8, incl	$\frac{1}{16}$ (1.6)	$\frac{1}{32}$ (0.8)
Over 8 to 18, incl	$\frac{3}{32}$ (2.4)	$\frac{1}{32}$ (0.8)
Over 18	$\frac{1}{8}$ (3.2)	$\frac{1}{32}$ (0.8)

14.2.1 The defect may be removed by grinding provided that the remaining wall thickness is within specified limits.

14.2.2 Repaired in accordance with the repair welding provisions of 14.6.

14.2.3 The section of pipe containing the defect may be cut off within the limits of requirements on length.

14.2.4 Rejected.

14.3 To provide a workmanlike finish and basis for evaluating conformance with 14.2, the pipe manufacturer shall remove by grinding the following noninjurious imperfections:

14.3.1 Mechanical marks, abrasions (Note 5) and pits, any of which imperfections are deeper than $\frac{1}{16}$ in. (1.58 mm).

NOTE 5—Marks and abrasions are defined as cable marks, dinges, guide

marks, roll marks, ball scratches, scores, die marks, and the like.

14.3.2 Visual imperfections, commonly referred to as scabs, seams, laps, tears or slivers, found by exploration in accordance with 14.1 to be deeper than 5 % of the nominal wall thickness.

14.4 At the purchaser's discretion, pipe shall be subject to rejection if surface imperfections acceptable under 14.2 are not scattered, but appear over a large area in excess of what is considered a workmanlike finish. Disposition of such pipe shall be a matter of agreement between the manufacturer and the purchaser.

14.5 When imperfections or defects are removed by grinding, a smooth curved surface shall be maintained, and the wall thickness shall not be decreased below that permitted by this specification. The outside diameter at the point of grinding may be reduced by the amount so removed.

14.5.1 Wall thickness measurements shall be made with a mechanical caliper or with a properly calibrated nondestructive testing device of appropriate accuracy. In case of dispute, the measurement determined by use of the mechanical caliper shall govern.

14.6 Weld repair shall be permitted only subject to the

approval of the purchaser and in accordance with Specification A 530/A 530M.

14.7 The finished pipe shall be reasonably straight.

15. Number of Tests and Retests

15.1 One of either of the tests specified in 9.1 shall be made on one length of pipe from each lot (Note 2).

15.2 For pipe NPS 2 and under, the bend test specified in 9.2 shall be made on one pipe from each lot (Note 2). The bend tests specified in 9.2.2 shall be made on one end of each pipe.

15.3 The flattening test specified in 10 shall be made on one length of pipe from each lot (Note 2).

15.4 Retests shall be in accordance with Specification A 530 and as provided in 13.5 and 13.6.

15.5 If a specimen breaks in an inside or outside surface flaw, a retest shall be allowed.

15.6 Should a crop end of a finished pipe fail in the flattening test, one retest may be made from the broken end.

16. Test Specimens and Methods of Testing

16.1 Specimens cut either longitudinally or transversely shall be acceptable for the tension test.

16.2 Test specimens for the bend test specified in 9.2 and for the flattening tests specified in 10 shall consist of sections cut from a pipe. Specimens for flattening tests shall be smooth on the ends and free from burrs, except when made on crop ends.

16.3 Test specimens for the bend test specified in 9.2.2 shall be cut from one end of the pipe and, unless otherwise specified, shall be taken in a transverse direction. One test specimen shall be taken as close to the outer surface as possible and another from as close to the inner surface as possible. The specimens shall be either $\frac{1}{2}$ by $\frac{1}{2}$ in. (12.7 mm) in section or 1 by $\frac{1}{2}$ in. (25.4 by 12.7 mm) in section with the corners rounded to a radius not over $\frac{1}{16}$ in. (1.6 mm) and need not exceed 6 in. (152 mm) in length. The side of the samples placed in tension during the bend shall be the side closest to the inner and outer surface of the pipe respectively.

17. Lengths

17.1 Pipe lengths shall be in accordance with the following regular practice:

17.1.1 The lengths required shall be specified in the order, and

17.1.2 No jointers are permitted unless otherwise specified.

17.2 If definite lengths are not required, pipe may be ordered in single random lengths of 16 to 22 ft (4.9 to 6.7 m), with 5 % 12 to 16 ft (3.7 to 4.9 m), or in double random lengths with a minimum average of 35 ft (10.7 m) and a minimum length of 22 ft with 5 % 16 to 22 ft.

18. Rejection

18.1 Each length of pipe that develops injurious defects during shop working or application operations will be rejected, and the manufacturer shall be notified. No rejections under this or any other specifications shall be marked as specified in 19 for sale under this specification except where such pipe fails to comply with the weight requirements alone, in which case it may be sold under the weight specifications with which it does comply.

19. Product Marking

19.1 In addition to the marking prescribed in Specification A 530/A 530M, the marking shall include the hydrostatic test pressure when tested or the letters "NH" when not tested, the length and schedule number, and on pipe sizes larger than NPS 4 the weight shall be given. Length shall be marked in feet and tenths of a foot, or metres to two decimal places, depending on the units to which the material was ordered, or other marking subject to agreement.

19.2 *Bar Coding*—In addition to the requirements in 19.1, bar coding is acceptable as a supplemental identification method. The purchaser may specify in the order a specific bar coding system to be used.

APPENDIX

(Nonmandatory Information)

X1. DIMENSIONS AND WALL THICKNESSES

X1.1 Following are Tables X1.1 and X1.2 cited in the text of this standard.

TABLE X1.1 Table of Minimum Wall Thicknesses on Inspection for Nominal (Average) Pipe Wall Thickness

NOTE 1—The following equation, upon which this table is based, may be applied to calculate minimum wall thickness from nominal (average) wall thickness:

$$t_n \times 0.875 = t_m$$

where:
 t_n = nominal (average) wall thickness, in. (mm), and
 t_m = minimum wall thickness, in. (mm).

NOTE 2— The wall thickness is expressed to three decimal places, the fourth decimal place being carried forward or dropped, in accordance with Practice E 29. This table is a master table covering wall thicknesses available in the purchase of different classifications of pipe, but it is not meant to imply that all of the walls listed therein are obtainable under this specification.

Nominal (Average) Thickness (t_n)		Minimum Thickness on Inspection (t_m)		Nominal (Average) Thickness (t_n)		Minimum Thickness on Inspection (t_m)		Nominal (Average) Thickness (t_n)		Minimum Thickness on Inspection (t_m)	
in.	mm	in.	mm	in.	mm	in.	mm	in.	mm	in.	mm
0.068	1.73	0.060	1.52	0.281	7.14	0.246	6.25	0.864	21.94	0.756	19.20
0.083	2.11	0.073	1.85	0.294	7.47	0.257	6.53	0.875	22.22	0.766	19.46
0.088	2.24	0.077	1.96	0.300	7.62	0.262	6.65	0.906	23.01	0.793	20.14
0.091	2.31	0.080	2.03	0.307	7.80	0.269	6.83	0.938	23.82	0.821	20.85
0.095	2.41	0.083	2.11	0.308	7.82	0.270	6.86	0.968	24.59	0.847	21.51
0.109	2.77	0.095	2.41	0.312	7.92	0.273	6.93	1.000	25.40	0.875	22.22
0.113	2.87	0.099	2.51	0.318	8.07	0.278	7.06	1.031	26.19	0.902	22.91
0.119	3.02	0.104	2.64	0.322	8.18	0.282	7.16	1.062	26.97	0.929	23.60
0.125	3.18	0.109	2.77	0.330	8.38	0.289	7.34	1.094	27.79	0.957	24.31
0.126	3.20	0.110	2.79	0.337	8.56	0.295	7.49	1.125	28.58	0.984	24.99
0.133	3.38	0.116	2.95	0.344	8.74	0.301	7.64	1.156	29.36	1.012	25.70
0.140	3.56	0.122	3.10	0.358	9.09	0.313	7.95	1.219	30.96	1.066	27.08
0.141	3.58	0.123	3.12	0.365	9.27	0.319	8.10	1.250	31.75	1.094	27.79
0.145	3.68	0.127	3.23	0.375	9.52	0.328	8.33	1.281	32.54	1.121	28.47
0.147	3.73	0.129	3.28	0.382	9.70	0.334	8.48	1.312	33.32	1.148	29.16
0.154	3.91	0.135	3.43	0.400	10.16	0.350	8.89	1.375	34.92	1.203	30.56
0.156	3.96	0.136	3.45	0.406	10.31	0.355	9.02	1.406	35.71	1.230	31.24
0.172	4.37	0.150	3.81	0.432	10.97	0.378	9.60	1.438	36.53	1.258	31.95
0.179	4.55	0.157	3.99	0.436	11.07	0.382	9.70	1.500	38.10	1.312	33.32
0.188	4.78	0.164	4.17	0.438	11.12	0.383	9.73	1.531	38.89	1.340	34.04
0.191	4.85	0.167	4.24	0.469	11.91	0.410	10.41	1.562	39.67	1.367	34.72
0.200	5.08	0.175	4.44	0.500	12.70	0.438	11.13	1.594	40.49	1.395	35.43
0.203	5.16	0.178	4.52	0.531	13.49	0.465	11.81	1.635	41.53	1.431	36.35
0.210	5.33	0.184	4.67	0.552	14.02	0.483	12.27	1.750	44.45	1.531	38.89
0.216	5.49	0.189	4.80	0.562	14.27	0.492	12.50	1.781	45.24	1.558	39.57
0.218	5.54	0.191	4.85	0.594	15.09	0.520	13.21	1.812	46.02	1.586	40.28
0.219	5.56	0.192	4.88	0.600	15.24	0.525	13.34	1.875	47.62	1.641	41.68
0.226	5.74	0.198	5.03	0.625	15.88	0.547	13.89	1.969	50.01	1.723	43.76
0.237	6.02	0.207	5.26	0.656	16.66	0.574	14.58	2.000	50.80	1.750	44.45
0.250	6.35	0.219	5.56	0.674	17.12	0.590	14.99	2.062	52.37	1.804	45.82
0.258	6.55	0.226	5.74	0.688	17.48	0.602	15.29	2.125	53.98	1.859	47.22
0.276	7.01	0.242	6.15	0.719	18.26	0.629	15.98	2.200	55.88	1.925	48.90
0.277	7.04	0.242	6.15	0.750	19.05	0.656	16.66	2.344	59.54	2.051	52.10
0.279	7.09	0.244	6.19	0.812	20.62	0.710	18.03	2.500	63.50	2.188	55.58
0.280	7.11	0.245	6.22	0.844	21.44	0.739	18.77				

TABLE X1.2 Dimensions, Weights and Test Pressures for Plain End Pipe
 (As appears in American National Standard B 36.10)

NPS Designator	Wall Thickness	Nominal Weight	Weight Class	Schedule No.	Test Pressure	
					Grade I	Grade II
					in. (mm)	lb/ft (kg/m)
1/8	0.068 (1.73)	0.24 (0.36)	std	40	2500 (17.2)	...
	0.095 (2.41)	0.31 (0.46)	XS	80	2500 (17.2)	...
1/4	0.088 (2.24)	0.42 (0.63)	std	40	2500 (17.2)	...
	0.119 (3.02)	0.54 (0.80)	XS	80	2500 (17.2)	...
3/8	0.091 (2.31)	0.57 (0.85)	std	40	2500 (17.2)	...
	0.126 (3.20)	0.74 (1.10)	XS	80	2500 (17.2)	...
1/2	0.109 (2.77)	0.85 (1.27)	std	40	2500 (17.2)	...
	0.147 (3.73)	1.09 (1.62)	XS	80	2500 (17.2)	...
3/4	0.294 (7.47)	1.71 (2.55)	XXS	...	2500 (17.2)	...
	0.113 (2.87)	1.13 (1.68)	std	40	2500 (17.2)	...
	0.154 (3.91)	1.47 (2.19)	XS	80	2500 (17.2)	...
	0.308 (7.82)	2.44 (3.63)	XXS	...	2500 (17.2)	...

TABLE X1.2 *Continued*

NPS Designator	Wall Thickness		Nominal Weight	Weight Class	Schedule No.	Test Pressure	
						Grade I	Grade II
	in. (mm)	lb/ft (kg/m)	psi (MPa)	psi (MPa)			
1	0.133 (3.38)	1.68 (2.50)	std	40	2500 (17.2)	...	
	0.179 (4.55)	2.17 (3.23)	XS	80	2500 (17.2)	...	
	0.358 (9.09)	3.66 (5.45)	XXS	...	2500 (17.2)	...	
1¼	0.140 (3.56)	2.27 (3.38)	std	40	2500 (17.2)	...	
	0.191 (4.85)	3.00 (4.47)	XS	80	2500 (17.2)	...	
	0.382 (9.70)	5.21 (7.76)	XXS	2500 (17.2)	
1½	0.145 (3.68)	2.72 (4.05)	std	40	2500 (17.2)	...	
	0.200 (5.08)	3.63 (5.41)	XS	80	2500 (17.2)	...	
	0.400 (10.16)	6.41 (9.55)	XXS	2500 (17.2)	
2	0.154 (3.91)	3.65 (5.44)	std	40	2500 (17.2)	...	
	0.218 (5.54)	5.02 (7.48)	XS	80	2500 (17.2)	...	
	0.344 (8.74)	7.46 (11.12)	...	160	2500 (17.2)	...	
	0.436 (11.07)	9.03 (13.45)	XXS	2500 (17.2)	
2½	0.203 (5.16)	5.79 (8.62)	std	40	2500 (17.2)	...	
	0.276 (7.01)	7.66 (11.41)	XS	80	2500 (17.2)	...	
	0.375 (9.52)	10.01 (14.91)	...	160	2500 (17.2)	...	
	0.552 (14.02)	13.70 (20.41)	XXS	2500 (17.2)	
3	0.216 (5.49)	7.58 (11.29)	std	40	2500 (17.2)	...	
	0.300 (7.62)	10.25 (15.27)	XS	80	2500 (17.2)	...	
	0.438 (11.13)	14.32 (21.34)	...	160	...	2500 (17.2)	
	0.600 (15.24)	18.58 (27.67)	XXS	2500 (17.2)	
3½	0.226 (5.74)	9.11 (13.57)	std	40	2400 (16.5)	...	
	0.318 (8.08)	12.51 (18.63)	XS	80	2800 (19.3)	...	
	0.237 (6.02)	10.79 (16.07)	std	40	2200 (15.2)	...	
4	0.337 (8.56)	14.98 (22.31)	XS	80	2800 (19.3)	...	
	0.438 (11.13)	19.00 (28.30)	...	120	...	2800 (19.3)	
	0.531 (13.49)	22.51 (33.53)	...	160	...	2800 (19.3)	
	0.674 (17.12)	27.54 (41.02)	XXS	2800 (19.3)	
	0.258 (6.55)	14.62 (21.78)	std	40	1900 (13.1)	...	
	0.375 (9.52)	20.78 (30.95)	XS	80	2800 (19.3)	...	
	0.500 (12.70)	27.04 (40.28)	...	120	...	2800 (19.3)	
5	0.625 (15.88)	32.96 (49.09)	...	160	...	2800 (19.3)	
	0.750 (19.05)	38.55 (57.42)	XXS	2800 (19.3)	
	0.280 (7.11)	18.97 (28.26)	std	40	1800 (12.4)	...	
	0.432 (10.97)	28.57 (42.56)	XS	80	...	2300 (15.9)	
	0.562 (14.27)	36.39 (54.20)	...	120	...	2800 (19.3)	
	0.719 (18.26)	45.35 (67.55)	...	160	...	2800 (19.3)	
	0.864 (21.95)	53.16 (79.68)	XXS	2800 (19.3)	
8	0.250 (6.35)	22.36 (33.31)	...	20	1200 (8.3)	...	
	0.277 (7.04)	24.70 (36.79)	...	30	1300 (9.0)	...	
	0.322 (8.18)	28.55 (42.53)	std	40	1600 (11.0)	...	
	0.406 (10.31)	35.64 (53.10)	...	60	...	1700 (11.7)	
	0.500 (12.70)	43.39 (64.63)	XS	80	...	2100 (14.5)	
	0.594 (15.09)	50.95 (75.92)	...	100	...	2500 (17.2)	
	0.719 (18.26)	60.71 (90.43)	...	120	...	2800 (19.3)	
	0.812 (20.62)	67.76 (100.96)	...	140	...	2800 (19.3)	
	0.875 (22.22)	72.42 (107.87)	XXS	2800 (19.3)	
	0.906 (23.01)	74.69 (111.29)	...	160	...	2800 (19.3)	
10	0.250 (6.35)	28.04 (41.77)	...	20	1000 (6.9)	...	
	0.279 (7.09)	31.20 (46.47)	...	30	1100 (7.6)	...	
	0.307 (7.80)	34.24 (51.00)	...	40	1200 (8.3)	...	
	0.365 (9.27)	40.48 (60.29)	std	40	1400 (9.7)	...	
	0.500 (12.70)	54.74 (81.55)	XS	60	...	1700 (11.7)	
	0.594 (15.09)	64.43 (96.00)	...	80	...	2000 (13.8)	
	0.719 (18.26)	77.03 (114.74)	...	100	...	2400 (16.5)	
	0.844 (21.44)	89.29 (133.04)	...	120	...	2800 (9.3)	
	1.000 (25.40)	104.13 (155.15)	XXS	140	...	2800 (9.3)	
	1.125 (28.58)	115.65 (172.32)	...	160	...	2800 (9.3)	
12	0.250 (6.35)	33.38 (49.72)	...	20	800 (5.5)	...	
	0.330 (8.38)	43.77 (65.20)	...	30	1100 (7.6)	...	
	0.375 (9.52)	49.56 (73.82)	std	...	1200 (8.3)	...	
	0.406 (10.31)	53.52 (79.74)	...	40	...	1100 (7.6)	
	0.500 (12.70)	65.42 (97.44)	XS	1400 (9.7)	
	0.562 (14.27)	73.15 (108.96)	...	60	...	1600 (11.0)	
	0.688 (17.48)	88.63 (132.01)	...	80	...	1900 (13.1)	
	0.844 (21.44)	107.32 (159.91)	...	100	...	2400 (16.5)	
	1.000 (25.40)	125.49 (186.98)	XXS	120	...	2800 (19.3)	
	1.125 (28.58)	139.68 (208.12)	...	140	...	2800 (19.3)	
	1.312 (33.32)	160.27 (238.80)	...	160	...	2800 (19.3)	

TABLE X1.2 *Continued*

NPS Designator	Wall Thickness		Nominal Weight	Weight Class	Schedule No.	Test Pressure		
						Grade I	Grade II	
	in. (mm)	lb/ft (kg/m)				psi (MPa)	psi (MPa)	
14	0.250 (6.35)	36.71 (54.68)	10	750 (5.2)	...	
	0.312 (7.92)	45.61 (67.94)	20	950 (6.6)	...	
	0.375 (9.52)	54.57 (81.28)	std	...	30	1100 (7.6)	...	
	0.438 (11.13)	63.44 (94.49)	40	...	1100 (7.6)	
	0.500 (12.70)	72.09 (107.38)	XS	1300 (9.0)	
	0.594 (15.09)	85.05 (126.72)	60	...	1500 (10.3)	
	0.750 (19.05)	106.13 (158.08)	80	...	1900 (13.1)	
	0.938 (23.83)	130.85 (194.90)	100	...	2400 (16.5)	
	1.094 (27.79)	150.79 (234.68)	120	...	2800 (19.3)	
	1.250 (31.75)	170.22 (253.63)	140	...	2800 (19.3)	
	1.406 (35.71)	189.11 (281.77)	160	...	2800 (19.3)	
	16	0.250 (6.35)	42.05 (62.63)	10	650 (4.5)	...
		0.312 (7.92)	52.27 (77.86)	20	800 (5.5)	...
		0.375 (9.52)	62.58 (93.21)	std	...	30	1000 (6.9)	...
0.500 (12.70)		82.77 (123.29)	XS	...	40	...	1100 (7.6)	
0.656 (16.66)		107.50 (160.18)	60	...	1500 (10.3)	
0.844 (21.44)		136.62 (203.56)	80	...	1900 (13.1)	
1.031 (26.19)		164.82 (245.58)	100	...	2300 (15.9)	
1.219 (30.96)		192.43 (286.72)	120	...	2700 (18.6)	
1.438 (36.52)		223.64 (333.22)	140	...	2800 (19.3)	
1.594 (40.49)		245.25 (365.42)	160	...	2800 (19.3)	
18		0.250 (6.35)	47.39 (70.59)	10	600 (4.1)	...
		0.312 (7.92)	58.94 (87.79)	20	750 (5.2)	...
		0.375 (9.52)	70.59 (105.14)	std	900 (6.2)	...
		0.438 (11.13)	82.15 (122.36)	30	...	900 (6.2)
	0.500 (12.70)	93.45 (139.19)	XS	1000 (6.9)	
	0.562 (14.27)	104.67 (155.91)	40	...	1100 (7.6)	
	0.750 (19.05)	138.17 (205.80)	60	...	1500 (10.3)	
	0.938 (23.83)	170.92 (254.59)	80	...	1900 (13.1)	
	1.156 (29.36)	207.96 (309.86)	100	...	2300 (15.9)	
	1.375 (34.92)	244.14 (363.77)	120	...	2800 (19.3)	
	1.562 (39.67)	274.22 (408.54)	140	...	2800 (19.3)	
	1.781 (45.24)	308.50 (459.67)	160	...	2800 (19.3)	
	20	0.250 (6.35)	52.73 (78.54)	10	500 (3.4)	...
		0.375 (9.52)	78.60 (117.07)	std	...	20	800 (5.5)	...
0.500 (12.70)		104.13 (155.10)	XS	...	30	...	900 (6.2)	
0.594 (15.09)		123.11 (183.43)	40	...	1100 (7.6)	
0.812 (20.62)		166.40 (247.85)	60	...	1500 (10.3)	
1.031 (26.19)		208.87 (311.22)	80	...	1900 (13.1)	
1.281 (32.54)		256.10 (381.59)	100	...	2300 (15.9)	
1.500 (38.10)		296.37 (441.59)	120	...	2700 (18.6)	
1.750 (44.45)		341.10 (508.24)	140	...	2800 (19.3)	
1.969 (50.01)		379.17 (564.96)	160	...	2800 (19.3)	
24		0.250 (6.35)	63.41 (94.45)	10	450 (3.1)	...
		0.375 (9.52)	94.62 (140.94)	std	...	20	650 (4.5)	...
		0.500 (12.70)	125.49 (186.92)	XS	750 (5.2)
		0.562 (14.27)	140.68 (209.54)	30	...	850 (5.9)
	0.688 (17.48)	171.29 (255.14)	40	...	1000 (6.9)	
	0.969 (24.61)	238.85 (355.89)	60	...	1500 (10.3)	
	1.219 (30.96)	296.58 (441.90)	80	...	1800 (12.4)	
	1.531 (38.89)	367.39 (547.41)	100	...	2300 (15.9)	
	1.812 (46.02)	429.39 (639.79)	120	...	2700 (18.6)	
	2.062 (52.37)	483.12 (719.85)	140	...	2800 (19.3)	
	2.344 (59.64)	542.14 (807.79)	160	...	2800 (19.3)	
	26	0.250 (6.35)	68.75 (102.40)	400 (2.8)	...
		0.312 (7.92)	85.60 (127.50)	10	500 (3.4)	...
		0.375 (9.52)	102.63 (152.87)	std	610 (4.2)	...
0.500 (12.70)		136.17 (202.83)	XS	...	20	...	690 (4.8)	

The American Society for Testing and Materials takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, 100 Barr Harbor Drive, West Conshohocken, PA 19428.