



Designation: A 3 – 87 (Reapproved 1995)

Standard Specification for Steel Joint Bars, Low, Medium, and High Carbon (Non-Heat-Treated)¹

This standard is issued under the fixed designation A 3; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

1. Scope

1.1 This specification covers steel joint bars for connecting steel rails in mine, industrial, and standard railroad track.

1.2 Three grades of joint bars are defined for applications where non-heat treated bars are suitable:

1.2.1 Grade 1, low-carbon, primarily for industrial and mine use.

1.2.2 Grade 2, medium-carbon, primarily for industrial and mine use.

1.2.3 Grade 3, high-carbon, for general use in standard railroad track. They may be used in the production of insulated track joints.

1.3 The values stated in inch-pound units are to be regarded as the standard. The values given in parentheses are for information only.

2. Referenced Documents

2.1 ASTM Standards:

A 370 Test Methods and Definitions for Mechanical Testing of Steel Products²

2.2 U.S. Military Standards:

MIL-STD-129 Marking for Shipment and Storage³

MIL-STD-163 Steel Mill Products, Preparation for Shipment and Storage³

2.3 U.S. Federal Standards:

Federal Standard No. 123 Marking for Shipments (Civil Agencies)³

3. Ordering Information

3.1 Orders for joint bars under this specification shall include the following information as appropriate:

3.1.1 *Quantity*—number of pairs of bars,

3.1.2 *Type*—design or type bar along with section designation and weight of rails being joined,

3.1.3 *Grade*—in accordance with 1.2 and Table 1 and Table 2,

3.1.4 *Dimension*—overall length,

3.1.5 *Punching*—type (elliptical, oval, round, or combinations), size, number, location, spacing, and elevation of punched holes, with dimensional drawing if necessary,

3.1.6 *Special Requirements*—notching, shearing, bundling, etc., including details, and

3.1.7 *Certification and Test Report Requirements*—(See 11.1 and 12.1).

4. Manufacture

4.1 The steel shall be made by one or more of the following processes: open-hearth, basic-oxygen, or electric-furnace.

4.1.1 The steel may be cast by a continuous process, or in ingots.

4.2 Grade 2, medium-carbon, joint bars may be punched, slotted, and shaped in the case of special designs, either hot or cold. Joint bars that are punched, slotted, or shaped cold shall be subsequently annealed.

4.3 Grade 3, high-carbon, joint bars shall be uniformly heated for punching, slotting, and shaping.

5. Chemical Requirements

5.1 The steel shall conform to the requirements as to chemical composition prescribed in Table 1.

5.2 *Heat or Cast Analysis*—An analysis of each heat or cast shall be made by the manufacturer to determine the percentages of carbon, manganese, phosphorus, and sulfur. The analysis shall be made from a test sample taken preferably during the pouring of the heat or cast. The chemical composition thus determined shall conform to the requirement in Table 1. Manganese and sulfur determinations are for information only.

5.3 *Product Analysis*—When ladle tests are not available, finished material representing the heat may be product tested. The product analysis allowance beyond the limits of the specified ladle analysis shall be within the limits for product analyses specified in Table 2.

5.3.1 An analysis may be made by the purchaser from a sample taken from a finished joint bar representing each heat or cast. The chemical composition thus determined shall conform

¹ This specification is under the jurisdiction of ASTM Committee A-1 on Steel, Stainless Steel and Related Alloys, and is the direct responsibility of Subcommittee A01.01 on Steel Rails and Accessories.

Current edition approved July 31, 1987. Published August 1987. Originally published as A3 – 1901. Last previous edition A3 – 78.

² *Annual Book of ASTM Standards*, Vol 01.03.

³ Available from Naval Publications and Forms Center, 5801 Tabor Ave., Philadelphia PA 19120.



TABLE 1 Chemical Requirements

Elements	Composition, %		
	Grade 1	Grade 2	Grade 3
Carbon, min	...	0.30	0.45
Phosphorus, max	0.05	0.05	0.04

TABLE 2 Product Analysis

	Allowance Beyond Limits of Specified Chemical Analysis	
	Percent under min limit	Percent over max limit
Carbon	0.04	0.04
Phosphorus	...	0.008

to the requirements in Table 1.

6. Tensile Requirements

6.1 *Properties*—The material as represented by a tension test specimen shall conform to the tensile properties prescribed in Table 3.

6.2 *Test Specimen*—The tension test specimen shall be taken from the middle of the head at the center of a finished joint bar, and shall be machined to the form and dimensions for a standard round tension test specimen with 2-in. or (50- mm) gage length, as described in Test Methods and Definitions A 370.

6.3 *Number of Tests*—One tension test shall be made from each heat or cast of steel.

6.4 *Retests*—If the results of the tension test of any test lot do not conform to the requirements specified, the manufacturer may rework such lot not more than twice, in which case two additional tension tests shall be made from such lot, and both shall conform to the requirements specified in Table 2.

7. Dimensions and Permissible Variations

7.1 The joint bars shall be true to template, and shall accurately fit the rails for which they are intended.

7.2 The joint bars shall be either sheared or sawed to length, punched to the dimensions specified by the purchaser and alignment adjusted, all subject to the permissible variations prescribed in 7.3, 7.4, and Table 4.

7.3 Any variation from a straight line in a vertical plane shall be such as will make the bars high in the center.

TABLE 3 Tensile Requirements

	Grade 1		Grade 2		Grade 3	
	ksi	MPa	ksi	MPa	ksi	MPa
Tensile strength, min	55	380	68	470	85	585
Elongation in 2 in. or 50 mm, min	22		20		15	

7.4 For girder rail applications only, any variation from a straight line in a horizontal plane shall be such as will make the bars convex towards the web of the rail.

8. Workmanship, Finish, and Appearance

8.1 The joint bars shall be straight, subject to the variations prescribed in 7.3, 7.4, and Table 4.

8.2 The general appearance with respect to soundness and surface finish shall be consistent with good commercial practice as determined by visual inspection.

9. Inspection

9.1 The manufacturer shall afford the purchaser’s inspector all reasonable facilities necessary to satisfy that the material is being produced and furnished in accordance with this specification. Mill inspection by the purchaser shall not interfere unnecessarily with the manufacturer’s operations. All tests and inspections shall be made at the place of manufacture, unless otherwise agreed upon.

10. Rejection and Rehearing

10.1 Material that fails to conform to the requirements of this specification may be rejected. Rejections shall be reported to the manufacturer or supplier promptly and in writing. In case of dissatisfaction with the test results, the manufacturer or supplier may make claim for a rehearing.

11. Certification

11.1 When specified in the purchase order or contract, a manufacturer’s certification shall be furnished to the purchaser that the material was produced and tested in accordance with this specification and has been found to meet the requirements.

11.2 When specified in the purchase order or contract, a report of the chemical and mechanical test results shall be furnished.

12. Product Marking

12.1 The name or brand of the manufacturer and the year of manufacture shall be rolled in raised letters and figures on the side of the rolled bars, and a portion of this marking shall appear on each finished joint bar.

12.2 In addition to the markings in 12.1, the following markings shall appear on Grade 3, high-carbon joint bars:

12.2.1 The section designation shall be included with the rolled raised characters.

12.2.2 A serial number representing the heat or cast shall be hot-stamped on the outside of the web of each bar, near one end.

13. U.S. Government Procurement

13.1 When specified in the contract or purchase order, material shall be preserved, packaged, and packed in accordance with the requirements of MIL-STD-163. The applicable levels shall be as specified in the contract or order. Marking for shipment of such material shall be in accordance with Fed. Std. No. 123 for civil agencies and MIL-STD-129 for military agencies.



TABLE 4 Permissible Variations in Dimensions

Specified size of holes		$\pm 1/32$ in. (0.8 mm)
Specified location of holes		$\pm 1/16$ in. (1.6 mm)
Specified length of bar		$\pm 1/8$ in. (3.2 mm)
Maximum camber in either plane—tee rail applications (see 7.3)		
	Grades 1, 2	Grade 3
24-in. (610-mm) bars	$1/16$ in. (1.6 mm)	$1/32$ in. (0.8 mm)
36-in. (914-mm) bars	$1/8$ in. (3.2 mm)	$1/16$ in. (1.6 mm)
Maximum vertical camber-girder rail applications (see 7.3) (Grades 1 and 2 only)		
24-in. (610-mm) bars	$3/64$ in. (1.2 mm)	
36-in. (914-mm) bars	$3/32$ in. (2.4 mm)	
Maximum horizontal camber-girder rail applications (see 7.4) (Grades 1 and 2 only)		
24-in. (610-mm) bars	$1/16$ in. (1.6 mm)	
36-in. (914-mm) bars	$1/8$ in. (3.2 mm)	

The American Society for Testing and Materials takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, 100 Barr Harbor Drive, West Conshohocken, PA 19428.

This standard is copyrighted by ASTM, 100 Barr Harbor Drive, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (<http://www.astm.org>).