



Standard Specification for Steel Screw Spikes¹

This standard is issued under the fixed designation A 66; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

1. Scope

1.1 This specification covers steel screw spikes used as fastenings between railroad rails, tie plates, and ties.

1.2 Supplementary Requirement S1 specifying copper content is provided. It shall apply only when specified by the purchaser.

1.3 The values stated in inch-pound units are to be regarded as the standard.

2. Referenced Documents

2.1 ASTM Standards:

A 370 Test Methods and Definitions for Mechanical Testing of Steel Products²

A 700 Practices for Packaging, Marking, and Loading Methods for Steel Products for Domestic Shipment³

3. Ordering Information

3.1 Orders for screw spikes under this specification shall include the following information as appropriate:

3.1.1 *Quantity* (weight),

3.1.2 *Style of Head*—A, B, or C⁴ or other, including drawings if necessary,

3.1.3 *Type of Point*—pilot point or not pointed,

3.1.4 *Dimensions*—diameter and length, under head,

3.1.5 *Supplementary Requirement* if to apply (see S1)

3.1.6 *Certification and Test Report* (see 11.1).

4. Manufacture

4.1 The steel shall be made by any of the following processes: electric-furnace or basic-oxygen.

4.2 The steel may be cast by a continuous process, or in ingots.

4.3 The heads and threads of the spikes may be formed by hot- or cold-forming methods.

5. Mechanical Requirements

5.1 Tensile Requirements:

5.1.1 The material as represented by a tension test of a full-size finished spike, or a specimen machined from a finished spike, shall conform to the requirements prescribed in Table 1.

5.1.2 Tension tests of full-size spikes shall be performed using a 10° wedge as described in Test Methods A 370, Supplement S11.1.5.

5.1.3 Where the design of the spike is such that full-size testing is impracticable, the tension test may be made on a specimen machined from a finished spike. Dimensions of the test specimen shall conform to the requirements of Test Methods A 370.

5.1.4 When a machined specimen test is performed, the elongation requirement prescribed in Table 1 shall apply.

5.1.5 The yield point shall be determined by the drop of the beam or halt in the gage of the testing machine.

5.2 *Bend Requirement*—The body of a full-size finished spike shall withstand the bend test described in Table 2 without cracking on the outside of the bent portion.

6. Dimensions and Permissible Variations

6.1 The finished spikes shall conform to the dimensions specified by the purchaser, subject to the permissible variations prescribed in Table 3.

6.2 The threads shall be sharp and true to gage and of the design specified by the purchaser.

7. Workmanship, Finish, and Appearance

7.1 The head of the finished spikes shall be concentric with and firmly joined to the body.

7.2 The material shall be free of injurious imperfections and shall have a workmanlike finish.

8. Number of Tests and Retests

8.1 One tension test and one bend test shall be made from each lot of 100 kegs or fraction thereof.

8.2 If the percentage of elongation of a machined tension test specimen is less than that specified in Table 1 and any part of the fracture is more than $\frac{3}{4}$ in. (19 mm) from the center of

¹ This specification is under the jurisdiction of ASTM Committee A01 on Steel, Stainless Steel and Related Alloys, and is the direct responsibility of Subcommittee A01.01 on Steel Rails and Accessories.

Current edition approved April 10, 2001. Published May 2001. Originally published as A 66 – 16 T. Last previous edition A 66 – 87 (1995).

² *Annual Book of ASTM Standards*, Vol 01.03.

³ *Annual Book of ASTM Standards*, Vol 01.05.

⁴ Consult manufacturer's literature for design details for A, B, and C-style heads.

TABLE 1 Tension Test Requirements

	Specimen	
	Full size	Machined
Tensile strength, min, psi (MPa)	60 000 (415)	60 000 (415)
Yield point, min	0.5 × tensile strength	0.5 × tensile strength
Elongation in 2 in. or 50 mm, min, %	...	18

TABLE 2 Bend Test Requirement

Body bend, cold	90°—around pin 3 times spike diameter
-----------------	---------------------------------------

TABLE 3 Permissible Variations in Dimensions

	Over		Under	
	in.	mm	in.	mm
Diameter, unthreaded portion	1/32	0.8
Diameter, threaded portion	1/32	0.8
Reach of head	1/8	3.2	1/16	1.6
Width across flats	0	0.0	1/32	0.8
Length	1/8	3.2	1/8	3.2

the gage length, as indicated by scribe scratches marked on the specimen before testing, a retest shall be allowed.

8.3 If, during the tension or bend tests, a previously undiscovered material or manufacturing flaw should be disclosed that interferes with the test or the interpretation of results, the substitution of another sample spike shall be permitted after it is demonstrated to the satisfaction of the purchaser or his representative, that the condition is not typical of the remainder of the lot.

8.4 If any test specimen fails because of mechanical reasons such as failure of testing equipment or improper specimen preparation, it may be discarded and another specimen taken.

9. Inspection

9.1 The manufacturer shall afford the purchaser's inspector all reasonable facilities necessary to satisfy that the material is being produced and furnished in accordance with the specification. Mill inspection by the purchaser shall not interfere unnecessarily with the manufacturer's operations. All tests and inspections shall be made at the place of manufacture, unless otherwise agreed upon.

10. Rejection and Rehearing

10.1 Material that fails to conform to the requirements of this specification may be rejected. Rejections shall be reported to the manufacturer or supplier promptly and in writing. In case of dissatisfaction with the test results, the manufacturer or supplier may make claim for a rehearing.

11. Certification and Test Report

11.1 When specified in the purchaser order or contract, a manufacturer's certification shall be furnished to the purchaser that the material was produced and tested in accordance with this specification and has been found to meet the requirements.

11.2 When specified in the purchase order or contract, a report of the chemical and mechanical test results shall be furnished.

11.3 A Material Test Report, Certificate of Inspection, or similar document printed from or used in electronic form from an electronic data interchange (EDI) transmission shall be regarded as having the same validity as a counterpart printed in the certifier's facility. The content of the EDI transmitted document must meet the requirements of the invoked ASTM standard(s) and conform to any existing EDI agreement between the purchaser and the supplier.

11.4 Notwithstanding the absence of a signature, the organization submitting either a printed document (Material Test Report, Certificate of Inspection or similar document) or an EDI transmission is responsible for the content of the report.

12. Product Marking

12.1 The manufacturer's symbol shall appear on the head of the spike.

12.2 Bar Coding:

12.2.1 The Automotive Industry Action Group (AIAG) Bar Code Standard for Primary Metals for Steel Products may be considered as a possible auxiliary method of identification on the containers. Use of this method shall be by agreement between purchaser and supplier.

13. U. S. Government Procurement

13.1 When specified in the contract or purchase order, material shall be prepared for shipment and storage in accordance with the requirements of Practices A 700.

14. Keywords

14.1 rails; railway applications; steel screw spikes; track spikes

SUPPLEMENTARY REQUIREMENTS

The following supplementary requirement shall apply only when specified by the purchaser in the inquiry, contract, and order.

S1. Copper may be specified to a minimum of 0.20 %.

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).