



Designation: F 467M – 01

METRIC

## Standard Specification for Nonferrous Nuts for General Use [Metric]<sup>1</sup>

This standard is issued under the fixed designation F 467M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

*This standard has been approved for use by agencies of the Department of Defense.*

### 1. Scope

1.1 This specification covers the requirements for commercial wrought nonferrous nuts in nominal thread diameters M6 to M36 inclusive in a number of alloys in common use and intended for general service applications.

1.2 Applicable bolts, cap screws, and studs for use with nuts covered by this specification are covered by Specification F 468M.

NOTE 1—This specification is the metric companion of Specification F 467.

### 2. Referenced Documents

#### 2.1 ASTM Standards:

- B 154 Test Method for Mercurous Nitrate Test for Copper and Copper Alloys<sup>2</sup>
- D 3951 Practice for Commercial Packaging<sup>3</sup>
- E 18 Test Methods for Rockwell Hardness and Rockwell Superficial Hardness of Metallic Materials<sup>4</sup>
- E 29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications<sup>5</sup>
- E 34 Test Methods for Chemical Analysis of Aluminum and Aluminum Base Alloys<sup>6</sup>
- E 38 Methods for Chemical Analysis of Nickel-Chromium and Nickel-Chromium-Iron Alloys<sup>7</sup>
- E 53 Test Methods for Chemical Analysis of Copper<sup>6</sup>
- E 54 Test Methods for Chemical Analysis of Special Brasses and Bronzes<sup>6</sup>
- E 55 Practice for Sampling Wrought Nonferrous Metals and Alloys for Determination of Chemical Composition<sup>6</sup>

- E 62 Test Methods for Chemical Analysis of Copper and Copper Alloys (Photometric Methods)<sup>6</sup>
  - E 75 Test Methods for Chemical Analysis of Copper-Nickel and Copper-Nickel-Zinc Alloys<sup>6</sup>
  - E 76 Test Methods for Chemical Analysis of Nickel-Copper Alloys<sup>6</sup>
  - E 92 Test Method for Vickers Hardness of Metallic Materials<sup>4</sup>
  - E 101 Test Method for Spectrographic Analysis of Aluminum and Aluminum Alloys by the Point-to-Plane Technique<sup>8</sup>
  - E 120 Test Methods for Chemical Analysis of Titanium and Titanium Alloys<sup>6</sup>
  - E 165 Practice for Liquid Penetrant Inspection Method<sup>9</sup>
  - E 227 Test Method for Optical Emission Spectrometric Analysis of Aluminum and Aluminum Alloys by the Point-to-Plane Technique<sup>6</sup>
  - E 354 Test Methods for Chemical Analysis of High-Temperature, Electrical, Magnetic, and Other Similar Iron, Nickel, and Cobalt Alloys<sup>6</sup>
  - E 478 Test Methods for Chemical Analysis of Copper Alloys<sup>6</sup>
  - E 1409 Test Method for Determination of Oxygen in Titanium and Titanium Alloys by the Inert Gas Fusion Technique<sup>6</sup>
  - F 468M Specification for Nonferrous Bolts, Hex Cap Screws, and Studs for General Use [Metric]<sup>10</sup>
  - F 606M Test Methods for Determining the Mechanical Properties of Externally and Internally Threaded Fasteners, Washers, and Rivets [Metric]<sup>10</sup>
  - F 1470 Guide for Fastener Sampling for Specified Mechanical Properties and Performance Inspection<sup>10</sup>
- #### 2.2 ANSI Standards:

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee F16 on Fasteners and is the direct responsibility of Subcommittee F16.04 on Nonferrous Fasteners.

Current edition approved Apr. 10, 2001. Published June 2001. Originally published as F 467M – 79. Last previous edition F 467M – 98.

<sup>2</sup> Annual Book of ASTM Standards, Vol 02.01.

<sup>3</sup> Annual Book of ASTM Standards, Vol 15.09.

<sup>4</sup> Annual Book of ASTM Standards, Vol 03.01.

<sup>5</sup> Annual Book of ASTM Standards, Vol 14.02.

<sup>6</sup> Annual Book of ASTM Standards, Vol 03.05.

<sup>7</sup> Discontinued 1989; Replaced by E 350.

<sup>8</sup> Discontinued; see 1995 Annual Book of ASTM Standards, Vol 03.05.

<sup>9</sup> Annual Book of ASTM Standards, Vol 03.03.

<sup>10</sup> Annual Book of ASTM Standards, Vol 01.08.

B 1.13M Metric Screw Threads<sup>11</sup>

B 18.2.4.1M Metric Hex Nuts, Style 1<sup>11</sup>

### 3. Ordering Information

3.1 Orders for nuts under this specification shall include the following information:

- 3.1.1 Quantity (numbers of pieces of each item and size),
- 3.1.2 Name of item,
- 3.1.3 Nominal thread diameter and thread pitch,
- 3.1.4 Alloy number (Table 1),
- 3.1.5 Stress relieving, if required (4.2.3),
- 3.1.6 “Shipment lot” testing, as required (Section 9),
- 3.1.7 Source inspection, if required (Section 14),
- 3.1.8 Certificate of compliance or test report, if required (Section 16),
- 3.1.9 Additional requirements, if any, to be specified on the purchase order (4.2.1, 7.2, 8.2, 11.1, and 12.1),
- 3.1.10 Supplementary requirements, if any, and
- 3.1.11 ASTM specification and year of issue.

NOTE 2—A typical ordering description is as follows: 10 000 pieces, Hex Nut, M8 × 1.25 Alloy 270, Furnish Certificate of Compliance, Supplementary Requirement S1, ASTM Specification F 467M – XX.

### 4. Materials and Manufacture

#### 4.1 Materials:

4.1.1 The nuts shall be manufactured from material having a chemical composition conforming to the requirements in Table 1 and capable of developing the required mechanical properties for the specified alloy in the nut.

4.1.2 The starting condition of the raw material shall be at the discretion of the fastener manufacturer but shall be such that the nuts conform to all the specified requirements.

#### 4.2 Manufacture:

4.2.1 *Forming*—Unless otherwise specified, the nuts shall be hot pressed, cold formed, or machined from suitable

material at the option of the manufacturer.

4.2.2 *Condition*—Except as provided in 4.2.3, the nuts shall be furnished in the condition specified below:

Alloy	Condition
Copper (all alloys)	As formed or stress relieved at manufacturer’s option
Nickel alloys 400 and 405	As formed or stress relieved at manufacturer’s option
Nickel alloy 500	Solution annealed and aged
Aluminum alloys:	
2024-T4	Solution treated and naturally aged
6061-T6	Solution treated and artificially aged
6262-T9	Solution treated, artificially aged, and cold worked
Titanium	As formed

4.2.3 *Stress Relieving*—When required, stress relieving shall be specified by the purchaser for all copper alloys and nickel alloys 400 and 405.

### 5. Chemical Composition

5.1 *Chemical Composition*—The nuts shall conform to the chemical composition specified in Table 1 for the specified alloy.

#### 5.2 Manufacturer’s Analysis:

5.2.1 Except as provided in 5.2.2, when test reports are required on the inquiry or purchase order (3.1.8), the manufacturer shall make individual analyses of randomly selected nuts from the product to be shipped and report the results to the purchaser. Alternatively, if heat and lot identities have been maintained, the analysis of the raw material from which the nuts have been manufactured may be reported instead of product analysis.

5.2.2 For aluminum nuts, instead of 5.2.1, the manufacturer may furnish a certificate of conformance certifying compliance with the chemical composition specified in Table 1.

#### 5.3 Product Analysis:

5.3.1 Product analyses may be made by the purchaser from nuts representing each lot. The chemical composition thus determined shall conform to the requirements in Table 1.

5.3.2 In the event of disagreement, a referee chemical analysis of samples from each lot shall be made in accordance with 11.1 and 12.1.

<sup>11</sup> Available from American National Standards Institute, 11 West 42nd Street, 13th Floor, New York, NY 10036.

**TABLE 1 Chemical Requirements**

UNS Designation Number	Alloy	General Name	Composition, %														
			Aluminum	Copper, min	Iron, max	Manganese, max	Nickel, max	Phosphorus	Silicon	Zinc, max <sup>A</sup>	Lead, max	Tin	Arsenic, max				
C11000	110	ETP copper		99.9													
C27000	270	brass		63.0–68.5	0.07								balance	0.10			
C46200	462	naval brass		62.0–65.0	0.10								balance	0.20	0.5–1.0		
C46400	464	naval brass		59.0–62.0	0.10								balance	0.20	0.5–1.0		
C51000	510	phosphor bronze		balance <sup>A</sup>	0.10								0.30	0.05	4.2–5.8		
C61400	614	aluminum bronze	6.0–8.0	88.0 <sup>B</sup>	1.5–3.5	1.0											
C63000	630	aluminum bronze	9.0–11.0	78.0 <sup>B</sup>	2.0–4.0	1.5											
C64200	642	aluminum silicon bronze	6.3–7.6	88.65 <sup>B</sup>	0.30	0.10		4.0–5.5					0.50	0.05	0.20 max		0.15
C65100	651	silicon bronze		96.0 <sup>B</sup>	0.8	0.7		0.25					1.5	0.05	0.20 max		
C65500	655	silicon bronze		94.8 <sup>B</sup>	0.8	1.5		0.6					1.5	0.05			
C66100	661	silicon bronze		94.0 <sup>B</sup>	0.25	1.5							1.5	0.05			
C67500	675	manganese bronze	0.25 max	57.0–60.0	0.8–2.0	0.05–0.5		19.0–23.0 <sup>A</sup>					balance	0.20	0.5–1.5		
C71000	710	cupro-nickel		74.0 <sup>B</sup>	0.60	1.00		29.0–33.0 <sup>A</sup>					1.00	0.05			
C71500	715	cupro-nickel		65.0 <sup>B</sup>	0.40–0.7	1.00							1.00	0.05			

<sup>A</sup> Elements shown as balance shall be arithmetically computed by deducting the sum of the other named elements from 100.

<sup>B</sup> Minimum content of copper plus all other elements with specified limits shall be 99.5 %.

<sup>C</sup> An alloy containing as high as 2.6 % silicon is acceptable provided the sum of all the elements other than copper, silicon, and iron does not exceed 0.30 %.

**TABLE 1 Continued**  
Nickel and Nickel-Base Alloys

UNS Designation Number	Alloy	General Name	Aluminum	Carbon, max	Chromium	Copper <sup>A</sup>	Iron, max	Manganese, max	Nickel <sup>A</sup>	Phosphorus, max	Silicon, max	Titanium	Cobalt, max	Molybdenum	Sulfur, max	Vanadium	Tungsten
N10001	335	Ni-Mo		0.05	1.0 max		4.0–6.0	1.0	balance	0.025	1.00		2.50	26.0–30.0	0.030	0.2–0.4	3.0–4.5
N10276	276	Ni-Mo-Cr		0.02	14.5–16.5		4.0–7.0	1.00	balance	0.040	0.08		2.50	15.0–17.0	0.030	0.35 max	
N04400	400	Ni-Cu Class A		0.3		balance	2.5	2.0	63.0–70.0		0.5		<sup>B</sup>		0.024		
N04405	405	Ni-Cu Class B		0.3		balance	2.5	2.0	63.0–70.0		0.5		<sup>B</sup>		0.025–0.060		
N05500	500	Ni-Cu-Al	2.30–3.15	0.25		balance	2.0	1.5	63.0–70.0		0.5	0.35–0.85	<sup>B</sup>		0.01		
N06686	686	Ni-Cr-Mo-W	19.0–23.0	0.010 max			5.0 max	0.75 max	balance	0.04 max	0.08 max	0.02–0.25		15.0–17.0	0.02 max		3.0–4.4

<sup>A</sup>Elements shown as balance shall be arithmetically computed by deducting the sum of the other named elements from 100.

<sup>B</sup> Cobalt is to be counted as nickel.

TABLE 1 Continued

Composition, %													
Aluminum-Base Alloys <sup>A</sup>													
UNS Designation Number	Alloy	General Name	Aluminum <sup>A</sup>	Chromium	Copper	Iron, max	Manganese, max	Silicon, max	Titanium, max	Zinc, max	Magnesium	Other Elements, max	
												Each	Total
A92024	2024	Aluminum 2024	balance	0.10 max	3.8-4.9	0.50	0.30-0.9	0.50	0.15 <sup>B</sup>	0.25	1.2-1.8	0.05	0.15
A96061	6061	Aluminum 6061	balance	0.04-0.35	0.15-0.40	0.7	0.15	0.40-0.8	0.15	0.25	0.8-1.2	0.05	0.15
A96262	6262	Aluminum 6262	balance	0.04-0.14	0.15-0.40	0.7	0.15	0.40-0.8	0.15	0.25	0.8-1.2	<sup>C</sup>	

<sup>A</sup> Analysis shall regularly be made only for the elements specified in this table. If, however, the presence of other elements is suspected or indicated in amounts greater than the specified limits, further analysis shall be made to determine that these elements are not present in excess of the specified limits.

<sup>B</sup> Titanium + zirconium 0.20 % max.

<sup>C</sup> Lead 0.4-0.7 %; bismuth 0.4-0.7 %.

TABLE 1 Continued

UNS Designation Number	Alloy	General Name	Aluminum, Al	Carbon, C	Iron, Fe	Titanium, Ti	Hydrogen, H	Nitrogen, N	Oxygen, O	Palladium, Pd	Vanadium, V	Chromium, Cr	Molybdenum, Mo	Zirconium, Zr	Tin, Sn	Silicon, Si	Ruthenium, Ru	Residuals <sup>B</sup>	
																		each, max	total, max
R50250	1	Titanium Gr 1		0.10	0.20	balance	0.0125	0.05	0.18									0.1	0.4
R50400	2	Titanium Gr 2		0.10	0.30	balance	0.0125	0.05	0.25									0.1	0.4
R50700	4	Titanium Gr 4		0.10	0.50	balance	0.0125	0.07	0.40									0.1	0.4
R56400	5	Titanium Gr 5	5.5–6.75	0.10	0.40	balance	0.0125	0.05	0.20		3.5–4.5							0.1	0.4
R56401	23	Titanium Ti-6Al-4V ELI	5.5–6.5	0.08	0.25	balance	0.0125	0.05	0.13		3.5–4.5							0.1	0.4
R52400	7	Titanium Gr 7		0.10	0.30	balance	0.0125	0.05	0.25									0.1	0.4
R58640	19	Titanium Ti-38-6-44	3.0–4.0	0.05	0.30	balance	0.0200	0.03	0.12	0.12–0.25	7.5–8.5	5.5–6.5	3.5–4.5	3.5–4.5			0.10 <sup>B</sup>	0.15	0.4
R55111	32	Titanium Ti-5-1-1-1	4.5–5.5	0.08	0.25	balance	0.0125	0.03	0.11	0.10 <sup>C</sup>	0.6–1.4		0.6–1.2	0.6–1.4	0.6–1.4	0.06–0.14		0.1	0.4

<sup>A</sup> All reported values are maximums, unless a range is specified.

<sup>B</sup> A residual is an element present in a metal or an alloy in small quantities inherent to the manufacturing process but not added intentionally. Residual elements need not be reported unless a report is specifically required by the purchaser.

<sup>C</sup> Ruthenium and Palladium, or both, may be added to Grade 19 for enhanced corrosion resistance as negotiated between purchaser and vendor. Chemical analysis is not required unless specifically negotiated.

## 6. Mechanical Properties

6.1 The nuts shall be tested in accordance with the mechanical testing requirements for the applicable type and shall meet the mechanical requirements in Table 2 for the specified alloy.

6.2 Where both proof load and hardness tests are performed, the proof load test results shall take precedence for acceptance purposes.

## 7. Dimensions

7.1 *Nuts*—Unless otherwise specified, the dimensions of nuts shall be in accordance with the requirements of ANSI B18.2.4.1M.

7.2 *Threads*—Unless otherwise specified, the nuts shall have threads in accordance with ANSI B1.13M, tolerance Class 6H.

## 8. Workmanship, Finish, and Appearance

8.1 *Workmanship*—Nuts shall have a workmanlike finish free of injurious burrs, seams, laps, irregular surfaces, and other imperfections affecting serviceability.

8.2 *Finish*—Unless otherwise specified, the nuts shall be furnished without any additive chemical or metallic finish.

## 9. Sampling

9.1 A lot, for the purposes of selecting test specimens, shall consist of not more than 100 000 pieces offered for inspection at one time having the following common characteristics:

9.1.1 One type of item,

9.1.2 Same alloy and temper, and

9.1.3 One nominal diameter and thread pitch.

## 10. Number of Tests and Retests

10.1 *Normal Testing*—The requirements of this specification shall be met in continuous mass production for stock (see Table 3). The manufacturer shall make sample inspections as specified below to ensure that the product conforms to the specified requirements. When tests of individual shipments are required, Supplementary Requirement S1 shall be specified.

Number of Pieces in lot	No. of Tests	Acceptance Criteria	
		Acceptance No.	Rejection No.
50 and under	2	0	1
51 to 500	3	0	1
501 to 35 000	5	0	1
35 001 to 100 000	8	0	1

### 10.2 Retests:

10.2.1 When tested in accordance with the required sampling plan, a lot shall be subject to rejection if any of the test specimens fails to meet the applicable test requirements.

10.2.2 If the failure of a test specimen is due to improper preparation of the specimen or to incorrect testing technique, the specimen shall be discarded and another specimen substituted.

## 11. Significance of Numerical Limits

11.1 For purposes of determining compliance with the specified limits for requirements of the properties listed in this specification, an observed value or calculated value shall be rounded in accordance with Practice E 29.

## 12. Test Specimens

12.1 *Chemical Tests*—When required, samples for chemical analysis shall be taken in accordance with Practice E 55 by drilling, sawing, milling, turning, clipping, or such other methods capable of producing representative samples.

### 12.2 Mechanical Tests :

12.2.1 Nuts shall be proof load tested in full section.

12.2.2 The hardness shall be determined on the top or bottom face of the nut.

## 13. Test Methods

13.1 *Chemical Analysis*—When required, the chemical composition shall be determined by any recognized commercial test method. In the event of disagreement, the following test methods shall be used for referee purposes.

**TABLE 2 Mechanical Property Requirements**

Alloy	Mechanical Property Marking	Hardness, min <sup>A</sup>	Proof Stress, MPa
Cu 110	F 467MA	65 HRF	205
Cu 270	F 467MB	55 HRF	415
Cu 462	F 467MC	65 HRB	345
Cu 464	F 467MD	55 HRB	345
Cu 510	F 467ME	60 HRB	415
Cu 614	F 467MG	70 HRB	520
Cu 630	F 467MH	85 HRB	690
Cu 642	F 467MJ	75 HRB	520
Cu 651	F 467MK	75 HRB	485
Cu 655	F 467ML	60 HRB	345
Cu 661	F 467MM	75 HRB	485
Cu 675	F 467MN	60 HRB	380
Cu 710	F 467MP	50 HRB	310
Cu 715	F 467MR	60 HRB	380
Ni 335	F 467MS	20 HRC	790
Ni 276	F 467MT	20 HRC	760
Ni 400	F 467MU	75 HRB	550
Ni 405	F 467MV	60 HRB	485
Ni 500	F 467MW	24 HRC	900
Ni 686	F 467MBN	23 HRC	790
Al 2024-T4 <sup>B</sup>	F 467MX	70 HRB	380
Al 6061-T6	F 467MY	40 HRB	275
Al 6262-T9	F 467MZ	60 HRB	360
Ti 1	F 467MAT	140 HV	275
Ti 2	F 467MBT	150 HV	380
Ti 4	F 467MCT	200 HV	585
Ti 5	F 467MDT	30 HRC	930
Ti 7	F 467MET	160 HV	380
Ti 19	F 467MFT	24 HRC	825
Ti 23	F 467MGT	25 HRC	860
Ti-5-1-1-1	F 467MHT	24 HRC	725

<sup>A</sup> For aluminum and titanium alloys hardness values are for information only.

<sup>B</sup> Aluminum alloy 2024-T4 shall be supplied in naturally aged condition. This material is not recommended for nuts in nominal thread diameter larger than M6.

**TABLE 3 Mechanical Test Requirements on Nuts**

Product	Proof Load, kN <sup>A</sup>	Tests Conducted Using Full-Size Product	
		Hardness	Proof Load
Jam, slotted, and castle nuts	all	<sup>B</sup>	...
	up to 530	...	<sup>B</sup>
All other nuts	over 530	<sup>B</sup>	...
Tests in accordance with section		11.2.2	12.2.1

<sup>A</sup> Proof load of nut equals proof stress (MPa) multiplied by stress area (mm<sup>2</sup>).

<sup>B</sup> Mandatory tests.

Alloy	Test Method
Copper	E 53, E 54, E 62, E 75, E 478
Aluminum	E 34, E 101, E 227
Nickel	E 38, E 76, E 354
Titanium	E 120, E 1409

### 13.2 Mechanical :

13.2.1 The proof load test shall be conducted in accordance with the appropriate methods of Test Methods F 606M. Loads to be determined using Table 2 and Table 4.

13.2.2 The hardness shall be determined in accordance with Test Methods E 18 and E 92. For nominal thread diameters M6 to M10, one reading shall be taken. For diameters M12 and larger, the hardness shall be the average of four readings located 90° to one another.

## 14. Inspection

14.1 When specified on the inquiry or purchase order, the product shall be subject to inspection by the purchaser at the place of manufacture prior to shipment. The inspector representing the purchaser shall have controlled entry only to those parts of the manufacturer's operations that concern the manufacture of the ordered product and only when and where work on the contract of the purchaser is being performed. The manufacturer shall afford the inspector all reasonable facilities to satisfy him that the product is being furnished in accordance with this specification. All inspections and tests shall be conducted so as not to interfere unnecessarily with the operations of the manufacturer.

**TABLE 4 Tensile Stress Areas**

Nominal Nut Diameter and Thread Pitch	Stress Area, <sup>A</sup> mm <sup>2</sup>	Nominal Nut Diameter and Thread Pitch	Stress Area, <sup>A</sup> mm <sup>2</sup>
M6 × 1	20.1	M16 × 2	157
M8 × 1.25	36.6	M20 × 2.5	245
M10 × 1.5	58.0	M24 × 3	353
M12 × 1.75	84.3	M30 × 3.5	561
M14 × 2	115	M36 × 4	817

<sup>A</sup> Tensile stress areas are computed using the following formula:  
 $A_s = 0.7854 (D - 0.9382P)^2$

where:

- $A_s$  = stress area, mm<sup>2</sup>,
- $D$  = nominal nut diameter (basic major diameter), mm, and
- $P$  = thread pitch, mm.

## 15. Rejection and Rehearing

15.1 Unless otherwise specified, any rejection based on tests specified herein and made by the purchaser shall be reported to the manufacturer as soon as practical after receipt of the product by the purchaser.

## 16. Certification and Test Reports

16.1 *Certificate of Compliance*—When specified in the contract or purchase order, the manufacturer shall furnish certification that the product was manufactured and tested in accordance with this specification and conforms to all specified requirements.

16.2 *Test Reports*—When “Shipment Lot Testing” in accordance with Supplementary Requirement S2 is specified in the contract or purchase order, the manufacturer shall furnish a test report showing the results of the mechanical tests for each lot shipped.

## 17. Product, Packaging and Package Marking

17.1 *Individual Nuts*—All products shall be marked with a symbol identifying the manufacturer. In addition, they shall be marked with the alloy/mechanical property marking specified in Table 2. The markings shall be raised or depressed at the option of the manufacturer.

### 17.2 Packaging:

17.2.1 Unless otherwise specified packaging shall be in accordance with Practice D 3951.

17.2.2 When special packaging requirements are required by the purchaser, they shall be defined at the time of inquiry and order.

17.3 *Package Marking*—Each shipping unit shall include or be plainly marked with the following:

- 17.3.1 ASTM specification,
- 17.3.2 Alloy number,
- 17.3.3 Alloy/mechanical property marking
- 17.3.4 Size,
- 17.3.5 Name and brand or trademark of the manufacturer,
- 17.3.6 Number of pieces,
- 17.3.7 Country of origin, and
- 17.3.8 Purchase order number.

## 18. Keywords

- 18.1 general use; nonferrous; nuts

## SUPPLEMENTARY REQUIREMENTS

One or more of the following supplementary requirements shall be applied only when specified by the purchaser in the inquiry, contract, or order. Supplementary requirements shall in no way negate any requirement of the specification itself.

### S1. Stress Corrosion Requirements, Copper Alloys

S1.1 Copper alloy nuts shall exhibit no evidence of cracking after immersion for 30 min in an aqueous solution of mercurous nitrate when tested in accordance with Test Method B 154.

S1.1.1 **Caution**—Mercury is a definite health hazard and equipment for the detection and removal of mercury vapor

produced in volatilization is recommended. The use of rubber gloves in testing is advisable.

### S2. Shipment Lot Testing

S2.1 When Supplementary Requirement S2 is specified on the order (3.1.6), the manufacturer shall make sample tests on the individual lots for shipment to ensure that the product conforms to the specified requirements.



S2.2 The manufacturer shall make an analysis of a randomly selected finished nut from each lot of product to be shipped. Heat or lot control shall be maintained. The analysis of the starting material from which the nuts have been manufactured may be reported in place of the product analysis.

S2.3 The manufacturer shall perform mechanical property tests in accordance with this specification and Guide F 1470 on the individual lots for shipment.

S2.4 The manufacturer shall furnish a test report for each lot in the shipment showing the actual results of the chemical analysis and mechanical property tests performed in accordance with Supplementary Requirement S2.

### **S3. Dye Penetrant Inspection**

S3.1 When dye penetrant inspection is specified on the purchase order, the nuts shall be tested in accordance with

Practice E 165 or other mutually acceptable procedures and shall conform to acceptance criteria as mutually agreed upon between the purchaser and the manufacturer.

### **S4. Heat Control (Alloys 400, 405, and 500 Only)**

S4.1 When Supplementary Requirement S4 is specified on the inquiry or order, the manufacturer shall control the product by heat analysis and identify the finished product in each shipment by the actual heat number.

S4.2 When Supplementary Requirement S4 is specified on the inquiry and order, Supplementary Requirement S2 shall be considered automatically invoked with the addition that the heat analysis shall be reported to the purchaser on the test reports.

*The ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.*

*This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.*

*This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website ([www.astm.org](http://www.astm.org)).*