



Standard Test Method for Mercurous Nitrate Test for Copper and Copper Alloys¹

This standard is issued under the fixed designation B 154; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

1. Scope *

1.1 This test method describes the technique for conducting the mercurous nitrate test for residual stresses in wrought copper and cast or wrought copper-based alloy products. This test method is intended to cover the mercurous nitrate test of certain copper-alloy products supplied in accordance with ASTM specifications prepared by Committee B05. This test method is not intended to be used on assembled parts.

NOTE 1—For any particular copper alloy, reference should be made to the material specification.

1.2 *Units*—The values stated in SI units are to be regarded as the standard. The values given in parentheses are for information only.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determines the applicability of regulatory limitations prior to use.* For specific precautionary and hazard statements see Sections 1, 6, and 7. (**Warning**—Mercury is a definite health hazard in use and disposal.)

2. Referenced Documents

2.1 The following documents in the current issue of the Book of Standards form a part of this specification to the extent referenced herein:

2.2 *ASTM Standards:*

B 846 Terminology for Copper and Copper Alloys²

D 1193 Specification for Reagent Water³

3. Terminology

3.1 Definitions of terms related to copper and copper alloys, refer to Terminology B 846.

4. Summary of Test Method

4.1 The prepared test specimen is immersed totally in

mercurous nitrate solution for 30 min at ambient temperature. Upon removal from the solution, the test specimen is washed and immediately examined visually for cracks.

5. Significance and Use

5.1 This test method is an accelerated test for detecting the presence of residual (internal) stresses that might result in failure of individual parts in storage or in service due to stress corrosion cracking. This test method is not intended for assemblies under applied stress. If used for that purpose, the results shall be for information only and not a cause for rejection of the assembly, its component parts, or the original mill product.

6. Reagents and Materials

6.1 *Purity of Reagents*—Reagent grade chemicals shall be used in all tests. Unless otherwise indicated, it is intended that all reagents conform to the specifications of the Committee on Analytical Reagent of the American Chemical Society where such specifications are available.⁴ Other grades may be used, provided it is first ascertained that the reagent is of sufficiently high purity to permit its use without lessening the accuracy of the determination.

6.2 *Purity of Water*—Unless otherwise indicated, references to water shall be understood to mean Type IV reagent water or better, as defined of Specification D 1193.

6.3 *Mercurous Nitrate Solution*—The solution shall be an aqueous mercurous nitrate solution containing 10 g of mercurous nitrate solution (HgNO_3) and 10 mL of nitric acid (HNO_3) (sp gr 1.42) per litre of solution.

6.4 *Preparation*—The aqueous mercurous nitrate solution shall be prepared by either of the following procedures, A or B. Used solutions may be replenished as described in 6.5.

6.4.1 *Procedure A*—Dissolve 11.4 g of $\text{HgNO}_3 \cdot 2\text{H}_2\text{O}$ or 10.7 g of $\text{HgNO}_3 \cdot \text{H}_2\text{O}$ in approximately 40 mL of distilled water acidified with 10 mL of HNO_3 (sp gr 1.42). After the crystals are completely dissolved, dilute the solution with

¹ This test method is under the jurisdiction of ASTM Committee B05 on Copper and Copper Alloys and is the direct responsibility of Subcommittee B05.06 on Methods of Test.

Current edition approved Oct. 10, 2001. Published December 2001. Originally published as B 154 – 41 T. Last previous edition B 154 – 95.

² *Annual Book of ASTM Standards*, Vol 02.01.

³ *Annual Book of ASTM Standards*, Vol 11.01.

⁴ *Reagent Chemicals, American Chemical Society Specifications*, American Chemical Society, Washington, DC. For suggestions on the testing of reagents not listed by the American Chemical Society, see *Analar Standards for Laboratory Chemicals*, BDH Ltd., Poole, Dorset, U.K., and the *United States Pharmacopeia and National Formulary*, U.S. Pharmacopeial Convention, Inc. (USPC), Rockville, MD.

*A Summary of Changes section appears at the end of this standard.



water to 1000 mL. (**Warning**—The mercurous nitrate crystals are obtainable in both the monohydrate and dihydrate form and should be handled with caution because of their highly toxic effects.) (**Warning**—When weighing crystals, the weight of the water of crystallization should be taken into consideration. The mercurous nitrate crystals are photosensitive and when they have turned yellow are difficult to dissolve.) (**Warning**—Care should be exercised when handling and mixing chemicals. Qualified personnel using appropriate chemical-laboratory techniques should only do the handling and mixing.)

6.4.2 *Procedure B*—Dissolve 76 g of mercury in 114 mL of diluted HNO₃ (1 part water to 1 part HNO₃) (sp gr 1.42). Carefully dilute with distilled water to 1000 mL. This provides a concentration of 100 g of HgNO₃ after a slight loss due to heating. Add the water in small portions while stirring to prevent local overdilution. This gradual dilution, together with the excess acid, will prevent precipitation of basic salts of mercury. Dilute 100 mL of this solution (10 %) with 7 mL of HNO₃ (sp gr 1.42) and 893 mL of water. (**Warning**—Mercury is a definite health hazard and therefore equipment for the detection and removal of mercury vapor produced in volatilization is recommended. The use of rubber gloves in testing is advisable.)

6.5 *Replenishment of Solution*—The spent solution may be reclaimed by replenishing the mercurous nitrate solution, to a 1 volume percent concentration, as follows:

6.5.1 Measure 50 mL of the spent HgNO₃ solution in a graduated cylinder.

6.5.2 Transfer to an Erlenmeyer flask, and add 10 mL of HNO₃ (1 + 1).

6.5.3 Add slowly 1 weight per volume percent potassium permanganate (KMnO₄) solution from a buret with a constant shaking until there is an excess as indicated by the pink color, which persists for several minutes.

6.5.4 Add iron (II) sulfate (FeSO₄) crystals until the solution, when shaken, becomes clear. Then titrate the solution with 0.1 N potassium thiocyanate (KCNS) solution to the appearance of a reddish brown color. Repeat this procedure with 50 mL of a standard 1 weight per volume percent of HgNO₃ solution.

6.5.5 The ratio, *R*, of the number of millilitres of KCNS solution required to titrate the spent solution, to the number of millilitres required to titrate the standard solution, determines the number of millilitres, *X*, of 10 volume percent HgNO₃ in 3 volume percent HNO₃ solution required to replenish 1 L of spent solution. Values of *R* and *X* for a litre volume are given in Table 1.

7. Hazards

7.1 **Warning**—Mercury is a definite health hazard in use and disposal.

7.2 *Suggested Mercurous Nitrate Disposal:*

7.2.1 To mercurous nitrate solutions add sodium hydroxide (NaOH) to pH 10 to 11.

7.2.2 Filter precipitated mercury and other heavy metals.

7.2.3 Though the filtrate is low in free mercurous or mercuric ions, it must be further treated before disposal.

7.2.4 To each litre of filtrate, add two drops (0.1 cm³) of 24 volume percent ammonium sulfide (NH₄)₂S.

TABLE 1 Replenishment of Spent Mercurous Nitrate Solution to 1 % Concentration

NOTE 1— $X = 111.1 (1 - R)$

Where:

R = fraction of mercury remaining in solution (determined by titration), and

X = number of millilitres of 10 volume percent mercurous nitrate solution to be added to 1 L of spent mercurous nitrate solution to raise the concentration of mercurous nitrate to 1 %.

<i>R</i>	<i>X</i>	<i>R</i>	<i>X</i>
0.10	100.0	0.56	48.9
0.12	97.8	0.58	46.7
0.14	95.5	0.60	44.4
0.16	93.3	0.62	42.2
0.18	91.1	0.64	40.0
0.20	88.9	0.66	37.8
0.22	86.7	0.68	35.6
0.24	84.4	0.70	33.3
0.26	82.2	0.72	31.1
0.28	80.0	0.74	28.9
0.30	77.8	0.76	26.7
0.32	75.5	0.78	24.4
0.34	73.3	0.80	22.2
0.36	71.1	0.82	20.0
0.38	68.9	0.84	17.8
0.40	66.7	0.86	15.6
0.42	64.4	0.88	13.3
0.44	62.2	0.90	11.1
0.46	60.0	0.92	8.9
0.48	57.8	0.94	6.7
0.50	55.6	0.96	4.4
0.52	53.3	0.98	2.2
0.54	51.1		

7.2.5 After the second filtering, the filtrate may be discarded.

NOTE 2—If heating is used in either of the previous procedures, the container should be covered with a watch glass to prevent loss of HNO₃ and water to the atmosphere. After solution is complete, use a small volume of retained dilution water to rinse the watch glass into the container.

7.2.5.1 Monitor the filtrate to assure it meets appropriate health safety standards, or is disposed of properly.

7.2.6 The precipitates should be collected and stored with the mercury-contaminated test samples and sold to a licensed mercury disposal-service.

8. Sampling and Test Specimen Preparation

8.1 The test specimen shall be prescribed in the specification for the material being tested. In the event that a test specimen size is not prescribed in a given rod, wire, or tube specification, a full cross-section length of 150 mm shall be tested.

8.2 The presence of burrs on the test-specimen may contribute to acceleration of stress corrosion cracking if not removed prior to the mercurous nitrate test.

8.3 The burrs shall be removed by fine file or abrasive paper to facilitate this test.

NOTE 3—The presence of burrs on the test specimen may contribute to acceleration of liquid-metal embrittlement of the mercurous nitrate

solution, if not removed prior to performance of the test.

9. Procedure

9.1 Degrease the specimen in a suitable alkaline degreasing solution or organic solvent. If necessary, totally immerse the specimen in an aqueous solution of 15 volume percent sulfuric acid (H₂SO₄) or 40 volume percent nitric acid until all oxides are completely removed from its surface or pickle in such solutions as may be prescribed in the specification for the material being tested. Remove the specimen from the pickling solution and wash it immediately in running water. Drain the specimen free of excess water and, at room temperature, immerse it totally in the mercurous nitrate solution prepared in accordance with 6.4. Use at least 15 mL of mercurous nitrate solution per 1000 square millimetres of exposed surface of the test specimen.

9.2 After 30 min remove the specimen from the mercurous nitrate solution and wash it in running water. Wipe off any excess mercury from the surface of the specimen. Immediately

examine it visually for cracks unless a time limitation is provided in the product specification.

9.2.1 Tested specimens are mercury contaminated and must be disposed of properly. They may not be included with returns for remelting or machined into product.

9.2.2 Make sure that rinse water and wiping material are monitored to ensure that they meet appropriate health safety standards, or are disposed of properly.

9.3 Do not reuse the solution unless it is replenished to 1 % in accordance with the procedure in 6.5.

10. Precision and Bias

10.1 No statement is made about the precision or bias of this test method since the procedure is directed at a subjective visual interpretation of the condition of the specimen and its relation to an applicable product specification.

11. Keywords

11.1 mercurous nitrate; residual stresses; stress corrosion

SUMMARY OF CHANGES

Committee B05 has identified the location of selected changes to this standard since the last issue (B154-95) that may impact the use of this standard.

(1) Added Section 2, Reference Documents, and renumbered subsequent sections.

(2) Added Section 4, Summary of Test Method, and renumbered subsequent sections.

(3) Renamed Mercurous Nitrate Solution (Section 4) to Reagents and Materials (Section 6) as outlined in the Blue Book. Renamed Test Specimen (Section 6) to Sampling and Test Specimen Preparation (Section 8) as outlined in the Blue Book.

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).