



## Standard Specification for Phosphor Bronze Wire<sup>1</sup>

This standard is issued under the fixed designation B 159/B 159M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

*This standard has been approved for use by agencies of the Department of Defense.*

### 1. Scope \*

1.1 This specification establishes the requirements for round, square and flat phosphor bronze wire of UNS Alloy Nos. C51000, C52100, and C52400 for general and spring applications.

1.1.1 Rectangular and square wire of the three alloys are generally available in sizes up to a maximum of 0.188 in. [5 mm] thick and 1.250 in. [32 mm] wide.

1.1.2 Round wire from Copper Alloy UNS No. C51000 is generally available in sizes up to 0.500 in. [13 mm] in diameter.

1.2 The values stated in either inch-pound units or in SI units are to be regarded separately as standard. Within the text, the SI units are shown in brackets. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in nonconformance with the standard.

1.3 Additional requirements for these products are established in Specification B 250/B 250M, see Section 3.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

NOTE 1—It is to be understood that this specification is general. Since the product is used for many applications where the requirements of the operations used are too particular to be specified by any of the ordinary mechanical tests, it is frequently advisable to submit samples or drawings to the manufacturer and secure an adjustment of temper to suit the actual application for which the product is intended.

NOTE 2—Product in rod, bar and shape form is produced to Specification B 139/B 139M.

### 2. Referenced Documents

#### 2.1 ASTM Standards:

2.1.1 The following documents in the current issue of the Book of Standards form a part of this specification.

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee B05 on Copper and Copper Alloys and is the direct responsibility of Subcommittee B05.02 on Rod, Bar, Wire, Shapes and Forgings.

Current edition approved Nov. 10, 2001. Published February 2002. Originally published as B 159 – 41 T. Last previous edition B 159 – 96a<sup>ε1</sup>.

B 139/B 139M Specification for Phosphorus Bronze Rod, Bar, and Shapes<sup>2</sup>

B 250/B 250M Specification for General Requirements for Wrought Copper-Alloy Wire<sup>2</sup>

B 601 Practice for Temper Designations for Copper and Copper Alloys—Wrought and Cast<sup>2</sup>

B 846 Terminology for Copper and Copper Alloys<sup>2</sup>

E 8 Test Methods for Tension Testing of Metallic Materials<sup>3</sup>

E 8M Test Methods for Tension Testing of Metallic Materials [Metric]<sup>3</sup>

E 62 Test Methods for Chemical Analysis of Copper and Copper Alloys (Photometric Methods)<sup>4</sup>

E 290 Test Method for Bend Testing of Material for Ductility<sup>3</sup>

E 478 Test Methods for Chemical Analysis of Copper Alloys<sup>5</sup>

### 3. General Requirements

3.1 The following sections of Specification B 250/B 250M are a part of this specification:

3.1.1 Terminology,

3.1.2 Materials and Manufacture,

3.1.3 Workmanship, Finish, and Appearance,

3.1.4 Sampling,

3.1.5 Number of Tests and Retests,

3.1.6 Specimen Preparation,

3.1.7 Test Methods,

3.1.8 Significance of Numerical Limits,

3.1.9 Inspection,

3.1.10 Rejection and Rehearing,

3.1.11 Certification,

3.1.12 Test Reports,

3.1.13 Packaging and Package Markings, and

3.1.14 Supplementary Requirements.

3.2 In addition, when a section with a title identical to one of those referenced in 3.1 appears in this specification, it contains additional requirements which supplement those appearing in Specification B 250/250M.

<sup>2</sup> *Annual Book of ASTM Standards*, Vol 02.01.

<sup>3</sup> *Annual Book of ASTM Standards*, Vol 03.01.

<sup>4</sup> *Annual Book of ASTM Standards*, Vol 03.05.

<sup>5</sup> *Annual Book of ASTM Standards*, Vol 03.06.

**\*A Summary of Changes section appears at the end of this standard.**

#### 4. Terminology

4.1 For definition of terms related to copper and copper alloys, refer to Terminology B 846.

#### 5. Ordering Information

5.1 Include the following information when placing orders for product under this specification.

5.1.1 ASTM designation and year of issue (for example, B 159/B 159M – XX),

5.1.2 Copper Alloy UNS No. (for example, C51000),

5.1.3 Temper designation (Section 8),

5.1.4 Dimensions (diameter, distance between parallel faces, and so forth),

5.1.5 Type of edge (square corners, rounded corners, and so forth),

5.1.6 How furnished (coil spool, reel, specific lengths, and so forth), and

5.1.7 When product is purchased for agencies of the U.S. government (Section 11).

5.2 The following options are available under this specification and shall be specified in the contract or purchase order when required:

5.2.1 Heat identification or traceability details,

5.2.2 Certification.

5.2.3 Mill Test Reports, and

5.2.4 Special packaging and package markings.

#### 6. Materials and Manufacture

##### 6.1 Materials:

6.1.1 The material of manufacturer shall be a casting billet of Copper Alloy UNS No. C51000, C52100, or C52400 of such purity and soundness as to be suitable for processing into the products prescribed herein.

6.1.2 In the event heat identification or traceability is required, the purchaser shall specify the details desired.

##### 6.2 Manufacture:

6.2.1 The product shall be manufactured by such hot-working, cold-working, and annealing processes as to produce a uniform wrought structure in the finished product.

#### 7. Chemical Composition

7.1 The material composition shall conform to the requirements of Table 1 for the Copper Alloy UNS No. specified in the ordering information.

7.1.1 These composition limits do not preclude the presence of other elements. When required, limits may be established and analysis required for unnamed elements by agreement between the supplier and the purchaser.

**TABLE 1 Chemical Requirements**

Copper Alloy UNS No.	C51000	C52100	C52400
	Composition, %		
Copper, incl silver	remainder	remainder	remainder
Lead, max	0.05	0.05	0.05
Iron, max	0.10	0.10	0.10
Tin	4.2–5.8	7.0–9.0	9.0–11.0
Zinc, max	0.30	0.20	0.20
Phosphorus	0.03–0.35	0.03–0.35	0.03–0.35

7.2 Copper listed as the “remainder” is the difference between the sum of results for all elements determined and 100 %.

7.3 When all elements listed in Table 1 for the Copper Alloy UNS No. prescribed in the ordering information are determined, the sum of results shall be 99.5 % min.

#### 8. Temper

8.1 Tempers, as defined in Practice B 601, available under this specification are O61 (annealed), H01 (1/4 hard), H02 (1/2 hard), H03 (3/4 hard), H04 (hard), H06 (extra hard), H08 (spring), and H10 (extra spring).

8.1.1 Tempers not covered by this specification shall be by agreement between purchaser and supplier.

NOTE 3—The purchaser shall confer with the supplier for availability of product in specific alloy, temper, form, and size.

#### 9. Mechanical Property Requirements

##### 9.1 Tensile Requirements:

9.1.1 When tested in accordance with Test Methods E 8 and E 8M:

9.1.1.1 Round and square wire for general application produced from Copper Alloy UNS Nos. C51000, C52100, and C52400 shall conform to the requirements prescribed in Table 2.

9.1.1.2 Round or square wire produced from Copper Alloy UNS No. C51000 in H08 (spring) temper shall conform to the requirements prescribed in Table 3.

9.1.1.3 Rectangular wire produced from Copper Alloy UNS Nos. C51000, C52100, and C52400 shall conform to the requirements prescribed in Table 4.

#### 10. Performance Requirements

##### 10.1 Bending Requirements:

10.1.1 Wire in sizes up to 0.250 in. [7 mm] inclusive produced from Copper Alloy UNS No. C51000 shall withstand being bent cold (room temperature) through an angle of 120° on a radius equal to the diameter or distance between parallel surfaces in accordance with Test Method E 290. When so bent, tempers H08 and H10 shall not develop cracks or other flaws visible to the unaided eye on the outside surface of the bend.

#### 11. Purchases for U.S. Government

11.1 Product purchased for agencies of the U.S. government

**TABLE 2 Mechanical Requirements for Round or Square Wire for General Purposes**

Standard	Temper	Tensile Strength, ksi [Mpa] <sup>A</sup>		
		Copper Alloy UNS No.		
	Name	C51000	C52100	C52400
O61	annealed	43.0–58.0 [295–400]	53.0–68.0 [365–470]	60.0–75.0 [415–515]
H01	quarter-hard	60.0–76.0 [415–525]	74.0–91.0 [510–625]	83.0–102.0 [570–705]
H02	half-hard	80.0–97.0 [550–670]	95.0–115.0 [655–795]	108.0–129.0 [745–890]
H03	three-quarter-hard	96.0–115.0 [660–795]	113.0–135.0 [780–930]	125.0–148.0 [860–1020]
H04	hard	108.0–128.0 [745–880]	125.0–150.0 [860–1035]	135.0–160.0 [930–1100]
H08	spring	see Table 3	...	...

<sup>A</sup>ksi = 1000 psi.



TABLE 3 Mechanical Requirements for H08 (Spring Temper) UNS No. C51000 Round or Square Wire

Table with 3 columns: Diameter or Distance Between Parallel Surfaces, in. [mm], Tensile Strength, min, ksi [Mpa]^A, Elongation in 2 in. [50 mm] min, %

^Aksi = 1000 psi.

TABLE 4 Mechanical Strength Requirements for Flat Wire (Other Than Square Wire)

Table with 5 columns: Temper, Standard, Name, Copper Alloy UNS No. (C51000, C52100, C52400), Tensile Strength, ksi^A

^Aksi = 1000 psi.

shall conform to the additional requirements prescribed in the Supplementary Requirements section of Specification B 250/B 250M (see Section 11).

12. Dimensions, Mass, and Permissible Variations

12.1 The dimensions and tolerances for product produced to this specification shall be as specified in the following tables and related paragraphs or specified titles found in Specification B 250/B 250M:

12.1.1 Diameter or Distance Between Parallel Surfaces—Table 2.

12.1.1.1 Thickness—Table 4.

12.1.1.2 Width—Table 6.

12.1.1.3 Length (Flat Wire Product)—Tables 7 and 8.

12.1.1.4 Straightness (Flat Wire Product)—Table 9.

12.1.1.5 Edge Contours—Edge Contour section.

13. Test Methods

13.1 Chemical Analysis:

13.1.1 Product composition shall, in case of dispute, be determined as follows:

Table with 2 columns: Element, Test Methods

13.1.2 Test method(s) to be followed for the determination of elements required by contractual or purchase order agreement shall be as agreed upon between the supplier and the purchaser.

14. Keywords

14.1 phosphor bronze alloy wire; UNS No. C51000 wire; UNS No. C52100 wire; UNS No. C52400 wire

SUMMARY OF CHANGES

Committee B05 has identified the location of selected changes to this standard since the last issue (B 159-96) that may impact the use of this standard.

- (1) Combined Specifications B 159 and B 159M.
(2) Added section on Materials and Manufacture.

- (3) Renumbered sections as needed.

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).