



## Standard Specification for Cartridge Brass Sheet, Strip, Plate, Bar, and Disks (Blanks)<sup>1</sup>

This standard is issued under the fixed designation B 19; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

*This standard has been approved for use by agencies of the Department of Defense.*

### 1. Scope

1.1 This specification establishes the requirements for UNS No. C26000<sup>2</sup> sheet, strip, plate, bar, and disks for the manufacturer of ammunition of component parts thereof.

1.2 Values given in inch-pound units are the standard. Values given in parenthesis are for information only.

### 2. Referenced Documents

#### 2.1 ASTM Standards:

B 154 Test Method for Mercurous Nitrate Test for Copper and Copper Alloys<sup>3</sup>

B 248 Specification for General Requirements for Copper and Copper Alloy Plate, Sheet, Strip, and Rolled Bar<sup>3</sup>

B 601 Practice for Temper Designations for Copper and Copper Alloys—Wrought and Cast<sup>3</sup>

E 3 Methods of Preparation of Metallographic Specimens<sup>4</sup>

E 8 Test Methods for Tension Testing of Metallic Materials<sup>4</sup>

E 112 Test Methods for Determining Average Grain Size<sup>4</sup>

E 255 Practice for Sampling Copper and Copper Alloys for Determination of Chemical Determination of Chemical Composition<sup>5</sup>

E 478 Test Methods for Chemical Analysis of Copper Alloys<sup>5</sup>

E 527 Practice for Numbering Metals and Alloys (UNS)<sup>6</sup>

#### 2.2 Federal Standards:<sup>7</sup>

Fed. Std. No. 123 Marking for Shipment (Civil Agencies)

Fed. Std. No. 185 Identification Marking of Copper and Copper-Base Alloy Mill Products

#### 2.3 Military Standards:<sup>7</sup>

MIL-STD-105 Sampling Procedures and Tables for Inspection by Attributes

MIL-STD-129 Marking for Shipment and Storage

MIL-C-3993 Packaging of Copper and Copper-Base Alloy Mill Products

### 3. Ordering Information

3.1 Contracts or purchase orders for product under this specification should contain the following information:

3.1.1 ASTM designation and year of issue (for example, B19-XX),

3.1.2 Product form: sheet, strip, plate, bar, or disks (blanks),

3.1.3 Temper (Section 6),

3.1.4 Dimension: thickness, width, length,

3.1.5 How furnished: flat lengths, coils, or blanks,

3.1.6 Quantity: total weight each temper, form, and size, and

3.1.7 When severe drawing or deep cupping is required.

3.2 The following options are available and should be specified in the contract or purchase order when required:

3.2.1 Heat identification or traceability details,

3.2.2 Caliber or diameter of Type IV cups or disks (Section 10),

3.2.3 Mercurous Nitrate Test (Section 9),

3.2.4 Product Marking (Section 18),

3.2.5 On site inspection (Section 12),

3.2.6 Certification (Section 3),

3.2.7 Test Report (Mill) (Section 3), and

3.2.8 Product Marking (Section 18).

### 4. Material and Manufacture

#### 4.1 Material:

4.1.1 The material of manufacture shall be a cast bar of copper alloy UNS C26000 of such purity, uniformity, and soundness as to be suitable for processing into the products prescribed herein.

#### 4.2 Manufacturing:

4.2.1 The product shall be manufactured by such hot working, cold working, and annealing processes as to produce a uniform wrought structure in the specified temper for the finished product.

4.2.2 The products shall be furnished with slit edges unless otherwise specified.

4.3 In the event heat identification or traceability is required,

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee B-5 on Copper and Copper Alloys and is the direct responsibility of Subcommittee B05.01 on Plate, Sheet and Strip.

Current edition approved Feb. 15, 1995. Published April 1995. Originally published as B 19 – 19 T. Last previous edition B 19 – 86 (1993) <sup>$\epsilon$ 1</sup>.

<sup>2</sup> The UNS system for copper and copper alloys (see Practice E 527) is a simple expansion of the former standard designation system accomplished by the addition of a prefix “C” and a suffix “00”. The suffix can be used to accommodate composition variations of the base alloy.

<sup>3</sup> Annual Book of ASTM Standards, Vol 02.01.

<sup>4</sup> Annual Book of ASTM Standards, Vol 03.01.

<sup>5</sup> Annual Book of ASTM Standards, Vol 03.05.

<sup>6</sup> Annual Book of ASTM Standards, Vol 01.01.

<sup>7</sup> Available from Standardization Documents Order Desk, Bldg. 4 Section D, 700 Robbins Ave., Philadelphia, PA 19111-5094, Attn: NPODS.

the purchaser shall specify the details desired in the contract or purchase order.

**5. Chemical Composition**

5.1 The product material shall conform to the requirements prescribed in Table 1.

5.1.1 These specification limits do not preclude the presence of other elements. Limits for unnamed elements may be established and analysis required by agreement between manufacturer and purchaser.

5.2 Either copper or zinc may be taken as the difference between the sum of all elements analyzed and 100 %. When all elements in Table 1 are analyzed, their sum shall be 99.7 % min.

**6. Temper**

6.1 Product tempers, as defined in Practice B 601, shall be as follows:

6.1.1 *Rolled Product:* B 601, H01, H02, H03, H04, H06, H08, and H10.

6.1.2 *Annealed Product:* OS015, OS025, OS035, OS050, OS070, and OS100.

6.1.3 The purchaser should confer with the manufacturer or supplier for availability of product in a specific temper, form, and size.

**7. Mechanical Property Requirements**

7.1 Materials furnished under this specification shall conform to the tension test requirements specified in this specification.

7.1.1 Rolled-to-temper material shall conform to the requirements specified in Table 2.

7.1.2 Annealed material shall conform to the requirements specified in Table 3.

7.1.3 Material furnished as-hot rolled shall conform to the requirements specified in Table 3.

**8. Grain Size Requirements**

8.1 Annealed sheet, strip, and bar furnished under this specification shall conform to the requirements specified in Table 4.

8.2 Except for material ordered by the U.S. Government, annealed material to be used for the manufacture of cartridge brass cups and disks shall conform to the requirements of Table 5.

8.3 Annealed plate, bar, and disks ordered by the U.S. Government shall meet the following requirements:

8.3.1 Material up to 0.500 in. (12.70 mm) in thickness inclusive, except material for 20 mm disks, shall be furnished to a grain size of 0.055 to 0.120 mm inclusive.

**TABLE 1 Chemical Requirements**

NOTE 1—If the presence of bismuth is suspected during analysis, further analysis shall be made, and if bismuth is found in excess of 0.006 %, the lot shall be rejected.

Copper	Composition, %		Zinc
	Lead, max	Iron, max	
68.5 to 71.5	0.07	0.05	remainder

**TABLE 2 Tensile Strength Requirements for Rolled Tempers**

NOTE 1—Plate is generally available in only the soft O60, quarter-hard H01, and half-hard H02 tempers. Required properties for other tempers shall be agreed upon between the manufacturer or supplier and the purchaser at time of placing the order or contract.

Temper Designation		Tensile Strength, ksi <sup>A</sup> (MPa) <sup>B</sup>	
		min	max
Standard	Former		
H01	quarter hard	49 (340)	59 (405)
H02	half hard	57 (395)	67 (460)
H03	three-quarter hard	64 (440)	74 (510)
H04	hard	71 (490)	81 (560)
H06	extra hard	83 (570)	92 (635)
H08	spring	91 (625)	100 (690)
H10	extra spring	95 (655)	104 (720)

<sup>A</sup> ksi 1000 psi.

<sup>B</sup> See Appendix X1.

8.3.2 Material over 0.500 in. (12.70 mm) in thickness, except material for 20-mm disks, shall be furnished to a grain size of 0.070 to 0.150 mm inclusive.

8.3.3 Disks (blanks) of 20 mm and material for blanking 20-mm disks (blanks) shall be furnished to a grain size of 0.070 to 0.130 mm inclusive.

8.4 Material ordered as-hot rolled shall be furnished to a grain size as agreed upon between the manufacturer or supplier and the producer.

8.5 Material to be used for the manufacture of primer cup and primer anvils shall conform to the grain size requirements of Table 6.

**9. Mercurous Nitrate Test**

9.1 When specified in the contract or purchase order, the product shall meet the requirements of Test Method B 154.

9.1.1 Mercury is a recognized health hazard. Proper equipment for the detection and removal of vapors is recommended. The use of suitable gloves while testing is advised.

**10. Dimensions and Permissible Variations**

10.1 The dimensions and tolerances covered by this specification, except as covered herein, shall be as specified in the current edition of Specification B 248, with particular reference to Section 5 and the dimensional tables of that specification.

10.2 The diameter of the disks measured at the large end shall not vary from that specified in the order by more than the amounts shown in Table 7.

10.3 Disks shall not vary in thickness by more than the amounts shown in Table 8, except that disks for 20-mm cartridge cases shall be not less than the thickness specified and shall not exceed the specified thickness by more than 0.008 in. (0.20 mm) in the area 1 in. (25 mm) in diameter in the center of the disk.

10.4 Material to be used for the manufacture of primer cup and primer anvil shall conform to the dimensional tolerances requirements shown in Table 6.

10.5 Special dimensional tolerances shall be as agreed upon between the manufacturer or supplier and the purchaser.

10.6 Straightness shall be determined by placing the piece on a level surface so that the arc or departure from straightness is horizontal. The maximum depth of arc shall be measured to

**TABLE 3 Tension Test Requirements of Annealed and As-Hot Rolled Materials**

NOTE 1—On annealed material under 0.020 in. (0.51 mm) in thickness, grain size only shall be specified.

Thickness, in. (mm)	Tensile Strength, min ksi <sup>A</sup> (MPa) <sup>B</sup>	Elongation in 2 in. (50 mm), min, %
	annealed temper, OS025, 0.015– 0.035 mm nominal grain size	
0.020 to 0.050 (0.508 to 1.27), incl	45 (310)	40
Over 0.050 to 0.100 (1.27 to 2.54), incl	45 (310)	42
Over 0.100 to 0.150 (2.54 to 3.81), incl	45 (310)	45
Over 0.150 (3.81)	45 (310)	50
	annealed temper, OS070, 0.050– 0.100 mm nominal grain size	
0.020 to 0.050 (0.508 to 1.27), incl	44 (305)	45
Over 0.050 to 0.100 (1.27 to 2.54), incl	44 (305)	47
Over 0.100 to 0.150 (2.54 to 3.81), incl	44 (305)	50
Over 0.150 to 0.250 (3.81 to 6.35), incl	44 (305)	55
Over 0.250 to 0.500 (6.35 to 12.7), incl	43 (295)	55
Over 0.500 (12.7)	40 (275)	60
	as-hot rolled, M20	
0.250 to 0.500 (6.35 to 12.7), incl	43 (295)	55
Over 0.500 (12.7)	40 (275)	60

<sup>A</sup> 1 ksi = 1000 psi.

<sup>B</sup> See Appendix X1.

**TABLE 4 Grain Size Requirements for Annealed Material**

Temper	Nominal	Grain Size, mm	
		Min	Max
OS015	0.015	<sup>A</sup>	0.025
OS025	0.025	0.015	0.035
OS035	0.035	0.025	0.050
OS050	0.050	0.035	0.070
OS070	0.070	0.050	0.100
OS100	0.100	0.060	0.150

<sup>A</sup> No minimum grain size required, but the material shall be fully recrystallized.

**TABLE 5 Grain Size Requirements for Material for Manufacture of Cartridge Brass Cups and Disks**

Type	Temper	Grain Size, mm		Use
		Min	Max	
I	OS065	0.035	0.090	Strip for 0.30 and 0.45 caliber cups
II	OS110	0.080	0.140	Strips for 0.50 caliber cups
III	OS055	0.055	0.115	Disks 0.500 in. (12.7 mm) and under in thickness
IV	OS115	0.075	0.150	Disks over 0.500 in. (12.7 mm) in thickness

the nearest 1/32 in. (0.8 mm) by means of a straightedge and a steel scale.

## 11. Workmanship, Finish, and Appearance

11.1 Cartridge brass shall be free of injurious external and internal defects of a nature that will interfere with the purpose for which the material is intended, and it shall be well-cleaned and free of dirt.

11.2 In addition to the above requirement, cartridge brass disks shall be free of oxidation, pinholes, surface splits, dirt inclusions, segregations, or any other defects, internal or external, that will interfere with the purpose intended. They shall be free of oil and grease, acid, dirt, grit of any kind, and shall be clean and bright.

## 12. Quality Assurance

12.1 *Responsibility for Inspection*—Unless otherwise specified in the contract or purchase order, the manufacturer is

responsible for the performance of all inspection and test requirements specified. Except as otherwise specified in the contract or purchase order, the manufacturer may use his own or any other suitable facilities for the performance of the inspection and test requirements unless disapproved by the purchaser at the time the order is placed. The purchaser shall have the right to perform any of the inspections or tests set forth when such inspections and tests are deemed necessary to assure that the material conforms to prescribed requirements.

## 13. Sampling

13.1 The lot size, portion size, and selection of pieces for materials purchased shall be as follows:

13.1.1 *Lot Size*—20 000 lb (9070 kg) or fraction thereof.

13.1.2 *Portion Size*—Pieces from at least ten individual lengths of the finished product. If the lot consists of less than the number of lengths indicated in the portion size, a piece shall be taken from each individual length.

13.2 For materials purchased by the U.S. Government, sampling shall be accomplished as follows:

13.2.1 The lot size, portion size, and selection of pieces shall conform to the sampling plan of Table 9 for chemical analysis, for tension tests, for grain size determinations and for the mercurous nitrate test.

13.2.2 *Sampling for Visual and Dimensional Examination*—If the weight of each piece is more than 150 lb (68 kg), every piece shall be examined. If the weight of each piece is 150 lb or less, a representative sample shall be selected in accordance with MIL-STD-105, inspection level II, acceptable quality level (AQL) of 1.5 %, and shall be visually examined to determine compliance with the requirements of the contract for identification marking and workmanship, and shall be measured for compliance with the dimensional requirements of this specification and the contract.

13.3 When material is furnished in rolls or on reels or spools, the sample for examination shall be taken within 10 ft (3.0 m) of the outer end. If the sample is rejected due to handling marks, an additional 20 ft (6.1 m) shall be selected for examination.

**TABLE 6 Dimensional Tolerances, Grain Size, and Temper of Brass for Primer Cup and Primer Anvils**

Item	Size case, caliber	Thickness, in. (mm)	Permissible Variation in Thickness Plus and Minus, in. (mm)	Standard Temper Designations	Nominal Grain Size, mm or temper
Cup	0.50	0.035 (0.899)	0.0008 (0.020)	OS100	0.100 (OS100)
	0.45	0.018 (0.458) or 0.020 (0.508)	0.001 (0.025)	OS050	0.050 (OS050)
	7.62 mm	0.027 (0.686) or 0.029 (0.737)	0.0008 (0.020)	OS100	0.100 (OS100)
	5.56 mm	0.027 (0.686)	0.0005 (0.0125)	OS070	0.070 (OS070)
	0.30	0.027 (0.686)	0.0008 (0.020)	OS100	0.100 (OS100)
Anvil	0.30 carbine	0.020 (0.508)	0.001 (0.025)	OS070	0.070 (OS070)
	0.50	0.0485 (1.2315)	0.001 (0.025)	OS025	0.025 (OS025)
	0.45	0.038 (0.965)	0.001 (0.025)	H01	¼hard (H01)
	7.62 mm	0.038 (0.965)	0.001 (0.025)	H01 or H02	¼ or ½ hard (H01 or H02)
	5.56 mm	0.038 (0.965)	0.001 (0.025)	H01 or H02	¼ or ½ hard (H01 or H02)
	0.30	0.038 (0.965)	0.001 (0.025)	H01 or H02	¼ or ½ hard (H01 or H02)
	0.30 carbine	0.034 (0.864)	0.001 (0.025)	H01	¼ hard (H01)

**TABLE 7 Diameter Tolerances for Disks (Blanks)**

Diameter, in. (mm)	Tolerances, in. (mm)	
	Plus	Minus
Up to 1 (25.4) incl	0.005 (0.127)	0
Over 1 to 3 (25.4 to 76.2) incl	0.010 (0.254)	0
Over 3 to 12 (76.2 to 305) incl	0.015 (0.381)	0
Over 12 to 14 (305 to 356) incl	0.020 (0.508)	0
Over 14 (356)	0.030 (0.762)	0

**TABLE 8 Permissible Variation in Thickness of Disks (Blanks)**

Thickness, in. (mm)	Permissible Variations in Thickness, in. (mm)	
	Plus	Minus
Up to 0.150 (3.81) incl	0.005 (0.127)	0
Over 0.150 to 0.300 (3.81 to 7.62) incl	0.006 (0.152)	0
Over 0.300 to 0.400 (7.62 to 10.16) incl	0.008 (0.203)	0
Over 0.400 to 0.600 (10.16 to 15.24) incl	0.015 (0.381)	0
Over 0.600 to 0.900 (15.24 to 22.86) incl	0.020 (0.508)	0
Over 0.900 (22.86)	0.030 (0.762)	0

13.4 *Chemical Analysis*—A sample for chemical analysis shall be taken and prepared in accordance with Practice E 255. Drilling, millings, etc., shall be taken in approximately equal weight from each of the sample pieces selected in accordance with 13.1.2 or 13.2.1 and combined into composite samples. The minimum weight of the composite sample that is to be divided into three equal parts shall be 150 g. The maximum number of samples from which a composite sample may be made shall be ten.

13.4.1 Instead of sampling in accordance with Practice E 255, the manufacturer shall have the option of determining conformance to chemical composition as follows: Conformance shall be determined by the manufacturer by analyzing samples taken at the time the castings are poured or samples taken from the semi-finished product. If the manufacturer determines the chemical composition of the material during the course of manufacture, he shall not be required to sample and analyze the finished product. The number of samples taken for determination of chemical composition shall be as follows:

13.4.1.1 When samples are taken at the time the castings are poured, at least one sample shall be taken for each group of castings poured simultaneously from the same source of molten metal.

13.4.1.2 When samples are taken from the semi-finished

product, a sample shall be taken to represent each 10 000 lb (4540 kg) or fraction thereof, except that not more than one sample shall be required per piece.

## 14. Number of Tests and Retests

### 14.1 Tests:

14.1.1 Chemical composition shall be determined as the per cent average of results from at least two replicate analyses.

14.2 *Other Test*—Other tests shall be performed using the samples selected in accordance with 13.1.2 or 13.2, as appropriate. The required tests shall be made on each of the specimens so selected.

### 14.3 Retests:

14.3.1 When requested by the manufacturer or supplier, a retest may be permitted should test results obtained by the purchaser fail to conform with specification requirements.

14.3.2 Retesting shall be as directed in the product specification for the initial test(s) except that the number of test specimens shall be twice that required for the initial test.

14.3.3 Test results for all specimens shall conform to the product specification requirements in retest and failure to conform shall be cause for lot rejection.

## 15. Specimen Preparation

### 15.1 Chemical Analysis:

15.1.1 Preparation of the analytical specimen shall be the responsibility of the reporting laboratory.

### 15.2 Grain Size:

15.2.1 The test specimen shall be prepared in accordance with Methods E 3.

### 15.3 Tensile Test:

15.3.1 For tension testing, machined test specimens as specified in Test Methods E 8 shall be used. Specimens shall be taken so that the longitudinal axis of such specimens is parallel to the direction of rolling.

15.3.2 If the diameter of the disk is less than the minimum specimen length required for the performance of the test, specimens shall be taken from the original material for which the disks were blanked.

15.3.3 In the event that disks are to be annealed subsequent to blanking and the disk diameter will not provide the required specimen length, the necessary pieces of original material shall

**TABLE 9 Sampling for U.S. Government Contracts**

NOTE 1—If the number of original castings from which the material is processed is less than the number of samples specified, not more than one sample need be taken from each piece for chemical analysis.

Lot Size, lb	Chemical Analysis	Tension Test	Grain Size Test	Mercurous Nitrate Test
Plate, sheet, strip and bar:				
up to 2000	2	2	5	...
2001 to 20 000	4	4	10	...
Disks:				
Up to 20 000	4	1	2	1
20 001 to 40 000	8	2	4	2
40 001 to 60 000	12	3	6	3
60 001 to 80 000	16	4	8	4
80 001 to 100 000	20	5	10	5

be prepared and annealed with the disks which these samples are to represent.

## 16. Test Methods

### 16.1 Chemical Analysis:

16.1.1 Chemical Composition, in case of disagreement shall be determined as follows:

Element	Method
Copper	E 478
Lead	E 478 (AA)
Iron	E 478
Zinc	E 478 (Titrimetric)

16.1.2 Test methods for elements required by contractual or purchase order agreement shall be as agreed upon between the manufacturer and the purchaser.

## 17. Rejection and Rehearing

### 17.1 Rejection:

17.1.1 Material that fails to conform to the requirements of this specification when inspected or tested by the purchaser or his agent may be rejected.

17.1.2 Samples that represent rejected material shall be preserved for two weeks from the date of the test report. In case of dissatisfaction with the results of the tests, the producer or supplier may claim for a rehearing with this time.

17.1.3 Material that show injurious defects during subsequent manufacturing operations may be rejected. If rejected, the producer or supplier shall be responsible only for replacement of the material to the purchaser. As much of the rejected original material as possible shall be returned to the producer or supplier.

17.1.4 For visual and dimensional examination of materials purchased by the U.S. Government, any sample unit having one or more defects shall be rejected. If the number of

nonconforming sample units in the sample exceeds the acceptance number specified in MIL-STD-105, inspection Level II, acceptance quality level (AQL) of 1.5 %, the entire lot shall be rejected.

### 17.2 Rehearing:

17.2.1 As a result of product rejection, the manufacturer or supplier may petition the purchaser for a retest to be conducted by the manufacturer, or supplier, and the purchaser.

17.2.2 Samples of the rejected product to be taken in accordance with the product specification and tested by both parties using the test method(s) specified in the product specification, or, alternatively, upon agreement of both parties, an independent laboratory may be selected for the test(s) using the specified test methods.

## 18. Product Marking

18.1 When specified in the contract or purchaser order, all material shall be properly marked for identification or classification with the name or brand of the producer, commercial designations, and specification information (that is, type, class, etc.). The method of marking shall be at the manufacturer's option and may be made by stamping, stenciling, casting, rolled-raised lettering, tagging, or labeling, as suited to the product.

18.2 For U.S. Government applications, all material shall, when specified, be marked in accordance with Fed. Std. No. 185 except that the ASTM specification number and the alloy number shall be used.

## 19. Keywords

19.1 bar; brass bar; brass disks (blanks); brass plate; brass sheet; brass strip; cartridge brass bar; cartridge brass disks (blanks); cartridge brass plate; cartridge brass sheet; cartridge brass strip; disks (blanks); plate; strip

*The American Society for Testing and Materials takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.*

*This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, 100 Barr Harbor Drive, West Conshohocken, PA 19428.*