



Standard Specification for Seamless Copper Alloy Pipe and Tube¹

This standard is issued under the fixed designation B 315; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

1. Scope *

1.1 This specification² establishes the requirements for seamless, copper alloy pipe and tube in nominal pipe sizes, both regular and extra strong, and seamless tube in straight lengths for general engineering purposes. Pipe and tube are produced in the copper alloy UNS Numbers: C61300, C61400, C63020, C65100, and C65500.

NOTE 1—Inquiry should be made of the manufacturer or supplier concerning the availability of product in a specific alloy.

1.2 The values stated in inch-pound units are the standard. The SI values given in parentheses are for information only.

1.3 The following pertains only to the test method described in 9.1.2 of this specification. *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:

- B 846 Terminology for Copper and Copper Alloys³
- E 8 Test Methods of Tension Testing of Metallic Materials⁴
- E 18 Test Methods for Rockwell Hardness and Rockwell Superficial Hardness of Metallic Materials⁴
- E 29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications⁵
- E 54 Test Methods for Chemical Analysis of Special Brasses and Bronzes⁶
- E 62 Test Methods for Chemical Analysis of Copper and Copper Alloys (Photometric Methods)⁶
- E 243 Practice for Electromagnetic (Eddy-Current) Examination of Copper and Copper-Alloy Tubes⁷

E 255 Practice for Sampling Copper and Copper Alloys for Determination of Chemical Composition⁶

E 478 Test Methods for Chemical Analysis of Copper Alloys⁸

3. Terminology

3.1 For definitions of terms related to copper and copper alloys refer to Terminology B 846.

3.2 *Definitions of Terms Specific to This Standard:*

3.2.1 *pecially cleaned*—sufficiently free of oxides as to exhibit the golden color associated with the alloy.

4. Ordering Information

4.1 Orders for product under this specification shall include the following information:

- 4.1.1 ASTM Designation and year of issue (for example B 315 – XX),
- 4.1.2 Alloy (Section 6, Table 1),
- 4.1.3 Temper (Section 7),
- 4.1.4 Pipe size regular (Table 3),
- 4.1.5 Pipe size, extra-strong (Table 3),
- 4.1.6 Tube diameter (Table 9),
- 4.1.7 Tube wall thickness (Table 6, Table 7, or Table 8),
- 4.1.8 Length (Table 10 or Table 11),
- 4.1.9 Total length of each size,
- 4.1.10 Whether the product is to be subsequently welded (see Table 1 and Footnote B),
- 4.1.11 Finish (11.2 and 11.3), and
- 4.1.12 When copper alloy UNS No. C63020 is ordered under this specification, tube diameter, wall thickness, length, sizes, and tolerances shall be a part of the purchase order as agreed upon between the supplier and the purchaser.

4.2 When product is to be subjected to welding or brazing, the purchase order or contract shall specify product to be “pecially cleaned.”

4.3 The following options are available under this specification and must be specified in the contract or purchase order when required:

- 4.3.1 Heat identification or traceability (12.1.3.4),
- 4.3.2 Certification (Section 19), and
- 4.3.3 Test Report (Section 20).

¹ This specification is under the jurisdiction of ASTM Committee B-5 on Copper and Copper Alloys and is the direct responsibility of Subcommittee B05.04 on Pipe and Tube.

Current edition approved Sept. 10, 1999. Published November 1999. Originally published as B 315 – 57T. Last previous edition B 315 – 93.

² For ASME Boiler and Pressure Vessel Code applications see related Specification SB315 in Section II of that Code.

³ Annual Book of ASTM Standards, Vol 02.01.

⁴ Annual Book of ASTM Standards, Vol 03.01.

⁵ Annual Book of ASTM Standards, Vol 14.02.

⁶ Annual Book of ASTM Standards, Vol 03.05.

⁷ Annual Book of ASTM Standards, Vol 03.03.

⁸ Annual Book of ASTM Standards, Vol 03.06.

*A Summary of Changes section appears at the end of this standard.

TABLE 1 Chemical Requirements

Copper Alloy UNS No.	C61300 ^A	C61400	C63020 ^B	C65100	C65500
	Composition, % Max (Unless Shown as a Range or Minimum)				
Copper ^C	remainder	remainder	74.5 min	remainder	remainder
Lead	0.01	0.01	0.03	0.05	0.05
Iron	2.0–3.0	1.5–3.5	4.0–5.5	0.8	0.8
Zinc	0.10	0.20	0.30	1.5	1.5
Aluminum	6.0–7.5	6.0–8.0	10.1–16.0
Manganese	0.20	1.0	1.5	0.7	0.50–1.3
Silicon	0.10	0.8–2.0	2.8–3.8
Tin	0.20–0.50	...	0.25
Nickel (including cobalt)	0.15	...	4.2–6.0	...	0.6
Phosphorus	0.015	0.015

^AWhen the product is for subsequent welding applications and is so specified by the purchaser, chromium shall be 0.05 % max, cadmium 0.05 % max, zinc 0.05 % max, and zirconium 0.05 % max.

^BChromium shall be 0.05 max and cobalt 0.20 max.

^CIncluding silver.

5. Materials and Manufacture

5.1 Material:

5.1.1 The material of manufacture shall be a cast billet, bar, tube, or so forth of copper alloy UNS No. C61300, C61400, C63020, C65100, or C65500 and of such purity and soundness as to be suitable for processing in to the products prescribed herein.

5.1.2 In the event heat identification or traceability is required, the purchaser shall specify the details desired.

NOTE 2—Because of the discontinuous nature of the processing of castings into wrought products, it is not always practical to identify a specific casting analysis with a specific quantity of finished material.

5.2 Manufacture:

5.2.1 The product shall be produced by hot-working or cold-working operations, or both. Unless otherwise specified, the product shall be finished by such cold working and annealing or heat treatment as necessary to meet the properties specified.

5.2.2 Copper alloy UNS No. C63020 tube shall be quench hardened and tempered (TQ30) as follows:

5.2.2.1 Heat to 1550 to 1650°F (843 to 899°C) for 2-h minimum and quench in water. Then, temper at 900 to 1000°F (482 to 538°C) for 2-h minimum and air cool to room temperature.

6. Chemical Composition

6.1 The material shall conform to the compositional requirements as listed in Table 1 for the alloy specified in the contract or purchase order

6.2 These composition limits do not preclude the presence of other elements. Limits may be established and analysis required for unnamed elements by agreement between the manufacturer and the purchaser.

6.2.1 When the copper concentration is specified as the remainder, the percentage of copper may be calculated as the difference between the sum of all the elements determined and 100 %.

6.2.1.1 When all the elements listed for an alloy in Table 1 are determined, the sum of the determined elements for the alloy shall be as shown in the following table:

Copper Alloy UNS No.	Copper Plus Named Elements, % min
C61300	99.8
C61400	99.5
C63020	99.5
C65100	99.5
C65500	99.5

7. Temper

7.1 The standard tempers for products described in this specification are listed as follows and in Table 2:

7.1.1 Alloys C61300 and C61400 are supplied in tempers M30 (hot-extruded), O30 (hot-extruded and annealed), and O61 (annealed).

7.1.2 Alloy C63020 is supplied in temper TQ30 (quench hardened and tempered).

7.1.3 Alloy C65100 is supplied in tempers O30 (extruded and annealed), O61 (annealed), and H50 (extruded and cold worked).

TABLE 2 Tensile Requirements

Copper Alloy UNS No.	C61300 and C61400		C63020	C65100		C65500
	M30 (Extruded) or O61 (Annealed)	TQ30 (Quench-Hardened and Tempered)	O30 (Extruded and Annealed) or O61 (Annealed)	H50 (Extruded and Cold-Worked)	O30 (Extruded and Annealed) and O61 (Annealed)	
Tensile Strength, min, ksi ^A (Mpa) ^B	65 (447)	130 (896)	40 (275)	50 (345)	50 (345)	
Yield Strength at 0.5 % extension under load, ksi ^A (MPa) ^B	28 (193) min	89 (621) ^C	10 (69) min	40 (275) min	15 to 29 (103 to 200)	
Elongation in 2 in. or 50 mm, min %	30	6	35	7	35	

^Aksi = 1000 psi.

^BSee Appendix.

^CYield strength at 0.2 % offset, min, ksi^A (Mpa)^B.

7.1.4 Alloy C65500 is supplied in tempers O30 (extruded and annealed) and O61 (annealed).

8. Mechanical Property Requirements

8.1 *Tensile, Yield, and Elongation:*

8.1.1 Product furnished under this specification shall conform to the tensile, yield, and elongation requirements prescribed in Table 2, for the alloy specified in the ordering information, when tested in accordance with Test Methods E 8.

8.1.1.1 Only tensile, yield, or elongation test results shall be a basis for rejection based upon mechanical properties.

8.2 *Rockwell Hardness:*

8.2.1 Product furnished from Alloy C63020 in TQ30 temper shall have a minimum hardness of 26 on the Rockwell C scale when tested in accordance with Test Methods E 18.

8.2.1.1 Rockwell hardness test results shall not be a basis for product rejection.

9. Other Requirements

9.1 *Nondestructive Testing:*

9.1.1 Unless otherwise agreed upon between the supplier and the purchaser, the pipe or tube shall be tested for defects either in the final drawn, annealed, or specified temper or in the drawn temper before the final anneal. Unless otherwise specified, the manufacturer shall have the option of testing the pipe or tube by one of the following tests:

9.1.2 *Electromagnetic Examination (Eddy Current)*—Each tube or pipe in nominal sizes from 1/8 in. (3.2 mm) up to and including 2 1/2 in. (63.5 mm), regular and extra-strong, shall be subjected to an eddy-current test. Tests shall follow the procedures of Practice E 243 except for the determination of “end effect.” The pipe or tube shall be passed through an eddy-current testing unit adjusted to detect an artificial defect of a size and shape defined as follows:

NOTE 3—End effect is that length of the pipe or tube that travels through the coil until the testing unit has stabilized and is able to detect flaws. The magnitude of the spike generated when an end passes through the test coils is such that it disrupts testing momentarily.

9.1.2.1 *Artificial Defects*—Round bottom-notch standards with a profile as defined in Practice E 243, rounded to the nearest 0.001 in. (0.025 mm) shall be 10 % of the specified wall thickness. Notch-depth tolerances shall be ±0.0005 in. (0.013 mm). Alternatively, when a manufacturer uses speed-insensitive equipment that can select a maximum unbalance signal, a maximum unbalance signal of 0.3 % shall be used.

9.1.2.2 *Retesting*—Pipes or tubes that do not activate the signaling device of the eddy-current tester shall be considered as conforming to the requirements of this test. Lengths with discontinuities, indicated by the testing unit, at the option of the manufacturer, may be reexamined or retested to determine whether the discontinuity is cause for rejection. Signals that are found to have been caused by soil, moisture, or minor mechanical damage shall not be cause for rejection, provided the pipe or tube dimensions are still within the prescribed limits and the pipe or tube is suitable for its intended application.

9.1.3 *Pressure Tests*—Each pipe or tube selected in accordance with 13.3 shall withstand the pressure test of either 9.1.3.1 or 9.1.3.2.

9.1.3.1 *Hydrostatic Test*—Each pipe or tube shall withstand,

without showing evidence of leakage, an internal hydrostatic pressure sufficient to subject the material to a fiber stress of 7000 psi (48 MPa). The pipe or tube need not be tested at a hydrostatic pressure of over 1000 psi (6.9 MPa) unless so specified. At the option of the manufacturer, annealed pipe with wall thickness up to 0.083 in. (2.11 mm), inclusive, may be tested in the drawn condition, before annealing. Fiber stress shall be determined by the following equation for thin, hollow cylinders under tension:

$$P = 2St/(D - 0.8t) \tag{1}$$

where:

P = hydrostatic pressure, psi (MPa);

t = thickness of pipe or tube wall, in. (mm);

D = outside diameter of the pipe or tube, in. (mm); and

S = allowable fiber stress of the material, psi (MPa).

9.1.3.2 *Pneumatic Test*—Each pipe or tube shall be pressurized to a minimum of 60 psi (415 kPa), air for 5 s, without showing evidence of leakage. The test method used shall permit easy visual detection of any leakage, such as by submerging the tube under water or by pressure differential method.

10. Dimensions, Mass, and Permissible Variations

10.1 *General:*

10.1.1 The standard method of specifying wall thickness shall be in decimal fractions of an inch.

10.1.2 For the purpose of determining conformance with the dimensional requirements prescribed in this specification, any measured value outside the specified limiting values for any dimension may be cause for rejection.

10.1.3 Tolerances on a given tube may be specified with respect to any two, but not all three, of the following: outside diameter, inside diameter, wall thickness.

NOTE 4—Blank spaces in the tolerance tables indicate either that the product is not generally available or that no tolerances have been established.

10.2 *Dimensions*—Dimensions and theoretical weights of nominal pipe sizes shall be in accordance with Table 3.

10.3 *Wall Thickness Tolerances*—Wall thickness tolerances for pipe shall be in accordance with Tables 4 and 5. Wall thickness tolerances for tube shall be in accordance with Tables 6-8.

10.4 *Diameter Tolerances*—Diameter tolerances for pipe and tube shall be as follows:

10.4.1 *Diameter Tolerances for Pipe:*—

Nominal Pipe Size, in. (mm)	Diameter Tolerance, in. (mm)
1 1/2 (38.1) and under	+0.016 – 0.031 (+0.40 – 0.79)
Over 1 1/2 (38.1)	±1 % of specified diameter

10.4.2 The dimensional limits of nominal pipe sizes are shown in Tables 4 and 5.

10.4.3 Diameter tolerances for tube shall be in accordance with Table 9.

10.5 *Length Tolerances:*

10.5.1 Length tolerances shall be in accordance with Table 10.

10.5.2 *Schedule of Tube Lengths*—Specific and stock

TABLE 3 Dimensions and Weights of Copper Alloy Pipe, Standard Pipe Sizes

Nominal or Standard Pipe Size, in.	Dimension, in. (mm)				Theoretical Weight, lb/ft (kg/m)		
	Outside Diameter	Inside Diameter	Wall Thickness	Cross-Sectional Area of Bore, in. ² (cm ²)	Copper Alloy UNS No.		
					C61300 and C61400	C65500	C65100
Regular							
1/8	0.405 (10.3)	0.269 (6.83)	0.068 (1.73)	0.057 (0.367)	0.246 (0.366)	0.266 (0.395)	0.273 (0.406)
1/4	0.540 (13.7)	0.364 (9.25)	0.088 (2.24)	0.104 (0.670)	0.427 (0.634)	0.462 (0.686)	0.474 (0.704)
3/8	0.675 (17.1)	0.493 (12.5)	0.091 (2.31)	0.191 (1.23)	0.571 (0.849)	0.617 (0.917)	0.633 (0.941)
1/2	0.840 (21.3)	0.622 (15.8)	0.109 (2.77)	0.304 (1.96)	0.856 (1.27)	0.925 (1.37)	0.949 (1.41)
3/4	1.050 (26.7)	0.824 (20.9)	0.113 (2.87)	0.533 (3.44)	1.14 (1.69)	1.23 (1.83)	1.26 (1.88)
1	1.315 (33.4)	1.049 (26.6)	0.133 (3.38)	0.864 (3.57)	1.69 (2.51)	1.83 (2.72)	1.87 (2.79)
1 1/4	1.660 (42.2)	1.380 (35.1)	0.140 (3.56)	1.496 (9.66)	2.29 (3.40)	2.47 (3.68)	2.53 (3.77)
1 1/2	1.900 (48.3)	1.610 (40.9)	0.145 (3.68)	2.036 (13.1)	2.74 (4.07)	2.95 (4.40)	3.03 (4.51)
2	2.375 (60.3)	2.067 (52.5)	0.154 (3.91)	3.356 (21.7)	3.67 (5.45)	3.97 (5.91)	4.07 (6.06)
2 1/2	2.875 (73.0)	2.469 (62.7)	0.203 (5.16)	4.788 (30.9)	5.83 (8.66)	6.30 (9.37)	6.46 (9.61)
3	3.500 (88.9)	3.068 (77.9)	0.216 (5.49)	7.393 (47.7)	7.62 (11.3)	8.24 (12.3)	8.45 (12.6)
3 1/2	4.000 (102)†	3.548 (90.1)	0.226 (5.74)	9.887 (63.8)	9.16 (13.6)	9.90 (14.7)	10.2 (15.1)
4	4.500 (114)	4.026 (102)	0.237 (6.02)	12.730 (82.1)	10.9 (16.2)	11.7 (17.5)	12.0 (17.9)
5	5.562 (141)	5.046 (128)	0.258 (6.55)	19.998 (129)	14.7 (21.8)	15.9 (23.6)	16.3 (24.3)
6	6.625 (168)	6.065 (154)	0.280 (7.11)	28.890 (186)	19.1 (28.4)	20.6 (30.7)	21.2 (31.5)
8	8.625 (219)	7.981 (203)	0.322 (8.18)	50.030 (323)	28.7 (42.7)	31.0 (46.2)	31.9 (47.4)
10	10.750 (273)	10.020 (255)	0.365 (9.27)	78.8 (508)	40.8 (90.1)	44.1 (65.6)	45.2 (67.3)
12	12.750 (324)	12.000 (305)	0.375 (9.52)	113.0 (729)	49.9 (74.1)	53.9 (80.2)	55.3 (82.3)
Extra Strong							
1/8	0.405 (10.3)	0.215 (5.46)	0.095 (2.41)	0.036 (0.232)	0.316 (0.470)	0.342 (0.508)	0.351 (0.522)
1/4	0.540 (13.7)	0.302 (7.67)	0.119 (3.02)	0.072 (0.464)	0.538 (0.799)	0.582 (0.865)	0.597 (0.887)
3/8	0.675 (17.1)	0.423 (10.7)	0.126 (3.20)	0.141 (0.909)	0.743 (1.10)	0.803 (1.19)	0.824 (1.22)
1/2	0.840 (21.3)	0.546 (13.9)	0.147 (3.73)	0.234 (1.51)	1.10 (1.63)	1.183 (1.76)	1.214 (1.80)
3/4	1.050 (26.7)	0.742 (18.8)	0.154 (3.91)	0.432 (2.79)	1.48 (2.20)	1.60 (2.39)	1.65 (2.45)
1	1.315 (33.4)	0.957 (24.3)	0.179 (4.55)	0.719 (4.64)	2.19 (3.25)	2.36 (3.52)	2.42 (3.61)
1 1/4	1.660 (42.2)	1.278 (32.5)	0.191 (4.85)	1.283 (8.28)	3.01 (4.47)	3.26 (4.85)	3.34 (4.97)
1 1/2	1.900 (48.3)	1.500 (38.1)	0.200 (5.08)	1.767 (11.4)	3.65 (5.42)	3.95 (5.88)	4.05 (6.03)
2	2.375 (60.3)	1.939 (49.3)	0.218 (5.54)	2.953 (19.1)	5.05 (7.50)	5.46 (8.12)	5.60 (8.34)
2 1/2	2.875 (73.0)	2.323 (59.0)	0.276 (7.01)	4.238 (27.3)	7.71 (11.4)	8.33 (12.4)	8.55 (12.7)
3	3.500 (88.9)	2.900 (73.7)	0.300 (7.62)	6.605 (42.6)	10.3 (15.3)	11.1 (16.6)	11.4 (17.0)
3 1/2	4.000 (102)	3.364 (85.5)	0.318 (8.08)	8.888 (57.3)	12.6 (18.7)	13.6 (20.2)	13.9 (20.8)
4	4.500 (114)	3.826 (97.2)	0.337 (8.56)	11.497 (74.)	15.1 (22.4)	16.3 (24.2)	16.7 (24.9)
5	5.562 (141)	4.812 (122)	0.375 (9.53)	18.186 (117)	20.9 (31.1)	22.6 (33.6)	23.2 (34.5)
6	6.625 (168)	5.761 (146)	0.432 (10.9)	26.067 (168)	28.7 (42.6)	31.1 (46.2)	31.9 (47.4)
8	8.625 (219)	7.625 (194)	0.500 (12.7)	45.664 (295)	43.6 (64.8)	47.2 (70.2)	48.4 (72.0)
10	10.750 (273)	9.750 (248)	0.500 (12.7)	74.7 (482)	55.1 (81.9)	59.5 (88.5)	61.1 (90.9)

TABLE 4 Dimensional Limits for Standard Pipe Sizes
Copper Alloy UNS No. C61300 and C61400

Nominal or Standard Pipe Size	Outside Diameter, in. (mm)	Regular				Extra Strong			
		Min	Max	Wall Thickness, in. (mm)	Min	Max	Wall Thickness, in. (mm)	Min	Max
1/8	0.405 (10.3)	0.374 (9.50)	0.421 (10.7)	0.068 (1.73)	0.061 (1.55)	0.075 (1.91)	0.095 (2.41)	0.086 (2.18)	0.105 (2.67)
1/4	0.540 (13.7)	0.509 (12.9)	0.556 (14.1)	0.088 (2.24)	0.079 (2.01)	0.097 (2.46)	0.119 (3.02)	0.107 (2.72)	0.131 (3.33)
3/8	0.675 (17.1)	0.644 (16.4)	0.691 (17.6)	0.091 (2.31)	0.082 (2.08)	0.100 (2.54)	0.126 (3.20)	0.113 (2.87)	0.139 (3.53)
1/2	0.840 (21.3)	0.809 (20.5)	0.856 (21.7)	0.109 (2.77)	0.098 (2.49)	0.120 (3.05)	0.147 (3.73)	0.132 (3.35)	0.162 (4.11)
3/4	1.050 (26.7)	1.019 (25.9)	1.066 (27.1)	0.113 (2.87)	0.102 (2.59)	0.124 (3.15)	0.154 (3.91)	0.139 (3.53)	0.169 (4.29)
1	1.315 (33.4)	1.284 (32.6)	1.331 (33.8)	0.133 (3.38)	0.120 (3.05)	0.146 (3.71)	0.179 (4.55)	0.161 (4.09)	0.197 (5.00)
1 1/4	1.660 (42.2)	1.629 (41.4)	1.676 (42.6)	0.140 (3.56)	0.126 (3.20)	0.154 (3.91)	0.191 (4.85)	0.172 (4.37)	0.210 (5.33)
1 1/2	1.900 (48.3)	1.869 (47.5)	1.916 (48.7)	0.145 (3.68)	0.131 (3.33)	0.160 (4.06)	0.200 (5.08)	0.180 (4.57)	0.220 (5.59)
2	2.375 (60.3)	2.351 (59.7)	2.399 (60.9)	0.154 (3.91)	0.139 (3.53)	0.169 (4.29)	0.218 (5.54)	0.196 (4.98)	0.240 (6.10)
2 1/2	2.875 (73.0)	2.846 (72.3)	2.904 (73.8)	0.203 (5.16)	0.183 (4.65)	0.223 (5.66)	0.276 (7.01)	0.248 (6.30)	0.304 (7.72)
3	3.500 (88.9)	3.465 (88.0)	3.535 (89.8)	0.216 (5.49)	0.194 (4.93)	0.238 (6.05)	0.300 (7.62)	0.270 (6.86)	0.330 (8.38)
3 1/2	4.000 (102)	3.960 (101)	4.040 (103)	0.226 (5.74)	0.203 (5.16)	0.249 (6.32)	0.318 (8.08)	0.286 (7.26)	0.350 (8.89)
4	4.500 (114)	4.455 (113)	4.545 (115)	0.237 (6.02)	0.213 (5.41)	0.261 (6.63)	0.337 (8.56)	0.303 (7.70)	0.371 (9.42)
5	5.562 (141)	5.506 (140)	5.618 (143)	0.258 (6.55)	0.232 (5.89)	0.284 (7.21)	0.375 (9.53)	0.338 (8.59)	0.413 (10.5)
6	6.625 (168)	6.559 (167)	6.691 (170)	0.280 (7.11)	0.252 (6.40)	0.308 (7.82)	0.432 (11.0)	0.389 (9.88)	0.475 (12.1)
8	8.625 (219)	8.539 (217)	8.711 (221)	0.322 (8.18)	0.290 (7.37)	0.354 (8.99)	0.500 (12.7)	0.450 (11.4)	0.550 (14.0)
10	10.750 (273)	10.643 (270)	10.858 (276)	0.365 (9.27)	0.329 (8.36)	0.402 (10.2)	0.500 (12.7)	0.450 (11.4)	0.550 (14.0)
12	12.750 (324)	12.623 (321)	12.878 (327)	0.375 (9.53)	0.338 (8.59)	0.413 (10.5)

lengths with ends shall be in accordance with Table 11.

10.6 *Squareness of Cut*—For pipe and tube in straight

lengths, the departure from squareness of the end of any pipe or tube shall not exceed the following:

TABLE 5 Dimensional Limits for Standard Pipe Sizes
Copper Alloy UNS No. C65100 and C65500

Nominal or Standard Pipe Size	Outside Diameter, in. (mm)	Min	Max	Regular			Extra Strong		
				Wall Thickness, in. (mm)	Min	Max	Wall Thickness, in. (mm)	Min	Max
1/8	0.405 (10.3)	0.374 (9.50)	0.421 (10.7)	0.068 (1.73)	0.065 (1.65)	0.083 (2.11)	0.095 (2.41)	0.090 (2.29)	0.123 (3.12)
1/4	0.540 (13.7)	0.509 (12.9)	0.556 (14.1)	0.088 (2.24)	0.084 (2.13)	0.102 (2.59)	0.119 (3.02)	0.107 (2.72)	0.144 (3.66)
3/8	0.675 (17.1)	0.644 (16.4)	0.691 (17.6)	0.091 (2.31)	0.086 (2.18)	0.103 (2.62)	0.126 (3.20)	0.120 (3.05)	0.146 (3.71)
1/2	0.840 (21.3)	0.809 (20.5)	0.856 (21.7)	0.109 (2.77)	0.104 (2.64)	0.122 (3.10)	0.147 (3.73)	0.140 (3.56)	0.166 (4.22)
3/4	1.050 (26.7)	1.019 (25.9)	1.066 (27.1)	0.113 (2.87)	0.107 (2.72)	0.124 (3.15)	0.154 (3.91)	0.146 (3.71)	0.171 (4.34)
1	1.315 (33.4)	1.284 (32.6)	1.331 (33.8)	0.133 (3.38)	0.126 (3.20)	0.145 (3.68)	0.179 (4.55)	0.170 (4.32)	0.196 (4.98)
1 1/4	1.660 (42.2)	1.629 (41.4)	1.676 (42.6)	0.140 (3.56)	0.133 (3.38)	0.151 (3.84)	0.191 (4.85)	0.181 (4.60)	0.207 (5.26)
1 1/2	1.900 (48.3)	1.869 (47.5)	1.916 (48.7)	0.145 (3.68)	0.138 (3.51)	0.156 (3.96)	0.200 (5.08)	0.190 (4.83)	0.216 (5.49)
2	2.375 (60.3)	2.351 (59.7)	2.399 (60.9)	0.154 (3.91)	0.146 (3.71)	0.164 (4.17)	0.218 (5.54)	0.207 (5.26)	0.233 (5.92)
2 1/2	2.875 (73.0)	2.846 (72.3)	2.904 (73.8)	0.203 (5.16)	0.193 (4.90)	0.217 (5.51)	0.276 (7.01)	0.262 (6.65)	0.295 (7.49)
3	3.500 (88.9)	3.465 (88.0)	3.535 (89.8)	0.216 (5.49)	0.205 (5.21)	0.230 (5.84)	0.300 (7.62)	0.285 (7.24)	0.321 (8.15)
3 1/2	4.000 (102)	3.960 (101)	4.040 (103)	0.226 (5.74)	0.215 (5.46)	0.240 (6.10)	0.318 (8.08)	0.302 (7.67)	0.340 (8.64)
4	4.500 (114)	4.455 (113)	4.545 (115)	0.237 (6.02)	0.225 (5.72)	0.252 (6.40)	0.337 (8.56)	0.320 (8.13)	0.360 (9.14)
5	5.562 (141)	5.506 (140)	5.618 (143)	0.258 (6.55)	0.245 (6.22)	0.275 (6.99)	0.375 (9.53)	0.356 (9.04)	0.400 (10.2)
6	6.625 (168)	6.559 (167)	6.691 (170)	0.280 (7.11)	0.266 (6.76)	0.298 (7.57)	0.432 (11.0)	0.410 (10.4)	0.461 (11.7)
8	8.625 (219)	8.539 (217)	8.711 (221)	0.322 (8.18)	0.299 (7.59)	0.349 (8.86)	0.500 (12.7)	0.465 (11.8)	0.554 (13.8)
10	10.750 (273)	10.643 (270)	10.858 (276)	0.365 (9.27)	0.336 (8.53)	0.400 (10.2)	0.500 (12.7)	0.460 (11.7)	0.548 (13.9)
12	12.750 (324)	12.623 (321)	12.878 (327)	0.375 (9.53)	0.345 (8.76)	0.410 (10.4)

TABLE 6 Wall Thickness Tolerances for Copper Alloy UNS No. C61300 and C61400 Tube (Not Applicable to Pipe)

NOTE 1—Maximum deviation at any point—the following tolerances are plus and minus; if tolerances all plus or all minus are desired, double the values given.

Wall Thickness, in. (mm)	Outside Diameter, in. (mm)		
	Over 5/8 to 1 (15.9 to 25.4) incl	Over 1 to 2 (25.4 to 50.8) incl	Over 2 to 4 (50.8 to 102) incl
Over 0.024 (0.610) to 0.034 (0.864), incl	0.003 (0.076)	0.004 (0.10)	0.004 (0.10)
Over 0.034 (0.864) to 0.057 (1.45), incl	0.0045 (0.11)	0.005 (0.13)	0.006 (0.15)
Over 0.057 (1.45) to 0.082 (2.08), incl	0.005 (0.13)	0.006 (0.15)	0.008 (0.20)
Over 0.082 (2.08) to 0.119 (3.02), incl	0.007 (0.18)	0.008 (0.20)	0.009 (0.23)
Over 0.119 (3.02) to 0.164 (4.17), incl	0.009 (0.23)	0.010 (0.25)	0.012 (0.30)

10.6.1 Pipe:

Outside Diameter	Tolerance
Up to 5/8 in. (15.9 mm), incl	0.010 in. (0.25 mm)
Over 5/8 in. (15.9 mm)	0.016 in./in. (0.016 mm/mm) of diameter

10.6.2 Tube:

Outside Diameter	Tolerance
Up to 5/8 in. (15.9 mm), incl	0.010 in. (0.25 mm)
Over 5/8 in. (15.9 mm)	0.016 in./in. (0.016 mm/mm) of diameter

10.7 The nominal density of materials used in the manufacture of products for this specification are shown in Table X2.1.

11. Workmanship, Finish and Appearance

11.1 The product shall be free from defects, but blemishes of a nature that do not interfere with the intended application are acceptable.

11.2 Copper alloy UNS Nos. 65100 and 65500 may be supplied in the following finishes:

11.2.1 *Specially Cleaned*—Intended for brazing and welded operations.

11.2.2 Plain-pickled, or with dull iridescent film, on both the inside and outside surfaces

NOTE 5—Plain-pickled material normally has a brick red color with cuprous and silicon oxides still adherent.

11.3 Copper alloy UNS Nos. C61300 and C61400 shall be supplied with the normal as-extruded or annealed tarnish unless otherwise specified on the purchase order.

12. Sampling

12.1 *Sampling*—The lot size, portion size, and selection of sample pieces shall be as follows:

12.1.1 *Lot Size*—For tube, the lot size shall be 10 000 lb (550 kg) or fraction thereof. For pipe, the lot size shall be as follows:

Nominal Pipe Size, in (mm)	Lot Weight, lb. (kg)
Up to 4 (101.6), incl	10 000 (4 550) or fraction thereof
Over 4 (101.6)	40 000 (18 100) or fraction thereof

12.1.2 *Portion Size*—Sample pieces shall be taken for test purposes from each lot according to the following schedule. (Each sample shall be from a separate tube or pipe.)

Number of Pieces in Lot	Number of Sample Pieces to Be Taken
1 to 50	1
51 to 200	2
201 to 1500	3
Over 1500	0.2 % of total number of pieces in the lot

12.1.3 *Chemical Analysis*—Samples for chemical analysis shall be taken in accordance with Practice E 255. Drillings,

TABLE 7 Wall Thickness Tolerances for Copper Alloy UNS No. C65500 Tube (Not Applicable to Pipe)

NOTE 1—Maximum deviation at any point—the following tolerances are plus and minus: if tolerances all plus or all minus are desired, double the values given.

Wall Thickness, in. (mm)	Outside Diameter, ^A in. (mm)							
	1/32 to 1/8 (0.792 to 3.18), incl	Over 1/8 to 5/16 (3.18 to 15.9), incl	Over 5/16 to 1 (15.9 to 25.4), incl	Over 1 to 2 (25.4 to 50.8), incl	Over 2 to 4 (50.8 to 102), incl	Over 4 to 7 (102 to 173), incl	Over 7 to 10 (173 to 251), incl	
Up to 0.017 (0.432), incl	0.0025 (0.064)	0.0015 (0.038)	0.002 (0.051)	0.0025 (0.064)
Over 0.017 (0.432) to 0.024 (0.610), incl	0.004 (0.10)	0.0025 (0.064)	0.0025 (0.064)	0.003 (0.076)
Over 0.024 (0.610) to 0.034 (0.864), incl	0.004 (0.10)	0.003 (0.076)	0.003 (0.076)	0.004 (0.10)	0.005 (0.13)
Over 0.034 (0.864) to 0.057 (1.45), incl	0.004 (0.10)	0.001 (0.10)	0.0045 (0.11)	0.0045 (0.11)	0.0065 (0.17)	0.009 (0.23)
Over 0.057 (1.45) to 0.082 (2.08), incl	...	0.0045 (0.11)	0.005 (0.13)	0.005 (0.13)	0.0075 (0.19)	0.010 (0.25)	0.013 (0.33)	0.013 (0.33)
Over 0.082 (2.08) to 0.119 (3.02), incl	...	0.005 (0.13)	0.0065 (0.17)	0.0065 (0.17)	0.009 (0.23)	0.011 (0.28)	0.014 (0.36)	0.014 (0.36)
Over 0.119 (3.02) to 0.164 (4.17), incl	...	0.007 (0.18)	0.007 (0.18)	0.0075 (0.19)	0.010 (0.25)	0.013 (0.33)	0.015 (0.38)	0.015 (0.38)
Over 0.164 (4.17) to 0.219 (5.56), incl	0.009 (0.23)	0.010 (0.25)	0.012 (0.30)	0.015 (0.38)	0.018 (0.46)	0.018 (0.46)
Over 0.219 (5.56) to 0.283 (7.19), incl	0.012 (0.30)	0.013 (0.33)	0.015 (0.38)	0.018 (0.46)	0.020 (0.51)	0.020 (0.51)
Over 0.283 (7.19) to 0.379 (9.62), incl	0.014 (0.36)	6 ^B	6 ^B	8 ^B	8 ^B	8 ^B
Over 0.379 (9.62)	6 ^B	6 ^B	8 ^B	8 ^B	8 ^B

^AWhen tube is ordered by outside and inside diameters, the maximum plus and minus deviation of the wall thickness from the nominal at any point shall not exceed the values given in this table by more than 50 %.

^BPercent of the specified wall thickness expressed to the nearest 0.001 in. (0.025 mm).

TABLE 8 Wall Thickness Tolerances for Copper Alloy UNS No. C65100 Tube (Not Applicable to Pipe)

NOTE 1—Maximum deviation at any point—the following tolerances are plus and minus: if tolerances all plus or all minus are desired, double the values given.

Wall Thickness, in. (mm)	Outside Diameter, ^A in. (mm)							
	1/32 (0.792) to 1/8 (3.18), incl	Over 1/8 (3.18) to 5/16 (15.9), incl	Over 5/16 (15.9) to 1 (25.4), incl	Over 1 (25.4) to 2 (50.8), incl	Over 2 (50.8) to 4 (102), incl	Over 4 (102) to 7 (213), incl	Over 7 (213) to 10 (254), incl	
Up to 0.017 (0.432), incl	0.002 (0.051)	0.001 (0.025)	0.0015 (0.038)	0.002 (0.051)
Over 0.017 (0.432) to 0.024 (0.610), incl	0.003 (0.076)	0.002 (0.051)	0.002 (0.051)	0.0025 (0.064)
Over 0.024 (0.610) to 0.034 (0.864), incl	0.003 (0.076)	0.0025 (0.064)	0.0025 (0.064)	0.003 (0.076)	0.004 (0.10)
Over 0.034 (0.864) to 0.057 (1.45), incl	0.003 (0.076)	0.003 (0.076)	0.0035 (0.089)	0.0035 (0.089)	0.005 (0.13)	0.007 (0.18)
Over 0.057 (1.45) to 0.082 (2.08), incl	...	0.0035 (0.089)	0.004 (0.10)	0.004 (0.10)	0.006 (0.15)	0.008 (0.20)	0.010 (0.26)	0.010 (0.26)
Over 0.082 (2.08) to 0.119 (3.02), incl	...	0.004 (0.10)	0.005 (0.13)	0.005 (0.13)	0.007 (0.18)	0.009 (0.23)	0.011 (0.28)	0.011 (0.28)
Over 0.119 (3.02) to 0.164 (4.17), incl	...	0.005 (0.13)	0.006 (0.15)	0.006 (0.15)	0.008 (0.20)	0.010 (0.25)	0.012 (0.30)	0.012 (0.30)
Over 0.164 (4.17) to 0.219 (5.56), incl	...	0.007 (0.18)	0.0075 (0.19)	0.008 (0.20)	0.010 (0.25)	0.012 (0.30)	0.014 (0.36)	0.014 (0.36)
Over 0.219 (5.56) to 0.283 (7.19), incl	0.009 (0.23)	0.010 (0.25)	0.012 (0.30)	0.014 (0.36)	0.016 (0.44)	0.016 (0.44)
Over 0.283 (7.19) to 0.379 (9.62), incl	0.012 (0.30)	5 ^B	5 ^B	6 ^B	6 ^B	6 ^B
Over 0.379 (9.62), incl	5 ^B	5 ^B	6 ^B	6 ^B	6 ^B

^AWhen tube is ordered by outside and inside diameters, the maximum plus and minus deviation of the wall thickness from the nominal at any point shall not exceed the values given in this table by more than 50 %.

^BPercent of the specified wall thickness expressed to the nearest 0.001 in. (0.025 mm).

millings, and so forth shall be taken in approximately equal weight from each of the sample pieces selected in accordance with 12.1.2 and combined into one composite sample. The minimum weight of the composite sample shall be 150 minimum.

12.1.3.1 Instead of sampling in accordance with Practice E 255, the manufacturer shall have the option of determining conformance to chemical composition as follows: The manufacturer shall analyze samples taken at the time the castings are poured or from the semifinished product. When the chemical composition of the product is determined during the course of manufacture, sampling and analysis of the finished product shall not be required. The number of samples taken for determination of chemical compositions shall be as follows:

12.1.3.2 When samples are taken at the time the castings are poured, at least one sample shall be taken for each group of castings poured simultaneously from the same source of molten metal.

TABLE 9 Average Diameter Tolerances for Tube (Not Applicable to Pipe)

Copper Alloy UNS No.	Tolerance, ±in. (mm) ^A		
	Specified Diameter, in. (mm)	C61300 and C61400	C65100 C65500
Up to 1/8 (3.18), incl	...	0.002 (0.051) ^B	0.003 (0.076) ^B
Up to 1/8 (3.18), incl	...	0.002 (0.051) ^C	0.025 (0.064) ^C
Over 1/8 (3.18) to 5/16 (15.9), incl	0.004 (0.10)	0.002 (0.051)	0.0025 (0.064)
Over 5/16 (15.9) to 1 (25.4), incl	0.005 (0.13)	0.0025 (0.064)	0.003 (0.076)
Over 1 (25.4) to 2 (50.8), incl	0.006 (0.15)	0.003 (0.076)	0.004 (0.10)
Over 2 (50.8) to 3 (76.2), incl	0.007 (0.18)	0.004 (0.10)	0.005 (0.13)
Over 3 (76.2) to 4 (102), incl	...	0.005 (0.13)	0.006 (0.15)
Over 4 (102) to 5 (127), incl	...	0.006 (0.15)	0.008 (0.20)
Over 5 (127) to 6 (152), incl	...	0.007 (0.18)	0.009 (0.23)
Over 6 (152) to 8 (203), incl	...	0.008 (0.20)	0.010 (0.25)
Over 8 (203) to 10 (254), incl	...	0.010 (0.25)	0.013 (0.33)

^ATolerance applies to inside or outside diameters, except as noted.

^BOn inside diameter.

^COn outside diameter.

12.1.3.3 When samples are taken from the semifinished

TABLE 10 Length Tolerances

NOTE 1—Tolerances are all plus—If all minus tolerances are desired, use the same value. If tolerances plus and minus are desired, halve the values given.

Length	Tolerances, in. (mm), Applicable Only to Full Length Pieces		
	Outside Diameters up to 1 in. (25.4 mm), incl	Outside Diameters over 1 in. (25.4 mm) to 4 in. (102 mm), incl	Outside Diameters over 4 in. (102 mm)
Specific lengths:			
Up to 6 in. (152 mm), incl	1/32(0.79)	1/16 (1.6)	...
Over 6 in. (152 mm) to 2 ft (610 mm), incl	1/16(1.6)	3/32 (2.4)	1/8 (3.2)
Over 2 ft (610 mm) to 6 ft (1.83 m), incl	3/32(2.4)	1/8 (3.2)	1/4 (6.4)
Over 6 ft (1.83 m) to 14 ft (4.27 m), incl	1/4(6.4)	1/4 (6.4)	1/4 (6.4)
Over 14 ft (4.27 m)	1/2(13)	1/2 (13)	1/2 (13)
Specific lengths with ends	1 (25)	1 (25)	1 (25)
Stock lengths with or without ends	1 ^A (25)	1 ^A (25)	1 ^A (25)

^AAs stock lengths are cut and placed in stock in advance of orders, departure from this tolerance is not practicable.

TABLE 11 Schedule of Tube Lengths (Specific and Stock) with Ends

Outside Dimensions, in. (mm)	Specific Length, ft (m)	Shortest Permissible Length, ^A % of Specific Length	Maximum Permissible Weight of Ends, % of Lot Weight
Up to 1 (25.4), incl	6 (1.83) to 20 (6.10), incl	70	20
Over 1 (25.4) to 2 (50.8), incl	6 (1.83) to 20 (6.10), incl	60	25
Over 2 (50.8) to 3 (76.2), incl	6 (1.83) to 20 (6.10), incl	55	30
Over 3 (76.2) to 4 (102), incl	6 (1.83) to 20 (6.10), incl	50	40

^AExpressed to nearest 1/3 ft.

product, a sample shall be taken to represent each 10 000 lb (4 550 kg), or fraction thereof for all tube and for pipe sizes up to 4 in. For pipe sizes over 4 in., a sample shall be taken to represent 40 000 lb (18 100 kg). In all instances, not more than one sample shall be required per piece.

12.1.3.4 In the event that heat identification or traceability is required, the purchaser shall specify the details desired.

NOTE 6—Because of the discontinuous nature of the processing of castings into wrought products, it is not practical to identify specific casting analysis with a specific quantity of finished material

12.1.4 *Pressure Tests*—See 13.1.3.

13. Number of Test and Retests

13.1 *Tests*:

13.1.1 *Chemical Analysis*—At least two replicate analyses for each element with a limiting value shall be conducted.

13.1.2 *Mechanical Tests*—For the mechanical tests, a specimen shall be taken from each of the pieces selected in accordance with 12.1. The required mechanical test shall be made on each of the specimens so selected.

13.1.3 *Pressure Tests*—For the purpose of pressure testing only, a number of lengths of pipe or tube to be tested as

described in 9.1.2 shall be randomly selected from the lot as follows:

Lot Size	Number of Pipes or Tubes	Sample Size
1–8		5
9–50		7
51–150		20
151–280		32
281–500		50
501–1200		80
1201–3200		125

13.2 Retests:

13.2.1 If the chemical analysis fails to conform to the specified limits, analysis shall be made on a new composite sample prepared from additional pieces selected in accordance with 12.1. The results of this retest shall comply with the specified requirements.

13.2.2 If the percentage elongation of any tension test specimen is less than that specified and if any part of the fracture is outside the middle two thirds of the gage length or in a punched or scribed mark within the reduced section, a retest shall be allowed.

13.2.3 If the results of testing to determine the mechanical properties fail to meet the specified limits, testing shall be repeated on each of two additional specimens taken from different pieces of material from the same production lot. The results of both retest shall comply with the specified requirements.

13.2.4 If any test specimen representing a lot fails to conform to the requirements of 9.1.2, two additional specimens may be submitted for check analysis, or subjected to any tests in which the original specimen failed, but both of these specimens shall conform to the requirements specified.

14. Specimen Preparation

14.1 *Chemical Analysis*—Preparation of the analytical test specimen is the responsibility of the reporting laboratory.

14.2 *Tensile Test*:

14.2.1 The test specimen shall be of the full section of the tube and shall conform to the requirements of the section titled Specimens for Pipe and Tube in Test Methods E 8.

14.2.2 When the limitations of the testing equipment preclude the use of a full-section specimen, a specimen conforming to Type 1, Fig. 13, of Test Methods E 8, Tension Test Specimens for Large Diameter Tubular Products, shall be used.

14.3 *Rockwell Hardness*:

14.3.1 The test specimen shall be of the size and shape to permit testing with the available test equipment.

14.3.2 The surface of the specimen shall be sufficiently flat and smooth to permit the accurate determination of hardness.

14.3.3 The test specimen shall be sufficiently free of scale and foreign material to permit the accurate determination of hardness.

14.3.4 Care shall be taken to avoid changing the material's condition through either cold working or heating, or both.

15. Test Methods

15.1 The properties enumerated in this specification shall, in case of disagreement, be determined in accordance with the following applicable methods of the American Society for

Testing and Materials:

Test	Test Method
Copper	E 478
Lead	E 478
Iron	E 478
Zinc	E 478
Aluminum	E 54
Manganese	E 62
Silicon	E 62
Tin	E 478
Nickel (including cobalt)	E 478
Phosphorus	E 62
Electromagnetic (eddy current)	E 243
Rockwell hardness	E 18
Yield test	E 8
Tension test	E 8
Elongation	E 8

See also 14.2, 14.3, and 14.4.

15.2 Tension test specimens shall be taken from the full section of the tube and shall conform to the requirements of Specimens for Pipe and Tube of Test Methods E 8, unless the limitations of the testing equipment preclude the use of such a specimen. Test specimens conforming to Type 1, Figure 13, Tension Test Specimens for Large-Diameter Tubular Products, of Test Methods E 8 may be used when a full-section specimen cannot be tested.

15.3 Whenever tension test results are obtained from both full-size and from machined test specimens and they differ, the results obtained from full-size test specimens shall be used to determine conformance to the specification requirements.

15.4 Tension test results on material covered by this specification are not seriously affected by variations in the speed of testing. A considerable range of testing speeds is permissible; however, the rate of stressing to obtain the yield strength should not exceed 100 ksi (690 mPa)/min. Above the yield strength, the movement per minute of the testing machine head under load should not exceed 0.5 in./in. (12 mm/mm) of gage length (or distance between grips for full-section specimens).

16. Significance of Numerical Limits

16.1 For determining compliance with the specified limits of the properties listed in the following table, an observed or a calculated value shall be rounded as indicated in accordance with the rounding method of Practice E 29.

Property	Rounded Unit for Observed or Calculated Value
Chemical composition	nearest unit in the last right-hand significant digit used in expressing the limiting value
Tensile strength/yield strength	nearest ksi (nearest 5 Mpa)
Elongation	nearest 1 %

17. Inspection

17.1 The manufacturer shall inspect and make tests necessary to verify that the product furnished conforms to the specification requirements.

17.2 The manufacturer shall afford the inspector represent-

ing the purchaser all reasonable facilities to satisfy that the material is being furnished in accordance with the specified requirements.

18. Rejection and Rehearing
18.1 Rejection:

18.1.1 Product that fails to conform to the specification requirements, when tested by the purchaser or purchaser's agent, may be rejected.

18.1.2 Rejection shall be reported to the manufacturer or supplier promptly. In addition, a written notification of rejection shall follow.

18.1.3 In case of dissatisfaction with the results of the test upon which rejection is based, the manufacturer, or supplier, may make claim for a rehearing.

18.2 *Rehearing*—As a result of product rejection, the manufacturer, or supplier, may make claim for a retest to be conducted by the manufacturer, or supplier, and the purchaser. Samples of the rejected product shall be taken in accordance with the product specification and subjected to test by both parties using the test method(s) specified in the product specification, or, alternately, upon agreement of both parties, an independent laboratory may be selected for the test(s) using the test method(s) specified in the product specification.

19. Certification

19.1 When specified in the contract or purchase order, the purchaser shall be furnished certification that samples representing each lot have been tested or inspected, or both, as directed in this specification and the requirements have been met.

19.2 When identified in the ordering information that the product is purchased for ASME Boiler and Pressure Vessel Code applications, certification to this specification shall be mandatory.

20. Report

20.1 When specified in the contract or purchase order, a report of test results shall be furnished.

21. Packaging and Package Marking

21.1 The product shall be separated by size, composition, and temper, and prepared in such a manner as to ensure acceptance by common carrier for transportation and to afford protection from the normal hazards of transportation.

21.2 Each shipping unit shall be legibly marked with the purchase order number, metal or alloy designation, temper, size, gross and net weight, and name of supplier. The specification number shall be shown, when specified.

22. Keywords

22.1 seamless copper alloy pipe; seamless copper alloy tube

APPENDIXES

(Nonmandatory Information)

X1. METRIC EQUIVALENTS

X1.1 The SI unit for strength properties is shown in accordance with the International System of Units (SI). The derived SI unit for force is the Newton (N), which is defined as the force that when applied to a body having a mass of one kilogram gives it an acceleration of one metre per second squared ($N = kg \cdot m/s^2$). The derived SI unit for pressure or

stress is the Newton per square metre (N/m^2), which has been named the Pascal (Pa) by the General Conference on Weights and Measures. Since $1 \text{ ksi} = 6\,894\,757 \text{ Pa}$, the metric equivalents are expressed as megapascal (MPa), which is the same as MN/m^2 and N/mm^2 .

X2. DENSITY OF COPPER ALLOYS

X2.1 The densities of the alloys covered by this specification are given in Table X2.1.

TABLE X2.1 Densities

Copper Alloy UNS Number	Density, lb/in. ³ (g/cm ³)
C61300	0.285 (7.89)
C61400	0.285 (7.89)
C63020	0.269 (7.45)
C65100	0.316 (8.78)
C65500	0.308 (8.53)

SUMMARY OF CHANGES

Committee B05 has identified the location of selected changes to this specification since the last issue that may impact the use of this standard.

- (1) This specification has been changed editorially to match the structure and selected wording of the Outline of Form. Included is the addition and use of referenced standards for simplification purposes.
- (2) Table 2 has been changed technically. Specifically, the H80 temper for Alloy C65100 has been changed to H50 to match

the description that was printed in Section 7. The O30 temper listed in Section 7 of the previous edition for Alloy C65100 has been added to Table 2. The hardness values for the TQ30 temper of Alloy C63020 has been added to Table 2.

The American Society for Testing and Materials takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).