



Designation: **B 36/B 36M – 9501**

Standard Specification for Brass Plate, Sheet, Strip, And Rolled Bar¹

This standard is issued under the fixed designation B 36/B 36M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

1. Scope*

1.1 This specification ~~covers~~ establishes the requirements for brass plate, sheet, strip, and rolled bar of the following alloys:²

¹ This specification is under the jurisdiction of ASTM Committee ~~B-5~~ B05 on Copper and Copper Alloys and is the direct responsibility of Subcommittee B05.01 on Plate, Sheet, and Strip.

Current edition approved ~~Feb. 15, 1995. Published April 1995.~~ 10, 2001. Published August 2001. Originally published as B 36 – 20 T. Last previous edition ~~B 36 – 91a^{ε1}.~~ B 36/36M – 95.

***A Summary of Changes section appears at the end of this standard.**

		Nominal Composition	
Copper Alloy UNS No.³	Previously Used Designation	Copper, %	Zinc, %
<u>Copper Alloy UNS No.</u>	<u>Previously Used Designation</u>	<u>Copper, %</u>	<u>Zinc, %</u>
C21000	4	95	-5
C21000	1	95	5
C22000	2	90	10
C22000	2	90	10
C22600	...	87.5	12.5
C22600	...	87.5	12.5
C23000	3	85	15
C23000	3	85	15
C24000	4	80	20
C24000	4	80	20
C26000	6	70	30
C26000	6	70	30
C26800	8	66	34
C26800	8	66	34
C27200	9	63	37
C27200	9	63	37
C28000	...	60	40
C28000	...	60	40

1.2 The values stated in either inch-pound units or SI units are to be regarded separately as standard. ~~Within the text, the SI units are shown in brackets.~~ The values stated in each system are may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from ~~the~~ two systems may results in nonconformance with the ~~specification.~~³ standard.

2. Referenced Documents

2.1 The following documents ~~of in the current issue in effect on date of material purchase~~ Book of Standards form a part of this specification to the extent referenced herein:

2.2 *ASTM Standards:*

B 248 Specification for ~~General~~ Requirements for Wrought Copper and Copper- Alloy Plate, Sheet, Strip, and Rolled Bar³

² SAE Specifications CA210, CA220, CA230, CA240, CA260, CA268, and CA272 conform to the requirements for Copper Alloy UNS Nos. C21000, C22000, C23000, C24000, C26000, C26800, and C27200, respectively.

³ The UNS system for copper and copper alloys (see Practice E 527) is a simple expansion

³ *Annual Book of the former standard designation system accomplished by the addition of a prefix "C" and a suffix "00." The suffix can be used to accommodate composition variations of the base alloy-ASTM Standards, Vol 02.01.*

~~B 248M Specification for General Requirements for Wrought Copper and Copper- Alloy Plate, Sheet, Strip, and Rolled Bar [Metric]³~~
~~B 601 Practice for Temper Designations for Copper and Copper Alloys—Wrought and Cast³~~
~~B 846 Standard Terminology for Copper and Copper Alloys³~~
~~E 8 Test Methods of for Tension Testing of Metallic Materials⁴~~
~~E 8M Test Methods of for Tension Testing of Metallic Materials [Metric]⁴~~
~~E-527 Practice 112 Test Methods for Numbering Metals and Determining Grain Size⁴~~
~~E 478 Test Methods for Chemical Analysis of Copper Alloys-(UNS)⁵⁶~~

3. Ordering Information

~~3.1 Orders for material under this specification should include the General Requirements~~
~~3.1 The following information:~~
~~3.1.1 Quantity;~~
~~3.1.2 Name sections of material: brass;~~
~~3.1.3 Form Specification B 248 [B 248M] constitute a part of material: plate, sheet, strip, or rolled bar;~~
~~3.1.4 Alloy number (see 1.1);~~
~~3.1.5 Temper (see Section 5);~~
~~3.1.6 Dimensions: thickness this specification:~~
~~3.1.1 Terminology~~
~~3.1.2 Materials and width; Manufacture~~
~~3.1.3 Dimensions, Mass, and length if applicable.~~
~~3.1.7 How furnished: rolls, stock lengths with or without ends, specific lengths with or without ends (see 8.4);~~
~~3.1.8 Type permissible Variations~~
~~3.1.4 Workmanship, Finish, and Appearance~~
~~3.1.5 Sampling~~
~~3.1.6 Number of edge, if required: slit, sheared, sawed, square corners, rounded corners, rounded edges, or full-rounded edges (see 8.6);~~
~~3.1.9 Type of width tests and straightness tolerances, if required: slit-metal tolerances, square-sheared-metal tolerances, sawed-metal tolerances, straightened or edge-rolled metal tolerances (see 8.3 and 8.5).~~
~~3.1.10 ASTM Specification B 36/B-36M, year Retests~~
~~3.1.7 Specimen Preparation~~
~~3.1.8 Test Methods~~
~~3.1.9 Significance of issue; Numerical Limits~~
~~3.1.10 Inspection~~
~~3.1.11 Rejection and whether inch-pound or SI units are applicable (see 1.2).~~
~~3.1.11 Special tests or exceptions, if any. Rehearing~~
~~3.1.12 Certification~~
~~3.1.13 Test Reports~~
~~3.1.14 Packaging and Package Marking~~
3.2 ~~In addition, when material is purchased for agencies of the U. S. Government, it shall conform a section with a title identical to the Supplementary Requirements as defined that referenced in 3.1, appears in this specification, it contains additional requirements which supplement those appearing in Specification B 248 when specified in the contract or purchase order. [B 248M].~~

4. Terminology

~~4.1 For definitions of terms related to copper and copper alloys, refer to Terminology B 846.~~

5. Ordering Information

~~5.1 Orders for products should include the following information:~~
~~5.1.1 ASTM designation and year of issue,~~
~~5.1.2 Copper alloy UNS No. designation,~~
~~5.1.3 Quantity,~~
~~5.1.4 Form of material: plate, sheet, strip, or rolled bar,~~
~~5.1.5 Temper (Section 7),~~
~~5.1.6 Dimensions: thickness, width, and length if applicable,~~
~~5.1.7 Tolerances (Section 10),~~

⁴ Annual Book of ASTM Standards, Vol 023.01.

⁶ Annual Book of ASTM Standards, Vol 03.046.

- 5.1.8 How furnished: rolls, stock lengths with or without ends, specific lengths with or without ends (Section 10),
- 5.1.9 Type of edge, if required (Section 10),
- 5.1.10 When the product is purchased for agencies of the U.S. Government.
- 5.2 The following options are available and should be specified at the time of placing the order when required:
 - 5.2.1 Heat identification or traceability details,
 - 5.2.2 Certification,
 - 5.2.3 Mill test report,
 - 5.2.4 Special tests or exceptions, if any.
 - 5.2.5 Supplemental requirements for agencies of the U.S. Government as given in Specification B 248 [B 248M].

6. Chemical Composition

- 4.6.1 ~~The materials shall conform to the compositions prescribed~~ chemical compositional requirements in Table 1:
- 4.2 ~~These specification~~ for the copper alloy UNS No. designation specified in the ordering information.
- 6.2 These composition limits do not preclude the presence of other elements. Limits for unnamed elements may be established and analysis required for unnamed elements by agreement between the manufacturer or supplier and purchaser.
- 4.6.3 Either copper or zinc may be taken as the difference between the sum of all elements analyzed and 100 %. When all elements in Table 1 are analyzed, their the sum of the results shall be as shown in the in the table as follows:

—	Copper Plus Named Elements, % min
Copper Alloy UNS No.	Copper Plus Named Elements, % min
C21000	99.8
C22000	99.8
C22600	99.8
C23000	99.8
C24000	99.8
C26000	99.7
C26800	99.7
C27200	99.7
C28000	99.7

57. Temper

- 57.1 ~~As Hot-Rolled (M20) Material~~ The standard temper of sheet and plate and produced by hot rolling is as designated in Table 2.

TABLE 1 Chemical Requirements

	Copper Alloy UNS No.	Copper, %	Lead, max, %	Iron, max, %	Zinc
C21000	C21000 (95-Cu, 5 Zn)	94.0 to 96.0	0.03	0.05	remainder
	C21000 (95-Cu, 5 Zn)	94.0 to 96.0	0.03	0.05	remainder
	C22000 (90-Cu, 10 Zn)	89.0 to 91.0	0.05	0.05	remainder
	C22000	89.0 to 91.0	0.05	0.05	remainder
	C22600 (87.5-Cu, 12.5-Zn)	86.0 to 89.0	0.05	0.05	remainder
	C22600	86.0 to 89.0	0.05	0.05	remainder
	C23000 (85-Cu, 15 Zn)	84.0 to 86.0	0.05	0.05	remainder
	C23000	84.0 to 86.0	0.05	0.05	remainder
	C24000 (80-Cu, 20 Zn)	78.5 to 81.5	0.05	0.05	remainder
	C24000	78.5 to 81.5	0.05	0.05	remainder
	C26000 (70-Cu, 30 Zn)	68.5 to 71.5	0.07	0.05	remainder
	C26000	68.5 to 71.5	0.07	0.05	remainder
	C26800 ^A (66-Cu, 34 Zn)	64.0 to 68.5	0.15	0.05	remainder
	0.26800 ^A	64.0 to 68.5	0.15	0.05	remainder
	C27200 ^B (63-Cu, 37 Zn)	62.0 to 65.0	0.07	0.07	remainder
	C27200 ^B	62.0 to 65.0	0.07	0.07	remainder
	C28000 ^C (60-Cu, 40 Zn)	59.0 to 63.0	0.30	0.07	remainder
C28000 ^C	59.0 to 63.0	0.30	0.07	remainder	

^A-Material shall be free from beta constituent when examined at a magnification of 75 diameters.

^B-Small amounts of beta constituent, if present, may interfere in some instances with severe forming or drawing; therefore, suitability for forming or drawing should be established between manufacturer and purchaser.

^C-It is anticipated that this material will contain the beta constituent that may interfere with severe forming or drawing operations.

TABLE 2 Tensile Strength Requirements and Approximate Rockwell Hardness Values for Rolled Temper (H) Product

NOTE 1—Plate is generally available in only the as hot-rolled (M20) temper. Required properties for other tempers shall be agreed upon between the manufacturer and the purchaser at the time of placing the order.

Rolled Temper		Tensile Strength, ksi [MPa] ^A		Approximate Rockwell Hardness ^B							
Temper Designation		Min	Max	B Scale				Superficial 30-T			
Standard	Former			0.020 (0.508) to 0.036 in. (0.914 mm) incl		Over 0.036 in. (0.914) mm		0.012 (0.305) to 0.028 in. (0.711 mm) incl		Over 0.028 in. (0.711 mm)	
				Min	Max	Min	Max	Min	Max	Min	Max
Copper Alloy UNS No. C21000											
M20	As hot-rolled	32 [220]	42 [290]
H01	Quarter hard	37 [255]	47 [325]	20	48	24	52	34	51	37	54
H02	Half-hard	42 [290]	52 [355]	40	56	44	60	46	57	48	59
H03	Three-quarter-hard	46 [315]	56 [385]	50	61	53	64	52	60	54	62
H04	Hard	50 [345]	59 [405]	57	64	60	67	57	62	59	64
H06	Extra hard	56 [385]	64 [440]	64	70	66	72	62	66	63	67
H08	Spring	60 [415]	68 [470]	68	73	70	75	64	68	65	69
H10	Extra spring	61 [420]	69 [475]	69	74	71	76	65	69	66	70
Copper Alloy UNS No. C22000											
M20	As hot-rolled	33 [230]	43 [295]
H01	Quarter-hard	40 [275]	50 [345]	27	52	31	56	34	51	37	54
H02	Half-hard	47 [325]	57 [395]	50	63	53	66	50	59	52	61
H03	Three-quarter-hard	52 [355]	62 [425]	59	68	62	71	55	62	58	64
H04	Hard	57 [395]	66 [455]	65	72	68	75	60	65	62	67
H06	Extra hard	64 [440]	72 [495]	72	77	74	79	64	68	66	69
H08	Spring	69 [475]	77 [530]	76	79	78	81	67	69	68	70
H10	Extra spring	72 [495]	80 [550]	78	81	80	83	68	70	69	71
Copper Alloy UNS No. C22600											
H01	Quarter-hard	42 [290]	52 [355]	29	58	29	58	39	58	39	58
H02	Half-hard	48 [330]	58 [400]	52	68	52	68	54	64	54	64
H03	Three-quarter-hard	53 [365]	63 [435]	61	73	61	73	59	68	59	68
H04	Hard	58 [400]	67 [460]	67	77	67	77	64	70	64	70
H06	Extra hard	65 [450]	73 [505]	74	81	74	81	68	73	68	73
H08	Spring	70 [485]	78 [540]	78	83	78	83	71	74	71	74
H10	Extra spring	74 [510]	82 [565]	81	86	81	86	73	76	73	76
Copper Alloy UNS No. C23000											
M20	As hot-rolled	37 [255]	47 [325]
H01	Quarter-hard	44 [305]	54 [370]	33	58	37	62	42	57	45	60
H02	Half-hard	51 [350]	61 [420]	56	68	59	71	56	64	58	66
H03	Three-quarter-hard	57 [395]	67 [460]	66	73	69	76	63	68	65	70
H04	Hard	63 [435]	72 [495]	72	78	74	80	67	71	68	72
H06	Extra hard	72 [495]	80 [550]	78	83	80	85	70	74	71	75
H08	Spring	78 [540]	86 [595]	82	85	84	87	74	76	75	77
H10	Extra spring	82 [565]	90 [620]	84	87	86	89	75	77	76	78
Copper Alloy UNS No. C24000											
M20	As hot-rolled	41 [285]	51 [350]
H01	Quarter-hard	48 [330]	58 [400]	38	61	42	65	42	57	45	60
H02	Half-hard	55 [380]	65 [450]	59	70	62	73	56	64	58	66
H03	Three-quarter-hard	61 [420]	71 [490]	69	76	72	79	63	68	65	70
H04	Hard	68 [470]	77 [530]	76	82	78	84	68	72	69	73
H06	Extra hard	78 [540]	87 [600]	83	87	85	89	72	75	73	76
H08	Spring	85 [585]	93 [640]	87	90	89	92	75	77	76	78
H10	Extra spring	89 [615]	97 [670]	88	91	90	93	76	78	77	79
Copper Alloy UNS No. C26000											
M20	As hot-rolled	41 [285]	51 [350]
H01	Quarter-hard	49 [340]	59 [405]	40	61	44	65	43	57	46	60
H02	Half-hard	57 [395]	67 [460]	60	74	63	77	56	66	58	68
H03	Three-quarter-hard	64 [440]	74 [510]	72	79	75	82	65	70	67	72
H04	Hard	71 [490]	81 [560]	79	84	81	86	70	73	71	74
H06	Extra hard	83 [570]	92 [635]	85	89	87	91	74	76	75	77
H08	Spring	91 [625]	100 [690]	89	92	90	93	76	78	76	78

TABLE 2—Tensile Strength Requirements

7.2 *Rolled (H)*—The standard tempers of rolled material are as designated in Table 2 with the prefix “H”. Former designations and the standard designations as defined in Practice B 601 are shown.

7.3 *Annealed (OS)*—The standard tempers of annealed material are as designated in Tables 3 and 4. Nominal grain size and

TABLE 2 *Continued*

Rolled Temper		Tensile Strength, ksi [MPa] ^A		Approximate Rockwell Hardness ^B							
Temper Designation		Min	Max	B Scale				Superficial 30-T			
Standard	Former			0.020 (0.508) to 0.036 in. (0.914 mm) incl		Over 0.036 in. (0.914) mm		0.012 (0.305) to 0.028 in. (0.711 mm) incl		Over 0.028 in. (0.711 mm)	
				Min	Max	Min	Max	Min	Max	Min	Max
H10	Extra spring	95 [655]	104 [715]	91	94	92	95	77	79	77	
Copper Alloy UNS No. C26800											
M20	As hot-rolled	40 [275]	50 [345]
H01	Quarter-hard	49 [340]	59 [405]	40	61	44	65	43	57	46	60
H02	Half-hard	55 [380]	65 [450]	57	71	60	74	54	64	56	66
H03	Three-quarter-hard	62 [425]	72 [495]	70	77	73	80	65	69	67	71
H04	Hard	68 [470]	78 [540]	76	82	78	84	68	72	69	73
H06	Extra-hard	79 [545]	89 [615]	83	87	85	89	73	75	74	76
H08	Spring	86 [595]	95 [655]	87	90	89	92	75	77	76	78
H10	Extra spring	90 [620]	99 [685]	88	91	90	93	76	78	77	79
Copper Alloy UNS No. C27200											
M20	As hot-rolled	41 [285]	51 [350]
H01	Quarter-hard	49 [340]	59 [405]	40	61	44	65	43	57	46	60
H02	Half-hard	56 [385]	66 [455]	57	74	60	76	54	67	56	68
H03	Three-quarter-hard	63 [435]	73 [505]	71	78	74	81	64	70	66	71
H04	Hard	70 [485]	80 [550]	76	82	78	84	67	72	68	73
H06	Extra hard	81 [560]	91 [625]	82	87	85	89	71	75	72	76
Copper Alloy UNS No. C28000											
M20	As hot-rolled	40 [275]	55 [380]
H01	Quarter-hard	50 [345]	62 [425]	40	65	45	70	45	65	45	70
H02	Half-hard	58 [400]	70 [485]	50	75	52	80	50	70	50	75
H03	Three-quarter-hard	60 [415]	75 [515]	55	80	55	82	52	78	55	80
H04	Hard	70 [485]	85 [585]	60	85	60	87	55	80	55	82
H06	Extra hard	82 [565]	95 [655]	65	92	65	90	60	85	60	85

^AMPa (Mega Pascals) See Appendix X1.

^BRockwell hardness values apply as follows: the B scale values apply to metal 0.020 in. (0.508 mm) and over in thickness, and the 30-T scale values apply to metal 0.012 in. (0.305 mm) and over in thickness.

the R standard designations are defined in Practice B 601 are shown.

7.4 *Annealed-To-Temper (O)*—The standard tempers of annealed-to-temper material are as designated in Table 5 with the prefix “O.” Former designations V and the standard designations as defined in Practice B 601 are shown.

7.5 Special or nonstandard tempers are subject to negotiation between the manufacturer and purchaser (See 5.1.5).

8. Grain Size

8.1 Grain size shall be standard requirement for all products of the annealed (OS) tempers.

8.2 Acceptance or rejection based upon grain size shall depend only on the average grain size of the test specimens and shall be within the limits prescribed in Table 3 when determined in accordance with Test Methods E 112.

8.3 The average grain size shall be determined on a plane parallel to the surface of the product.

9. Mechanical Properties

9.1 Tensile Strength Requirements of Rolled Tempers

9.1.1 Product furnished under this specification shall conform to the tensile strength requirements prescribed in Table 2 when tested in accordance with Test Methods E 8 [E 8M]. The test specimens shall be taken so the longitudinal axis of the specimen is parallel to the direction of rolling.

TABLE 3 Grain Size Requirements for Annealed Mate (OS)
Product

Copper Alloy UNS No.	Standard Temper Designation (B 601)	Grain Size		
		Nominal	Min	Max
C21000	OS050	0.050	0.035	0.090
	OS035	0.035	0.025	0.050
	OS025	0.025	0.015	0.035
	OS015	0.015	^A	0.025
C22000	OS050	0.050	0.035	0.090
	OS035	0.035	0.025	0.050
	OS025	0.025	0.015	0.035
	OS015	0.015	^A	0.025
C22600	OS050	0.050	0.035	0.090
	OS035	0.035	0.025	0.050
	OS025	0.025	0.015	0.035
	OS015	0.015	^A	0.025
C23000	OS070	0.070	0.050	0.100
	OS050	0.050	0.035	0.070
	OS035	0.035	0.025	0.050
	OS025	0.025	0.015	0.035
	OS015	0.015	^A	0.025
C24000	OS070	0.070	0.050	0.120
	OS050	0.050	0.035	0.070
	OS035	0.035	0.025	0.050
	OS025	0.025	0.015	0.035
	OS015	0.015	^A	0.025
C26000 —and and C26800	OS120	0.120	0.070	...
	OS070	0.070	0.050	0.120
	OS070	0.070	0.050	0.120
	OS050	0.050	0.035	0.070
	OS035	0.035	0.025	0.050
	OS025	0.025	0.015	0.035
	OS015	0.015	^A	0.025
C27200	OS035	0.035	0.025	0.050
	OS025	0.025	0.015	0.035
	OS015	0.015	^A	0.025
<u>C27200</u>	OS035	0.035	0.025	0.050
	OS025	0.025	0.015	0.035
	OS025	0.025	0.015	0.035
	OS015	0.015	^A	0.025
				0.035
C28000	OS035	0.035	0.025	0.050
	OS025	0.025	0.015	0.035
	OS015	0.015	^A	0.025
<u>C28000</u>	OS035	0.035	0.025	0.050
	OS025	0.025	0.015	0.035
	OS025	0.025	0.015	0.035
	OS015	0.015	^A	0.025
				0.035

^AAlthough no minimum grain size is required, this material must be fully recrystallized.

9.1.2 Acceptance or rejection based upon mechanical properties shall depend only on tensile strength.
 9.2 Tensile Strength Requirements of Annealed-to-Temper

 **B 36/B 36M – 9501**

TABLE 4 Approximate Rockwell Hardness of Annealed Metal (OS)

<u>Product</u>					
Anneal Temper, Nom- inal Grain Size	Standard Temper Designation (B 601)	Approximate Rockwell Hardness ^A			
		Anneal Temper, Nominal Grain Size	Standard Temper Designation (B 601)	Approximate Rockwell Hardness ^A	
				F Scale	
Min	Max	Min	Max	Min	Max
UNS No. C21000					
0.050-mm	OS050	40 ^B	52 ^B	...	—4
0.050-mm	OS050	40 ^B	52 ^B	...	4
0.035-mm	OS035	47 ^B	54 ^B	...	—7
0.035-mm	OS035	47 ^B	54 ^B	...	7
0.025-mm	OS025	60 ^B	64 ^B	—4	—17
0.025-mm	OS025	50 ^B	61 ^B	1	17
0.015-mm	OS015	54 ^B	65 ^B	—7	—23
0.015-mm	OS015	54 ^B	65 ^B	7	23
UNS No. C22000					
0.050-mm	OS050	—50	—60	—4	—16
0.050-mm	OS050	50	60	1	16
0.035-mm	OS035	—54	—64	—7	—21
0.035-mm	OS035	54	64	7	21
0.025-mm	OS025	58	70	13	31
0.015-mm	OS015	62	75	19	39
UNS No. C22600					
0.050-mm	OS050	—48	—58	—6	—18
0.050-mm	OS050	48	58	6	18
0.035-mm	OS035	52	62	10	23
0.025-mm	OS025	55	67	14	29
0.015-mm	OS015	58	76	18	40
UNS No. C23000					
0.070-mm	OS070	—53	—60	—6	...
0.070-mm	OS070	53	60	6	...
0.050-mm	OS050	56	63	10	...
0.035-mm	OS035	58	76	13	24
0.025-mm	OS025	60	72	16	34
0.015-mm	OS015	62	79	19	48
UNS No. 24000					
0.070-mm	OS070	—53	—64	—2	—24
0.070-mm	OS070	53	64	2	24
0.050-mm	OS050	—57	—67	—8	—27
0.050-mm	OS050	57	67	8	27
0.035-mm	OS035	61	72	16	35
0.025-mm	OS025	63	77	20	42
0.015-mm	OS015	66	83	25	50
UNS Nos. C26000 and C26800					
0.120-mm	OS120	50	62	...	21
0.070-mm	OS070	—52	—67	—3	—27
0.070-mm	OS070	52	67	3	27
0.050-mm	OS050	61	73	20	35
0.035-mm	OS035	65	76	25	38
0.025-mm	OS025	67	79	27	42
0.015-mm	OS015	72	85	33	50
UNS No. C27200					
0.035-mm	OS035	65	76	25	38
0.025-mm	OS025	67	79	27	42
0.015-mm	OS015	72	85	33	50
UNS No. C28000					
0.035-mm	OS035	65	80	26	44
0.025-mm	OS025	68	83	28	48
0.015-mm	OS015	72	90	30	55

^ARockwell hardness values apply as follows: The F scale applies to metal 0.020 in. (0.508 mm) in thickness and over; the 30-T scale applies to metal 0.015 in. (0.3842 mm) in thickness and over.

^BThis alloy in these several annealed tempers is too soft for Rockwell F hardness tests below 0.030 in. (0.762 mm) in thickness.

9.2.1 Product furnished under this specification shall conform to the tensile strength requirements prescribed in Table 5 when

**TABLE 5 Tensile Strength Requirements and Approximate Rockwell Hardness Values for Annealed-to-Tempers
(O) Product**

NOTE 1—Required properties for other tempers shall be agreed upon between the manufacturer and the purchaser at the time of placing the order.

Annealed-to-Temper		Tensile Strength, -ksi [MPa] ^A Tensile Strength, MPa ^B		Approximate Rockwell Hardness ^{C,B}					
Temper Designation		Min	Max	Min	Max	B Scale		Superficial 30-T	
Standard	Former					Min	Max	Min	Max
Copper Alloy UNS No. C22000									
O84	Quarter-hard	40	50	275	345	...	45	28	52
O81	Quarter-hard	40 [275]	50 [345]	275	345	...	45	28	52
Copper Alloy UNS No. C22600									
O84	Quarter-hard	42	52	290	355	20	50	30	54
O81	Quarter-hard	42 [290]	52 [355]	290	355	20	50	30	54
Copper Alloy UNS No. C23000									
O84	Quarter-hard	44	54	305	370	30	53	35	54
O81	Quarter-hard	44 [305]	54 [370]	305	370	30	53	35	54
Copper Alloy UNS No. C24000									
O84	Quarter-hard	48	58	330	400	33	53	38	54
O81	Quarter-hard	48 [330]	58 [400]	330	400	33	53	38	54
Copper Alloy UNS No. C26000									
O84	Quarter-hard	49	59	340	405	32	55	36	53
O81	Quarter-hard	49 [340]	59 [405]	340	405	32	55	36	53
O82	Half-hard	57	67	395	460	52	72	50	66
O82	Half-hard	57 [395]	67 [460]	395	460	52	72	50	66
Copper Alloy UNS No. C26800									
O84	Quarter-hard	49	59	340	405	33	55	37	55
O81	Quarter-hard	49 [340]	59 [405]	340	405	33	55	37	55
O82	Half-hard	55	65	380	450	52	72	51	67
O82	Half-hard	55 [380]	65 [450]	380	450	52	72	51	67

^Aksi = 1000 psi.

^BMPa (Mega Pascals) See Appendix X1

^CRockwell hardness values apply as follows: The B scale applies to metal 0.020 (0.058 mm) in thickness and over; the 30T applies to metal 0.015 in. (0.381 mm) in thickness and over.

tested in accordance with Test Methods E 8 [E 8M]. The test specimens shall be taken so the longitudinal axis of the specimen is parallel to the direction of rolling.

9.2.2 Acceptance or rejection based upon mechanical properties shall depend only on tensile strength.

9.3 Rockwell Hardness

9.3.1 The approximate Rockwell hardness values given in Table 2, Table 4, and Table 5 are for general information and assistance in testing and shall not be used as a basis for product rejection.

NOTE 1—Plate is generally available in only 1—The Rockwell hardness test offers a quick and convenient method of checking for general conformity to the as hot-rolled (M20) temper. Required properties specification requirements for o temper, tensile strength and grain size.

10. Dimensions and Permissible Variations

10.1 The dimensions and tolerances for product described by this specification shall be agreed upon between as specified in Specification B 248 [B 248M] with particular reference to the manufacturer following related paragraphs in that specification.

10.1.1 Thickness.

10.1.2 Width:

10.1.2.1 Slit Metal and Slit Metal With Rolled Edges.

10.1.2.2 Square-ed-Sheared Metal.

10.1.2.3 Sawed Metal.

10.1.3 Length:

10.1.3.1 Specific and Stock Lengths With and Without Ends.

10.1.3.2 Schedule of Lengths (Specific and Stock) With Ends.

10.1.3.3 Length Tolerances for Square-Sheared Metal.

10.1.3.4 Length Tolerances for Sawed Metal.

10.1.4 Straightness:

10.1.4.1 Slit Metal or Slit Metal Either Straightened or Edge-Rolled.

10.1.4.2 Squared-sheared Metal.

10.1.4.3 Sawed metal.

10.1.5 Edges:

10.1.5.1 Square Edges.

10.1.5.2 Rounded Corners.

10.1.5.3 Rounded Edges.

10.1.5.4 Full-Rounded Edges.

11. Test Methods

11.1 Chemical Analysis:

11.1.1 Composition shall be determined, in the order case of disagreement, as follows:

Rolled Temper		Tensile Strength, ksi ^a		Tensile Strength, MPa ^a		Approximate Rockwell Hardness ^c						
Temper Designation						B-Scale				Superficial 30-T		
Standard	Former	Min	Max	Min	Max	0.020 (0.508) to 0.036 in. (0.914 mm) incl		Over 0.036 in. (0.914 mm)	0.012 (0.305) to 0.028 in. (0.711 mm) incl		Over 0.028 in. (0.711 mm)	
						Min	Max		Min	Max	Min	Max
Copper Alloy UNS No. C21000												
M20	As hot-rolled	32	42	220	290
M20	As hot-rolled Element	32	42	220	290 Method
H01	Quarter-hard	37	47	255	325	20	48	24	52	34	54	37 54
H02	Half-hard	42	52	290	355	40	56	44	60	46	57	48 59
H02	Half-hard Copper	42	52	290	355	40	56	44	60	46	57	48 59 E 478
H03	Three-quarter-hard	46	56	315	385	50	64	53	64	52	60	54 62
H03	Three-quarter-hard Iron	46	56	315	385	50	64	53	64	52	60	54 62 E 478
H04	Hard	50	59	345	405	57	64	60	67	57	62	59 64
H04	Hard Lead	50	59	345	405	57	64	60	67	57	62	59 64 E 478 (AA)
H06	Extra-hard	56	64	385	440	64	70	66	72	62	66	63 67
H06	Extra-hard Zinc	56	64	385	440	64	70	66	72	62	66	63 67
H08	Spring	60	68	415	470	68	73	70	75	64	68	65 69
H10	Extra-spring	61	69	420	475	69	74	71	76	65	69	66 70
Copper Alloy UNS No. C22000												
M20	As hot-rolled	33	43	230	295
H01	Quarter-hard	40	50	275	345	27	52	31	56	34	54	37 54
H02	Half-hard	47	57	325	395	50	63	53	66	50	59	52 61
H03	Three-quarter-hard	52	62	355	425	59	68	62	71	55	62	58 64
H04	Hard	57	66	395	455	65	72	68	75	60	65	62 67
H06	Extra-hard	64	72	440	495	72	77	74	79	64	68	66 69
H08	Spring	69	77	475	530	76	79	78	81	67	69	68 70
H10	Extra-spring	72	80	495	550	78	81	80	83	68	70	69 71
Copper Alloy UNS No. C22600												
H01	Quarter-hard	42	52	290	355	29	58	29	58	39	58	39 58
H02	Half-hard	48	58	330	400	52	68	52	68	54	64	54 64
H03	Three-quarter-hard	53	63	365	435	61	73	61	73	59	68	59 68
H04	Hard	58	67	400	460	67	77	67	77	64	70	64 70
H06	Extra-hard	65	73	450	505	74	81	74	81	68	73	68 73
H08	Spring	70	78	485	540	78	83	78	83	71	74	71 74
H10	Extra-spring	74	82	510	565	81	86	81	86	73	76	73 76
Copper Alloy UNS No. C23000												
M20	As hot-rolled	37	47	255	325
H01	Quarter-hard	44	54	305	370	33	58	37	62	42	57	45 60
H02	Half-hard	51	61	350	420	56	68	59	71	56	64	58 66
H03	Three-quarter-hard	57	67	395	460	66	73	69	76	63	68	65 70
H04	Hard	63	72	435	495	72	78	74	80	67	71	68 72
H06	Extra-hard	72	80	495	550	78	83	80	85	70	74	71 75
H08	Spring	78	86	540	595	82	85	84	87	74	76	75 77
H10	Extra-spring	82	90	565	620	84	87	86	89	75	77	76 78
Copper Alloy UNS No. C24000												
M20	As hot-rolled	41	51	285	350
H01	Quarter-hard	48	58	330	400	38	64	42	65	42	57	45 60
H02	Half-hard	55	65	380	450	59	70	62	73	56	64	58 66
H03	Three-quarter-hard	61	71	420	490	69	76	72	79	63	68	65 70
H04	Hard	68	77	470	530	76	82	78	84	68	72	69 73
H06	Extra-hard	78	87	540	600	83	87	85	89	72	75	73 76
H08	Spring	85	93	585	640	87	90	89	92	75	77	76 78
H10	Extra-spring	89	97	615	670	88	91	90	93	76	78	77 79
Copper Alloy UNS No. C26000												
M20	As hot-rolled	41	51	285	350
H01	Quarter-hard	49	59	340	405	40	64	44	65	43	57	46 60

TABLE 2—Continued

Rolled Temper		Tensile Strength, ksi ^A		Tensile Strength, MPa ^B		Approximate Rockwell Hardness ^C							
Temper Designation		Min	Max	Min	Max	B-Scale				Superficial 30-T			
Standard	Former					0.020 (0.508) to 0.036 in. (0.914 mm) incl		Over 0.036 in. (0.914 mm)		0.012 (0.305) to 0.028 in. (0.711 mm) incl		Over 0.028 in. (0.711 mm)	
						H02	—Half-hard	57	—67	395	460	60	74
H03	—Three-quarter-hard	64	—74	440	510	72	79	75	82	65	70	67	72
H04	—Hard	74	—84	490	560	79	84	84	86	70	73	74	74
H06	—Extra hard	83	—92	570	635	85	89	87	91	74	76	75	77
H08	—Spring	94	—100	625	690	89	92	90	93	76	78	76	78
H10	—Extra spring	95	—104	655	745	94	94	92	95	77	79	77	79
Copper Alloy UNS No. C26800													
M20	—As hot-rolled	40	50	275	345	—	—	—	—	—	—	—	—
H01	—Quarter-hard	49	—59	340	405	40	64	44	65	43	57	46	60
H02	—Half-hard	55	—65	380	450	57	74	60	74	54	64	56	66
H03	—Three-quarter-hard	62	—72	425	495	70	77	73	80	65	69	67	74
H04	—Hard	68	—78	470	540	76	82	78	84	68	72	69	73
H06	—Extra hard	79	—89	545	615	83	87	85	89	73	75	74	76
H08	—Spring	86	—95	595	655	87	90	89	92	75	77	76	78
H10	—Extra spring	90	—99	620	685	88	94	90	93	76	78	77	79
Copper Alloy UNS No. C27200													
M20	—As hot-rolled	44	—54	285	350	—	—	—	—	—	—	—	—
H01	—Quarter-hard	49	—59	340	405	40	64	44	65	43	57	46	60
H02	—Half-hard	56	—66	385	455	57	74	60	76	54	67	56	68
H03	—Three-quarter-hard	63	—73	435	505	74	78	74	84	64	70	66	74
H04	—Hard	70	—80	485	550	76	82	78	84	67	72	68	73
H06	—Extra hard	84	—94	560	625	82	87	85	89	74	75	72	76
Copper Alloy UNS No. C28000													
M20	—As hot-rolled	40	—55	275	380	—	—	—	—	—	—	—	—
H01	—Quarter-hard	50	—62	345	425	40	65	45	70	45	65	45	70
H02	—Half-hard	58	—70	400	485	50	75	52	80	50	70	50	75
H03	—Three-quarter-hard	60	—75	445	545	55	80	55	82	52	78	55	80
H04	—Hard	70	—85	485	585	60	85	60	87	55	80	55	82
H06	—Extra hard	82	—95	565	655	65	92	65	90	60	85	60	85
H06	—Extra hard	82	—95	565	655	65	92	65	90	60	85	60	85E 478 (Titanium)

63 66

A ksi = 1000 psi.

^B MPa (Mega Pascals) See Appendix X1.

^C Rockwell hardness values apply as follows: the B scale values apply

11.1.2 Test method(s) to metal 0.020 in. (0.508 mm) and over in thickness, and the 30-T scale values apply to metal 0.012 in. (0.305 mm) and over in thickness.

5.2 *Rolled (H) Material*—The standard tempers of rolled material are as designated in Table 2 with the prefix “H”. Former designations and the standard designations as defined in Practice B 601 are shown. Special or nonstandard tempers are subject to negotiation between the manufacturer and the purchaser (See 3.1.5).

5.3 *Annealed (OS) Material*—The standard tempers of annealed material are as designated in Table 3 and Table 4. Nominal grain size and the standard designations as defined in Practice B 601 are shown. Special or nonstandard tempers are subject to negotiation between the manufacturer and the purchaser (see 3.1.5).

5.4 *Annealed-To-Temper (O) Material*—The standard tempers of annealed-to-temper material are as designated in Table 5 with the prefix “O”. Former designations and the standard designations as defined in Practice B 601 are shown. Special or nonstandard tempers are subject to negotiation between the manufacturer and the purchaser (See 3.1.5).

6. Mechanical Properties

6.1 Tensile Strength of Rolled Tempers:

6.1.1 Products ordered to this specification in inch-pound units shall be tested in accordance with Test Methods E 8, and shall conform to tensile strength requirements prescribed in ksi units in Table 2.

6.1.2 Products ordered to this specification in SI units shall be tested in accordance with Test Methods E 8M, and shall conform to tensile strength requirements prescribed in MPa units in Table 2.

6.1.3 Acceptance or rejection based on mechanical properties shall depend only on the tensile strength.

6.1.4 Tension test specimens shall be taken so the longitudinal axis of the specimen is parallel to the direction of rolling.

6.2 Tensile Strength of Annealed-to-Tempers:

6.2.1 Products ordered to this specification in inch-pound units shall be tested in accordance with Test Methods E 8, and shall

conform to tensile strength requirements prescribed in ksi units in Table 5.

6.2.2 Products ordered to this specification in SI units shall be tested in accordance with Test Methods E 8M, and shall conform to tensile strength requirements prescribed in MPa units in Table 5.

6.2.3 Acceptance or rejection based on mechanical properties shall depend only on the tensile strength.

6.2.4 Tension test specimens shall be taken so the longitudinal axis of the specimen is parallel to the direction of rolling.

6.3 *Rockwell Hardness*—Since Rockwell hardness tests offer a quick and convenient method of checking brass of any temper followed for general conformity to the requirements for tensile strength or grain size, the approximate Rockwell hardness values for each temper are given in Table 2, Table 4, and Table 5 for general information and assistance in testing.

7. Grain Size determination of Annealed Tempers

7.1 Grain size shall be the standard test for material of all thicknesses in annealed tempers, and acceptance other element(s) resulting from contractual or rejection purchase order agreement shall depend on the grain sizes. The average grain size of each of two samples of annealed material as determined on a plane parallel to the surface of the material shall be within the limits prescribed in Table 3.

8. Dimensions and Permissible Variations

8.1 The inch-pound dimensions and tolerances for products covered by this specification shall be as prescribed in agreed upon between the current edition of Specification B 248, and the SI dimensions and tolerances covered by this specification shall be as prescribed in the current edition of Specification B 248M, with particular reference to Section 5 and the following tables of those specifications:

8.2 *Thickness*—See 4.2, Table 1.

8.3 *Width*:

8.3.1 *Slit Metal and Slit Metal With Rolled Edges*—See 4.3, Table 4.

8.3.2 *Square-Sheared Metal*—See 5.3, Table 5.

8.3.3 *Sawed Metal*—See 5.3, Table 6.

8.4 *Length*:

8.4.1 *Specific and Stock Lengths With and Without Ends*—See 5.4, Table 7.

8.4.2 *Schedule of Lengths (Specific and Stock) With Ends*—See 5.4, Table 8.

8.4.3 *Length Tolerances for Square-Sheared Metal*—See 5.4, Table 9.

8.4.4 *Length Tolerances for Sawed Metal*—See 5.4, Table 10.

8.5 *Straightness*:

8.5.1 *Slit Metal manufacturer or Slit Metal Either Straightened or Edge-Rolled*—See 5.5, Table 11.

8.5.2 *Square-Sheared Metal*—See 5.5, Table 12.

8.5.3 *Sawed Metal*—See 5.5, Table 13.

8.6 *Edges*—See 5.6.

8.6.1 *Square Edges*—See 5.6.1, Table 14.

8.6.2 *Rounded Corners*—See 5.6.2, Table 15.

8.6.3 *Rounded Edges*—See 5.6.3, Table 16.

8.6.4 *Full-Rounded Edges*—See 5.6.4, Table 17.

9. General Requirements

9.1 Products furnished under this specification in inch-pound units shall conform to the applicable requirements of the current edition of Specification B 248.

9.2 Products furnished under this specification in the SI units shall conform to the applicable requirements of the current edition of Specification B 248M.

10. supplier and purchaser.

12. Keywords

102.1 brass plate; brass rolled bar; brass sheet; brass strip

APPENDIX

(Nonmandatory Information)

X1. METRIC EQUIVALENTS

X1.1 The SI unit for strength properties now shown is in accordance with the International System of Units (SI). The derived SI unit for force is the newton (N), which is defined as that force which when applied to a body having a mass of one kilogram gives it an acceleration of one metre per second squared ($N = \text{kg}\cdot\text{m}/\text{s}^2$). The derived SI unit for pressure or stress is the newton per square metre (N/m^2), which has been named the pascal (Pa) by the General Conference on Weights and Measures. Since $1 \text{ ksi} = 6\,894\,757 \text{ Pa}$ the metric equivalents are expressed as megapascal (MPa), which is the same as MN/m^2 and N/mm^2 .

SUMMARY OF CHANGES

Committee B05 has identified the location of selected changes to this standard since the last issue (B36/36M-95) that may impact the use of this standard.

- (1) This revision has brought this specification in line with the Outline of Form (Fifth Edition).
- (2) This revision has brought this specification in line with Standardizing of the use of the “M” designation.
- (3) The addition of Section 11.

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).