



# Standard Specification for Copper-Beryllium Alloy Sand Castings for General Applications<sup>1</sup>

This standard is issued under the fixed designation B 770; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

*This standard has been approved for use by agencies of the Department of Defense.*

## 1. Scope \*

1.1 This specification establishes requirements for copper-beryllium alloy sand castings for general applications and nominal compositions alloys defined by this specification are shown in Table 1.<sup>2</sup>

1.2 *Units*—The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units, which are provided for information only.

1.3 The following safety hazard caveat pertains only to the test methods described in this specification.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory requirements prior to use.*

## 2. Referenced Documents

2.1 The following documents in the current issue of the Book of Standards form a part of this specification to the extent referenced herein:

2.2 *ASTM Standards:*

B 30 Specification for Copper-Base Alloys in Ingot Form<sup>3</sup>

B 208 Practice for Preparing Tension Test Specimens for Copper-Base Alloys for Sand, Permanent Mold, Centrifugal and Continuous Castings<sup>3</sup>

B 601 Practice for Temper Designations for Copper and Copper Alloys—Wrought and Cast<sup>3</sup>

B 824 Specification for General Requirements for Copper Alloy Castings<sup>3</sup>

B 846 Terminology for Copper and Copper Alloys<sup>3</sup>

<sup>1</sup> This practice is under the jurisdiction of ASTM Committee B05 on Copper and Copper Alloys and is the direct responsibility of Subcommittee B05.05 on Castings and Ingots for Remelting.

Current edition approved April 10, 2002. Published June 2002. Originally published as B 770 – 87. Last previous edition B 770 – 96.

<sup>2</sup> The UNS system for copper and copper alloys (see Practice E 527) is a simple expansion of the former standard designation system accomplished by the addition of a prefix “C” and a suffix “00”. The suffix can be used to accommodate composition variations of the base alloy.

<sup>3</sup> *Annual Book of ASTM Standards*, Vol 02.01.

E 527 Practice for Numbering Metals and Alloys (UNS)<sup>4</sup>

## 3. General Requirements

3.1 The following sections of Specification B 824 constitute a part of this specification:

- 3.1.1 Terminology,
- 3.1.2 Material and Manufacture,
- 3.1.3 Chemical Composition,
- 3.1.4 Dimensions and Permissible Variations,
- 3.1.5 Workmanship, Finish and Appearance,
- 3.1.6 Sampling,
- 3.1.7 Number of Tests and Retests,
- 3.1.8 Specimen Preparation,
- 3.1.9 Test Methods,
- 3.1.10 Significance of Numerical Limits,
- 3.1.11 Inspection,
- 3.1.12 Rejection and Rehearing,
- 3.1.13 Certification,
- 3.1.14 Mill Test Report, and
- 3.1.15 Packaging and Package Marking.

3.2 In addition, when a section with a title identical to that referenced in 3.1 appears in this specification, it contains additional requirements which supplement those appearing in Specification B 824.

## 4. Terminology

4.1 For definitions of terms relating to copper and copper alloys, refer to Terminology B 846.

## 5. Ordering Information

5.1 Include the following information for orders for product:

- 5.1.1 ASTM designation number, title, and year of issue,
- 5.1.2 Copper Alloy UNS Number designation,
- 5.1.3 Temper,
- 5.1.4 Quantity of castings required,
- 5.1.5 Pattern or drawing number, and condition (cast, machined, and so forth),
- 5.1.6 When material is purchased for agencies of the U.S. government, the Supplementary Requirements of Specification

<sup>4</sup> *Annual Book of ASTM Standards*, Vol 01.01.

**\*A Summary of Changes section appears at the end of this standard.**

**TABLE 1 Nominal Compositions**

Copper Alloy UNS No.	Previous Designation	Copper	Nickel	Silicon	Beryllium	Cobalt	Chromium	Iron	Zirconium	Tin	Manganese
C81400	70C	99.1	...	...	0.06	...	0.8	...	...	...	...
C82000	10C	97	...	...	0.5	2.5	...	...	...	...	...
C82200	3C, 14C	98	1.5	...	0.5	...	...	...	...	...	...
C82400 <sup>A</sup>	165C, 165CT <sup>A</sup>	97.8	...	...	1.7	0.5	...	...	...	...	...
C82500 <sup>A</sup>	20C, 20CT <sup>A</sup>	97.2	...	0.3	2.0	0.5	...	...	...	...	...
C82510	21C	96.6	...	0.3	2.0	1.1	...	...	...	...	...
C82600 <sup>A</sup>	245C, 245CT <sup>A</sup>	96.8	...	0.3	2.4	0.5	...	...	...	...	...
C82800 <sup>A</sup>	275C, 275CT <sup>A</sup>	96.6	...	0.3	2.6	0.5	...	...	...	...	...
C96700	72C	67.2	31.0	...	1.2	...	...	0.6	0.3	0.3	0.6

<sup>A</sup> When fine-grained castings are specified, 0.02 to 0.12 Ti is added for grain refinement, usually in the remelt ingot. See Specification B 30.

B 824 may be specified.

5.2 The following options are available and should be specified in the contract or purchase order when required.

5.2.1 Chemical analysis of residual elements, if specified in the purchase order (Specification B 824),

5.2.2 Mechanical requirements, if specified in the purchase order (Section 10),

5.2.3 Pressure test requirements, if specified in the purchase order (Specification B 824),

5.2.4 Soundness requirements, if specified in the purchase order (Specification B 824),

5.2.5 Repair of castings (Section 12),

5.2.6 Certification, if specified in the purchase order (Specification B 824),

5.2.7 Foundry test report, if specified in the purchase order (Specification B 824),

5.2.8 Witness inspection, if specified in the purchase order (Specification B 824), and

5.2.9 Product marking, if specified in the purchase order (Specification B 824).

## 6. Materials and Manufacture

### 6.1 Material:

6.1.1 The material of manufacture shall be castings of the copper alloys listed in Table 1, as specified in the purchase order or contract, and of such purity and soundness as to be suitable for the products prescribed herein.

### 6.2 Manufacture:

6.2.1 The product shall be manufactured by casting and thermal treatment to meet the properties specified.

## 7. Chemical Composition

7.1 The castings shall conform to the chemical composition requirements prescribed in Table 2 for the Copper Alloy UNS Number designations specified in the ordering information.

7.2 These composition limits do not preclude the presence of other elements. Limits may be established for unnamed elements by agreement between manufacturer or supplier and purchaser.

7.3 Copper is customarily given as remainder but may be taken as the difference between the sum of all elements analyzed and 100 %.

7.4 When all elements in Table 2 are analyzed, their sum shall be 99.5 % minimum.

7.5 It is recognized that residual elements may be present in cast copper-base alloys. Analysis shall be made for residual elements only when specified in the purchase order (Specification B 824).

## 8. Temper

8.1 The standard tempers are listed as follows:

8.1.1 *TF00*—Cast, solution heat treated and precipitation heat treated.

8.1.2 *MO1*—As sand cast.

8.1.3 Special or non-standard tempers are subject to negotiation between the supplier and purchaser. Standard temper designations are in accordance with Practice B 601.

## 9. Precipitation Heat Treatment

9.1 For the purpose of determining conformance to the appropriate requirement in Table 3, the castings and test specimens shall be precipitation heat-treated at a uniform temperature from the solution heat-treated condition. Solution heat-treatment and precipitation heat-treatments are listed in Table 4. Other treatment times and temperatures may be preferable for end products made from this material.

9.2 Special combinations of properties such as increased ductility, electrical conductivity, dimensional accuracy, and endurance life may be obtained by special precipitation heat-treatments. The mechanical requirements of Table 3 do not apply to such special heat-treatments. Specific test requirements as needed shall be agreed upon between the manufacturer or supplier and purchaser of the end product.

## 10. Mechanical Property Requirements

10.1 When tension tests are required, separately cast test-bar specimens shall be used to determine mechanical properties and shall meet the requirements shown in Table 3 in the as cast or solution heat-treated and precipitation heat-treated condition.

## 11. Purchases for U. S. Government

11.1 When specified in the contract or purchase order, product purchased for an agency of the U. S. government shall conform to the special government regulations specified in the Special Requirements.

## 12. Casting Repair

12.1 The castings shall not be weld repaired without approval of the purchaser.

12.2 The castings shall not be impregnated without approval of the purchaser.

## 13. Sampling

### 13.1 Lot Size:

13.1.1 A lot shall consist of all castings produced from one furnace melt or crucible melt.

**TABLE 2 Chemical Requirements<sup>A</sup>**  
Composition, % max, except as indicated

Copper Alloy UNS No.	Copper, <sup>B</sup> min	Major Elements										Residual Elements						
		Beryllium	Cobalt	Nickel	Iron	Silicon	Zirconium	Titanium	Chromium	Lead	Manganese	Iron	Silicon	Zinc	Chromium	Lead	Aluminum	Tin
C81400	remainder	0.02-0.10	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
C82000	remainder	0.45-0.80	2.40-2.70 <sup>C</sup>	0.20	...	...	...	...	...	...	...	...	...	...	...	...	...	...
C82200	remainder	0.35-0.80	0.30	1.0-2.0	...	...	...	...	...	...	...	...	...	...	...	...	...	...
C82400 <sup>D</sup>	remainder	1.60-1.85	0.20-0.65	0.20	...	...	...	...	...	...	...	...	...	...	...	...	...	...
C82500 <sup>D</sup>	remainder	1.90-2.25	0.35-0.70 <sup>C</sup>	0.20	...	...	...	...	...	0.20-0.35	...	...	...	...	...	...	...	...
C82510	remainder	1.90-2.15	1.0-1.2	0.20	...	...	...	...	...	0.20-0.35	...	...	...	...	...	...	...	...
C82600 <sup>D</sup>	remainder	2.25-2.55	0.35-0.65	0.20	...	...	...	...	...	0.20-0.35	...	...	...	...	...	...	...	...
C82800 <sup>D</sup>	remainder	2.50-2.85	0.35-0.70 <sup>C</sup>	0.20	...	...	...	...	...	0.20-0.35	...	...	...	...	...	...	...	...
C96700	remainder	1.10-1.20	...	29.0-33.0	0.40-1.0	0.15	0.15-0.35	0.15-0.35	...	0.01	0.40-1.0	...	...	...	...	...	...	

<sup>A</sup> Analysis shall regularly be made only for the major elements. All others are considered residual elements, and if above the noted maximums, may influence performance of the casting, particularly in conductivity, magnetic permeability, and machinability.

<sup>B</sup> In reporting chemical analyses obtained by use of instruments such as spectrograph, X ray, and atomic absorption, copper may be indicated as "remainder", and taken by difference.

<sup>C</sup> Ni+Co.

<sup>D</sup> When fine grained castings are specified, 0.02-0.12 Ti is added for grain refinement, usually in the remelt ingot. See Specification B 30.

**TABLE 3 Mechanical Requirements**

NOTE 1—"TF00" property values denote product in the standard solution heat-treated and precipitation heat-treated condition.

NOTE 2—"M01" property values denote product in the as sand cast condition.

Copper Alloy UNS No.	Temper Designation	Tensile Strength, min		Yield Strength 0.2 % Offset		Elongation in 2 in., or 50 mm, min,%
		ksi <sup>A</sup>	MPa <sup>B</sup>	ksi <sup>A</sup>	MPa <sup>B</sup>	
C81400	TF00	53	366	36	248	11
C81400	M01	45	311	15	104	15
C82000	TF00	90	621	70	483	3
C82000	M01	45	311	15	104	15
C82200	TF00	90	621	70	483	5
C82200	M01	55	380	25	173	15
C82400	TF00	145	1001	135	932	1
C82400	M01	70	483	35	242	15
C82500	TF00	150	1035	120	828	1
C82500	M01	75	518	40	276	15
C82510	TF00	160	1104	150	1035	1
C82510	M01	80	552	45	311	10
C82600	TF00	165	1139	155	1070	1
C82600	M01	80	552	45	311	10
C82800	TF00	165	1139	155	1070	1/2
C96700	TF00	125	863	80	552	10

<sup>A</sup> ksi = 1000 psi.

<sup>B</sup> See Appendix.

**TABLE 4 Thermal Treatments**

NOTE 1—The values given for solution heat treatment, precipitation temperature, and heat treatment time are the same for UNS Nos. C82400, C82500, C82510, C82600, and C82800.

Copper Alloy UNS No.	Solution Heat Treatment		Precipitation Temperature	Heat Treatment Time, h
	Temperature	Time, h/in.		
{C81400 C96700	1800–1850°F (982–1010°C)	1 h/in. of cross section and water quench	900–950°F (482–510°C)	2
{C82000 C82200	1675–1700°F (913–927°C)	1 h/in. of cross section and water quench	850–900°F (454–482°C)	3
C82400 C82500 {C82510 C82600 C82800	1400–1475°F (760–802°C)	1 h/in. of cross section and water quench	625–650°F (330–343°C)	3

13.1.2 When two or more furnace melts or crucible melts, or both, are used to charge a ladle for pouring, the castings produced therefrom shall constitute a lot.

13.1.3 A lot may consist of such groups of melts as agreed upon by the manufacturer and purchaser and in such case a lot shall consist of not more than 1000 lb (455 kg) of castings (gates and risers removed).

13.1.4 Test bar specimens for the Copper Alloy UNS

Numbers in this specification shall be cast to the form and dimensions shown in Figs. 1, Figs. 2, Figs. 3, or Figs. 4 in Practice B 208.

**14. Keywords**

14.1 copper alloy castings; copper-base alloy castings; copper beryllium castings

**APPENDIX****(Nonmandatory Information)****X1. METRIC EQUIVALENTS**

X1.1 The SI unit for strength properties now shown is in accordance with the International System of Units (SI). The derived SI unit for force is the newton (N), which is defined as that force which when applied to a body having a mass of one kilogram gives it an acceleration of one metre per second squared ( $N = \text{kg}\cdot\text{m}/\text{s}^2$ ). The derived SI unit for pressure or

stress is the newton per square metre ( $\text{N}/\text{m}^2$ ), which has been named the pascal (Pa) by the General Conference on Weights and Measures. Since  $1 \text{ ksi} = 6\,894\,757 \text{ Pa}$  the metric equivalents are expressed as megapascal (MPa), which is the same as  $\text{MN}/\text{m}^2$  and  $\text{N}/\text{mm}^2$ .

**SUMMARY OF CHANGES**

Committee B05 has identified the location of selected changes to this standard since the last issue (B 770 - 96) that may impact the use of this standard.

(1) A comprehensive 5-year review was conducted. No technical changes were made as far as alloy temper and property requirements. Some sections were rearranged, renumbered, and, in some cases, reworded to conform to the new *Outline of Form and Style and the Form and Style for ASTM Standards* (Blue Book).

(2) The safety caveat was added.

(3) The Terminology section was added.

(4) The General Requirements section was expanded as directed in the *Outline of Form and Style*.

(5) The composition of alloy C96700 was adjusted to match the CDA UNS registered composition. A Ni+Co footnote was added to Cobalt entry for alloys C82000, C82500, and C82800 for the same reason.

*ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.*

*This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.*

*This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or [service@astm.org](mailto:service@astm.org) (e-mail); or through the ASTM website ([www.astm.org](http://www.astm.org)).*