



Designation: B 849 – 94

AMERICAN SOCIETY FOR TESTING AND MATERIALS
100 Barr Harbor Dr., West Conshohocken, PA 19428
Reprinted from the Annual Book of ASTM Standards. Copyright ASTM

Standard Specification for Pre-Treatments of Iron or Steel for Reducing Risk of Hydrogen Embrittlement¹

This standard is issued under the fixed designation B 849; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

INTRODUCTION

When atomic hydrogen enters steels and certain other metals, for example, aluminum and titanium alloys, it can cause a loss of ductility, load carrying ability, or cracking (usually as submicroscopic cracks) as well as catastrophic brittle failures at applied stresses well below the yield strength or even the normal design strength for the alloys. This phenomenon often occurs in alloys that show no significant loss in ductility, when measured by conventional tensile tests, and is referred to frequently as hydrogen-induced delayed brittle failure, hydrogen stress cracking, or hydrogen embrittlement. The hydrogen can be introduced during cleaning, pickling, phosphating, electroplating, autocatalytic processes, porcelain enameling, and in the service environment as a result of cathodic protection reactions or corrosion reactions. Hydrogen can also be introduced during fabrication, for example, during roll forming, machining, and drilling, due to the breakdown of unsuitable lubricants as well as during welding or brazing operations. Parts that have been machined, ground, cold-formed, or cold-straightened subsequent to hardening heat treatment are especially susceptible to hydrogen embrittlement damage.

The results of research work indicate that the susceptibility of any material to hydrogen embrittlement in a given test is related directly to its trap population. The time-temperature relationship of the heat treatment is therefore dependent on the composition and structure of steels as well as plating metals and plating procedures. Additionally, for most high-strength steels, the effectiveness of the heat treatment falls off rapidly with a reduction of time and temperature.

1. Scope

1.1 This specification covers procedures for reducing the susceptibility or degree of susceptibility to hydrogen embrittlement or degradation that may arise in electroplating, autocatalytic plating, porcelain enameling, chemical conversion coating, and phosphating and the associated pretreatment processes. This specification is applicable to those steels whose properties are not affected adversely by baking at 190 to 230°C or higher (see 6.1.1).

1.2 The heat treatment procedures established herein have been shown to be effective for reducing the susceptibility of steel parts of tensile strength 1000 MPa or greater that have been machined, ground, cold-formed, or cold-straightened subsequent to heat treatment. This heat-treatment procedure is used prior to any operation capable of hydrogen charging the parts, such as the cleaning procedures prior to electroplating,

autocatalytic plating, porcelain enameling, and other chemical coating operations.

NOTE 1—1 MPa = 145.1 psi.

1.3 This specification has been coordinated with ISO/DIS 9587 and is technically equivalent.

1.4 The values stated in SI units are to be regarded as the standard.

2. Referenced Documents

2.1 ASTM Standards:

- A 919 Terminology Relating to Heat Treatment of Metals²
- B 242 Practice for Preparation of High-Carbon Steel for Electroplating³
- B 322 Practice for Cleaning Metals Prior to Electroplating³
- B 374 Terminology Relating to Electroplating³
- B 851 Specification for Automated Controlled Shot Peening of Metallic Articles Prior to Nickel, Autocatalytic Nickel, or Chromium Plating, or as Final Finish³

¹ This specification is under the jurisdiction of ASTM Committee B-8 on Metallic and Inorganic Coatings and is the direct responsibility of Subcommittee B08.02 on Substrate Preparation.

Current edition approved March 15, 1994. Published May 1994.

² Annual Book of ASTM Standards, Vol 01.02.

³ Annual Book of ASTM Standards, Vol 02.05.

2.2 *ISO Standards:*

ISO 2080 Electroplating and Related Processes—Vocabulary⁴

ISO/DIS 9587 Pre-Treatments of Iron or Steel for Reducing the Risk of Hydrogen Embrittlement⁴

2.3 *Federal Standard:*

QQ-C-320 Chromium Plating (Electrodeposited)⁵

3. Terminology

3.1 *Definitions*—Many of the terms used in this specification can be found in Terminology B 374, A 919, or ISO 2080.

4. Requirements

4.1 Heat treatment shall be performed on basis metals to reduce the risk of hydrogen embrittlement in accordance with Table 1. The duration of heat treatment shall commence in all cases from the time at which the whole of each part attains the specified temperature.

4.2 Parts made from steel with actual tensile strengths ≥ 1000 MPa (with corresponding hardness values of 300 HV_{10kgf}, 303 HB, or 31 HR_c) and surface-hardened parts shall require heat treatment unless Class SR-0 is specified. Preparation involving cathodic treatments in alkaline or acid solutions shall be avoided.

4.3 Table 1 lists the stress-relief heat-treatment classes to be specified by the purchaser to the electroplater, supplier, or processor on the part drawing or purchase order. When no stress relief treatment class is specified by the purchaser, Class SR-1 shall be applied (see Note 4).

NOTE 2—The treatment class selected is based on experience with the part, or similar parts, and the specific alloy used or with empirical test data. Because of factors such as alloy composition and structure, size, mass, or design parameters, some parts may perform satisfactorily with no stress relief treatment. Class SR-0 treatment is therefore provided for parts that the purchaser wishes to exempt from treatment.

NOTE 3—The use of inhibitors in acid pickling baths is not necessarily guaranteed to minimize hydrogen embrittlement.

NOTE 4—Class SR-1, the longest treatment, is the default when the purchaser does not specify a class. The electroplater, supplier, or processor is not normally in possession of the necessary information, such as design considerations, induced stresses from manufacturing operations, etc., that must be considered when selecting the correct stress relief treatment. It is in the purchasers' interest that their part designer, manufacturing engineer, or other technically qualified individual specify the treatment class on the part drawing or purchaser order in order to avoid the extra cost of the default treatment.

5. Categorization of Steels

5.1 With the exception of surface-hardened parts, heat treatment conditions shall be selected on the basis of actual

TABLE 1 Classes of Stress Relief Requirements for High-Strength Steels (See Sections 4 through 6 for Details on the Use of Table 1)

Class	Stress-Relief Heat-Treatment Classes for High-Strength Steels		
	Steels of Tensile Strength (R _m), MPa	Temperature, °C	Time, h
SR-0	not applicable		
SR-1	over 1800	200–230	min 24
SR-2 ^A	over 1800	190–220	min 24
SR-3	1401 to 1800	200–230	min 18
SR-4 ^A	1450 to 1800	190–220	min 18
SR-5 ^A	1034 or greater	177–205	min 3
SR-6	1000 to 1400	200–230	min 3
SR-7 ^A	1050 to 1450	190–220	min 1
SR-8	surface-hardened parts ≤ 1400	130–160	min 8

^A Classes SR-2, SR-4, SR-5, and SR-7 are traditional treatments used in Federal Standard QQ-C-320. They do not apply to any other standard.

tensile strength. When only the minimum tensile strength is specified, or if the tensile strength is not known, the heat treatment condition shall be selected by relating known or measured hardness values to equivalent actual tensile strengths. The tensile strength shall be supplied by the purchaser.

5.2 Steels that have been wholly or partly surface hardened shall be considered as being in the category appropriate to the hardness of the surface-hardened layer.

6. Stress Relief

6.1 For high-strength steels, the following conditions apply. Stress relief treatment is not essential for steels of actual tensile strength below 1000 MPa. The conditions given in Table 1 are applied for steels of actual tensile strength above 1000 MPa. The heat treatment shall be conducted before the commencement of any preparation or cleaning treatment using aqueous solutions, such as those described in Practices B 242 or B 322, or before any treatment liable to cause embrittlement.

6.1.1 Suitable combinations of a shorter time at appropriate higher temperatures may be used if they have been shown not to be detrimental. For tempered steels, items shall not be heated above a temperature that shall be at least 50°C below the tempering temperature.

6.1.2 If stress relief is given after shot peening in accordance with Specification B 851 or other cold working processes to introduce beneficial compressive stresses, the temperature shall not exceed 230°C.

6.1.3 Items having surface-hardened areas that would suffer an unacceptable reduction in hardness by treatment in accordance with Table 1 shall be heat-treated at a lower temperature, but not below 130°C, for a minimum period of 8 h. This treatment is applicable for items made of steel with actual tensile strengths below 1400 MPa.

7. Keywords

7.1 delayed brittle failure; heat treatment; hydrogen embrittlement; hydrogen induced cracking; hydrogen stress cracking; pre-treatments of iron or steel; stress relief

⁴ Available from American National Standards Institute, 11 West 42nd Street, 13th Floor, New York, NY 10036.

⁵ Available from Standardization Documents Order Desk, Bldg. 4 Section D, 700 Robbins Ave., Philadelphia, PA 19111-5094, Attn: NPODS.

**NOTICE: This standard has either been superseded and replaced by a new version or discontinued.
Contact ASTM International (www.astm.org) for the latest information.**



The American Society for Testing and Materials takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, 100 Barr Harbor Drive, West Conshohocken, PA 19428.