



Designation: C 1032 – 96 (Reapproved 2002)

Standard Specification for Woven Wire Plaster Base¹

This standard is issued under the fixed designation C 1032; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last approval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope *

1.1 This specification covers woven wire plaster base, flat or self-furring, with or without stiffener wires, and with or without backing, designed for use as a base to receive gypsum or portland cement based plaster.

1.2 The values stated in inch-pound units are to be regarded as the standard. The SI equivalents of inch-pound units are approximate.

1.3 The text of this standard references notes and footnotes which provide explanatory material. These notes and footnotes (excluding those in tables and figures) shall not be considered as requirements of the standard.

2. Referenced Documents

2.1 ASTM Standards:

A 641 Specification for Zinc-Coated (Galvanized) Carbon Steel Wire²

C 11 Terminology Relating to Gypsum and Related Building Materials and Systems³

2.2 Federal Specifications:

UU-B-790a Building Paper, Vegetable Fiber: Kraft, Waterproofed, Water Repellent and Fire Resistant⁴

UU-P-31 B/Gen. Paper; General Specifications and Methods of Testing⁴

UU-P-31 B/171 Tensile Breaking Strength (Dry)⁴

3. Terminology

3.1 *Definitions*—Definitions shall be in accordance with Terminology C 11.

4. Material

4.1 In accordance with Specification A 641 and Table 1.

4.2 *Kraft Building Paper*, Federal Specification UU-B-790a.

¹ This specification is under the jurisdiction of ASTM Committee C11 on Gypsum and Related Building Materials and Systems and is the direct responsibility of Subcommittee C11.02 on Specifications and Test Methods for Accessories and Related Products.

Current edition approved May 10, 1996. Published July 1996. Originally published as C 1032 – 85. Last previous edition C 1032 – 95^{ε1}.

² *Annual Book of ASTM Standards*, Vol 01.06.

³ *Annual Book of ASTM Standards*, Vol 04.01.

⁴ Available from U.S. Government Printing Office Superintendent of Documents, 732 N. Capitol St., NW, Mail Stop: SDE, Washington, DC 20401.

TABLE 1 Minimum Wire Diameter for Size of Opening

Opening Size, in. (mm)	Wire Diameter, in. (mm)
1 (25.4)	0.035 (0.89)
1½ (38.0)	0.0510 (1.295)

5. Physical Properties

5.1 Backing:

5.1.1 Factory attached backing shall provide a one mesh wire to wire lap joint at one end and one edge of each flat sheet or roll. Attachment of the backing shall allow lapping of wire-to-wire and backing-to-backing of one mesh at ends and edges and shall permit full embedment in not less than ¼ in. (6.4 mm) of plaster of not less than one half the total length and width of the wire.

5.1.2 Backing shall have a minimum tensile breaking strength (dry) of 20 lbf/in. (3.5 kN/m) width, as tested in accordance with Federal Specification UU-P-31 B, Method 171.

6. Dimensions, Weight, and Permissible Variations

6.1 Openings:

6.1.1 Woven wire plaster base shall be fabricated to provide the size of openings in accordance with Table 1, except that any single opening shall be not more than 3.0 in.² (1935.5 mm²).

6.1.2 Wire diameter for opening size shall be in accordance with Table 1.

6.2 Diameter tolerance for galvanized wire shall be in accordance with Table number 2 of Specification A 641.

6.3 Weight for woven wire plaster base shall be in accordance with Table 2.

6.4 When included as part of the woven wire plaster base, factory fabricated stiffener wires shall have a diameter not less than that specified in Table 1 and shall be continuous, parallel to the long dimension of the plaster base, and shall occur at not more than 6-in. (154.4-mm) intervals.

6.5 Factory fabricated crimps for self-furring woven wire plaster base shall provide a nominal ¼-in. (6.4-mm) separation between the back plane of the plaster base and the surface of solid backing to permit embedment in both directions.

6.6 Width of woven wire plaster base shall be not less than 36 in. (914 mm).

6.7 Length of woven wire plaster base shall be in accordance with Table 3.

*A Summary of Changes section appears at the end of this standard.

TABLE 2 Minimum Weight for Size of Opening^A

Opening Size, in. (mm)	Weight per Square Yard, lb/yd ² (kg/m ²)
1 (25.4)	0.86 (0.466)
1½ (38.0)	1.40 (0.760)

^A The weight of attached backing is not included.

TABLE 3 Minimum Length of Flat Sheets and Rolls^A

Flat Sheets	100 linear in. (2.540 m)
Rolls	150 linear ft. (45.72 m)
Rolls, with backing	100 linear ft. (30.48 m)

^A Allowable variations shall be not more than $-\frac{3}{4}$ in. (-19.0 mm) in width or length.

7. Inspection

7.1 Inspection of the material shall be agreed upon between the purchaser and the producer or supplier as part of the purchase agreement.

8. Rejection and Rehearing

8.1 Material that fails to conform to the requirements of this specification shall be reported to the producer or supplier promptly and in writing. The notice of rejection shall contain a

statement documenting how the product has failed to conform to the requirements of the specification.

9. Certification

9.1 When specified in the purchase order or contract, the producer or supplier shall furnish a report certifying that at the time of shipment, the materials were in compliance with the requirements of this specification.

10. Packaging and Package Marking

10.1 *Packaging*—Woven wire plaster base shall be packaged in bundles, rolls or pallets.

10.2 *Marking*—When shipped for sale or resale, the name of the producer or the supplier and the brand and description of the contents shall be legibly marked on each pallet, bundle or roll. The quantity for bundles shall be square yards and number of sheet per bundle. The quantity for pallets, bundles or rolls shall indicate the mesh-opening size and wire thickness.

11. Keywords

11.1 backing; base; cement plaster; flat; gypsum plaster; plaster; self-furning; woven wire

SUMMARY OF CHANGES

This section identifies the location of changes to this specification that have been incorporated since the last issue, C 1032–96. Committee C-11 has highlighted those changes that

affect the technical interpretation or use of this specification.

(1) Standard was reapproved.

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).