



Designation: C 35 – 95 (Reapproved 2000)

Standard Specification for Inorganic Aggregates for Use in Gypsum Plaster¹

This standard is issued under the fixed designation C 35; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

1. Scope *

1.1 This specification covers perlite, vermiculite, natural and manufactured sand for use as gypsum plaster aggregates.

1.2 The values stated in inch-pound units are to be regarded as the standard. The values given in parentheses are provided for information purposes only.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:

C 11 Terminology Relating to Gypsum and Related Building Materials and Systems²

C 29/C 29M Test Method for Unit Weight and Voids in Aggregate³

C 40 Test Method for Organic Impurities in Fine Aggregates for Concrete³

C 136 Test Method for Sieve Analysis of Fine and Coarse Aggregates³

C 471 Test Methods for Chemical Analysis of Gypsum and Gypsum Products²

D 75 Practice for Sampling Aggregates⁴

E 11 Specification for Wire-Cloth and Sieves for Testing Purposes⁵

3. Terminology

3.1 Definitions shall be in accordance with Terminology C 11.

3.2 Definitions of Terms Specific to This Standard:

3.2.1 *manufactured sand, n*—the fine material resulting from the crushing and classification by screening, or otherwise, of rock, gravel or blast furnace slag.

3.2.2 *natural sand, n*—the fine granular material resulting from the natural disintegration of rock or from the crushing of friable sandstone.

3.2.3 *perlite aggregate, n*—a siliceous volcanic glass expanded by heat.

3.2.4 *vermiculite aggregate, n*—a micaceous mineral expanded by heat.

4. Chemical Composition

4.1 Water-soluble impurities in sand shall not exceed 0.15 weight % and sodium ion content shall not exceed 0.02 weight % when tested in accordance with Section 7.

4.2 Sand shall develop a color no darker than the standard, when subjected to the colorimetric test for organic impurities in accordance with Test Method C 40, unless it is established by adequate tests that the impurities causing the color are not harmful in plaster.

5. Mechanical Requirements

5.1 *Grading*—Shall be as follows when tested in accordance with Section 7.

5.1.1 Perlite and vermiculite shall be graded within the limits specified in Table 1.

5.1.2 *Natural and Manufactured Sand*— Shall be graded with not more than 50 % retained between any two consecutive sieves shown in Table 1, nor more than 25 % between the No. 50 (300 μm) and No. 100 (150 μm) sieves.

5.2 Density:

5.2.1 Perlite shall have a density of not less than 6 nor more than 12 lb/ft³ (96 to 192 kg/m³) when tested in accordance with Test Method C 29/C 29M using the shoveling procedure.

5.2.2 Vermiculite shall have a density of not less than 6 nor more than 10 lb/ft³ (96 to 160 kg/m³) when tested in accordance with Test Method C 29/C 29M using the shoveling procedure.

6. Sampling

6.1 *Apparatus*—Suitable thief tube.

6.2 *Bulk Aggregate*—Obtain specimens of sand in accordance with Practice D 75.

6.3 *Bagged Aggregate*—Obtain from one bag randomly selected from each 100 bags but not less than 6 bags from the shipment. For smaller shipments, not less than 6 % of the number of bags shall constitute the sample.

¹ This specification is under the jurisdiction of ASTM Committee C11 on Ceiling and Walls and is the direct responsibility of Subcommittee C11.02 on Specifications and Test Methods for Accessories and Related Products.

Current edition approved July 15, 1995. Published October 1995. Originally published as C 35-21 T. Last previous edition C 35 – 89a.

² *Annual Book of ASTM Standards*, Vol 04.01.

³ *Annual Book of ASTM Standards*, Vol 04.02.

⁴ *Annual Book of ASTM Standards*, Vol 04.03.

⁵ *Annual Book of ASTM Standards*, Vol 14.02.

*A Summary of Changes section appears at the end of this standard.

TABLE 1 Grading Requirements

Sieve Size	Percentage Retained on Each Sieve, Cumulative					
	Perlite, by volume		Vermiculite, by volume		Sand, by weight	
	Max	Min	Max	Min	Max	Min
No. 4 (4.75-mm)	0	...	0	...	0	...
No. 8 (2.36-mm)	5	0	10	0	5	0
No. 16 (1.18-mm)	60	5	75	40	30	5
No. 30 (600- μ m)	95	45	95	65	65	30
No. 50 (300- μ m)	98	75	98	75	95	65
No. 100 (150- μ m)	100	85	100	90	100	90
No. 200 (75- μ m)					100	95

6.3.1 Secure specimens by inserting a suitable thief tube the full distance between diagonally opposite corners of the bag with the bag lying in a horizontal position. Combine the portions to produce a composite specimen having a volume not less than 1 ft³ (0.028 m³). Prepare and test not less than one composite specimen separately for each 2000 bags of aggregate.

6.4 Reduce specimens obtained in accordance with 6.2 or 6.3 by quartering or riffing to obtain specimens of proper size for individual tests.

7. Test Methods

7.1 Apparatus:

7.1.1 *Sieve*—Specification E 11, Nos. 4, 8, 16, 30, 50, 100, 200 (4.75, 2.36, 1.18 mm, 600 μ m, 300 μ m, 150 μ m, 75 μ m).

7.1.2 *Graduated 250 mL Cylinder*.

7.1.3 *250 mL Beaker*.

7.1.4 *Tared Evaporating Dish*.

7.1.5 *Fast Paper Filter*.

7.1.6 *100 mL Volumetric Flask*.

7.1.7 *Deionized Water*.

7.1.8 *Spatula*.

7.1.9 *Weighing Scale*.

7.1.10 *Oven*.

7.1.11 *Desiccator*.

7.1.12 *Mechanical Shaker*.

7.1.13 *500 mL Graduated Cylinder*.

7.2 *Sieve Analysis for Sand*—Use Test Method C 136.

7.3 *Sieve Analysis for Perlite or Vermiculite*—Use Test Method C 136 except as modified as follows.

7.3.1 Use a specimen of 500 mL bulk volume.

7.3.1.1 Measure the volume of each sieve fraction in a 250 mL graduated cylinder. Pour the specimen loosely into the graduate without tamping or shaking. Level the surface with a spatula and read the volume to within ± 2 mL.

7.3.2 Express the volumes of the individual sieve fractions as percentages of the sum of the volumes of all fractions.

7.3.3 Calculate the cumulative percentages on each designated sieve by summing the individual percentages of all fractions larger than that sieve.

7.4 *Density of Lightweight Aggregate*—Test Method C 29/C 29M; Use shoveling procedure.

7.5 *Water Soluble Impurities of Sand*:

7.5.1 *Significance and Use*—Impurities can affect the setting properties, strength and bond performance of gypsum plaster. These procedures determine the water soluble impurities of the sand being evaluated.

7.5.2 Apparatus:

7.5.2.1 *Analytical Balance*, with a precision of 0.0001 g.

7.5.2.2 *Balance*, capable of weighing at least 10 g to a precision of 0.1 g.

7.5.2.3 *Desiccator*, containing calcium chloride or equivalent desiccant.

7.5.2.4 *Drying Oven*, capable of being controlled to 250°F (121°C).

7.5.2.5 *Filter Paper*—A “fast” filter paper shall be used.

NOTE 1—S & S Black Ribbon or Whitman No. 41 have been found suitable for this purpose.⁶

7.5.2.6 *Atomic Absorption or Ion Chromatography Equipment*.

7.5.2.7 *Mechanical Shaker*.

7.5.3 Procedure:

(Water Soluble Impurities.)

7.5.3.1 Weigh approximately 10 g of air-dried sand and record the weight to 0.1 g. Transfer to a 250-mL beaker. Add 100 mL of distilled water. Heat to boiling and allow to simmer on a hot plate for 5 min. Filter through a fast paper into a tared evaporating dish. Wash with hot distilled water until the volume of filtrate is about 125 mL. Evaporate to dryness in an oven without allowing the temperature of the dish to rise above 250°F (121°C). Cool residue in a desiccator, weigh to 0.001 g and calculate the percentage of residue on the initial weight of sand.

7.5.3.2 *Report*—Report percentage as water soluble impurities.

7.5.3.3 *Precision and Bias*—No estimate of the precision or bias, or both, is available at this time.

7.5.4 *Procedure*—(Sodium Ion Content.)

7.5.4.1 Weigh approximately 5 g of sand and record the weight to 0.01 g. Transfer to 100-mL volumetric flask. Add approximately 80 mL of deionized water to the flask. Shake on a mechanical shaker for 4 h. Remove and bring to a full volume with deionized water and allow to settle. Analyze for Na ion according to general atomic absorption in accordance with Test Methods C 471 or ion chromatography procedures.⁷

NOTE 2—To minimize contamination, care must be exercised to be sure all equipment is clean.

7.5.4.2 *Calculation and Report*—Calculate and report the percent Na as follows:

Curve concentration \times any dilution factor

$$\mu\text{g/g} = \frac{\times 100 \text{ mL final volume}}{\text{initial weight of sample}}$$

$$\frac{\mu\text{g/g}}{10\,000} = \% \text{ metal ion (Na}^{\text{+}}\text{)}$$

7.5.4.3 *Precision and Bias*—No estimate of the precision or bias is available at this time.

7.5.5 *Organic Impurities*—Test Method C 40.

8. Inspection

8.1 Inspection of the material shall be agreed upon between

⁶ Available from VWR Scientific.

⁷ Ion Chromatographs supplied by Dionex Inc., 1228 Titan Way, Sunnyvale, CA 94086 have been found suitable for this purpose.

the purchaser and the producer or supplier as part of the purchase agreement.

9. Rejection and Rehearing

9.1 Rejection of material shall be reported to the producer or supplier within 10 working days from the receipt of the shipment by the purchaser. Rejection of the material shall be based either on the specific cause of failure to conform to the requirements of this specification or the failure of the material to meet the minimum weight or approximate volume as stated on the shipment.

9.2 Failure to meet the minimum weight or approximate volume shall be determined as follows:

9.2.1 Individual Packages:

9.2.1.1 The contents, on a weight basis, are 5 % less than that indicated on the packages, or

9.2.1.2 The contents, on a volume basis, are 10 % less than that indicated on the package.

9.2.2 The Entire Shipment:

9.2.2.1 On a weight basis when the average contents of two packages for each 100 but not less than six packages selected at random, in any one shipment, are less than that indicated on the package. The net weight of the contents shall be determined by weighing the package or packages and deducting the weight of the container.

9.2.2.2 On a volume basis when the average contents of two packages for each 100 but not less than six packages selected at random, in any one shipment, differ by more than 5 % more or 10 % less from that indicated on the package. The volume of

the contents in the package shall be calculated by determining the weight of the contents of the package and then obtaining the weight per unit of volume of the aggregate, from an average weight package of the samples selected in 6.3.1, by the shoveling procedure given in Test Method C 29/C 29M, and then dividing the weight of the contents of the bag by the unit of volume of the aggregate.

10. Certification

10.1 When specified in the purchase order, the producer's or supplier's certification shall be furnished to the purchaser stating that the material was prepared or manufactured in accordance with this specification and has been found to meet the specified requirements.

11. Packaging and Package Marking

11.1 When lightweight aggregates covered by this specification are delivered in packages, the name of the type of aggregate, and minimum weight and approximate volume of the contents shall be plainly indicated thereon.

11.2 When delivered in bulk quantities, the bill of lading shall show the quantity by weight or unit of volume, and the name of the supplier.

11.2.1 Bulk materials shall be delivered in clean transport vessels, free of contaminants.

12. Keywords

12.1 aggregates; gypsum plaster; inorganic; manufactured sand; natural sand; perlite; vermiculite

SUMMARY OF CHANGES

This section identifies the location of changes to this specification that have been incorporated since the last issue. Committee C11 has highlighted those changes that affect the

technical interpretation or use of this specification.

(1) Reapproval of the standard.

The American Society for Testing and Materials takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).