



Designation: C 706 – 9802

Standard Specification for Limestone for Animal Feed Use¹

This standard is issued under the fixed designation C 706; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification covers limestone supplied for use as a mineral supplement in animal feeds.

NOTE 1—The calcium needed for animal nutrition is customarily supplied by limestone. Such limestone must be sufficiently fine to blend with mixed feeds and yet be free from excessive dusting.

1.2 *This standard does not purport to address all of the safety ~~problems~~, concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 *ASTM Standards:*

¹ This specification is under the jurisdiction of ASTM Committee ~~C-7~~ C07 on Lime and is the direct responsibility of Subcommittee C07.03 ~~for~~ on Industrial Uses .
Current edition approved ~~July~~ Dec. 10, 1998; 2002. Published ~~December~~ 1998; January 2003. Originally published as C 706 – 72; approved in 1972. Last previous edition approved in 1998 as C 706 – 928.

- C 25 Test Methods for Chemical Analysis of Limestone, Quicklime, and Hydrated Lime²
- C 50 Methods for Sampling, Inspection, Packaging, and Marking of Lime and Limestone Products²
- C 51 Terminology Relating to Lime and Limestone²
- C 110 Test Methods for Physical Testing of Quicklime, Hydrated Lime, and Limestone²
- E 11 Specification for Wire-Cloth and Sieves for Testing Purposes³

3. Terminology

3.1 Definitions of terms applying to this specification appear in Terminology C 51.

4. General Requirements

4.1 The product must be suitable for animal feeding.

5. Chemical Requirements

5.1 Limestone, as identified on feed labels, shall conform to the chemical requirements given in Table 1.

6. Physical Requirements

~~6.1 Screen~~

6.1 Sieve analysis and other physical requirements shall be specified by the purchaser.

7. Test Methods

7.1 *Chemical Analysis*—Unless otherwise agreed upon between the purchaser and the manufacturer, the chemical analysis of the limestone shall be ~~conducted~~ in accordance with Test Methods C 25.

7.2 *Fineness Particle Size*—Unless otherwise agreed upon between the purchaser and the manufacturer, the sieve analysis of the material shall be determined in accordance with Test Methods C 1010.

7.2.1 *Procedure*—If the entire sample is not to be dried, obtain lesser portions by riffing or quartering. Dry at between 115 to 120°C to a constant mass and cool to room temperature. Obtain a 90 to 120-g dry sample by riffing or quartering. If the material tends to cake, break up the agglomerates with a soft rubber pestle. Quantitatively transfer the weighed sample to an 8-in. diameter standard sieve or set of sieves (for example, Nos. 10, 20, 40, 60, 80, and 100 or other appropriate combination conforming to Specification E 11). Conduct the ~~sieving by lateral and vertical motion accompanied by a jarring action. Continue for a minimum of 5 min or until an additional 3 min of sieving time fails to change the results of any sieve fraction by 0.5 % of the total sample mass. Take care to avoid overloading any sieve when assaying closely sized materials. Determine the mass of each sieve fraction and report as the percentage of total sample mass.~~ analysis in accordance with Test Methods C 110.

8. Sampling, Inspection, etc.

8.1 The sampling, inspection, rejection, retesting, packaging, and marking shall be conducted in accordance with Methods C 50.

9. Keywords

9.1 animal; feed; limestone; mineral; supplement

² Annual Book of ASTM Standards, Vol 04.01.

³ Annual Book of ASTM Standards, Vol 14.02.

TABLE 1 Chemical Requirements

Limestone Classes (See C 51)	Calcium, min, percent (as CaCO ₃)	Magnesium, max, percent (as MgCO ₃)	Magnesium, min, percent (as MgCO ₃)	Moisture, max, percent
High Calcium	95	5	...	0.5
Magnesian	60	35 ^A	5	0.5
Dolomitic	49	46 ^A	35	0.5
Ground Limestone	82	^B	^B	0.5

^A The high magnesium content of these materials usually limits their use to special-purpose feeds.

^B As specified by the purchaser.

 **C 706 – 9802**

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).