



# Standard Practice for Quantities of Materials for Bituminous Surface Treatments<sup>1</sup>

This standard is issued under the fixed designation D 1369; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

*This standard has been approved for use by agencies of the Department of Defense.*

## 1. Scope

1.1 This practice covers the rates of application of bituminous materials and aggregates and types and grades of bituminous materials for single and multiple bituminous surface treatments as applied to suitably prepared pavements or bases.

1.2 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

## 2. Referenced Documents

### 2.1 ASTM Standards:

- C 29/C29M Test Method for Unit Weight and Voids in Aggregate<sup>2</sup>
- D 448 Classification for Sizes of Aggregate for Road and Bridge Construction<sup>3</sup>
- D 490 Specification for Road Tar<sup>3</sup>
- D 633 Volume Correction Table for Road Tar<sup>3</sup>
- D 946 Specification for Penetration-Graded Asphalt Cement for Use in Pavement Construction<sup>3</sup>
- D 977 Specification for Emulsified Asphalt<sup>3</sup>
- D 1139 Specification for Aggregate for Single or Multiple Bituminous Surface Treatments<sup>3</sup>
- D 1250 Guide for Petroleum Measurement Tables<sup>4</sup>
- D 2027 Specification for Cutback Asphalt (Medium-Curing Type)<sup>3</sup>
- D 2028 Specification for Cutback Asphalt (Rapid-Curing Type)<sup>3</sup>
- D 2397 Specification for Cationic Emulsified Asphalt<sup>3</sup>

## 3. Terminology

### 3.1 Definitions:

3.1.1 The types of surface treatments covered by this practice are as follows:

3.1.2 *multiple-surface treatment*—a wearing surface composed of bituminous material and aggregate, in which coarser aggregate is placed uniformly over an initial application of bituminous material and followed by one or more subsequent applications of bituminous material and smaller aggregate.

3.1.2.1 *Discussion*—Generally, the designated maximum size of the smaller aggregate is one half that of the aggregate used in the preceding application. Each application of aggregate is placed uniformly in a single layer, the thickness of which approximates the nominal maximum size of the aggregate.

3.1.3 *single-surface treatment*—a wearing surface of bituminous material and aggregate in which the aggregate is placed uniformly over the applied bituminous material in a single layer, the thickness of which approximates the nominal maximum size of the aggregate used.

## 4. Significance and Use

4.1 This practice is intended to be used as a guide by those involved in the design of bituminous surface treatments. It covers typical application rates for the various types of surface treatments and covers aggregate sizes and covers recommended grades of asphaltic material for both hot and cool weather conditions.

4.2 The typical bituminous material application rates given are for normal surfaces and non-porous aggregates. Provision is made for rate adjustment when other than normal surfaces or porous aggregates, or both, are involved.

## 5. Rates of Application

5.1 Typical quantities of materials for the several types of surface treatments are listed in Table 1 and Table 2.

5.2 The quantities of the various gradations are normally sufficient to provide a uniform cover over the area specified. The quantities of aggregate are shown by volume measurement in order to minimize the effect of variations due to specific gravity, particle shape, surface texture, and porosity. For job control, the quantity of aggregate by volume may be converted to a weight figure by determining the loose unit weight of the aggregate and calculating or using Table 3 and Table 4 to determine the pounds per square yard or kilograms per square metre.

5.3 The quantities of bituminous materials for the various

<sup>1</sup> This practice is under the jurisdiction of ASTM Committee D04 on Road and Paving Materials and is the direct responsibility of Subcommittee D04.24 on Bituminous Surface Treatments.

Current edition approved March 30, 1984. Published September 1984. Originally issued 1955. Last previous edition D 1369 – 84.

<sup>2</sup> *Annual Book of ASTM Standards*, Vol 04.02.

<sup>3</sup> *Annual Book of ASTM Standards*, Vol 04.03.

<sup>4</sup> *Annual Book of ASTM Standards*, Vol 05.01 (Description only; tables published separately in twelve volumes).

**TABLE 1 Quantities of Materials for Bituminous Surface Treatments (U.S. Customary Units)**

NOTE 1—The values are typical design or target values and are not necessarily obtainable to the precision indicated.

Surface Treatment			Aggregate		Bituminous Material <sup>A</sup>
Type	Application	Size No. <sup>B</sup>	Nominal Size (Square Openings)	Typical Rate of Application, ft <sup>3</sup> /yd <sup>2</sup>	Typical Rate of Application, gal/yd <sup>2</sup>
Single	initial	5	1 in. to ½ in.	0.50	0.42
		6	¾ in. to ⅝ in.	0.36	0.37
		7	½ in. to No. 4	0.23	0.23
		8	⅜ in. to No. 8	0.17	0.19
		9	No. 4 to No. 16	0.11	0.13
Double	initial	5	1 in. to ½ in.	0.50	0.42
	second	7	½ in. to No. 4	0.25	0.26
Double	initial	6	¾ in. to ⅝ in.	0.36	0.37
	second	8	⅜ in. to No. 8	0.18	0.20
Triple	initial	5	1 in. to ½ in.	0.50	0.42
	second	7	½ in. to No. 4	0.25	0.26
	third	9	No. 4 to No. 16	0.13	0.14
Triple	initial	6	¾ in. to ⅝ in.	0.36	0.37
	second	8	⅜ in. to No. 8	0.18	0.20
	third	9	No. 4 to No. 16	0.13	0.14

<sup>A</sup>Experience has shown that these quantities should be increased slightly (5 to 10 %) when the bituminous material to be used was manufactured for application with little or no heating.

<sup>B</sup>According to Classification D 448.

**TABLE 2 Quantities of Materials for Bituminous Surface Treatments (Metric Units)**

NOTE 1—The values are typical design or target values and are not necessarily obtainable to the precision indicated.

Surface Treatment			Aggregate		Bituminous Material <sup>A</sup>
Type	Application	Size No. <sup>B</sup>	Nominal Size (Square Openings, mm)	Typical Rate of Application, m <sup>3</sup> /m <sup>2</sup>	Typical Rate of Application, litre/m <sup>2</sup>
Single	initial	5	25.0 to 12.5	0.017	1.90
		6	19.0 to 9.5	0.012	1.68
		7	12.5 to 4.75	0.008	1.04
		8	9.5 to 2.36	0.006	0.86
		9	4.8 to 1.2	0.004	0.59
Double	initial	5	25.0 to 12.5	0.017	1.90
	second	7	2.5 to 4.75	0.008	1.18
Double	initial	6	19.0 to 9.5	0.012	1.68
	second	8	9.5 to 2.36	0.006	0.91
Triple	initial	5	25.0 to 12.5	0.017	1.90
	second	7	12.5 to 4.75	0.008	1.18
	third	9	4.75 to 1.18	0.004	0.63
Triple	initial	6	19.0 to 9.5	0.012	1.68
	second	8	9.5 to 2.36	0.006	0.91
	third	9	4.75 to 1.18	0.004	0.63

<sup>A</sup>Experience has shown that these quantities should be increased slightly (5 to 10 %) when the bituminous material to be used was manufactured for application with little or no heating.

<sup>B</sup>According to Classification D 448.

aggregate gradations are typical rates of application considered adequate to retain aggregate of the specified size on a normal surface. The quantity of bituminous material should be increased when highly absorptive or porous aggregate is used and when treating an old surface that is dry, in order to allow for bituminous material absorbed. The quantity of bituminous material should be decreased when treating an existing surface that is rich in bitumen, in order to compensate for such excess. Quantities of bituminous materials shown are for volumes of the material at 60°F (15.6°C). For application at elevated

temperatures these quantities should be adjusted to provide the desired volume at 60°F.

5.4 The typical rates of application shown in Table 1 and Table 2 may be adjusted for variations in the gradation of the aggregate from the coarse to the fine limit of the specification. The quantities of bituminous material and aggregate should be increased when the gradation of the aggregate approaches the coarse limit of the specification. Likewise, the quantities should be decreased when the aggregate approaches the fine limit of the specification. The amount of such increase or

**TABLE 3 Approximate Conversion Table—Loose Unit Weight To Pounds per Square Yard**

Loose Unit Weight		Approximate lb/yd <sup>2</sup> at various application rates (ft <sup>3</sup> /yd <sup>2</sup> )								
lb/yd <sup>3</sup>	lb/ft <sup>3</sup> (approx- imately)	0.10 ft <sup>3</sup>	0.15 ft <sup>3</sup>	0.20 ft <sup>3</sup>	0.25 ft <sup>3</sup>	0.30 ft <sup>3</sup>	0.35 ft <sup>3</sup>	0.40 ft <sup>3</sup>	0.45 ft <sup>3</sup>	0.50 ft <sup>3</sup>
1800	66.5	6.5	10	13.5	17	20	23.5	26.5	30	33.5
1900	70.5	7.0	10.5	14	17.5	21	24.5	28	31.5	35
2000	74	7.5	11	15	18.5	22	26	29.5	33.5	37
2100	78	8	11.5	15.5	19.5	23	27	31	35	39
2200	81.5	8	12	16.5	20.5	24.5	28.5	32.5	36.5	41
2300	85	8.5	13	17	21.5	25.5	30	34	38.5	42.5
2400	89	9	13.5	18	22	26.5	31	35.5	40	44.5
2500	92.5	9.5	14	18.5	23	28	32.5	37	41.5	46.5
2600	96.5	9.5	14.5	19.5	24	29	33.5	38.5	43.5	48
2700	100	10	15	20	25	30	35	40	45	50
2800	103.5	10.5	15.5	20.5	26	31	36.5	41.5	46.5	52
2900	107.5	10.5	16	21.5	27	32	37.5	43	48.5	53.5
3000	111	11	16.5	22	28	33	39	44.5	50	55

**TABLE 4 Approximate Conversion Table—Loose Unit Weight to Kilograms per Square Metre**

Loose Unit Weight, kg/m <sup>3</sup>		Approximate kg/m <sup>2</sup> at various application rates (m <sup>3</sup> /m <sup>2</sup> )								
		0.0028 m <sup>3</sup>	0.0042 m <sup>3</sup>	0.0057 m <sup>3</sup>	0.0071 m <sup>3</sup>	0.0085 m <sup>3</sup>	0.0099 m <sup>3</sup>	0.0113 m <sup>3</sup>	0.0127 m <sup>3</sup>	0.0142 m <sup>3</sup>
1067.9	3.53	5.42	7.32	9.22	10.85	12.75	14.38	16.27	18.17	
1127.2	3.80	5.70	7.59	9.49	11.39	13.29	15.19	17.09	18.99	
1186.5	4.07	5.97	8.14	10.04	11.93	14.10	16.00	18.17	20.07	
1245.9	4.34	6.24	8.41	10.58	12.48	14.65	16.82	18.99	21.16	
1305.2	4.34	6.51	8.95	11.12	13.29	15.46	17.63	19.80	22.24	
1364.5	4.61	7.05	9.22	11.66	13.83	16.27	18.44	20.89	23.06	
1423.9	4.88	7.32	9.76	11.93	14.38	16.82	19.26	21.70	24.14	
1483.2	5.15	7.59	10.04	12.48	15.19	17.63	20.07	22.51	25.23	
1542.5	5.15	7.87	10.58	13.02	15.73	18.17	20.89	23.60	26.04	
1601.8	5.42	8.14	10.85	13.56	16.27	18.99	21.70	24.41	27.12	
1661.2	5.70	8.41	11.12	14.10	16.82	19.80	22.51	25.23	28.21	
1720.5	5.70	8.68	11.66	14.65	17.36	20.34	23.33	26.31	29.02	
1779.8	5.97	8.95	11.93	15.19	17.90	21.16	24.14	27.12	29.84	

decrease should not be more than 20 % of the quantity given.

5.5 The types and grades of bituminous materials recommended for use with the various aggregate sizes are listed in Table 5 and Table 6.

## 6. Reference Specifications

6.1 The specifications for aggregates are covered in Specification D 1139.

6.2 The specifications for bituminous materials are covered by the following ASTM specifications: Specification D 946, Specification D 2027, Specification D 2028, Specification D 977, Specification D 2397, and Specification D 490.

## 7. Measurement of Materials

7.1 The following method and tables are applicable for measuring the quantities of bituminous materials and aggregates:

7.1.1 *Volume of Bituminous Material:*

Guide D 1250 and Table D 633.

7.1.2 *Unit Weight of Aggregate-Loose Weight*—To be made in accordance with Test Method C 29/C 29M.

**TABLE 5 Recommended Grades of Asphaltic Materials for Bituminous Surface Treatments<sup>A</sup>**

Nominal Size (Square Openings), in. (mm)	Size No.	Hot Weather (80°F + ) (26.7°C + )		Cool Weather <sup>B</sup> (50 to 80°F) (10 to 26.7°C)	
1 to ½ (25.0 to 12.5)	5	MC	3000	MC	3000
		RC	3000	RC	3000
		RS	2	RS	2
		CRS	2	CRS	1, 2
		120 to 150		120 to 150	
¾to ⅝ (19.0 to 9.5)	6	MC	3000	MC	800
		RC	3000	RC	800
		RS	2	RS	2
		CRS	1, 2	CRS	1, 2
		120 to 150			
½to No. 4 (12.5 to 4.75)	7	MC	3000	MC	800
		RC	800, 3000	RC	250, 800
		RS	2	RS	2
		CRS	1, 2	CRS	1, 2
		200 to 300 <sup>C</sup>			
¾to No. 8 (9.5 to 2.36)	8	RC	250, 800	RC	250, 800
		RS	1, 2	RS	1, 2
		CRS	1, 2	CRS	1, 2
No. 4 to No. 16 (4.75 to 1.18)	9	RC	250, 800	RC	250, 800
		RS	1, 2	RS	1, 2
		CRS	1, 2	CRS	1, 2

<sup>A</sup>Grades of asphaltic materials are according to Specifications D 946, D 977, D 2027, D 2028, and D 2397.

<sup>B</sup>Under certain conditions, the heavier grades of MC liquid asphalts may be used in cool weather.

<sup>C</sup>In some areas persistent difficulty in retaining aggregate has been experienced with 200 to 300 penetration asphalt cements. Where this has occurred, its use is not recommended.

**TABLE 6 Recommended Grades of Tar for Bituminous Surface Treatments<sup>A</sup>**

Nominal Size (Square Openings), in. (mm)	Size No.	Hot Weather (80°F + ) (26.7°C + )		Cool Weather (up to 80°F) (Up to 26.7°C)	
1 to ½(25.0 to 12.5)	5	...		...	
¾to ⅝ (19.0 to 9.5)	6	RT	10, 11	RT	9, 10
½to No. 4 (12.5 to 4.75)	7	RT	9, 10, 11	RT	8, 9, 10
¾to No. 8 (9.5 to 2.36)	8	RT	9, 10, 11	RT	8, 9, 10
No. 4 to No. 16 (4.75 to 1.18)	9	RT	8, 9, 10	RT	7, 8, 9

<sup>A</sup>According to Specification D 490.

The American Society for Testing and Materials takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).