



Designation: D 402 – 97



27/74 (88)

American Association State
Highway and Transportation Officials Standard
AASHTO No.: T78

Standard Test Method for Distillation of Cut-Back Asphaltic (Bituminous) Products¹

This standard is issued under the fixed designation D 402; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reappraisal. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reappraisal.

This standard has been approved for use by agencies of the Department of Defense. This method was adopted as a joint ASTM-IP standard in 1961.

1. Scope

1.1 This test method covers a distillation test for cut-back asphaltic (bituminous) products.

1.2 The values given in SI units are to be regarded as the standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:

D 86 Test Method for Distillation of Petroleum Products²

D 370 Test Method for Dehydration of Oil-Type Preservatives³

E 1 Specification for ASTM Thermometers⁴

E 133 Specification for Distillation Equipment⁵

2.2 IP Standards:

IP 123/ASTM D 86, Distillation of Petroleum Products

Thermometers as specified in IP Standards

Crow Receiver as specified in British Standards 658:1962

C.O.3—Standard Methods for Testing Tar and its Products
(Published by the U.K. Standardization of Tar Products
Tests Committee)

3. Summary of Method

3.1 Two hundred millilitres of the sample are distilled in a 500-mL flask at a controlled rate to a temperature in the liquid of 360°C (680°F) and the volumes of distillate obtained at specified temperatures are measured. The residue from the

distillation, and also the distillate, may be tested as required.

4. Significance and Use

4.1 This procedure measures the amount of the more volatile constituents in cut-back asphaltic products. The properties of the residue after distillation are not necessarily characteristic of the bitumen used in the original mixture nor of the residue which may be left at any particular time after application of the cut-back asphaltic product. The presence of silicone in the cut-back may affect the distillation residue by retarding the loss of volatile material after the residue has been poured into the residue container.

5. Apparatus

5.1 *Distillation Flask*, 500-mL side-arm, having the dimensions shown in Fig. 1.

5.2 *Condenser*, standard glass-jacketed, of nominal jacket length from 200 to 300 mm and overall tube length of 450 ± 10 mm (see Fig. 3).

5.3 *Adapter*, heavy-wall (1-mm) glass, with reinforced top, having an angle of approximately 105°. The inside diameter at the large end shall be approximately 18 mm, and at the small end, not less than 5 mm. The lower surface of the adapter shall be on a smooth descending curve from the larger end to the smaller. The inside line of the outlet end shall be vertical, and the outlet shall be cut or ground (not fire-polished) at an angle of 45 ± 5° to the inside line.

5.4 *Shield*, steel, lined with 3-mm fire proof insulation and fitted with transparent mica windows, of the form and dimensions shown in Fig. 2, used to protect the flask from air currents and to reduce radiation. The cover (top) shall be made in two parts of 6.4-mm (¼-in.) fire proof insulation.

5.5 *Shield and Flask Support*—Two 15-cm² sheets of 16-mesh Chromel wire gauze on a tripod or ring.

5.6 Heat Source—

5.6.1 Adjustable Tirrill-type gas burner or equivalent.

5.6.2 An electric heater equipped with a transformer capable of controlling from 0 to 750 W. The shield and support shall be a refractory with an opening of 3¼ in. (79 mm), with the upper surface beveled to 3¾ in. (86 mm) to accommodate

¹ This test method is under the jurisdiction of ASTM Committee D-4 on Road and Paving Materials and is the direct responsibility of Subcommittee D04.46 on Durability Tests.

Current edition approved Nov. 10, 1997. Published February 1998. Originally published as D 402 – 34 T. Last previous edition D 402 – 94.

In the IP, this method is under the jurisdiction of the Standardization Committee.

² *Annual Book of ASTM Standards*, Vol 05.01.

³ *Annual Book of ASTM Standards*, Vol 04.09.

⁴ *Annual Book of ASTM Standards*, Vol 14.03.

⁵ *Annual Book of ASTM Standards*, Vol 14.02.

ASTM D 402





FIG. 1 Distillation Flask



Flanged Open-End Cylinder
Made of 22-Gage Galvanized
Iron with 3 mm Asbestos Lining
Riveted to Metal

Two Mica Windows are
Provided of Right Angles
to the End Slot.

FIG. 2 Shield

the specified 500-mL flask. When the flask is placed on the refractory, there should be a distance of approximately $\frac{1}{8}$ in. (3 mm) between the bottom of the flask and the heating elements.

5.7 *Receiver*—A standard 100-mL graduated cylinder conforming to dimensions of Fig. 4 of Specification E 133, or a 100-mL crow receiver as shown in Fig. 4 of this test method.

NOTE 1—Receivers of smaller capacity having 0.1-mL divisions may be used when low volumes of total distillate are expected and the added accuracy required.

5.8 *Residue Container*—An 8-oz seamless metal container with slip on cover of 75 ± 5 mm in diameter, and 55 ± 5 mm in height.

5.9 *Thermometer*—ASTM Thermometers 8C (8F) conforming to Specification E 1, or IP Thermometer 6C conforming to IP Specifications for Standard Thermometers.

6. Sampling

6.1 Stir the sample thoroughly, warming if necessary, to ensure homogeneity before removal of a portion for analysis.

6.2 If sufficient water is present to cause foaming or bumping, dehydrate a sample of not less than 250 mL by heating in a distillation flask sufficiently large to prevent foaming over into the side arm. When foaming has ceased, stop the distillation. If any light oil has distilled over, separate and





FIG. 3 Distillation Apparatus



All dimensions are in millimetres

FIG. 4 Crow Receivers of Capacity 25, 50, and 100 mL

pour this back into the flask when the contents have cooled just sufficiently to prevent loss of volatile oil. Mix the contents of the flask thoroughly before removal for analysis. An alternative procedure is described in Test Method D 370.

7. Preparation of Apparatus

7.1 Calculate the weight of 200 mL of the sample from the specific gravity of the material at 15.6/15.6°C (60/60°F). Weigh this amount ± 0.5 g into the 500-mL flask.

7.2 Place the flask in the shield supported by two sheets of gauze on a tripod or ring. Connect the condenser tube to the tubulature of the flask with a tight cork joint. Clamp the condenser so that the axis of the bulb of the flask through the center of its neck is vertical. Adjust the adapter over the end of the condenser tube so that the distance from the neck of the flask to the outlet of the adapter is 650 ± 50 mm (see Fig. 3).

7.3 Insert the thermometer through a tightly fitting cork in the neck of the flask so that the bulb of the thermometer rests on the bottom of the flask. Raise the thermometer 6.4 mm ($\frac{1}{4}$ in.) from the bottom of the flask using the scale divisions on the

thermometer to estimate the 6.4-mm ($\frac{1}{4}$ -in.) distance above the top of the cork.

7.4 Protect the burner by a suitable shield or chimney. Place the receiver so that the adapter extends at least 25 mm but not below the 100-mL mark. Cover the graduate closely with a piece of blotting paper, or similar material, suitably weighted, which has been cut to fit the adapter snugly.

7.5 The flask, condenser tube, adapter, and receiver shall be clean and dry before starting the distillation. Place the 8-oz residue container on its cover in an area free from drafts.

7.6 Pass cold water through the condenser jacket. Use warm water if necessary to prevent formation of solid condensate in the condenser tube.

8. Procedure

8.1 Correct the temperatures to be observed in the distillation if the elevation of the laboratory at which the distillation is made deviates (150 m) 500 ft or more from sea level. Corrected temperatures for the effect of altitude are shown in Table 1 and Table 2. If the prevailing barometric pressure in millimetres of mercury is known, correct the temperature to be observed with the corrections shown in Table 3. *Do not correct for the emergent stem of the thermometer.*

NOTE 2—Table 3 covers a wide range of temperatures from 160 to 360°C and is to be preferred for world-wide specifications other than ASTM/IP specifications.

8.2 Apply heat so that the first drop of distillate falls from the end of the flask side-arm in 5 to 15 min. Conduct the distillation so as to maintain the following drop rates, the drop count to be made at the tip of the adapter:

- 50 to 70 drops per minute to 260°C (500°F)
- 20 to 70 drops per minute between 260 and 316°C (500 and 600°F)
- Not over 10 min to complete distillation from 316 to 360°C (600 to 680°F)

8.2.1 Record the volumes of distillate to the nearest 0.5 mL in the receiver at the corrected temperatures. If the volume of distillate recovered is critical, use receivers graduated in

TABLE 1 Corrected Fractionation Temperatures for Various Altitudes, °C

Elevation above Sea Level, m (ft)	Fractionation Temperatures for Various Altitudes, °C				
-305 (-1000)	192	227	363	318	362
-152 (-500)	191	226	261	317	361
0 (0)	190	225	260	316	360
152 (500)	189	224	259	315	359
305 (1000)	189	224	258	314	358
457 (1500)	188	223	258	313	357
610 (2000)	187	222	257	312	356
762 (2500)	186	221	256	312	355
914 (3000)	186	220	255	311	354
1067 (3500)	185	220	254	310	353
1219 (4000)	184	219	254	309	352
1372 (4500)	184	218	253	308	351
1524 (5000)	183	218	252	307	350
1676 (5500)	182	217	251	306	349
1829 (6000)	182	216	250	305	349
1981 (6500)	181	215	250	305	348
2134 (7000)	180	215	249	304	347
2286 (7500)	180	214	248	303	346
2438 (8000)	179	213	248	302	345

TABLE 2 Corrected Fractionation Temperatures for Various Altitudes, °F

Elevation above sea level, m (ft)	Fractionation Temperatures for Various Altitudes, °F				
-305 (-1000)	377	440	503	604	684
-152 (-500)	375	438	502	602	682
0 (0)	374	437	500	600	680
152 (500)	373	436	498	598	678
305 (1000)	371	434	497	597	676
457 (1500)	370	433	495	595	675
610 (2000)	369	431	494	593	673
762 (2500)	367	430	492	592	671
914 (3000)	366	429	491	590	669
1067 (3500)	365	427	490	588	667
1219 (4000)	364	426	488	587	666
1372 (4500)	363	425	487	585	665
1524 (5000)	361	423	485	584	663
1676 (5500)	360	422	484	582	661
1829 (6000)	359	421	483	581	660
1981 (6500)	358	420	481	580	658
2134 (7000)	357	418	480	578	656
2286 (7500)	356	417	479	577	655
2438 (8000)	355	416	478	575	653

TABLE 3 Factors for Calculating Temperature Corrections

Nominal Temperatures, °C (°F)	Correction ^A per 10 mm Difference in Pressure, °C (°F)
160 (320)	0.514 (0.925)
175 (347)	0.531 (0.957)
190 (374)	0.549 (0.989)
225 (437)	0.591 (1.063)
250 (482)	0.620 (1.116)
260 (500)	0.632 (1.138)
275 (527)	0.650 (1.170)
300 (572)	0.680 (1.223)
315.6 (600)	0.698 (1.257)
325 (617)	0.709 (1.277)
360 (680)	0.751 (1.351)

^A To be subtracted in case the barometric pressure is below 760 mm Hg; to be added in case barometric pressure is above 760 mm Hg.

0.1-mL divisions and immersed in a transparent bath maintained at 15.6 ± 3°C (60 ± 5°F).

NOTE 3—Some cut-back asphaltic products yield either no distillate or very little distillate over portions of the temperature range to 316°C

(600°F). In this case it becomes impractical to maintain the above distillation rates. For such cases the intent of the method shall be met if the rate of rise of temperature exceeds 5°C (9°F)/min.

8.3 When the temperature reaches the corrected temperature of 360°C (680°F), cut off the heat and remove the flask and thermometer. With the flask in a pouring position, remove the thermometer and immediately pour the contents into the residue container. The total time from cutting off the heat to starting the pour shall not exceed 15 s. When pouring, the side-arm should be substantially horizontal to prevent condensate in the side-arm from being returned to the residue.

NOTE 4—The formation of skin on the surface of a residue during cooling entraps vapors which will condense and cause higher penetration results when they are stirred back into the sample. If skin begins to form during cooling, it should be gently pushed aside. This can be done with a spatula with a minimum of disturbance to the sample.

8.4 Allow the condenser and any distillates trapped in the condenser neck to drain into the receiver and record the total volume of distillate collected as total distillate to 360°C (680°F).

8.5 When the residue has cooled until fuming just ceases, stir thoroughly and pour into the receptacles for testing for properties such as penetration, viscosity, or softening point. Proceed as required by the appropriate ASTM or IP method from the point that follows the pouring stage.

8.6 If desired, the distillate, or the combined distillates from several tests, may be submitted to a further distillation, in accordance with Test Method D 86 – IP 123, or, when the distillate is of coal-tar origin, Method C.O.3.

9. Calculation and Report

9.1 *Asphaltic Residue*—Calculate the percent residue to the nearest 0.1 as follows:

$$R = [(200 - TD)/200] \times 100 \quad (1)$$

where:

R = residue content, in volume percent, and

TD = total distillate recovered to 360°C (680°F), mL.

9.1.1 Report as the residue from distillation to 360 (680°F), percent volume by difference.

9.2 *Total Distillate*— Calculate the percent total distillate to the nearest 0.1 as follows:

$$TD \% = (TD/200) \times 100 \quad (2)$$

9.2.1 Report as the total distillate to 360°C (680°F), volume percent.

9.3 Distillate Fractions:

9.3.1 Determine the percentages by volume of the original sample by dividing the observed volume (in millilitres) of the fraction by 2. Report to the nearest 0.1 as volume percent as follows:

- Up to 190°C (374°F)
- Up to 225°C (437°F)
- Up to 260°C (500°F)
- Up to 316°C (600°F)

9.3.2 Determine the percentages by volume of total distillate by dividing the observed volume in millilitres of the fraction by the millilitres recovered to 360°C (680°F) and multiply by 100. Report to the nearest 0.1 as the distillate,

 **D 402**

volume percent of total distillate to 360°C (680°F) as follows:

Up to 190°C (374°F)

Up to 225°C (437°F)

Up to 260°C (500°F)

Up to 316°C (600°F)

9.4 Where penetration, viscosity, or other tests have been carried out, report with reference to this test method as well as to any other method used. *Example*—Penetration (ASTM D5 or IP 49) of residue from ASTM D402/IP 27.

10. Precision and Bias

10.1 The following criteria shall be used for judging the acceptability of results (95 % probability):

10.1.1 *Repeatability*— Duplicate values by the same operator shall not be considered suspect unless the determined

percentages differ by more than 1.0 volume % of the original sample.

10.1.2 *Reproducibility*— The values reported by each of two laboratories, shall not be considered suspect unless the reported percentages differ by more than the following:

Distillation Fractions, volume percent of the original sample:	
Up to 175°C (347°F)	3.5
Above 175°C (347°F)	2.0
Residue, Volume percentage by difference from the original sample	2.0

10.2 Criteria for judging variability of test results on the distillation residue have not been determined.

11. Keywords

11.1 cut-back asphalt; distillate; residue

The American Society for Testing and Materials takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).