



Designation: **D 5535 – 98 (Reapproved 2003)**

Standard Terminology Relating to Formed-in-Place Sealants for Joints and Cracks in Pavements¹

This standard is issued under the fixed designation D 5535; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This terminology ~~defines~~ covers terms related to joint and crack sealing in pavements. The terminology is useful for describing material types and pavement types and the application of sealants and fillers to pavements.

1.2 The values stated in SI units are to be regarded as the standard. The values given in parentheses are for information only.

2. Terminology

2.1 Terms and Their Definitions:

application temperature, *n*—the range of material temperature, as recommended by the manufacturer, that is to be used when installing sealant; for hot-applied sealants, the application temperature is any temperature between the minimum application temperature and safe heating temperature.

backer material, *n*—a compressible material that is placed in joints or cracks before applying sealant to prevent bonding of the sealant on the bottom of the joint, control sealant depth, and prevent sagging of the sealant.

bond breaker, *n*—a material installed in pavement cracks or joints that is intended to prevent adherence of the sealant to the bottom of the crack or joint.

chemically curing sealant, *n*—a sealant that cures primarily through chemical reaction.

hot-applied sealant, *n*—a compound that is applied in a molten state and cures primarily by cooling to ambient temperatures.

joint, *n*—a designed and constructed or saw~~ned~~ space or opening between adjoining pavement surfaces.

maximum heating temperature, *n*—the maximum temperature, as recommended by the manufacturer, to which a hot-applied sealant or filler for pavement cracks or joints can be heated while conforming to all specification requirements and result in appropriate application characteristics.

melter, *n*—a piece of equipment designed specifically to melt and heat hot-applied sealant and filler accurately and controllably.

melter-applicator, *n*—a piece of equipment designed specifically to melt, heat accurately and controllably, and apply hot-applied sealants and fillers to pavement cracks or joints uniformly.

minimum application temperature, *n*—the minimum temperature, as recommended by the manufacturer, to which a hot-applied sealant or filler for pavement cracks or joints must be heated while conforming to all specification requirements and result in appropriate application characteristics.

sealant, *n*—a material that has adhesive and cohesive properties to seal joints, cracks, or other narrow openings (generally less than ~~3-in. (76-mm)~~ 76-mm (3-in.) wide) in pavements against the entrance or passage of water or other debris.

3. Keywords

3.1 crack; joints; pavement; sealant

¹ This terminology is under the jurisdiction of ASTM Committee ~~D-4 D04~~ on Road and Paving Materials and is the direct responsibility of Subcommittee D04.33 on Formed-In-Place Sealants for Joints and Cracks in Pavements.

Current edition approved ~~February 10, 1998~~; Dec. 1, 2003. Published ~~February 1999~~; December 2003. Originally published as ~~D 5535-94~~; approved in 1994. Last previous edition approved in 1998 as D 5535-94 ϵ .

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

 **D 5535 – 98 (2003)**

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).