



Designation: D 693 – 98

Standard Specification for Crushed Aggregate for Macadam Pavements¹

This standard is issued under the fixed designation D 693; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

1. Scope

1.1 This specification covers crushed aggregate suitable for use in the construction of dry- or water-bound macadam base courses and bituminous penetration macadam base and surface courses of pavements.

1.2 The values stated in SI units are to be regarded as standard. The inch-pound units, shown in parentheses, are for information only.

2. Referenced Documents

2.1 ASTM Standards:

C 29/C29M Test Method for Unit Weight and Voids in Aggregate²

C 88 Test Method for Soundness of Aggregates by Use of Sodium Sulfate or Magnesium Sulfate²

C 131 Test Method for Resistance to Degradation of Small-Size Coarse Aggregate by Abrasion and Impact in the Los Angeles Machine²

C 136 Test Method for Sieve Analysis of Fine and Coarse Aggregates²

C 535 Test Method for Resistance to Degradation of Large-Size Coarse Aggregate by Abrasion and Impact in the Los Angeles Machine²

D 75 Practice for Sampling Aggregates³

D 448 Classification for Sizes of Aggregate for Road and Bridge Construction³

D 3665 Practice for Random Sampling of Construction Materials³

D 4318 Test Method for Liquid Limit, Plastic Limit, and Plasticity Index of Soils⁴

D 4791 Test Method for Flat Particles, Elongated Particles, or Flat and Elongated Particles in Coarse Aggregate³

3. Ordering Information

3.1 Orders for material under this specification shall include the following information:

3.1.1 Name of material (Crushed Aggregate for Macadam Construction),

3.1.2 ASTM designation (D 693 and year of issue),

3.1.3 Grading (Size Number) to be furnished (see 5.7 and Note 2),

3.1.4 Whether to be used in base course or surface course (see 5.1),

3.1.5 Whether for dry- or waterbound construction, or bituminous construction (see 5.4),

3.1.6 Quantity required, and

3.1.7 Special requirements.

4. General Characteristics

4.1 *Crushed Stone or Crushed Gravel*—The crushed stone or crushed gravel shall consist of reasonably clean, tough, durable fragments.

4.2 *Crushed Slag*—The crushed slag shall be air-cooled blast-furnace slag and shall consist of fragments reasonably clean, tough, durable, and consistent in density and quality.

4.3 *Choking Material for Dry- or Water-bound Macadam Base Courses*—The choking material shall consist of natural sand or the fine product resulting from crushing coarse aggregate.

5. Physical Requirements

5.1 *Degradation*—The aggregates (with the exception of Crushed Slag) shall conform to the following requirements:

	Base courses	Surface courses
Loss, Los Angeles Machine, max., %	50	40

5.2 *Bulk Density of Slag*—Air-cooled blast-furnace slag coarse aggregate, when tested in size No. 57 or No. 8, shall have a rodded bulk density not less than 1120 kg/m³ (70 lb/ft³).

5.3 *Crushed Pieces in Gravel*—Crushed gravel shall consist of particles with not less than 75 weight % of the portion retained on a 4.75-mm- (No. 4-) sieve having at least two fractured faces.

¹ This method is under the jurisdiction of ASTM Committee D-4 on Road and Paving Materials and is the direct responsibility of Subcommittee D04.50 on Aggregate Specifications.

Current edition approved Dec. 10, 1998. Published March 1999. Originally published as D693 – 42 T. Last previous edition D 693 – 84 (1993) ^{ϵ 1}.

² *Annual Book of ASTM Standards*, Vol 04.02.

³ *Annual Book of ASTM Standards*, Vol 04.03.

⁴ *Annual Book of ASTM Standards*, Vol 04.08.

NOTE 1—Some sources of gravel contain angular particles which will perform similarly to a mechanically crushed particle. Where laboratory tests or service records indicate this to be true, such angular particles may be considered as crushed.

5.4 *Soundness*—Coarse aggregate, for dry- or water-bound base courses, when subjected to five cycles of the soundness test, shall have a weighed loss of not more than 20 % when sodium sulfate is used or not more than 30 % when magnesium sulfate is used.

5.5 *Liquid Limit and Plasticity Index*—The fraction of the size No. 10 choking material (for dry- and water-bound courses) passing the 425 µm- (No. 40-) sieve shall have a liquid limit not greater than 30 and a plasticity index not greater than 6.

5.6 *Flat and Elongated Particles*—The portion retained on the 9.5-mm (3/8-in.) sieve shall not contain more than 15 %, by mass, of particles so flat and elongated that the ratio between the maximum (length) and the minimum (thickness) dimensions exceeds 5:1.

5.7 *Gradation*—The aggregate gradation shall be within the limits specified for the appropriate size in accordance with Specification D 448.

NOTE 2—See Appendix X1 for guidance in selecting aggregate sizes.

6. Methods of Sampling and Testing

6.1 Sample the aggregates and determine the properties in accordance with the following:

6.1.1 *Sampling*—Practice D 75.

6.1.2 *Degradation*—Test Method C 131 or Test Method C 535.

6.1.3 *Bulk Density*—Test Method C 29.

6.1.4 *Sieve Analysis*—Method C 136.

6.1.5 *Soundness*—Test Method C 88.

6.1.6 *Liquid Limit and Plasticity Index*—Test Method D 4318.

6.1.7 *Flat and Elongated Particles*—Test Method D 4791.

6.1.8 *Random Sampling*—Practice D 3665.

7. Inspection

7.1 Inspection of materials shall be agreed upon between the purchaser and the seller as part of the purchase contract.

7.2 This agreement shall provide clear definition of the size of a lot, place of sampling and the number of samples to be obtained to determine the acceptability of this lot.

8. Keywords

8.1 aggregate; choke aggregate; coarse aggregate; crushed aggregate; macadam

APPENDIX

(Nonmandatory Information)

X1. Guide for Selecting Aggregate Sizes

X1.1 Aggregate size numbers are selected from Specification D 448. An appropriate size should be selected for each use, depending on thickness of the base or the surface course, and on other local construction and service conditions.

X1.2 For dry- or water-bound macadam base course, the following combinations of size numbers are suggested:

Size No. of Coarse Aggregate	Size No. of Choke Aggregate
1, 2, or 3	10

X1.3 For penetration macadam courses, the size number of choke aggregate best suited for the work depends upon the size

of surface voids in the penetration course and on the fluidity of the bituminous binder. The following combinations of size numbers are suggested:

Size No. of Penetration Course Aggregate	Size No. of Choke Aggregate Viscous Binders	Fluid Binders
1	5, 56, or 57	67 or 68
2	5, 56, 57 or 6	67, 68 or 78
3	57, 6 or 7	68, 78 or 8

X1.4 The size of surface course aggregate depends upon the type of surface desired. The following sizes have been commonly used: 7, 78, 8 and 9.

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).