



## Standard Specification for Emulsified Asphalt<sup>1</sup>

This standard is issued under the fixed designation D 977; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

*This standard has been approved for use by agencies of the Department of Defense.*

### 1. Scope

1.1 This specification covers thirteen grades of emulsified asphalt for use in pavement construction in the manner designated.

### 2. Referenced Documents

#### 2.1 ASTM Standards:

D 140 Practice for Sampling Bituminous Materials<sup>2</sup>

D 244 Test Methods for Emulsified Asphalts<sup>2</sup>

### 3. Requirements

3.1 The emulsified asphalt shall be tested within 14 days of

delivery. The emulsified asphalt shall be homogeneous after thorough mixing provided separation has not been caused by freezing. Emulsified asphalts separated by freezing shall not be tested.

3.2 Emulsified asphalt shall conform to the requirements prescribed in Table 1.

### 4. Sampling

4.1 Samples of emulsified asphalt shall be taken in accordance with Practice D 140.

4.2 Samples shall be stored in clean, airtight sealed containers as specified in Practice D 140 at a temperature of not less than 4°C) until tested.

### 5. Test Methods

5.1 The properties of the emulsified asphalts given in Table 1 shall be determined in accordance with Test Methods D 244.

### 6. Keywords

6.1 anionic; emulsion; emulsified asphalt; high float; medium setting; rapid setting; slow setting

---

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee D-4 on Road and Paving Materials and is the direct responsibility of Subcommittee D04.41 on Emulsified Asphalt Specifications.

Current edition approved Dec. 10, 1998. Published March 1999. Originally published as D 977 – 48 T. Last previous edition D 977 – 97.

<sup>2</sup> *Annual Book of ASTM Standards*, Vol 04.03.

**TABLE 1 Requirements for Emulsified Asphalt**

NOTE 1—QS-1H emulsions shall meet the requirements outlined in D 3910 Standard Practices for Design, Testing and Construction of Slurry Seal.

NOTE 2—QS-1h is used for Quick Set Slurry Seal systems.

Type	Rapid-Setting						Medium-Setting						
	RS-1		RS-2		HFRS-2		MS-1		MS-2		MS-2h		
Grade	min	max	min	max	min	max	min	max	min	max	min	max	
<i>Tests on emulsions:</i>													
Viscosity, Saybolt Furol at 77°F (25°C), s	20	100	...	...	...	...	20	100	100	...	100	...	
Viscosity, Saybolt Furol at 122°F (50°C), s	...	...	75	400	75	400	...	...	...	...	...	...	
Storage stability test, 24-h, % <sup>A</sup>	...	1	...	1	...	1	...	1	...	1	...	1	
Demulsibility, 35 ml, 0.02 N CaCl <sub>2</sub> , %	60	...	60	...	60	...	...	...	...	...	...	...	
Coating ability and water resistance:													
Coating, dry aggregate	...	...	...	...	...	...	good	...	good	...	good	...	
Coating, after spraying	...	...	...	...	...	...	fair	...	fair	...	fair	...	
Coating, wet aggregate	...	...	...	...	...	...	fair	...	fair	...	fair	...	
Coating, after spraying	...	...	...	...	...	...	fair	...	fair	...	fair	...	
Cement mixing test, %	...	...	...	...	...	...	...	...	...	...	...	...	
Sieve test, % <sup>A</sup>	...	0.10	...	0.10	...	0.10	...	0.10	...	0.10	...	0.10	
Residue by distillation, %	55	...	63	...	63	...	55	...	65	...	65	...	
Oil distillate by volume of emulsion, %	...	...	...	...	...	...	...	...	...	...	...	...	
<i>Tests on residue from distillation test:</i>													
Penetration, 77°F (25°C), 100g, 5 s	100	200	100	200	100	200	100	200	100	200	40	90	
Ductility, 77°F, (25°C), 5 cm/min, cm	40	...	40	...	40	...	40	...	40	...	40	...	
Solubility in trichloroethylene, %	97.5	...	97.5	...	97.5	...	97.5	...	97.5	...	97.5	...	
Float test, 140°F (60°C), s	...	...	...	...	1200	...	...	...	...	...	...	...	

  

Type	Medium-Setting						Slow-Setting						Quick Setting		
	HFMS-1		HFMS-2		HFMS-2h		HFMS-2s		SS-1		SS-1h		QS-1H		
Grade	min	max	min	max	min	max	min	max	min	max	min	max	min	max	
<i>Tests on emulsions:</i>															
Viscosity, Saybolt Furol at 77°F (25°C), s	20	100	100	...	100	...	50	...	20	100	20	100	20	100	
Viscosity, Saybolt Furol at 122°F (50°C), s	...	...	...	...	...	...	...	...	...	...	...	...	...	...	
Storage stability test, 24-h, % <sup>A</sup>	...	1	...	1	...	1	...	1	...	1	...	1	...	1	
Demulsibility, 35 ml, 0.02 N CaCl <sub>2</sub> , %	...	...	...	...	...	...	...	...	...	...	...	...	...	...	
Coating ability and water resistance:															
Coating, dry aggregate	good	...	good	...	good	...	good	...	...	...	...	...	...	...	
Coating, after spraying	fair	...	fair	...	fair	...	fair	...	...	...	...	...	...	...	
Coating, wet aggregate	fair	...	fair	...	fair	...	fair	...	...	...	...	...	...	...	
Coating, after spraying	fair	...	fair	...	fair	...	fair	...	...	...	...	...	...	...	
Cement mixing test, %	...	...	...	...	...	...	...	...	...	2.0	...	2.0	...	N/A	
Sieve test, % <sup>A</sup>	...	0.10	...	0.10	...	0.10	...	0.10	...	0.10	...	0.10	...	0.10	
Residue by distillation, %	55	...	65	...	65	...	65	...	57	...	57	...	57	...	
Oil distillate by volume of emulsion, %	...	...	...	...	...	...	1	7	...	...	...	...	...	...	
<i>Tests on residue from distillation test:</i>															
Penetration, 77°F (25°C), 100 g, 5 s	100	200	100	200	40	90	200	...	100	200	40	90	40	90	
Ductility, 77°F, (25°C), 5 cm/min, cm	40	...	40	...	40	...	40	...	40	...	40	...	40	...	
Solubility in trichloroethylene, %	97.5	...	97.5	...	97.5	...	97.5	...	97.5	...	97.5	...	97.5	...	
Float test, 140°F (60°C), s	1200	...	1200	...	1200	...	1200	...	...	...	...	...	...	...	

<sup>A</sup>This test requirement on representative samples is waived if successful application of the material has been achieved in the field.

**NOTICE: This standard has either been superseded and replaced by a new version or discontinued. Contact ASTM International (www.astm.org) for the latest information.**

 **D 977**

*The American Society for Testing and Materials takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.*

*This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, 100 Barr Harbor Drive, West Conshohocken, PA 19428.*