



Designation: D 1327 – 97a

Standard Specification for Bitumen-Saturated Woven Burlap Fabrics Used in Roofing and Waterproofing¹

This standard is issued under the fixed designation D 1327; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

1. Scope

1.1 This specification covers woven burlap fabrics, saturated with either asphalt or refined coal-tar, as specified by the purchaser, for use in the membrane system of roofing or waterproofing or as specified by the manufacturer.

1.1.1 *Asphalt-saturated burlap fabric* shall be used with asphalt base plying cement; typical ones are mopping asphalts conforming to Specifications D 312, D 449, or appropriate solvent bearing bituminous materials.

1.1.2 *Coal-tar-saturated burlap fabric* shall be used with coal-tar base plying cements; typical ones are coal-tar pitches conforming to Specification D 450, or appropriate solvent bearing bituminous materials.

1.2 The values stated in inch-pound units are to be regarded as the standard. The values given in parentheses are for information only.

2. Referenced Documents

2.1 ASTM Standards:

D 146 Test Methods for Sampling and Testing Bitumen-Saturated Felts and Woven Fabrics for Roofing and Waterproofing²

D 312 Specification for Asphalt Used in Roofing²

D 449 Specification for Asphalt Used in Dampproofing and Waterproofing²

D 450 Specification for Coal-Tar Pitch Used in Roofing, Dampproofing, and Waterproofing²

D 1079 Terminology Relating to Roofing, Waterproofing, and Bituminous Materials²

2.2 AATCC Standard:

Method 30-1974 Test for Resistance of Textiles to Mildew and Rot³

3. Terminology

3.1 *Definitions*—For definitions of terms used in this specification, refer to Terminology D 1079.

4. Materials and Manufacture

4.1 The fabric to be saturated shall be composed of 100 % jute fiber except for two cotton threads in each selvage. If the selvage is used, it shall be no more than 1/4 in. (6 mm) wide. The minimum fabric construction used shall be 5.4 oz/yd² (180 g/m²) minimum burlap.

4.2 In the process of manufacture, the dry burlap fabric shall be saturated with bitumen.

5. Physical Properties

5.1 The material shall conform to the physical properties prescribed in Table 1.

5.2 The rolls shall not crack nor be so sticky as to cause tearing or material damage upon being unrolled at temperatures between 50 and 140°F (10 and 60°C).

5.3 *Resistance to Rotting*—The average percentage of the original strength retained by the saturated product shall be at least 1.75 times that retained by the control sample after 1 week.

6. Workmanship, Finish, and Appearance

6.1 The burlap fabric shall be thoroughly and uniformly saturated in such a manner that every fiber shall be visibly stained through by the saturant.

6.2 The meshes of the fabric shall not be completely closed or sealed by the process of saturation. There shall be sufficient porosity maintained to allow successive moppings of the plying cement to seep through.

¹ This specification is under the jurisdiction of ASTM Committee D-8 on Roofing, Waterproofing, and Bituminous Materials and is the direct responsibility of Subcommittee D08.04 on Felts and Fabrics for Bituminous Roofing and Waterproofing.

Current edition approved July 10, 1997. Published January 1998. Originally published as D 1327 – 54 T. Last previous edition D 1327 – 97.

² *Annual Book of ASTM Standards*, Vol 04.04.

³ Available from American Association of Textile Chemists and Colorists, P.O. Box 12215, Research Triangle Park, NC 27709.



TABLE 1 Physical Properties of Bitumen-Saturated Woven Burlap Fabric

	Min	Max
Gross mass per roll, lb (kg)	34.8 (15.8)	60.0 (27.2)
Mass of wrapping material and mandrel, lb(kg)	...	2.5 (1.13)
Width of roll, in. (mm)	35 (890)	41 (1040)
Width of selvage, in. (mm)	...	0.25 (6.5)
Average net mass per unit area, oz/yd ² (g/m ²)	9.8 (330)	...
Detached comminuted surfacing, lb/100 ft ² (g/m ²)	...	1.0 (50)
Moisture max, mass %	...	6.0 ^A
Average breaking strength at 70°F (21.1°C):		
Lengthwise (warp direction), lbf/in. (N)	50 (220)	...
Crosswise (fill direction), lbf/in. (N)	50 (220)	...
Pliability at 32°F (0°C)	no cracking	...
Mass of desaturated (unsaturated) fabric, oz/yd ² (g/m ²) ^B	5.3 (180) ^C	...
Mass of saturant, lb/100 ft ² (g/m ²) ^B	0.7 × (mass of desaturated moisture-free fabric in same area)	...
Thread count per in. (cm), both directions ^D	9 (3.5)	...
Ash, % ^D	...	2.0

^A At time of manufacture. Products with higher moisture content at time of installation may cause hot materials to foam, creating interply voids that may result in blisters.

^B In the case of coal-tar-saturated fabric, this value shall be the moisture-free fabric prior to saturation. Coal-tar-saturated fabric cannot be thoroughly desaturated by any known means; only an approximate value may be obtained through desaturation.

^C Nominal 7½-oz burlap weighs approximately 6¾ oz/yd² (230 g/m²). The minimum requirement allows for a 5 % tolerance in mass on the low side, and also assumes a max 7 % oil content and 12 % moisture regain, both of which are extracted in the desaturating process.

^D On desaturated fabrics in the case of coal-tar-saturated fabric, this property shall be determined on the fabric prior to saturation.

6.3 The surface of the fabric shall not be coated or covered with talc or any other substances that would tend to interfere with the adhesion between the fabric and the plying cement.

6.4 The surface shall be uniformly smooth and free of irregularities, folds, and knots.

6.5 The finished material shall be free of visible external defects, such as ragged or untrue edges, breaks, rents, or cracks.

7. Sampling and Test Methods

7.1 Sample the material and determine the properties enumerated in this specification in accordance with Test Methods D 146.

7.2 Determine resistance to rotting by the soil burial method described in Test 1 of AATCC Test Method 30-1974, modified as follows:

7.2.1 The control sample shall consist of at least five specimens of 7-oz/1 yd² (2389/m²) untreated Osnaburg containing not more than 8 % sizing.

7.2.2 Place each control specimen in the soil between two specimens of the warp and two specimens of the filling of the saturated fabric, all parallel to each other and approximately 1 in. (25 mm) apart. Remove all specimens for testing after 1 week.

7.2.3 The soil shall be sufficiently active to decrease the strength of the Osnaburg at the end of the week to 25 % or less of its original strength; if not, repeat the exposure with fresh soil and fresh specimens.

8. Inspection

8.1 *Inspection*—Inspection shall be in accordance with the requirements of this specification.

8.2 *Inspection Alternatives*—Alternative inspection requirements shall be determined by and as agreed upon between the purchaser and the supplier.

9. Rejection and Resubmittal

9.1 *Failure to Conform*—Failure to conform to any of the requirements as stated in this specification constitutes grounds for rejection.

9.2 *Rejection Redress*—The supplier shall have the right to inspect the rejected materials. The supplier and the purchaser shall agree to the quantity of rolls deemed unacceptable. The supplier shall then have the right to submit the same number of new rolls as replacement.

10. Packaging and Package Marking

10.1 Unless otherwise agreed upon between the supplier and purchaser, each product package shall be plainly marked with the supplier's name, the product brand, the ASTM designation, and type of bitumen if not evident in the label name of the product.

10.2 The rolls shall be securely wrapped or banded in a manner that completely encircles the roll and will prevent slipping or unrolling.

10.3 The rolls of saturated burlap fabric shall be wound on mandrels or rigid hollow fiber cylinders not less than 2 in. (50 mm) in diameter, extending not more than 4 in. (100 mm) beyond the ends of the rolls.

10.4 No roll shall contain more than two pieces, and no more than 3 % of the rolls in any lot shall contain two pieces. If a roll contains a manufacturing splice, the splice shall be clearly marked.

11. Keywords

11.1 asphalt or coal tar saturated; roofing; waterproofing; woven burlap fabric

**NOTICE: This standard has either been superseded and replaced by a new version or discontinued.
Contact ASTM International (www.astm.org) for the latest information.**



The American Society for Testing and Materials takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, 100 Barr Harbor Drive, West Conshohocken, PA 19428.

This standard is copyrighted by ASTM, 100 Barr Harbor Drive, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (<http://www.astm.org>).