



Designation: D 2824 – 02

Standard Specification for Aluminum-Pigmented Asphalt Roof Coatings, Nonfibered, Asbestos Fibered, and Fibered without Asbestos¹

This standard is issued under the fixed designation D 2824; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

1. Scope

1.1 This specification covers asphalt-based, aluminum roof coatings suitable for application to roofing or masonry surfaces by brush or spray.

1.2 The values stated in SI units are to be regarded as the standard. The values in parentheses are for information only.

1.3 The following precautionary caveat pertains only to the test method portion, Section 8, of this specification: *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:

D 962 Specification for Aluminum Powder and Paste Pigments for Paints²

D 6511 Test Methods for Solvent Bearing Bituminous Compounds³

3. Classification

3.1 *Type I*—Nonfibered, containing no fiber.

3.2 *Type II*—Fibered, containing asbestos fiber.

3.3 *Type III*—Fibered, containing no asbestos fiber.

4. Materials and Manufacture

4.1 Asphalt-based, aluminum roof coatings shall consist of an asphalt base, volatile petroleum solvents, and a leafing type of aluminum pigment conforming to the requirements of Specification D 962, with or without fiber added. They shall be

mixed to a smooth, uniform consistency suitable for application by brush, roller, or by spraying.

5. Composition

5.1 Asphalt-based, aluminum roof coatings complying with this specification shall conform to the following composition limits:

	Type I	Type II or Type III
Water, max, %	0.3	0.3
Nonvolatile matter (NVM), min, %	40	40
Insoluble in CS ₂ , max, % of NVM	40	50
Metallic aluminum, min, %	11	9

6. Physical Requirements

6.1 *Uniformity*—After a thoroughly stirred sample has stood for 72 h at room temperature $23 \pm 2^\circ\text{C}$ ($73.4 \pm ^\circ\text{F}$) in a closed container, it shall show no separation of solvent or settling that can not be overcome by moderate stirring.

6.2 *Consistency*—The roof coating shall be of a consistency that will spread readily and permit application by brush, roller, or spray to produce a film in which the aluminum pigment leafs to form a bright reflective surface on prepared roofing, saturated felt, and metal surfaces at ambient temperatures above 10°C (50°F).

6.2.1 *Type I*—Consistency at 25°C (77°F) shall be between 20 and 30 Stormer s/100 revolutions of the paddle-type rotor with a 100-g load in addition to the standardizing load.

6.2.2 *Type II and Type III*—Consistency at 25°C (77°F) shall be between 15 and 90 Stormer s/100 revolutions of the propeller-type rotor with a 300-g load in addition to the standardizing load.

6.3 *Reflectance*—The percent luminous reflectance of coatings, determined on samples before and after high temperature shelf aging, shall be not less than 50 %.

7. Sampling

7.1 See Section 4 of Test Methods D 6511.

¹ This specification is under the jurisdiction of ASTM Committee D08 on Roofing, Waterproofing, and Bituminous Materials and is the direct responsibility of Subcommittee D08.05 on Solvent-Bearing Bituminous Compounds for Roofing and Waterproofing.

Current edition approved Jan. 10, 2002. Published March 2002. Originally published as D 2824 – 69. Last previous edition D 2824 – 94.

² *Annual Book of ASTM Standards*, Vol 06.03.

³ *Annual Book of ASTM Standards*, Vol 04.04.



D 2824

8. Test Methods

Determine composition and physical requirements by using the procedures in Test Methods D 6511.

9. Inspection

9.1 Inspection of the material shall be as agreed upon between the purchaser and the seller as part of the purchase contract.

10. Rejection and Resubmittal

10.1 Failure to conform to any of the requirements prescribed in this specification may constitute grounds for rejection. In the case of rejection, the seller shall have the right to

reinspect the rejected material and resubmit the lot after removal of those packages not conforming to the requirements.

11. Packaging and Package Marking

11.1 All products shall be packaged and labeled in accordance with applicable regulations. Each package shall be marked to indicate the applicable ASTM International specification. Packages containing product meeting Type II shall bear a statement that the product contains asbestos.

12. Keywords

12.1 aluminum-pigmented; asbestos-fiber; asphalt; fibered without asbestos; nonfibered

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).