



Standard Practice for Evaluating the Effects of Heat on Asphalts¹

This standard is issued under the fixed designation D 3791; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This practice covers a procedure for evaluating some of the effects on asphalts of heating in the presence of little or no air.

1.2 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:²

- D 5 Test Method for Penetration of Bituminous Materials
- D 36 Test Method for Softening Point of Bitumen (Ring-and-Ball Apparatus)
- D 140 Practice for Sampling Bituminous Materials
- D 1079 Terminology Relating to Roofing, Waterproofing, and Bituminous Materials
- D 2170 Test Method for Kinematic Viscosity of Asphalts (Bitumens)
- D 2171 Test Method for Viscosity of Asphalts by Vacuum Capillary Viscometer
- D 4402 Test Method for Viscosity Determinations of Asphalts at Elevated Temperatures Using a Rotational Viscometer
- E 1 Specification for ASTM Thermometers
- E 145 Specification for Gravity-Convection and Forced-Ventilation Ovens

3. Terminology

3.1 *Definitions*—Definitions of terms used in this practice can be found in Terminology D 1079.

¹ This practice is under the jurisdiction of ASTM Committee D08 on Roofing and Waterproofing and is the direct responsibility of Subcommittee D08.03 on Surfacing and Bituminous Materials for Membrane Waterproofing and Built-Up Roofing.

Current edition approved Jan. 1, 2004. Published January 2004. Originally approved in 1979. Last previous edition approved in 1996 as D 3791 – 96.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

4. Summary of Practice

4.1 A sample of asphalt in a loosely covered container is heated to a temperature chosen by the investigator for a period of $5\text{ h} \pm 10\text{ min}$. Certain characteristics of the asphalt after heat exposure at the test temperature chosen are then compared with those characteristics before exposure.

NOTE 1—A set temperature is required when this practice is used as part of a specification. Historically, a temperature of 204°C (400°F) has been used.

5. Significance and Use

5.1 When asphalts are maintained at elevated temperatures in the presence of air, their characteristics may change. Certain blown asphalts also soften when maintained near, and particularly above, their final blowing temperatures under virtually air-free conditions. This may happen if the asphalt is overheated for application purposes. This practice provides a uniform heat-treatment procedure and methods for evaluating the effect of this treatment on some of the characteristics of asphalts. Changes observed when asphalts are overheated are not indicative of changes to be expected when asphalts are heated to normal application temperatures.

6. Apparatus

6.1 *Oven*—A forced-ventilation oven conforming to the requirements for Type IIA as prescribed in Specification E 145, capable of maintaining temperatures up to 300°C (572°F), and with a chamber at least 300 by 300 by 300 mm (12 by 12 by 12 in.).

6.2 *Thermometer*—ASTM Low-Distillation Thermometer, having a range from -1 to $+300^{\circ}\text{C}$ (30 to 580°F) and conforming to the requirements for Thermometers 7C or 7F as prescribed in Specification E 1.

6.3 *Containers*, triple-seal, friction-top, 1-L (1-qt) and 0.5-L (1-pt) cans with lids, free of any interior resinous or lacquer coatings.³

6.4 *Laboratory Timer*.

6.5 *Hot Plate*.

³ “Triple-Tite” cans, available from Continental Can Co., 633 3rd Ave., New York, NY, or equivalent, have been found suitable.

7. Sampling

7.1 Sample the asphalt in accordance with Practice D 140.

8. Test Specimen and Sample

8.1 Heat a minimum of 1 L (1 qt) of the asphalt on the hot plate. Stir occasionally to prevent local overheating. Keep covered whenever possible to minimize volatiles loss. Heat the material until sufficiently fluid to pour, but in no case more than 93°C (200°F) above the softening point of the asphalt.

8.2 When molten, pour the asphalt into a 0.5-L (1-pt) container to within 25 ± 2 mm (1.0 ± 0.1 in.) of the top, and also pour test specimens for determination of the characteristics of the original material in accordance with the methods listed in Section 10. Test these specimens within the time limits specified by the respective test procedures.

NOTE 2—Pour a small amount of the asphalt in the groove around the top of the can, sufficient to act as a seal when the lid is placed loosely in position.

8.3 Cover the container loosely with a lid and set aside to cool. Subject the sample to heat treatment within 18 to 24 h after pouring.

9. Procedure

9.1 Preheat the test oven to the selected temperature. Place the container on a shelf in the oven so as to permit air circulation around it.

9.2 Start the laboratory timer when the container has been placed in the oven and the door closed. Continue the heating for 5 h.

9.3 Remove the container from the oven after 5 h. Remove the lid; if a skin is present, remove it carefully before allowing the asphalt to cool. Stir the molten asphalt gently.

9.4 Cool the sample to approximately the original pouring temperature. Gently stir the sample to avoid air entrapment. Then, proceed to pour the test specimens.

10. Test Methods

10.1 Characteristics of asphalt before and after heat exposure may be evaluated in duplicate by any desired procedures, but the following methods are recommended:

10.1.1 *Softening Point*—Test Method D 36.

10.1.2 *Penetration*—Test Method D 5.

10.1.3 *Viscosity*—Test Method D 2170 or D 2171 or D 4402.

11. Report

11.1 Report the heat-exposure temperature used.

11.2 Report the presence or absence of a skin on the heat-exposed sample.

11.3 Report the tests used to evaluate the sample before and after heat exposure and the individual test result from each procedure.

12. Keywords

12.1 asphalts; heat exposure; overheated; physical property changes

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).