Standard Specification for Asphalt Roof Coatings – Asbestos-Free¹

This standard is issued under the fixed designation D 4479; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

1. Scope

- 1.1 This specification covers as bestos-free asphalt roof coatings of brushing or spraying consistency.
- 1.2 The following precautionary caveat pertains only to the test method portion, Section 8, of this specification: This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.

2. Referenced Documents

- 2.1 ASTM Standards:
- D 312 Specification for Asphalt Used in Roofing²
- D 449 Specification for Asphalt Used in Dampproofing and Waterproofing²
- D 946 Specification for Penetration-Graded Asphalt Cement for Use in Pavement Construction³
- D 6511 Test Methods for Solvents Bearing Bituminous Compounds²

3. Classification

- 3.1 *Type I* is made from asphalts characterized as self-healing, adhesive, and ductile, and conforming to the requirements of Specification D 312, Type I; Specification D 449, Types I or II; or Specification D 946.
- 3.2 *Type II* is made from asphalts characterized by high softening point and relatively low ductility, and conforming to the requirements of Specification D 312 Types II or III; or Specification D 449, Type III.

4. Materials and Manufacture

4.1 Asphalt roof coatings shall consist of an asphalt base, volatile petroleum solvents, and mineral or other stabilizers, or both, excluding asbestos fiber, mixed to a smooth, uniform

¹ This specification is under the jurisdiction of ASTM Committee D08 on Roofing, Waterproofing, and Bituminous Materials and is the direct responsibility of Subcommittee D08.05 on Solvent-Bearing Bituminous Compounds for Roofing and Waterproofing.

Current edition approved July 10, 2000. Published September 2000. Originally published as D 4479-85. Last previous edition D 4479-93.

consistency suitable for application by squeegee, three-knot brush, paint brush, roller, or by spraying.

5. Composition

5.1 Asphalt roof coatings complying with this specification shall conform to the following composition limits:

	min	max
Moisture, %		2.5
Nonvolatile matter, %	50	
Mineral or other stabilizer, or both,	5	20
Stabilizers, %		
Asphalt, %	40	

6. Physical Requirements

- 6.1 *Uniformity*—After a thoroughly stirred sample has stood for 72 h at room temperature $23 \pm 2^{\circ}\text{C}$ (73.4 \pm 3.6°F) in a closed container, it shall show no separation of solvent or settling that cannot be overcome by moderate stirring.
- 6.2 *Consistency* The roof coating shall be of a consistency that will spread readily and permit application by squeegee, brush, roller or spray at the rate of 1.25 m ²/litre (50 ft²/gal) on prepared roofing, saturated felt, and metal surfaces at ambient temperatures above 10°C (50°F). Consistency at 25°C (77°F) shall be between 50 and 400 Stormer s/100 revolutions.
- 6.3 Behavior at $60^{\circ}C$ ($140^{\circ}F$)—The roof coating shall show no evidence of blistering, and sag or slide shall be no greater than 6 mm ($\frac{1}{4}$ in.). Staining or absorption of the coating on the reverse side of the prepared roofing test panel shall not exceed 5 % of the coated area.
- 6.4 Pliability at $0^{\circ}C$ (32°F)—There shall be no cracking or separation of the roof coating from the metal.

7. Sampling

7.1 See Section 4 of Test Methods D 6511.

8. Test Methods

8.1 Determine composition and physical requirements by using the procedures in Test Methods D 6511.

9. Precision and Bias

9.1 See Section 21 of Test Methods D 6511.

10. Inspection

10.1 Inspection of the material shall be agreed upon by the

² Annual Book of ASTM Standards, Vol 04.04.

³ Annual Book of ASTM Standards, Vol 04.03.



purchaser and the seller as part of the purchase contract.

11. Rejection and Rehearing

11.1 Failure to conform to any of the requirements prescribed in this specification shall constitute grounds for rejection. In cases of rejection, the seller shall have the right to reinspect and resubmit the lot after removal of those packages not conforming to the specified requirements.

12. Packaging and Package Marking

12.1 All products shall be packaged and labeled in accordance with applicable regulations. Each package shall be marked to indicate the applicable ASTM specification, unless otherwise agreed upon between the supplier and purchaser.

13. Keywords

13.1 asbestos-free; asphalt; fibered; roof coating

The American Society for Testing and Materials takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).