



Designation: D 452 – 91 (Reapproved 1997)<sup>ε1</sup>

AMERICAN SOCIETY FOR TESTING AND MATERIALS  
100 Barr Harbor Dr., West Conshohocken, PA 19428  
Reprinted from the Annual Book of ASTM Standards. Copyright ASTM

## Standard Test Method for Sieve Analysis of Surfacing for Asphalt Roofing Products<sup>1</sup>

This standard is issued under the fixed designation D 452; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

<sup>ε1</sup> NOTE—Editorial updates were made throughout in January 1997.

### 1. Scope

1.1 This test method covers the determination of the particle size distribution of surfacing material, other than mineral granules, such as sand, mica, talc, or other powdered or flaky mineral particles, used on both sides of “smooth” roll roofing and on the reverse side of asphalt shingles and mineral-surfaced roll roofing.

1.2 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

### 2. Referenced Documents

#### 2.1 ASTM Standards:

E 11 Specification for Wire-Cloth Sieves for Testing Purposes<sup>2</sup>

### 3. Summary of Test Method

3.1 A weighed sample of surfacing material is separated through a series of sieves of progressively smaller openings for the determination with particle size distribution.

### 4. Significance and Use

4.1 This test method is used to determine the grading of materials used as surfacing. The results are used to determine compliance of the particle size distribution with applicable specification requirements.

### 5. Apparatus

5.1 *Sieves*—A set of the sieves listed in Table 1, conforming to Specification E 11. For routine testing, the group of sieves actually used shall include only those appropriate for the material being graded. Coarser or finer sieves, on which less than 0.05 mass % of the specimen would be found after sieving, need not be included in the group.

NOTE 1—For relatively coarse or flaky materials, such as coarse mica,

<sup>1</sup> This test method is under the jurisdiction of ASTM Committee D-8 on Roofing, Waterproofing, and Bituminous Materials and is the direct responsibility of Subcommittee D08.02 on Prepared Roofings, Shingles, and Siding Materials.

Current edition approved Nov. 15, 1991. Published January 1992. Originally published as D 452 – 37 T. Last previous edition D 452 – 85.

<sup>2</sup> *Annual Book of ASTM Standards*, Vol 14.02.

TABLE 1 Report Form

Retained on Sieve		Passing Sieve		Percent
1.70-mm	(No. 12)	...	...	...
1.18-mm	(No. 16)	1.70-mm	(No. 12) <sup>A</sup>	...
850-μm	(No. 20)	1.18-mm	(No. 16)	...
600-μm	(No. 30)	850-μm	(No. 20)	...
425-μm	(No. 40)	600-μm	(No. 30)	...
300-μm	(No. 50)	425-μm	(No. 40)	...
212-μm	(No. 70)	300-μm	(No. 50)	...
150-μm	(No. 100)	212-μm	(No. 70)	...
75-μm	(No. 200)	150-μm	(No. 100)	...
		75-μm	(No. 200)	...
Total				...

<sup>A</sup>Designates U.S. Standard Sieve.

sieves from 1.18-mm to 212-μm (Nos. 16 to 70) inclusive, will usually be found suitable. For finer surfacing materials, such as fine mica or talc flour, sieves from 600 to 75-μm (Nos. 30 to 200) inclusive, will usually give a satisfactory sieve analysis.

5.2 *Sieve Shaker*—A mechanically operated sieve shaker, which produces a uniform rotary motion and tapping action with 140 to 160 taps per minute. The sieve shaker shall be fitted with a hard maple plug to receive the impact of the tapping device. The entire apparatus shall be rigidly mounted by bolting to a solid foundation, preferably concrete.

5.3 *Sampling Splitter*—A riffle sampler with 9.5 or 12.7-mm (3/8 or 1/2-in.) divisions, for reducing the sample to the specimen required for sieve analysis.

5.4 *Oven*, capable of maintaining 105°C (221°F).

5.5 *Balance*—A laboratory balance sensitive to 0.1 g.

### 6. Sampling

6.1 Each shipment of surfacing of a single type shall be considered a unit for sampling. If a shipment contains more than one type, the entire quantity of each type in the vehicle shall be considered a unit for sampling.

6.2 Take the sample of surfacing shipped in bulk from the chute or conveyor while the vehicle is being loaded or unloaded. The ideal place is just where the material drops from the chute or belt. Collect equal portions from the full width and thickness of the stream at regular intervals, with such frequency that a minimum of five samples will be taken and the total mass of the sample will be not less than 7.3 kg (16 lb). Do not allow the sampling receptacle to overflow under any

circumstances. Overflow would tend to reject a higher proportion of the large particles than the small ones, and a representative sample would not be obtained. The sample should not include the initial material discharged from the chute or conveyor.

6.3 Take the sample from a shipment of surfacing shipped in bags, selected at random and equal in number to the cube root of the total number of bags in the vehicle. Collect equal portions of not less than 0.23 kg (0.5 lb) from each of the bags taken from sampling and combine.

## 7. Test Specimen

7.1 Reduce the sample by riffing to a specimen of 100 to 112 g. Use the entire specimen obtained from reduction of the sample for the sieve analysis.

## 8. Procedure

8.1 Assemble the group of sieves selected from Table 1 in order, with the sieve having the largest opening at the top and the one having the smallest opening at the bottom. Add a solid collecting pan below the bottom sieve. Dry the test specimen in an oven at about 105°C (221°F) for 2 h. Remove from the oven, cool in a desiccator, and then weigh to within  $\pm 0.1$  g. Place the specimen in the topmost sieve and complete the assembly by placing a solid cover over the top sieve. Securely fasten the sieve assembly in the mechanical sieve-shaking device (see 5.2).

8.2 Pass the specimen through the assembled group of sieves by subjecting it to the action of the sieve shaker for a period of  $20 \pm 1$  min. At the end of this period, remove the solid collecting pan containing the portion of the material passing the finest sieve and weigh the contents to within  $\pm 0.1$  g. Then reassemble the collecting pan with the sieves and

continue shaking for an additional 10 min. At the end of this period remove the collecting pan and weigh the contents again. If the additional material passing the finest sieve during this second shaking period does not exceed 0.5 mass % of the specimen, consider the sieving complete. If it does exceed 0.5 %, reassemble the collecting pan and sieves and shake for successive additional 10-min periods, weighing the material collected in the pan after each period of shaking, until the amount passing the finest sieve in a 10-min shaking period is less than 0.5 mass % of the specimen.

8.3 Carefully remove the portion of the specimen retained on each of the sieves and on the pan, and weigh each portion to within  $\pm 0.1$  g.

## 9. Report

9.1 Report the results of the sieve analysis to the nearest 0.1 % (omitting the results for those sieves on which less than 0.05 mass % of the test specimen was collected), as illustrated in Table 1.

9.2 The sum of the percentages reported shall be  $100 \pm 1.5$  %.

## 10. Precision and Bias

10.1 A retest made after recombining a freshly screened sample by the same operator using the same sieves should give results within  $\pm 1$  percentage point of the results previously obtained on each sieve. For example, if 25.0 % was retained originally on the 212- $\mu\text{m}$  (No. 70) sieve, a retest should give between 24.0 and 26.0 %.

## 11. Keywords

11.1 asphalt roofing; mineral; sieve; surfacing

*The American Society for Testing and Materials takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.*

*This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, 100 Barr Harbor Drive, West Conshohocken, PA 19428.*