



Designation: C 1195 – 91 (Reapproved 1995)

AMERICAN SOCIETY FOR TESTING AND MATERIALS
100 Barr Harbor Dr., West Conshohocken, PA 19428
Reprinted from the Annual Book of ASTM Standards. Copyright ASTM

Standard Test Method for Absorption of Architectural Cast Stone¹

This standard is issued under the fixed designation C 1195; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method covers the sampling, preparation of specimens, and determination of the absorption of architectural cast stone.

1.2 This test method describes two procedures: (1) cold water and (2) boiling water. The user of the test method should stipulate which is desired. If no stipulation is made, the cold water procedure will be used.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

1.4 The values stated in inch-pound units are to be regarded as the standard. The values given in parentheses are for information only.

2. Referenced Documents

2.1 ASTM Standards:

C 642 Test Method for Specific Gravity, Absorption, and Voids in Hardened Concrete²

3. Terminology

3.1 Definition:

3.1.1 *cast stone*—an architectural precast concrete building unit intended to simulate natural cut stone.

4. Significance and Use

4.1 This test method is to be used in determining the absorption of cast stone. Absorption is one measure of porosity of cast stone and, hence, its resistance to weathering and structural stress.

5. Sampling

5.1 Select the sample to represent the cast stone under consideration. The sample may be randomly selected by the purchaser or his authorized representative from each 500 ft³ (14 m³) of cast stone. Select a sample of adequate size to permit the preparation of three absorption test specimens.

6. Test Specimens

6.1 For absorption tests take three specimens from the sample. Select specimens from any portion of the sample, except that for faced cast stone, cut the specimens through the faced surface to consist of approximately equal parts of the facing mixture and the backup material.

6.2 Cut specimens from the sample with saws. The test specimens shall be 2-in. (50.8-mm) or 50-mm cubes. The allowable size tolerance of the cubes shall be $\pm 1/16$ in. (3.2 mm).

7. Conditioning

7.1 For this test, oven dry specimens at a temperature of 100 to 110°C (212 to 230°F) until the loss in mass is not more than 0.1 % in 24 h of drying. Remove specimens from the oven and allow to cool in room temperature for approximately 30 min before testing for absorption.

8. Procedure

8.1 Weigh the specimens immediately after conditioning and determine the mass to the nearest 0.02 g.

8.2 *Method A, Cold Water Test*—Immerse the specimens completely in filtered or distilled water at $23 \pm 1.7^\circ\text{C}$ ($73.4 \pm 3^\circ\text{F}$) for 48 h. At the end of this period, remove them from the water bath one at a time, surface dry with a damp cloth, and determine the mass to the nearest 0.02 g.

8.3 *Method B, Boiling Water Test*—Immerse the specimens completely in cold filtered or distilled water for 48 h and then immerse in boiling water at $100 \pm 5^\circ\text{C}$ ($212 \pm 9^\circ\text{F}$) for 5 h. Allow the specimens to cool to a final temperature of 20 to 25°C (68 to 77°F), surface dry, and weigh to the nearest 0.02 g.

9. Calculations

9.1 Calculate the absorption of each specimen as follows:

$$\text{absorption, mass \%} = [(B - A)/A] \times 100$$

where:

A = mass of the dried specimen, and

B = mass of the specimen after immersion.

9.2 The absorption is the average absorption of the three specimens.

10. Report

10.1 Report the following information:


10.1.1 Identification of the sample,

10.1.2 Mixture proportions,

¹ This test method is under the jurisdiction of ASTM Committee C-27 on Precast Concrete Products and is the direct responsibility of Subcommittee C27.20 on Architectural and Structural Products.

Current edition approved Aug. 15, 1991. Published October 1991.

² *Annual Book of ASTM Standards*, Vol 04.02.



- 10.1.3 Test method,
- 10.1.4 Absorption value,
- 10.1.5 Name of the project,
- 10.1.6 Date of casting, and
- 10.1.7 Age of sample when test begins.

Method C 642 for which data are not yet available. The precision of this test method will be stated when data become available.

11.2 *Bias*—Since there is no accepted reference material suitable for determining the bias of results of this test method, no statement on bias is being made.

11. Precision and Bias

11.1 *Precision*—The precision of this test is similar to Test

The American Society for Testing and Materials takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, 100 Barr Harbor Drive, West Conshohocken, PA 19428.