



Designation: C 1325 – 99

Standard Specification for Non-Asbestos Fiber-Mat Reinforced Cement Interior Substrate Sheets¹

This standard is issued under the fixed designation C 1325; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification covers *non-asbestos fiber-mat reinforced* cement substrate sheets manufactured to be dimensionally stable and suitable as either an unfinished substrate (see Note 1) or as a substrate for decoration such as natural stone or tile in internal wet and dry areas.

NOTE 1—When used as an unfinished substrate, consult the manufacturer's written installation literature for proper application details.

1.2 This specification is not applicable to asbestos-cement flat sheets (Specification C 220); non-asbestos fiber cement flat sheets for exterior applications such as claddings, facades, curtain walls, and soffits (Specification C 1186); gypsum backing board and coreboard (Specification C 442); water-resistant gypsum backing board (Specification C 630); glass mat gypsum backing board (Specification C 1178); particle boards (Definitions D 1554); and discrete non-asbestos fiber cement interior substrate sheets (Specification C 1288).

1.3 The values stated in inch-pound units are to be regarded as the standard. The values given in parentheses are provided for information only.

2. Referenced Documents

2.1 ASTM Standards:

- C 220 Specification for Flat Asbestos-Cement Sheets²
- C 442 Specification for Gypsum Backing Board and Coreboard³
- C 473 Test Methods for Physical Testing of Gypsum Panel Products³
- C 630 Specification for Water-Resistant Gypsum Backing Board³
- C 666 Test Method for Resistance of Concrete to Rapid Freezing and Thawing⁴
- C 947 Test Method for Flexural Properties of Thin-Section Glass-Fiber-Reinforced Concrete (Using Simple Beam

with Third-Point Loading)²

- C 1154 Terminology for Non-Asbestos Fiber-Reinforced Cement Products²
- C 1178 Specification for Glass Mat Water-Resistant Gypsum Backing Panel³
- C 1186 Specification for Flat Non-Asbestos Fiber-Cement Sheets²
- C 1288 Specification for Discrete Non-Asbestos Fiber-Cement Interior Substrate Sheets²
- D 1037 Methods for Evaluating the Properties of Wood-Base Fiber and Particle Panel Materials⁵
- D 1554 Definitions of Terms Relating to Wood-Base Fiber and Particle Panel Materials⁵
- D 2394 Method for Simulated Service Testing of Wood and Wood-Base Finish Flooring⁵
- E 84 Test Method for Surface Burning Characteristics of Building Materials⁶
- G 21 Practice for Determining Resistance of Synthetic Polymeric Materials to Fungi⁷
- G 22 Practice for Determining Resistance of Plastics to Bacteria⁷

2.2 ANSI Standards:⁸

- A118.1 Specification for Dry-Set Portland Cement Mortar
- A118.4 Specification for Latex-Portland Cement Mortar
- A136.1 Standard for Organic Adhesives for Installation of Ceramic Tile

3. Terminology

3.1 *Definitions:* Refer to Terminology C 1154.

4. Classification

4.1 *Flat Sheets Covered by This Specification are Intended for:*

4.1.1 Interior dry or wet area applications as a desired unfinished substrate or an unfinished substrate for decoration such as natural stone or tile, where substrate dimensional stability is required.

¹ This specification is under the jurisdiction of ASTM Committee C-17 on Fiber-Reinforced Cement Products and is the direct responsibility of Subcommittee C17.01 on Test Methods.

Current edition approved Nov. 10, 1999. Published December 1999. Originally published as C 1325-96. Last previous edition C 1325-96.

² *Annual Book of ASTM Standards*, Vol 04.05.

³ *Annual Book of ASTM Standards*, Vol 04.01.

⁴ *Annual Book of ASTM Standards*, Vol 04.02.

⁵ *Annual Book of ASTM Standards*, Vol 04.10.

⁶ *Annual Book of ASTM Standards*, Vol 04.07.

⁷ *Annual Book of ASTM Standards*, Vol 14.02.

⁸ Available from American National Standards Institute, 11 W. 42nd St., 13th Floor, New York, NY 10036.

4.2 Flat sheets may be supplied coated or uncoated.

5. Composition and Manufacture

5.1 *Composition*—This specification is applicable to *fiber-mat reinforced* non-asbestos cement substrate sheets consisting essentially of an inorganic hydraulic binder or a calcium silicate binder formed by the chemical reaction of a siliceous material and a calcareous material, reinforced by *fiber-mat* made of organic fibers, inorganic non-asbestos fibers, or both. Process aids, fillers, pigments, and other fibers that are compatible with the fiber-mat cement may be added.

5.2 *Manufacture*—These products may be formed either with or without pressure and cured, either under natural or accelerated conditions, to meet the property requirements of this specification.

6. Mechanical and Physical Properties

6.1 Mechanical and physical properties shall be determined on an uncoated product wherever practical. Where the products are supplied coated, this material shall also be tested with the results identified as applying to coated material.

6.2 *Sampling*—Obtain 5 samples of the particular cement substrate sheet to be tested from a commercial lot of not less than 50 000 ft² to conduct the tests described in this specification except for the Moisture Movement test (6.4.3).

6.3 Mechanical Properties:

6.3.1 *Flexural Strength*—When tested in accordance with Test Method C 947, flexural strength shall be not less than 750 psi (5170 kPa).

6.3.2 Sheets shall be tested and specified in both the wet and equilibrium conditions and shall meet the minimum wet and minimum equilibrium flexural strength requirements.

NOTE 2—When sampled from continuous production, these tests may be conducted on dry, equilibrium, or saturated specimens, provided a relationship can be established between this testing and the specified values.

6.4 Physical Properties:

6.4.1 *Density*—Nominal values and tolerances for density shall be stated by the manufacturer for each of the products. When tested in accordance with the test method specified in Test Methods C 1185, the value for the density shall comply with the value stated by the manufacturer.

6.4.2 *Modulus of Elasticity*—Values for the modulus of elasticity shall be stated by the manufacturer for each of the products. When tested in accordance with Test Method C 947, the value for modulus of elasticity shall comply with the value stated by the manufacturer. Calculate the modulus of elasticity for each sample specimen by the following equation:

$$E = 5(P_2 - P_1) \times L^3 / 27bd^3(y_2 - y_1) \quad (1)$$

where:

- E = modulus of elasticity, psi (kg/mm²),
- P_2 and P_1 = loads, lb (kg), taken from two points within the linear section of the plot,
- y_2 and y_1 = deflections, in. (mm) corresponding to the loads selected,
- b = width of specimen, in. (mm),
- d = thickness of specimen, in. (mm), and

L = span, in. (mm).

6.4.3 *Moisture Movement*—The linear variation with change in moisture content shall be stated as the percentage change in length based on a relative humidity change from 30 % to 90 % in accordance with Test Method D 1037. The linear variation with change shall be ≤ 0.07 %. For the purpose of this test, obtain 5 samples of the particular cement substrate sheet to be tested from a commercial lot of not less than 50 000 ft² once every six months.

7. Dimensions and Permissible Variations

7.1 *Method of Measurement*—The method of measurement shall be in accordance with Test Methods C 473.

7.2 *Nominal Length and Width*—Fiber-mat reinforced substrate sheets are typically supplied in nominal lengths of 48 in. (1219 mm), 60 in. (1524 mm), 72 in. (1828 mm), 84 in. (2134 mm), 96 in. (2438 mm) and nominal widths of 48 in. (1219 mm), 36 in. (914 mm), and 32 in. (811 mm). Greater or lesser nominal lengths and widths may be supplied.

7.3 *Nominal Thickness*—Fiber-mat reinforced substrate sheets are normally available in thicknesses of 1/4 in. (6 mm) to 5/8 in. (16 mm), although thicknesses outside of this range may be supplied.

7.4 *Length and Width Tolerance*—The permissible variation from the nominal value shall be $\pm 1/8$ in. (3 mm).

7.5 *Thickness Tolerance*—The maximum difference between extreme values of the thickness measurement within a sheet shall not exceed 0.03 in. (0.8 mm). Thickness variation from sheet to sheet shall not exceed 0.03 in. (0.8 mm).

7.6 *Squareness Tolerance*—The length of the diagonals shall not vary by more than 1/32 in./ft (2.6 mm/m) of the length of the sheets. Opposite sides of the sheet shall not vary in length by more than 1/32 in./ft (2.6 mm/m).

7.7 *Edge Straightness Tolerance*—The sheet edges shall be straight within 1/32 in./ft (2.6 mm/m) of length or width.

8. Workmanship

8.1 *Workmanship*—Sheets shall be free of defects that will impair erection, use, or serviceability.

9. Inspection and Acceptance

9.1 Inspection of material, if required, shall be at the point of shipment. The inspector representing the purchaser shall have authorized access to the carriers being loaded for shipment to the purchaser. The purchaser shall be afforded all reasonable and available facilities at the point of shipment for sampling and inspection of the material, which shall be conducted so as not to interfere unnecessarily with the loading of the carriers.

9.2 Third party certification, either continuous or at regular intervals, shall be recognized as an alternative to lot inspection.

9.3 Failure to conform to any one of the requirements of this specification shall constitute grounds for nonacceptance.

10. Product Marking

10.1 *Identification*—Product marking shall include trademark or other means of identification that ensures that the

manufacturer and product category can be identified. The method of marking shall be stated in the manufacturer's catalog.

11. Packaging and Storage

11.1 *Commercial Packaging*—Flat sheets shall be packaged so as to prevent damage during shipment.

11.2 *Storage*—Flat sheets shall be stacked on supports that will keep the sheets level and flat. The sheets shall be stacked with the edges square and flush and covered to provide protection from the weather until used.

12. Keywords

12.1 acceptance; air cured; appearance; density; edge straightness; finish; flexural strength; glass mat cement sheet;

inspection; interior wet area application; length and width tolerance; mechanical properties; minimum equilibrium strength; minimum wet strength; moisture content; moisture movement; nominal length; nominal thickness; nominal width; non-asbestos fiber-mat; packaging; physical properties; pressure cured; sampling; shipping; squareness tolerance; storage; supplementary requirements; supplementary tests; surface burning characteristics; thickness requirements; thickness tolerance; third party certification; tolerance; type tests; warm water resistance; workmanship

SUPPLEMENTARY REQUIREMENTS

S1. Supplementary Tests

S1.1 Supplementary tests for fiber-mat reinforced substrate sheets shall consist of once only supplementary test, with the manufacturer's statement of results provided upon customer's request. Fundamental changes in formulation or methods of manufacture, or both, shall require the subsequent retesting of the supplementary tests.

S1.2 Supplementary tests shall be determined on uncoated product wherever practical. Where fiber-mat reinforced substrate sheets are supplied coated, this material shall also be tested with the results identified as applying to coated material.

S1.3 *The following supplementary tests shall be required:*

- Moisture Content
- Warm Water Resistance
- Surface Burning Characteristics
- Shear Bond Strength (Dry-Set Portland Cement Mortar)
- Shear Bond Strength (Latex-Portland Cement Mortar)
- Shear Bond Strength (Organic Adhesive Type 1)
- Nail-Head Pull-Through (roofing nail)
- Modulus of Elasticity
- Mold Resistance
- Compression Indentation
- Falling Ball Impact
- Bacteria Resistance
- Freeze Thaw Resistance

S1.3.1 *Moisture Content*—State the percentage of moisture content of the fiber-mat reinforced cement substrate sheets when conditioned at $50 \pm 5\%$ relative humidity and a temperature of $73 \pm 4^\circ\text{F}$ ($23 \pm 2^\circ\text{C}$) in accordance with Test Method C 1185.

S1.3.2 *Warm Water Resistance*—The specimens, when tested in accordance with Test Method C 1185, shall not show visible cracks or structural alteration such as to affect their performance in use. The ratio of the average strengths as calculated from test results shall not be less than 70 %.

S1.3.3 *Surface Burning Characteristics*—When utilized as a finished substrate without decoration, fiber-mat reinforced cement substrate sheets shall have a reported flame spread index of 10 or less and a smoke developed index of not more

than 5 when tested in accordance with Test Method E 84. Tests shall be conducted on samples that have been cured for 28 days in a controlled atmosphere of $73 \pm 4^\circ\text{F}$ ($23 \pm 2^\circ\text{C}$) and $50 \pm 5\%$ relative humidity, then dried to constant weight in a $110 \pm 5^\circ\text{F}$ ($43 \pm 3^\circ\text{C}$) oven.

S1.3.4 *Shear Bond Strength (Dry-Set Portland Cement Mortar)*—Fiber-mat reinforced cement substrate sheets tested in accordance with ANSI A118.1 fiber-mat reinforced cement substrate sheet to fiber-mat reinforced cement substrate sheet) shall demonstrate a minimum shear bond strength at 7 day curing of 50 psi (344 kPa).

S1.3.5 *Shear Bond Strength (Latex-Portland Cement Mortar)*—Fiber-mat reinforced cement substrate sheets tested in accordance with ANSI A118.4 (fiber-mat reinforced cement substrate sheet to fiber-mat reinforced cement substrate sheet) shall demonstrate a minimum shear bond strength at 7 day curing of 50 psi (344 kPa).

S1.3.6 *Shear Bond Strength (Organic Adhesives Type 1)*—Fiber-mat reinforced cement substrate sheets tested in accordance with ANSI A136.1 (fiber-mat reinforced cement substrate sheet to fiber-mat reinforced cement substrate sheet) shall demonstrate a minimum shear bond strength at 7 day curing of 50 psi (344 kPa).

S1.3.7 *Nail-Head Pull Through*—Fiber-mat reinforced cement substrate sheets of $\frac{1}{2}$ in. (13 mm) thickness shall have a minimum saturated nail-head pull through resistance of 125 lb (560 N), when tested in accordance with Test Method D 1037 utilizing a roofing nail with a 0.375 in. (10 mm) diameter head and a shank diameter of 0.121 in. (3 mm).

S1.3.8 *Mold Resistance*—When tested in accordance with Practice G 21, samples shall show an observed growth rating of 0.

S1.3.9 *Compression Indentation*—When tested in accordance with Test Method D 2394, samples shall show a value greater than 1250 psi (8620 kPa) at less than 0.05 in. (1.3 mm).

S1.3.10 *Falling Ball Impact*—When tested in accordance with Test Method D 1037, samples shall show no damage to top or bottom surfaces at a 12 in. (305 mm) drop.

S1.3.11 *Bacteria Resistance*—When tested in accordance with Practice G 22, samples shall show an observed growth rating of 0.

S1.3.12 *Freeze Thaw Resistance*—When tested in accordance with Test Method C 666 (Procedure B) samples shall show no disintegration up to 25 cycles.

The American Society for Testing and Materials takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).