



Designation: C 1384 – 01

## Standard Specification for Admixtures for Masonry Mortars<sup>1</sup>

This standard is issued under the fixed designation C 1384; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

### 1. Scope \*

1.1 This specification pertains to admixtures for masonry mortars. Admixtures are substances other than Specification C 270 prescribed materials of water, aggregate, and cementitious materials that are used to improve one or more of the recognized desirable properties of conventional masonry mortar.

1.2 This specification does not cover coloring pigments.

NOTE 1—Information on coloring pigments can be found in Specification C 979.

1.3 This specification does not cover additives that are added to the cementitious materials during the manufacture of the cementitious materials.

1.4 Acceptance of an admixture is based on its performance in an admixed mortar. Acceptance of the admixed masonry mortar is based on attainment of performance either equivalent to that required for conventional mortar or improved performance of one or more indicated properties, while maintaining required performance levels for other properties.

1.5 The values stated in SI units are to be regarded as the standard. The values given in parentheses are for information only.

NOTE 2—The testing laboratory performing the test methods referenced in this specification should be evaluated in accordance with Practice C 1093.

### 2. Referenced Documents

#### 2.1 ASTM Standards:

- C 91 Specification for Masonry Cement<sup>2</sup>
- C 144 Specification for Aggregate for Masonry Mortar<sup>3</sup>
- C 150 Specification for Portland Cement<sup>2</sup>
- C 207 Specification for Hydrated Lime for Masonry Purposes<sup>2</sup>
- C 270 Specification for Mortar for Unit Masonry<sup>3</sup>
- C 305 Practice for Mechanical Mixing of Hydraulic Cement Pastes and Mortars of Plastic Consistency<sup>2</sup>
- C 403 Test Method for Time of Setting of Concrete Mix-

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee C12 on Mortars and Grouts for Unit Masonry and is the direct responsibility of Subcommittee C12.09 on Modified Mortars.

Current edition approved Jan. 10, 2001. Published February 2001. Originally published as C 1384–98. Last previous edition C 1384–00.

<sup>2</sup> Annual Book of ASTM Standards, Vol 04.01.

<sup>3</sup> Annual Book of ASTM Standards, Vol 04.05.

tures by Penetration Resistance<sup>4</sup>

C 595 Specification for Blended Hydraulic Cements<sup>2</sup>

C 723 Practice for Chemical-Resistant Resin Grouts for Brick or Tile<sup>3</sup>

C 778 Specification for Standard Sand<sup>2</sup>

C 780 Test Method for Preconstruction and Construction Evaluation of Mortars for Plain and Reinforced Unit Masonry<sup>3</sup>

C 979 Specification for Pigments for Integrally Colored Concrete<sup>4</sup>

C 1093 Practice for Accreditation of Testing Agencies for Unit Masonry<sup>3</sup>

C 1152 Test Method for Acid-Soluble Chloride in Mortar and Concrete<sup>4</sup>

C 1157 Performance Specification for Hydraulic Cement<sup>2</sup>

C 1218 Test Method for Water-Soluble Chloride in Mortar and Concrete<sup>4</sup>

C 1329 Specification for Mortar Cement<sup>2</sup>

C 1357 Test Method for Evaluating Masonry Bond Strength<sup>3</sup>

C 1403 Test Method for Rate of Water Absorption of Masonry Mortars<sup>3</sup>

C 1437 Test Method for Flow of Hydraulic Cement Mortar<sup>2</sup>

### 3. Terminology

#### 3.1 Definitions of Terms Specific to This Standard:

3.1.1 *admixed mortar, n*—masonry mortar that deviates from those combinations of materials recognized by Specification C 270 in that it also contains an admixture.

3.1.2 *admixture, n*—substance other than the Specification C 270 prescribed materials of water, aggregate, and cementitious materials that is added to a masonry mortar as an ingredient to improve one or more chemical or physical properties of the conventional masonry mortar.

3.1.3 *bond enhancer, n*—admixture incorporated into a masonry mortar to increase the bond strength between the mortar and the masonry unit.

3.1.4 *reference mortar, n*—mortar of the same composition as an admixed mortar except that the reference mortar does not include the admixture and may contain a different amount of water to obtain an equivalent flow or penetration as the admixed mortar.

<sup>4</sup> Annual Book of ASTM Standards, Vol 04.02.

\*A Summary of Changes section appears at the end of this standard.

3.1.5 *set accelerator, n*—admixture incorporated into a masonry mortar to shorten the time of setting of a mortar.

3.1.6 *set retarder, n*—admixture incorporated into a masonry mortar to lengthen the time of setting of a mortar.

3.1.7 *water repellent, n*—admixture incorporated into a masonry mortar to decrease the rate of water absorption of the hardened mortar.

3.1.8 *workability enhancer, n*—admixture incorporated into a masonry mortar to increase the ease of being worked and used. A workability enhancer will increase the board life and maintain the water retention of a mortar.

#### 4. Classification

4.1 Admixtures are classified by their effect on the performance characteristics of conventional masonry mortars. Admixed mortars are classified by their modified properties, as compared to a reference mortar. The following classifications are recognized:

4.1.1 Bond Enhancer.

4.1.2 Workability Enhancer.

4.1.3 Set Accelerator.

4.1.4 Set Retarder.

4.1.5 Water Repellent.

#### 5. Materials

5.1 *Cements*—The cement used in the evaluation of the admixture shall conform to applicable requirements specified in 5.1.1-5.1.5.

5.1.1 *Cement, Portland*—When the admixture is evaluated in a mortar containing portland cement, the portland cement shall conform to the requirements for Type I, IA, II, IIA, III, or IIIA of Specification C 150.

5.1.2 *Cement, Blended Hydraulic*—When the admixture is evaluated in a mortar containing blended hydraulic cement, the blended hydraulic cement shall conform to the requirements for Type IS, IS-A, IP, IP-A, I(PM) or I(PM)-A of Specification C 595.

5.1.3 *Cement, Hydraulic, Performance Specified*—When the admixture is evaluated in a mortar containing a performance specified hydraulic cement, the hydraulic cement shall conform to the requirements for Type GU, HE, MS, HS, MH, or LH of Specification C 1157.

5.1.4 *Cement, Masonry*—When the admixture is evaluated in a mortar containing a masonry cement, the masonry cement shall conform to the requirements of Specification C 91.

5.1.5 *Cement, Mortar*—When the admixture is evaluated in a mortar containing a mortar cement, the mortar cement shall conform to the requirements of Specification C 1329.

5.2 *Lime*—When the admixture is evaluated in a cement-lime mortar, the hydrated lime shall conform to Specification C 207.

5.3 *Sand*—The fine aggregate used in the tests will vary dependent on the test procedure.

5.3.1 Sands used for flexural bond strength and rate of water absorption tests shall be a blend of equal parts by weight of graded standard sand and standard 20-30 sand conforming with Specification C 778.

5.3.2 Sands used for soluble chloride, compressive strength, water retention, determination of air content of plastic mortar,

board life, and time of setting tests shall conform to the requirements of Specification C 144.

#### 6. Chemical Composition

6.1 The admixture shall not react adversely with embedded or attached materials common to masonry.

NOTE 3—Currently, there is no standard test method for determining the corrosion potential of masonry mortars toward embedded and attached materials. Nonetheless, the admixture shall not be offered for sale if the manufacturer has evidence that the admixture does react adversely with embedded or attached materials common to masonry.

6.2 At the maximum recommended dosage, the mortar admixture shall add not more than 65 ppm (0.0065 %) water-soluble chloride, or 90 ppm (0.0090 %) acid-soluble chloride to the mortar's overall chloride content as determined by testing of the reference and admixed mortars in accordance with 9.1.1.

#### 7. Physical Properties

7.1 All modified masonry mortars shall comply with the property specification requirements of Specification C 270. In addition, the admixed mortars shall conform to all of the specific classification requirements in Table 1 for which the admixture is obtaining qualification. Unless more specimens are required by a specific test method, a minimum of three specimens shall be tested and the results averaged. These result averages shall meet the requirements of this section.

7.2 Admixture compliance tests shall be the responsibility of the manufacturer of the admixture. These compliance tests shall be completed within the past five (5) years and prior to any admixture composition change.

#### 8. Mortar Types and Proportions

8.1 Design the reference mortar to be a specific type of cement/lime, mortar cement, or masonry cement mortar in conformance with the proportion specification of Specification C 270 except that the aggregate ratio shall be fixed at three times the sum of the separate volumes of cementitious materials. In addition, the aggregate shall meet the requirements in 5.3.

8.2 The corresponding admixed mortars shall have the same composition as the reference mortars but also shall include the admixture, and the water content shall be adjusted to yield the flow or penetration appropriate for each test method. The admixture dosage rate, time of addition, and mixing sequence shall follow the manufacturer's recommendations.

8.3 A complete set of tests shall be run for all applicable cement/lime, mortar cement, and masonry cement types for which the admixture is to be qualified.

#### 9. Test Methods

9.1 For all required tests, test both the reference mortar and the admixed mortar in accordance with the following test methods:

9.1.1 *Soluble Chloride Content*—Prepare six mortar cubes in accordance with the specimen preparation section of Test Method C 1403 including the drying procedure, except that mortar proportions shall be as specified in Section 8 and aggregates shall be as specified in 5.3. After 28 days of age,

**TABLE 1 Physical Requirements<sup>A</sup>**

	Bond Enhancer	Workability Enhancer	Set Accelerator	Set Retarder	Water Repellent
Compressive strength, min % of reference:					
7 day	80	80	80	70	80
28 day	80	80	80	80	80
Water retention, min % of reference:	report	100	report	report	report
Air content of plastic mortar, %	report	report	report	report	report
Board life, min % of reference	report	120	report	120	report
Time of setting <sup>B</sup> , allowable deviation from reference, h: min:					
Initial: at least	...	...	1:00 earlier	1:00 <sup>C</sup> later	...
not more than	1:00 earlier nor 1:30 later	1:00 earlier nor 3:30 later	3:30 earlier	8:00 <sup>C</sup> later	1:00 earlier nor 1:30 later
Final: at least	...	...	1:00 earlier	...	...
not more than	1:00 earlier nor 1:30 later	1:00 earlier nor 3:30 later	...	8:00 <sup>C</sup> later	1:00 earlier nor 1:30 later
Flexural bond strength, min % of reference	110	...	...	...	...
Rate of water absorption max % of reference 24 h	...	...	...	...	50

<sup>A</sup> The values in the table include allowance for normal variation in test results. In addition to meeting the requirements in this table, all admixed mortars must meet the property requirements of Specification C 270.

<sup>B</sup> All time of setting tests shall be performed at 23 ± 3°C (73.4 ± 5.4°F), except those for set accelerators, which shall be performed at 5 ± 2°C (41 ± 3.6°F) as specified in 9.1.5.

<sup>C</sup> The manufacturer's maximum recommended dosage rate shall be used when testing the initial and final set times for a set retarder.

determine the water-soluble chloride content of three cubes, as percent chloride by mass of mortar, in accordance with Test Method C 1218 and the acid-soluble chloride content of the other three cubes, as percent chloride by mass of mortar, in accordance with Test Method C 1152.

9.1.2 *Compressive Strength*—Prepare and test mortar in accordance with Specification C 270, except that mortar proportions shall be as specified in Section 8 and aggregates shall be as specified in 5.3. Test three specimens at 7 days and three specimens at 28 days.

9.1.3 *Water Retention*—Prepare and test mortar in accordance with Specification C 270, except that mortar proportions shall be as specified in Section 8 and aggregates shall be as specified in 5.3.

9.1.4 *Air Content of Plastic Mortar*—Prepare mortar and determine air content of the plastic mortar in accordance with Specification C 270 except that mortar proportions shall be as specified in Section 8 and aggregates shall be as specified in 5.3. Calculate the air content to the nearest 0.1 % as follows:

$$D = \frac{(W_1 + W_2 + W_3 + W_4 + W_5 + V_w)}{\frac{W_1}{P_1} + \frac{W_2}{P_2} + \frac{W_3}{P_3} + \frac{W_4}{P_4} + \frac{W_5}{P_5} + V_w} \quad (1)$$

$$A = 100 - \frac{W_M}{4D}$$

where:

$D$  = density of air-free mortar, g/cm<sup>3</sup>,

$W_1$  = weight of portland cement, g,  
 $W_2$  = weight of hydrated lime, g,  
 $W_3$  = weight of mortar cement or masonry cement, g,  
 $W_4$  = weight of sand, g,  
 $W_5$  = weight of mortar admixture, g,  
 $V_w$  = mL of water used,  
 $P_1$  = density of portland cement, g/cm<sup>3</sup>,  
 $P_2$  = density of hydrated lime, g/cm<sup>3</sup>,  
 $P_3$  = density of mortar cement or masonry cement, g/cm<sup>3</sup>,  
 $P_4$  = density of sand, g/cm<sup>3</sup>,  
 $P_5$  = density of mortar admixture, g/cm<sup>3</sup>,  
 $A$  = volume of air, %, and  
 $W_M$  = weight of 400 mL of mortar, g.

9.1.5 *Board Life*—Test mortar in accordance with Test Method C 780, Annex A2 or, alternately, Annex A3, except for the modifications in this section. The mortar proportions shall be as specified in Section 8 and aggregates shall be as specified in 5.3. Prepare the mortar in accordance with the procedures of Test Method C 780, modifying those as appropriate when the admixture is added to the mortar. Mix the mortar for 5 min, timing from when water and cementitious materials are combined or as recommended by the manufacturer. The mixer used shall conform to that described in Practice C 305, or to that described in Practice C 723, or shall be a paddle-type field mortar mixer.

9.1.5.1 If Test Method C 780, Annex A2 is used, prepare the mortar to have an initial penetration of 60 ± 5 mm. Measure

the initial penetration within 2 min from the completion of the mixing. Record the initial penetration as  $P_o$  and the time of this measurement as  $T_o$ . Test the sample using the disturbed sample procedure and measure the penetration at 15-min intervals until the penetration is less than 70 % of  $P_o$ . Record as  $T_f$  the interpolated time at which the penetration equals 70 % of  $P_o$ . Board life is defined as  $(T_f - T_o)$ , in minutes.

9.1.5.2 If Test Method C 780, Annex A3 is used, prepare the mortar to have an initial penetration resistance ( $P_o$ ) of either  $0.94 \pm 0.05$  psi or  $1.24 \pm 0.05$  psi as specified in the Annex A3. Board life is defined as  $T_f$  as specified in the Annex A3.

9.1.6 *Time of Setting*—Test mortar in accordance with Test Method C 403 except for the modifications in this section. The mortar proportions shall be as specified in Section 8 and aggregates shall be as specified in 5.3. Prepare the mortar in accordance with the procedures of Test Method C 780, modifying those as appropriate when the admixture is added to the mortar. Mix the mortar for 5 min, timing from when water and cementitious materials are combined or as recommended by the manufacturer. The mixer used shall conform to that described in Practice C 305, or to that described in Practice C 723, or shall be a paddle-type field mortar mixer. Prepare the mortar to have a flow of  $110 \pm 5$  mm as determined by Test Method C 1437. Prepare and test the mortar at a temperature of  $23 \pm 3^\circ\text{C}$  ( $73.4 \pm 5.4^\circ\text{F}$ ) for all admixture classifications except set accelerators. Prepare and test the mortar at a temperature of  $5 \pm 2^\circ\text{C}$  ( $41 \pm 3.6^\circ\text{F}$ ) for set accelerators.

9.1.7 *Flexural Bond Strength*—Prepare and test mortar in accordance with the Test Method for Laboratory-Prepared Specimens in Test Method C 1357 except that mortar proportions shall be as specified in Section 8 and aggregates shall be as specified in 5.3.

9.1.8 *Rate of Water Absorption*—Prepare and test mortar in accordance with Test Method C 1403, except that mortar proportions shall be as specified in Section 8 and aggregates shall be as specified in 5.3.

## 10. Product Marking

10.1 When the admixture is delivered in packages or containers, the admixture classification, the trade name of the

admixture, the name of the manufacturer, and the weight of the admixture shall be marked clearly on each package or container.

10.2 If the total chloride content of the admixture is greater than 0.1 % by mass, then the admixture package or container shall have a label stating that the admixture contains chloride. In this case, the admixture package or container shall contain a label stating that at the maximum recommended dosage, the mortar admixture shall add not more than 65 ppm (0.0065 %) water-soluble chloride or 90 ppm (0.0090%) acid-soluble chloride to the mortar's overall chloride content when tested according to this specification. If the admixture contains less than or equal to 0.1 % by mass of total chloride, then no label referring to chloride is necessary.

## 11. Report

11.1 Report the following information:

11.1.1 Trade name, manufacturer, classification(s) of the admixture, and the type(s) of mortar for which the admixture is qualified.

11.1.2 Results of the tests specified in Sections 6 and 7 for each type of mortar for which the admixture is qualified. Include the results for both the reference mortar and the admixed mortar. Also, include the flow or penetration value of the mortar used in each test as specified in each test method.

11.1.3 Brand name, manufacturer, and type of cement used in the test evaluation.

11.1.4 Brand name, manufacturer, and type of lime, if any, used in the test evaluation.

11.1.5 Description of, and test data on, the sand used in the test evaluation.

11.1.6 The mix design and weight of each component, including water, used in the mortar for each test batch. For those batches which contain an admixture, include the admixture dosage rate and time of addition.

## 12. Keywords

12.1 absorption; absorption rate; admixed mortar; admixture; bond enhancer; masonry mortar; set accelerator; set retarder; water repellent; workability enhancer

## SUMMARY OF CHANGES

Committee C12 has identified the location of selected changes to the standard since the C 1384–00 version that may impact the use of this standard.

(1) Test Method C 1437 was added to the Referenced Documents and as the reference test method for flow in Paragraph 9.1.6.

(2) Test Method C 1157 was added to the Referenced Documents and to Paragraph 5.1.3 to allow the use of C 1157 performance specified hydraulic cements.

(3) Paragraphs 6.2, 9.1, and 10.2 were revised to change the acceptable chloride limits from a “chloride per volume of

mortar” basis to a “chloride as a weight percent of mortar” basis.

(4) Paragraphs 1.1, 1.2, 2.1, and 3.1.1 were revised with changes throughout the standard to change all references from “modifiers” and “modified mortars” to “admixtures” and “admixed mortars.” The definition of “admixtures” was clarified.

(5) Definitions of the admixture classifications in Section 3 were changed to reference “admixture” instead of “substance.”



*ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.*

*This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.*

*This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or [service@astm.org](mailto:service@astm.org) (e-mail); or through the ASTM website ([www.astm.org](http://www.astm.org)).*