



Standard Specification for Sewer and Manhole Brick (Made From Clay or Shale)¹

This standard is issued under the fixed designation C 32; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

^{e1} NOTE—Grade MM was editorially moved up to align with its values in Table 1 in June 1999.

1. Scope

1.1 This specification covers brick intended for use in (1) drainage structures for the conveyance of sewage, industrial wastes, and storm water, and (2) related structures such as manholes and catch basins.

1.1.1 Sewer Brick:

1.1.1.1 *Grade SS*—Brick intended for use in structures requiring low absorption and resistance to the action of sewage carrying large quantities of abrasive material at velocities exceeding 8 ft (2.4 m)/s.

1.1.1.2 *Grade SM*—Brick intended for use in structures requiring resistance to the action of sewage carrying abrasive materials at velocities less than 8 ft (2.4 m)/s.

1.1.2 Manhole Brick:

1.1.2.1 *Grade MS*—Brick intended for use in manholes and catch basins not requiring high degrees of abrasive resistance but where a high and uniform degree of resistance to frost action and disintegration is needed when the brick may be frozen when permeated with water.

1.1.2.2 *Grade MM*—Brick intended for use in manholes not requiring high degrees of abrasive resistance but where a moderate and nonuniform degree of resistance to frost action and disintegration is needed when the brick may be permeated with water.

1.2 The property requirements of this standard apply at the time of purchase. The use of results from testing of brick extracted from masonry structures for determining conformance or non-conformance to the property requirements (Section 3) of this standard is beyond the scope of this standard.

1.3 Brick covered by this standard are manufactured from clay, shale, or similar naturally occurring substances and subjected to a heat treatment at elevated temperatures (firing). The heat treatment must develop sufficient fired bond between the particulate constituents to provide the strength and dura-

bility requirements of this specification. (See *firing* and *fired bond* in Terminology C 43.)

1.4 The values stated in inch-pound units are to be regarded as the standard. The metric equivalents of inch-pound units given in parentheses may be approximate.

2. Referenced Documents

2.1 ASTM Standards:

C 43 Terminology of Structural Clay Products²

C 67 Test Methods for Sampling and Testing Brick and Structural Clay Tile²

3. Physical Properties

3.1 Brick for sewer or drainage structures shall conform to the physical properties for the specified Grades SS or SM as established in Table 1.

3.2 Brick for manholes, catch basins, and other related structures shall conform to the physical properties for the specified Grades MS or MM as established in Table 1.

3.3 Unless otherwise specified by the purchaser, brick of Grade SS shall be accepted instead of Grade SM; also Grade MS shall be accepted instead of Grade MM.

3.4 Unless otherwise specified in the invitation for bids, brick shall be either solid or cored at the option of the seller. The net cross-sectional area of cored brick in any plane parallel to the bearing surface shall be at least 75 % of the gross cross-sectional area measured in the same plane. No part of any hole shall be less than $\frac{3}{4}$ in. (19 mm) from any edge of the brick.

4. Dimensions and Permissible Variations

4.1 The size of the brick shall be specified by the purchaser, selecting any of the standard sizes of building brick.

4.2 For any lot of sewer brick furnished under this specification, not more than 2 % of the brick shall vary from the nominal size requirements specified in 4.1 by more than

¹ This specification is under the jurisdiction of ASTM Committee C-15 on Manufactured Masonry Units and is the direct responsibility of Subcommittee C15.02 on Clay Brick and Structural Clay Tile.

Current edition approved Nov. 15, 1993. Published January 1994. Originally published as C 32–21 T. Last previous edition C 32–91.

² *Annual Book of ASTM Standards*, Vol 04.05.

TABLE 1 Physical Properties

Designation	Minimum Compressive Strength, Average Gross Area, psi (MPa)		Maximum Water Absorption by 5-h Boiling, %	
	Average of 5 Brick	Individual	Average of 5 Brick	Individual
Sewer brick:				
Grade SS	8000 (55)	6000 (41)	6.0	9.0
Grade SM ^A	5000 (34)	3750 (26)	12.0	15.0
Manhole brick:				
Grade MS ^A	3000 (21)	2500 (17)	17.0	20.0
Grade MM ^B	2500 (17)	2200 (15)	22.0	25.0

^A Where a high and uniform degree of resistance to frost action in the presence of moisture is required, Grades SM and MS shall conform to the additional requirements that the saturation coefficient (*C/B*), that is, ratio of absorption by 24-h submersion in cold water to that after 5-h submersion in boiling water, shall not exceed 0.80. If the average compressive strength is greater than 8000 psi or the average water absorption is less than 8.0 % after 24-h submersion in cold water, the requirement for saturation coefficient shall be waived.

^B Maximum saturation coefficient for Grade MM brick shall not exceed 0.90.

±1/8 in. (3 mm) in either transverse dimension, or by more than ±1/4 in. (6 mm) in length.

5. Finish and Appearance

5.1 Sewer brick shall have plain or smooth surfaces on both ends and on the face side.

5.2 Manhole brick shall have plain, slightly, or moderately textured surfaces.

6. Sampling and Testing

6.1 For test purposes brick that are representative of the commercial product shall be selected by a competent person

appointed by the purchaser, the place or places of selection to be designated when the purchase order is placed. The manufacturer or the seller shall furnish specimens for tests without charge.

6.2 Brick shall be sampled and tested in accordance with Test Methods C 67.

7. Inspection

7.1 The brick, as delivered to the site, shall conform by visual inspection to the requirements specified by the purchaser or to the sample or samples approved as standard of comparison and to the samples passing the tests for physical requirements. Minor indentions and surface cracks incidental to the usual methods of manufacture, or the small chipping resulting from the customary methods of handling in shipment and delivery, should not be deemed grounds for rejection.

7.2 Brick shall be of rectangular cross section with substantially straight edges and square corners.

7.3 Kiln marks or depressions not exceeding 3/16 in. (5 mm) in depth shall be permitted on the backside of the brick.

8. Keywords

8.1 brick; clay; drainage structures; industrial waste; manhole brick; physical properties; sewer brick; sewers; shale; storm water

The American Society for Testing and Materials takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, 100 Barr Harbor Drive, West Conshohocken, PA 19428.

This standard is copyrighted by ASTM, 100 Barr Harbor Drive, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (<http://www.astm.org>).