



# Standard Specification for Chemical-Resistant Resin Mortars<sup>1</sup>

This standard is issued under the fixed designation C 395; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

## 1. Scope

1.1 This specification covers the requirements for chemical-resistant resin mortars for bonding chemical-resistant brick or tile. Mortars of this group generally have better physical properties and resist a wider variety of chemicals than inorganic mortars. For the use of these materials, see Practice C 399.

NOTE 1—Resin mortars and grouts are differentiated as follows: resin mortars are troweled onto the brick or tile, in sufficient quantity to achieve a  $\frac{1}{8}$ -in. (3-mm) thick joint after the brick or tile are laid in place (buttering or bricklayer's method). Resin grouts are applied to the joints, generally  $\frac{1}{4}$ in. (6 mm) wide, after the brick or tile are set in place and the setting bed has hardened (grouting or tilesetter's method). Refer to Specification C 658.

1.2 The values stated in inch-pound units are to be regarded as the standard. The values given in parentheses are for information only.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

## 2. Referenced Documents

### 2.1 ASTM Standards:

- C 267 Test Methods for Chemical Resistance of Mortars, Grouts, and Monolithic Surfacing and Polymer Concretes<sup>2</sup>
- C 279 Specification for Chemical-Resistant Masonry Units<sup>2</sup>
- C 307 Test Method for Tensile Strength of Chemical-Resistant Mortar, Grouts, and Monolithic Surfacing<sup>2</sup>
- C 308 Test Methods for Working, Initial Setting, and Service Strength Setting Times of Chemical-Resistant Resin Mortars<sup>2</sup>
- C 321 Test Method for Bond Strength of Chemical-Resistant Mortars<sup>2</sup>
- C 399 Practice for Use of Chemical-Resistant Resin Mortars<sup>2</sup>
- C 413 Test Method for Absorption of Chemical-Resistant

Mortars, Grouts, and Monolithic Surfacing<sup>2</sup>

C 531 Test Method for Linear Shrinkage and Coefficient of Thermal Expansion of Chemical-Resistant Mortars, Grouts, Monolithic Surfacing, and Polymer Concretes<sup>2</sup>

C 579 Test Method for Compressive Strength of Chemical-Resistant Mortars, Grouts, Monolithic Surfacing, and Polymer Concretes<sup>2</sup>

C 658 Specification for Chemical-Resistant Resin Grouts for Brick or Tile<sup>2</sup>

C 904 Terminology Relating to Chemical-Resistant Non-metallic Materials<sup>2</sup>

## 3. Terminology

3.1 *Definitions*—For definitions of terms, refer to Terminology C 904.

## 4. Types of Resins, Fillers, and Setting Agents

4.1 The liquid resin may be phenolic, furan epoxy, polyester, vinyl ester, or some other resinous material capable of forming a chemical-resistant mortar when mixed with a suitable setting agent and filler.

4.2 The fillers may be silica, carbon, or some other chemical-resistant material.

4.3 The setting agents may include amines, polyamides, peroxides, acids or other reactants. Setting agents may be supplied as a separate component to be incorporated into the resin and filler at the time of mixing or may be supplied as a constituent of the filler.

## 5. Physical Properties

5.1 Resin mortars prepared from these materials shall conform to the respective physical requirements prescribed in Table 1.

## 6. General Requirements

6.1 The resin shall have a viscosity that will permit it to be readily mixed with the powder by manual methods. The filler materials shall have properly graded particles that will permit the preparation of a minimum joint thickness of  $\frac{1}{16}$ in. (1.6 mm).

## 7. Chemical Resistance

7.1 The chemical resistance of these mortars are best determined by use of Test Methods C 267. Specific recommendations for immersion service can usually be found in the

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee C03 on Chemical-Resistant Nonmetallic Materials and is the direct responsibility of Subcommittee C03.02 on Mortar and Monolithics.

Current edition approved May 10, 2001. Published July 2001. Originally published as C 395 – 57 T. Last previous edition C 395 – 95.

<sup>2</sup> *Annual Book of ASTM Standards*, Vol 04.05.

**TABLE 1 Physical Requirements**

Resin	Filler	Tensile Strength, min, psi (MPa)	Compressive Strength, min, psi (MPa)	Bond Strength, min, psi (MPa)	Working Time, Minutes, 73 ± 4°F (23 ± 2°C), min	Setting Time, max		Shrinkage, max (7 days at 73 ± 4°F (23 ± 2°C), %)	Maximum Absorption Limit, %
						Initial, h	Service Strength, days		
Furan	carbon	700 (5)	5000 (35)	150 (1)	10	6	7	1.0	1.0
Furan	silica	400 (3)	5000 (35)	150 (1)	10	6	7	1.0	1.0
Phenolic	carbon	800 (6)	4500 (31)	150 (1)	10	6	7	1.0	1.0
Phenolic	silica	400 (3)	6000 (41)	150 (1)	10	6	7	1.0	1.0
Polyester	carbon	1000 (7)	9000 (62)	150 (1)	10	6	7	1.5	1.0
Polyester	silica	1000 (7)	9000 (62)	250 (2)	10	6	7	1.5	1.0
Epoxy	carbon	1000 (7)	7000 (48)	250 (2)	10	6	7	0.5	1.0
Epoxy	silica	1000 (7)	7000 (48)	250 (2)	10	6	7	0.5	1.0
Vinylester	carbon	1000 (7)	9000 (62)	150 (1)	10	6	7	1.5	1.0
Vinylester	silica	1000 (7)	9000 (62)	250 (2)	10	6	7	1.5	1.0

manufacturer's literature, but direct consultation would be advisable when conditions are questionable.

## 8. Test Methods

8.1 Determine the properties enumerated in this specification in accordance with the following methods:

8.1.1 *Working Life and Setting Time*—Test Methods C 308.

8.1.2 *Tensile Strength*—Test Method C 307.

8.1.3 *Compressive Strength*—Test Method C 579.

8.1.4 *Bond Strength*—Test Method C 321. Use Type III brick, described in Specification C 279 in this test.

8.1.5 *Chemical Resistance*—Test Methods C 267.

8.1.6 *Shrinkage*—Test Method C 531.

8.1.7 *Absorption*—Test Method C 413.

## 9. Rejection

9.1 The resin mortar may be rejected if it fails to meet any

requirements of this specification.

## 10. Packaging and Package Marking

10.1 Each component shall be packaged to prevent deterioration in storage and shall be labeled in such a manner to indicate clearly the other components with which it is to be used.

10.2 The supplier, at his discretion and responsibility, may indicate on the package that the product contained therein meets the requirements of this specification.

## 11. Keywords

11.1 brick; chemical-resistant; mortar

*The American Society for Testing and Materials takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.*

*This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.*

*This standard is copyrighted by ASTM, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).*