This document is not an ASTM standard and is intended only to provide the user of an ASTM standard an indication of what changes have been made to the previous version. Because it may not be technically possible to adequetely depict all changes accurately, ASTM recommends that users consult prior editions as appropriate. In all cases only the current version of the standard as published by ASTM is to be considered the official document.



Designation: C 923 – 002

Standard Specification for Resilient Connectors Between Reinforced Concrete Manhole Structures, Pipes, and Laterals¹

This standard is issued under the fixed designation C 923; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

¹ This specification is under the jurisdiction of ASTM Committee C13 on Concrete Pipe and is the direct responsibility of Subcommittee C13.06 on Manholes and Specials. Current edition approved-June Sept. 10, 20002. Published-September 2000. November 2002. Originally published as C 923–79. Last previous edition C 923–9800.

1. Scope

1.1 This specification covers the minimum performance and material requirements for resilient connectors used for connections between reinforced concrete manholes <u>conforming to Specification C 478</u> and pipes, between wastewater structures and pipes, and between <u>wastewater structures and between precast</u> reinforced concrete pipe and laterals.

1.1.1 These connectors are designed to minimize leakage between the pipe and manhole, and between the pipe and lateral.

1.2 A complete metric companion to Specification C 923 has been developed—C 923M; therefore, no metric equivalents are presented in this specification.

NOTE 1—This specification covers the design, material, and performance of the resilient connection only. Connections covered by this specification are adequate for hydrostatic pressures up to 13 psi (30 ft) without leakage when tested in accordance with Section 7. Infiltration or exfiltration quantities for an installed system are dependent upon many factors other than the connections between manhole structures and pipe, and allowable quantities must be covered by other specifications and suitable testing of the installed pipeline and system.

1.3 The following precautionary caveat pertains only to the test methods portion, Section 7, of this specification: *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.* For a specific precaution statement, see 7.2.5.

2. Referenced Documents

2.1 ASTM Standards:

A <u>167493</u> Specification for Stainless <u>Steel</u> and <u>Heat–Resisting Chromium–Nickel</u> Steel<u>Plate</u>, <u>Sheet Wire</u> and <u>Strip Wire Rods</u> for Cold Heading and Cold Forging²

- A 666 Specification for Annealed or Cold-Worked Austenitic Stainless Steel Sheet, Strip, Plate, and Flat Bar²
- C 478 Specification for Precast Reinforced Concrete Manhole Sections³
- C 822 Terminology Relating to Concrete Pipe and Related Products³
- C 913 Specification for Precast Concrete Water and Wastewater Structures³
- D 395 Test Methods for Rubber Property-Compression Set⁴
- D 412 Test Methods for Vulcanized Rubber and Thermoplastic Rubbers and Thermoplastic Elastomers-Tension⁴
- D 471 Test Method for Rubber Property—Effect of Liquids⁴
- D 543 Test Method for Resistance of Plastics to Chemical Reagents⁵
- D 573 Test Method for Rubber—Deterioration in an Air Oven⁴
- D 624 Test Method for Tear Strength of Conventional Vulcanized Rubber and Thermoplastic Elastomer⁴
- D 746 Test Method for Brittleness Temperature of Plastics and Elastomers by Impact⁵
- D 883 Terminology Relating to Plastics⁵
- D 1171 Test Method for Rubber Deterioration—Surface Ozone Cracking Outdoors or Chamber (Triangular Specimens)⁴
- D 1566 Terminology Relating to Rubber⁴

Copyright © ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States.

² Annual Book of ASTM Standards, Vol 01.03.

³ Annual Book of ASTM Standards, Vol 04.05.

⁴ Annual Book of ASTM Standards, Vol 09.01.

⁵ Annual Book of ASTM Standards, Vol 08.01.

🕼 C 923 – 002

D 2240 Test Method for Rubber Property—Durometer Hardness⁴

NOTE 2—For more information about wastewater structures, see C 913 Specification for Precast Concrete Water and Wastewater Structures.³

3. Terminology

3.1 *Definitions:*

3.1.1 Terms relating to plastics and rubber shall be as defined in Terminologies D 883 and D 1566, respectively.

3.1.2 Terms relating to precast concrete pipe, manholes, and related products shall be as defined in Terminology C 822 and as modified in 3.1.3-3.1.6.

3.1.3 *connector*—the entire assembly including resilient seals and metallic or nonmetallic mechanical devices, if any, used therein.

3.1.4 *lateral*—the small diameter pipe connected to the main line pipe.

3.1.5 *pipe*—the inlet or outlet pipe connected to the manhole.

3.1.6 pipe stub—a short section of pipe, installed in the structure as an inlet or outlet pipe, for future connection.

4. Materials and Manufacture

4.1 All materials shall conform to the following requirements:

4.1.1 Resilient materials for connectors and filler rings shall be manufactured from natural or synthetic rubber and shall conform to the requirements prescribed in Table 1. If a splice is used in the manufacture of the seal, its strength shall be such that the seal shall withstand a 180° bend with no visible separation.

4.2 *Mechanical Devices*—Expansion rings, tension bands, and take-up devices used for mechanically compressing the resilient portion of the connector against the pipe, manhole or wastewater structure shall be made from a material or materials in combination that will ensure durability, strength, resistance to corrosion, and have properties that will ensure continued resistance to leakage. All metallic mechanical devices, including castings and bolt assemblies used to mechanically deform resilient materials shall be constructed of corrosion resistant materials meeting the physical properties and chemical composition requirements of Specifications A 1493 and A 6766.

Note 23—Experience has shown that successful performance of this product depends on the type of bedding and backfill and the care in the field installation of the manhole or wastewater structure and connecting pipes. The owner is cautioned to require inspection at the construction site.

5. Principles of Design

5.1 The design of the connector shall be such that positive seal is accomplished at two locations: (1) between the connector and the <u>wall of the manhole or</u> wastewater structure and (2) between the connector and the pipe. The seal between the connector and the <u>wall of the manhole or</u> wastewater structure <u>may shall</u> be made by either mechanical means, compression of the resilient material between the outside surface of the pipe and the pipe opening in the <u>wall of the manhole or</u> wastewater structure, or by casting the connector integrally with the <u>wall of the manhole or</u> wastewater structure. The seal between the connector and the pipe <u>may shall</u> be made by mechanical means or by compression of the resilient material against the outside of the pipe. Resilient filler rings-may be are not prohibited from being used between the pipe and the connector to provide a seal. Whichever design is used, it shall be capable of maintaining a resilient, hydrostatic seal under the performance conditions in accordance with Section 7. Devices used to effect mechanical seals shall conform to the requirements specified in Section 4.

5.2 For lateral to pipe connectors, the design of the connector shall be such that a positive seal is accomplished at two locations: (1) between the connector and the pipe wall and (2) between the connector and the lateral. The seal between the connector and

Test	Test Requirements ^A	ASTM Test Method
Chemical resistance:		D 543, at 22°C for 48 h
1 N sulfuric acid	no weight loss	
1 N hydrochloric acid	no weight loss	
Tensile strength	1200 psi, min	D 412
Elongation at break	350 %, min	
Hardness ^B	\pm 5 from the connector manufacturer's specified	D 2240 (Shore A durometer)
	hardness	
Accelerated oven-aging	decrease of 15 %, max, of original tensile strength, decrease of 20 %, max, of elongation	D 573, 70 \pm 1°C for 7 days
Compression set	decrease of 25 %, max, of original deflection	D 395, Method B, at 70°C for 22 h
Water absorption	increase of 10 %, max, of original by weight	D 471, immerse 0.75 by 2 - in. specimen in distilled water at 70°C for 48 h
Water absorption	increase of 10 %, max, of original by weight	D 471, immerse 0.75 by 2 in. specimen in distilled water at 70°C for 48 h
Ozone resistance	rating 0	D 1171
Low-temperature brittle point	no fracture at – 40°C	D 746
Tear resistance	200 lbf/in.	D 624, Die B

^A Specimens shall be prepared from connector specimens, and shall not be prepared from laboratory slabs or by direct molding.

^B The connector manufacturer shall select the hardness appropriate for each component of the connector. Thereafter, the hardness shall comply within the tolerances in Table 1.

the pipe wall-<u>may_shall</u> be made by either mechanical means, compression, or by casting the connector integrally with the pipe wall. The seal between the connector and the lateral-<u>may_shall</u> be made by either mechanical means or by compression of the resilient material against the outside of the pipe. Resilient filler rings-<u>may be are not prohibited from being</u> used between the lateral and the connector to provide a seal. Connector design must not allow either lateral or connector to extend past the cylindrical plane of the pipe inside diameter. The connector shall be capable of maintaining a resilient hydrostatic seal under the performance conditions in accordance with Section 7. Devices used to effect mechanical seals shall conform to the requirements specified in Section 4.

5.3 Purchaser shall require that all pipe stubs installed, to allow for future connection to the manhole or wastewater structure, be mechanically restrained from movement by means of, and in addition to, the resilient connectors.

6. Basis of Acceptance

6.1 For diameter 36 in. and smaller, at least one connector shall be tested for each 6 in. increment in diameter. For diameters larger than 36 in., at least one connector shall be tested for each 12 in. increment in diameter.

6.2 The acceptability of the resilient connector shall be determined by the results of the physical tests prescribed in this specification, if and where required, and by inspection, to determine whether the connector conforms to the specification with regards to design and freedom from defects.

6.3 When requested, a current certification shall be furnished as the basis of acceptance. The certification shall consist of the connector manufacturer's test report, or statement by the manufacturer, accompanied by a copy of the test results, that the resilient connector has been tested and inspected in accordance with the provisions of Section 4 and Section 7. Each certification so furnished shall be signed by the connector manufacturer or an authorized agent.

NOTE <u>34</u>—Certification shall be deemed current, if it represents present design, and bears a date that is no more than five years older than the current date.

7. Test Methods and Requirements

7.1 Install a pipe(s) and the resilient connector(s) to be tested in the base section of a manhole or wastewater structure. Subject the assembly to the prescribed hydrostatic pressure in 7.2 at the centerline of the connector for a period of 10 min. for each test condition. Restrain the pipe against axial movement during the tests.

NOTE 4—If 5—The user of this specification is advised that if manhole bases greater than 48 in. inside diameter are required to accommodate large diameter connectors for the test, all safety requirements and procedures should be reviewed prior to the test.

7.1.1 Install a lateral and resilient connector to be tested into the pipe. Subject the assembly to the prescribed hydrostatic pressure in 7.2 at the centerline of the connector for a period of 10 min. for each test condition. Restrain the lateral against axial movement during the tests.

7.2 There shall be no leakage under any of the following conditions:

7.2.1 Straight alignment of the pipe(s)/lateral(s) subjected to a hydrostatic pressure of 13- psi (30 ft₇) for 10 min.

7.2.2 Axial deflection of the pipe(s)/lateral(s). Upon completion of the test for straight alignment in 7.2.1 the pipe(s)/lateral(s) shall be axially deflected at least 7° in any direction and subjected to a hydrostatic pressure of 10 psi (23 ft.) for 10 min.

7.2.3 When the pipe is loaded in shear in accordance with the requirements shown in Fig. 1 and subjected to a hydrostatic pressure of 10 psi (23 ft.) for 10 min.


7.2.4 When the lateral is loaded in shear in accordance with the loading requirements of Fig. 1 and does not exceed 1 in. of axial movement at the connector and subjected to a hydrostatic pressure of 10 psi (23 ft.) for 10 min.

7.2.5 **Caution**—Pressure can be is not prohibited from being relieved while deflecting or loading test section.

7.3 Leakage shall be construed to mean freely dripping water emanating at the interface between the connector and base of the manhole or wastewater structure, or the pipe; between the connector and the filler rings; or through the body of the connector and the filler rings; or through the body of the connector itself.

7.4 Moisture appearing at random locations on the base of the outlet in the form of patches or beads adhering to the surfaces shall not be considered leakage.

7.5 A delay of up to 24 h-can be allowed is not prohibited prior to making observations of leakage.



8. Product Marking

8.1 Each connector shall be marked legibly by the connector manufacturer with his trade name and the size designation or part number.

9. Keywords

9.1 definitions; design test method; marking; material requirements acceptance criteria; product marking; resilient connector

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).