



# Standard Practice for Fabrication of Thermal Insulating Fitting Covers for NPS Piping, and Vessel Lagging<sup>1</sup>

This standard is issued under the fixed designation C 450; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

## 1. Scope

1.1 This practice provides tables of dimensions of preformed insulation that may be used in fabricating covers for use on valves, ells, tees, flanges, and vessels in the pressure range from 150 to 1500 psi (1 to 10 MPa). These tables, which are part of this standard, are published separately as the ASTM Recommended Dimensional Standards for Fabrication of Thermal Insulation Fitting Covers for NPS Piping, and Vessel Lagging. The tables provide dimensions for use in forming pipe fitting covers for NPS pipe operating at high temperature and low temperature. The tables also include dimensions for use in forming thermal insulation into curved segments, and lagging, for application on vessels. This practice does not apply to reflective-type insulation.

1.2 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

1.3 The values stated in inch-pound units are to be regarded as the standard. The values given in parentheses are provided for information purposes only.

## 2. Referenced Documents

### 2.1 ASTM Standards:

C 585 Practice for Inner and Outer Diameters of Rigid Thermal Insulation for Nominal Sizes of Pipe and Tubing (NPS System)<sup>2</sup>

### 2.2 ASTM Adjuncts:

ADJCO450 Recommended Dimensional Standards for Fabrication of Thermal Insulating Fitting Covers for NPS Piping and Vessel Lagging<sup>3</sup>

## 3. Significance and Use

3.1 This system of dimensions provides a guide for forming

thermal insulation in advance of field application. Forming may be done by cutting, grinding, milling, or molding, depending upon the method most suitable for the thermal insulation being fabricated. It is equally applicable for all temperature ranges.

## 4. Apparatus

4.1 Thermal insulation can be formed into shapes by numerous methods. In general, insulations may be cut by circular or band saws, shaped by grinders or millers, or molded. Each method has certain advantages and disadvantages, depending upon the material to be formed, number of cuts required, material waste permissible, and quantity of fittings being produced. Adhesives and fabrication cements can be applied from dip pots, rollers, doctor blades, brush, or trowel, depending upon the materials being used. For these reasons, although standardized equipment may be devised for certain forming functions, no completely standardized equipment recommendation can be suggested.

## 5. Basis of Design

5.1 All dimensions presented are based on the use of pipe insulation manufactured to Practice C 585 and to the Basic Dimensional Standards for Pipe Insulation as given in Tables 1 and Tables 2 of the ASTM Recommended Dimensional Standards for Prefabrication and Field Fabrication of Thermal Insulation Fitting Covers for NPS Piping, and Vessel Lagging.<sup>3</sup>

5.2 The tables provide dimensions for insulation fitting covers for installation on nominal pipe size (NPS) pipe operating at high and low temperatures.

5.3 Dimensions presented for cutting beveled blocks from preformed thermal insulation (lags) are based on blocks 6 in. (152 mm) wide by the thickness required.

5.4 Dimensions given for flanged pairs, flanged fittings, and flanged valves do not allow for flange bolt removal. When bolt removal is required, the covering length over the flange shall be increased as specified by the purchaser.

## 6. Fabrication

6.1 The main body of the insulation fitting may be cut from standard pipe size pipe covering of the proper size and same thickness tolerance as the pipe insulation.

6.2 Where two insulations of different temperature ratings

<sup>1</sup> This practice is under the jurisdiction of ASTM Committee C16 on Thermal Insulation and is the direct responsibility of Subcommittee C16.20 on Homogeneous Inorganic Thermal Insulations.

Current edition approved July 10, 2002. Published November 2002. Originally published as C 450 – 60 T. Last previous edition C 450 – 99<sup>e1</sup>.

<sup>2</sup> *Annual Book of ASTM Standards*, Vol 04.06.

<sup>3</sup> Available at a nominal cost from ASTM Headquarters. Order Adjunct: ADJCO450.

are required, each should be placed in its proper location in the fitting in double layer construction.

6.3 Where only one insulation is required, and it can be obtained in sufficient thickness, multiple layers as indicated are not essential.

6.4 Flat block, cut to proper curvature, may be used in place of preformed pipe insulation. The user should be informed when supplying a fabricated product instead of a molded or preformed pipe insulation, there may result differences in thermal or mechanical performance characteristics of the end product.

6.5 Any method of forming may be used if the resulting fitting conforms to inside and outside dimensions listed.

6.6 Where the body of the flange cover extends over adjacent pipe insulation, the portion of the cover can be made by using the pipe insulation as the body and adding an insert collar. It can also be done by adding an insert or section, commonly called a “dutchman,” made of block.

6.7 Valves manufactured by various companies for the same pressure and nominal pipe size may not have like bonnet dimensions, nor height of bonnet flange above centerline of valve. Because of this, the valve insulation is designed to fit the largest valve of a size, type, and pressure. In some instances, additional insulation may be required to fill or build up the insulation for proper fitting around the bonnet. In other instances it may be necessary to cut back insulation around the bonnet to provide access to the packing gland. Cutout for hand wheel assembly and packing gland should be done at time of application.

## 7. Assembly and Tolerances

7.1 All formed pieces should fit tightly together so that both sides and length of the insulation joint can close within a maximum of  $\frac{1}{16}$  in. (1.6 mm).

7.2 Low-temperature pipe insulation fabricated from block or board stock should contain no more than four cemented “through” joints per full section of insulation, excluding the half section mating plane.

7.3 Finished pieces should be identified by tags, attached strip, etc. for ease of field installation.

7.4 The inner and outer surface of vessel insulation sections should be concentric with the outer surface. The deviation from concentricity should not exceed  $\frac{3}{16}$  in. (5 mm).

7.5 Cements to be used in the fabrication of fitting covers must be specified for each insulation material by the manufacturer of the insulating material.

## 8. Insulation Fabrication Shop Requirements

8.1 Insulation can be shop fabricated by several methods. Each method has certain advantages and disadvantages, depending on the number of pieces to be cut, cuts required,

material properties, and resultant material waste. Fabrication may be by sawing, grinding, routing, or combination thereof. Grinding and routing are generally limited to fabrication of block or board into threaded and socketwelded fittings, such as elbows and tees. Selection of fabrication method should consider any resulting reduction in material physical properties.

8.2 Equipment is commonly improvised, as grinders for fabrication of insulation are not commercially available. The most essential piece of equipment is a band saw. Almost any band saw that can be set at the proper blade speed and has a minimum cutting depth of 22 in. (559 mm) can be used. Essential details are as follows:

8.2.1 *Cutting Blade Speeds*—The proper speed of the band saw blade for cellular glass is approximately 1040 ft/min (317 m/min). Calcium silicates and perlite silicate insulation may be cut at a speed of 1040 ft/min (317 m/min), but somewhat higher speeds will also work satisfactorily.

8.2.2 *Blades for Cutting Cellular Glass*—Band saw blades should be 1 in. (25 mm) wide by 0.035 in. (0.9 mm) thick, flexible-back, three-pitch, raker-tooth blades. These blades have special teeth designated as “P.A.”

8.2.3 *Blades for Cutting Calcium Silicate or Perlite Silicate Fiber Insulation*—Blades should be  $\frac{1}{2}$  in. (13 mm) wide by 0.035 in. (0.9 mm) thick, skip-tooth blades, 5 teeth/in.

8.2.4 *Abrasives for Grinders*—Grinders are sometimes used to form insulation into various shapes. This can be done by hand or machine, by coating a tool (wood or steel) with an abrasive consisting of grit in glue. The recommended grit sizes are No. 16 and No. 24. The finer grit is used for power-driven equipment, and the heavier grit for hand-powered equipment.

## 9. Field Application Sequence

9.1 Insulation coverings for welded or screwed fittings should be applied before the pipe insulation.

9.2 Pipe insulation should be installed up to all flanges, flanged fittings, and flanged valves. Provide sufficient space for future bolt removal where required.

9.3 Covers for flanges, flanged fittings, and flanged valves should be installed so as to extend, not less than specified thickness, over adjacent pipe insulation or minimum 2 in. (50mm).

9.4 Where required, junction of pipe insulation and flanged fittings covers can, by use of nonsetting cements, sealants or other methods, be used as an expansion or contraction joint.

## 10. Keywords

10.1 thermal insulating materials; thermal insulating materials—fabrication; thermal insulating materials—fittings; thermal insulating materials—pipe

*ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.*

*This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.*

*This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or [service@astm.org](mailto:service@astm.org) (e-mail); or through the ASTM website ([www.astm.org](http://www.astm.org)).*