



Designation: C 1526 – 02

Standard Specification for Serpentine Dimension Stone¹

This standard is issued under the fixed designation C 1526; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification covers the material characteristics, physical requirements, and sampling appropriate for the selection of serpentine (serpentine marble) for general building and structural purposes.

1.2 Dimension serpentine shall include stone that is sawed, cut, split, or otherwise finished or shaped and shall specifically exclude molded, cast, or otherwise artificially aggregated units composed of fragments, and also crushed and broken stone.

2. Referenced Documents

2.1 ASTM Standards:

C 97 Test Methods for Absorption and Bulk Specific Gravity of Dimension Stone²

C 99 Test Method for Modulus of Rupture of Dimension Stone²

C 119 Terminology Relating to Dimension Stone²

C 170 Test Method for Compressive Strength of Dimension Stone²

C 241 Test Method for Abrasion Resistance of Stone Subjected to Foot Traffic²

C 880 Test Method for Flexural Strength of Dimension Stone²

C 1353 Test Method for Abrasion Resistance of Stone Subjected to Foot Traffic by the Taber Abrader Method²

3. Terminology

3.1 *Definitions*—All definitions are in accordance with Terminology C 119.

4. Physical Properties

4.1 Serpentine supplied under this specification shall conform to the physical requirements prescribed in Table 1.

4.2 Serpentine shall be free of minerals that may cause objectionable staining under normal environments of use.

4.3 Warping of serpentine due to localized water absorption is a natural characteristic of the material and shall be taken into

TABLE 1 Physical Requirements

Physical Property	Test Requirements	Classifications	Test Methods
Absorption by weight, max, %	0.20 0.60	I Exterior II Interior	C 97
Density, min, lb/ft ³ (kg/m ³)	160 (2560)	I, II	C 97
Compressive strength, min, psi (MPa)	10000 (69)	I, II	C 170
Modulus of rupture, min, psi (MPa)	1000 (6.9)	I, II	C 99
Abrasion resistance, min, $H_a^{A,B,C}$	10	I, II	C 241/C 1353
Flexural strength, min, psi (MPa)	1000 (6.9)	I, II	C 880

^A Pertains to foot traffic only. Where two or more stone varieties are combined for color and design effects, there should be no greater difference than five points in abrasion resistance.

^B The supplier of the No. 60 Alundum abrasive, Norton, has indicated that the formula for Norton treatment 138S has been changed. The new abrasive is currently more aggressive, resulting in lower abrasion resistance values (H_a) than when the standard was initially established. As such, care should be taken when interpreting H_a values from tests using the new abrasive, particularly with regard to current ASTM stone standard specification requirements for abrasion resistance, which were developed when the original abrasive was still in use.

^C It is not necessary to perform both tests. Availability of the proper equipment and materials by the testing laboratory may determine which test is performed.

account in assessing the permissible natural variations suitable for a particular application. Setting serpentine with a non-water-based setting material in a full-coverage setting bed over a rigid substrate can prevent warping from occurring after installation.

4.4 Alteration of the color and finish of serpentine with exposure to the weather can occur and shall be taken into account in assessing the suitability of serpentine for a particular application. Alteration of serpentine, due to weather exposure, can result in whitish mineral deposits on the surface of the stone and can also result in a faded appearance and loss of polish.

4.5 The desired color and texture, with their permissible natural variations in material characteristics for material to be produced for the project, shall be established by control samples. Representative samples shall be selected prior to production by viewing a sufficient number of samples that show the complete range of variations in color and texture of the serpentine specified.

5. Sampling

5.1 Samples, if required, for testing to determine the characteristics and physical properties shall be representative of the serpentine to be used.

¹ This specification is under the jurisdiction of ASTM Committee C18 on Dimension Stone and is the direct responsibility of Subcommittee C18.03 on Material Specifications.

Current edition approved Oct. 10, 2002. Published November 2002.

² *Annual Book of ASTM Standards*, Vol

**NOTICE: This standard has either been superceded and replaced by a new version or discontinued.
Contact ASTM International (www.astm.org) for the latest information.**



ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).