



Standard Specification for Materials for Soil-Aggregate Subbase, Base, and Surface Courses¹

This standard is issued under the fixed designation D 1241; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

1. Scope *

1.1 This specification covers the quality and grading of the following materials for use in the construction of subbase, base, and surface courses: sand-clay mixtures; gravel; stone or slag screenings; sand; crusher-run coarse aggregate consisting of gravel, crushed stone, or slag combined with soil mortar; or any combination of these materials. The requirements are intended to cover only materials having normal or average specific gravity, absorption, and gradation characteristics. Where other materials are to be used, appropriate limits suitable to their use must be specified.

1.2 The following precautionary caveat pertains only to the Test Methods portion, Section 9, of this specification. *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:

- C 117 Test Method for Material Finer than 75- μ m (No. 200) Sieve in Mineral Aggregates by Washing²
- C 131 Test Method for Resistance to Degradation of Small-Size Coarse Aggregate by Abrasion and Impact in the Los Angeles Machine²
- C 136 Test Method for Sieve Analysis of Fine and Coarse Aggregates
- D 75 Practice for Sampling Aggregates³
- D 420 Guide to Site Characterization for Engineering, Design, and Construction Purposes⁴
- D 421 Practice for Dry Preparation of Soil Samples for

Particle-Size Analysis and Determination of Soil Constants⁴

D 653 Terminology Relating to Soil, Rock, and Contained Fluids⁴

D 3740 Practice for Minimum Requirements for Agencies Engaged in the Testing and/or Inspection of Soil and Rock as Used in Engineering Design and Construction⁴

D 4318 Test Method for Liquid Limit, Plastic Limit, and Plasticity Index of Soils⁴

3. Terminology

3.1 For definitions of terms in this standard, refer to Terminology D 653.

4. Types

4.1 The following types of mixtures are specified:

4.1.1 *Type I*—Mixtures consisting of stone, gravel, or slag with natural or crushed sand and fine mineral particles passing a No. 200 (75- μ m) sieve and conforming to the requirements of Table 1 for Gradation A, B, C, or D.

4.1.2 *Type II*—Mixtures consisting of natural or crushed sand with fine mineral particles passing a No. 200 (75- μ m) sieve, with or without stone, gravel, or slag, and conforming to the requirements of Table 1 for Gradation E or F.

5. General Requirements

5.1 *Coarse Aggregate*—Coarse aggregate retained on a No. 10 (2.00-mm) sieve, for use in Type I and Type II mixtures, shall consist of hard, durable particles or fragments of stone, gravel, sand, or slag; materials that break up when alternately frozen and thawed or wetted and dried shall not be used. Coarse aggregate shall have a percentage of wear, by the Los Angeles Abrasion (Test Method) test, of not more than 50.

NOTE 1—A higher or lower percentage of wear may be specified by the engineer, depending upon the materials available for the work.

5.2 *Fine Aggregate*—Fine aggregate passing a No. 10 (2.00-mm) sieve, for use in Type I and Type II mixtures, shall consist of natural or crushed sand and fine mineral particles passing the No. 200 (75- μ m) sieve. The fraction passing the No. 200 sieve shall not be greater than two thirds of the

¹ This specification is under the jurisdiction of ASTM Committee D18 on Soil and Rock and is the direct responsibility of Subcommittee D18.08 on Special and Construction Control Tests.

Current edition approved Nov. 10, 2000. Published February 2001. Originally issued 1952. Replaces D556, D557, D1241 – 64 T. Last previous edition D 1241 – 68 (1994)¹.

² *Annual Book of ASTM Standards*, Vol 04.02.

³ *Annual Book of ASTM Standards*, Vol 04.03.

⁴ *Annual Book of ASTM Standards*, Vol 04.08.

*A Summary of Changes section appears at the end of this standard.

TABLE 1 Gradation Requirements for Soil-Aggregate Materials

Sieve Size (Square Openings)	Weight Percent Passing Square Mesh Sieves					
	Type I				Type II	
	Gradation A	Gradation B	Gradation C	Gradation D	Gradation E	Gradation F
2-in. (50-mm)	100	100
1-in. (25.0-mm)	...	75 to 95	100	100	100	100
3/8-in. (9.5-mm)	30 to 65	40 to 75	50 to 85	60 to 100
No. 4 (4.75-mm)	25 to 55	30 to 60	35 to 65	50 to 85	55 to 100	70 to 100
No. 10 (2.00-mm)	15 to 40	20 to 45	25 to 50	40 to 70	40 to 100	55 to 100
No. 40 (425- μ m)	8 to 20	15 to 30	15 to 30	25 to 45	20 to 50	30 to 70
No. 200 (75- μ m)	2 to 8	5 to 15	5 to 15	8 to 15	6 to 15	8 to 15

fraction passing the No. 40 (425- μ m) sieve as determined by Test Method . The fraction passing the No. 40 sieve shall have a liquid limit not greater than 25 and a plasticity index not greater than 6 as determined by Test Method .

5.3 The composite soil-aggregate material of Types I and II shall be free of vegetable matter and lumps or balls of clay and shall conform to the grading requirements of Table 1.

6. Subbase Materials

6.1 Soil-aggregate materials for subbase shall conform to the requirements of Section 5 and Table 1 for Type I, Gradation A, B, C, or D, or for Type II, Gradation E or F. The type and grading desired shall be specified.

NOTE 2—Where local experience has shown that, in order to prevent damage by frost action, it is necessary to have lower percentages of the subbase materials passing the No. 200 (75- μ m) sieve than are required by Table 1, the engineer should specify such lower percentages.

7. Base-Course Materials

7.1 Soil-aggregate materials for base course shall conform to the requirements of Section 5 and Table 1 for Type I, Gradation A, B, C, or D, or for Type II, Gradation E or F. The type and grading desired shall be specified.

NOTE 3—Where local experience has shown that, in order to prevent damage by frost action, it is necessary to have lower percentages of the base-course materials passing the No. 200 (75- μ m) sieve than are required by Table 1, the engineer should specify such lower percentages.

8. Surface-Course Materials

8.1 Soil-aggregate materials for surface course shall conform to the requirements of Section 5 and Table 1 for Type I, Gradation C or D; or for Type II Gradation E or F. The type and grading shall be specified.

NOTE 4—Where it is planned that the soil-aggregate surface course is to be maintained for several years without bituminous surface treatment or other superimposed impervious surfacing, the engineer should specify a minimum of 8 % passing the No. 200 (75- μ m) sieve instead of the minimum percentages shown in Table 1 for Gradation C, D, or E, and should specify a maximum liquid limit of 35 and plasticity index range from 4 to 9, instead of the limits given in 5.2.

9. Test Methods

9.1 Sample the material and determine the properties enumerated in this specification in accordance with the following ASTM standards:

9.1.1 *Sampling*—Practice D 75.³

9.1.2 *Sieve Analysis*—Test Method C 117², and Test Method C 136.²

9.1.3 *Percentage of Wear*—Test Method C 131.²

9.1.4 *Surveying and Sampling Soils for Highway Subgrades*—Guide D 420.⁴

9.1.5 *Preparing Soil Samples*—Method D 421.⁴

9.1.6 *Liquid Limit, Plastic Limit, and Plasticity Index*—Test Method D 4318.⁴

NOTE 5—The precision of these test methods is dependent on the competence of the personnel performing them and the suitability of the equipment and facilities used. Agencies that meet the criteria of Practice D 3740 are generally considered capable of competent and objective testing. Users of these test methods are cautioned that compliance with Practice D 3740 does not in itself assure reliable testing. Reliable testing depends on many factors; Practice D 3740 provides a means of evaluating some of those factors.

10. Keywords

10.1 acceptance tests; base courses; coarse aggregates; cohesionless soils; crushed stones; earth materials; fills; gradation; granular materials; gravels; soil-aggregate materials.

SUMMARY OF CHANGES

In accordance with Committee D18 policy, this section identifies the location of changes to this standard since the last edition (1994) that may impact the use of this standard.

- (1) Added Terminology, Section 3.
- (2) In Referenced Documents, Section 2, added Standards D 653, and D 3740.
- (3) In Test Methods, Section 9, added new note on the use of D 3470.
- (4) Dropped Sections 8 and 9.
- (5) In Keywords, Section 10, revised list.

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).