



Standard Specification for Petroleum Used for Blending with Creosote^{1, 2}

This standard is issued under the fixed designation D 1859; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last approval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification covers petroleum for blending with creosote conforming to Specification D 390, for use in the preservative treatment of timber.

2. Referenced Documents

2.1 ASTM Standards:

D 88 Test Method for Saybolt Viscosity³

D 93 Test Methods for Flash Point by Pensky–Martens Closed Cup Tester⁴

D 96 Test Methods for Water and Sediment in Crude Oils by Centrifuge Method (Field Procedure)⁴

D 270 Methods of Sampling Petroleum and Petroleum Products⁵

D 445 Test Method for Kinematic Viscosity of Transparent and Opaque Liquids (and the Calculation of Dynamic Viscosity)⁶

D 1298 Test Method for Density, Relative Density (Specific Gravity), or API Gravity of Crude Petroleum and Liquid Petroleum Products by Hydrometer Method⁴

2.2 Other Standard:

AWPA P4 Standard for Petroleum Oil for Blending with Creosote⁶

3. Properties

3.1 Petroleum for blending with creosote shall conform to the following requirements:

Specific gravity, 60/60°F (16/16°C), min		0.96 ^A
Water and sediment, max, %		1
Flash point, min, °F (°C)		175 (79)
	min	4.2
Viscosity at 210°F, kinematic, cSt	max	10.2
	min	40
Viscosity at 210°F, Saybolt, SUS	max	60

^A Unless experience or test shows that a petroleum of lower specific gravity may be used without the formation of excessive sludge.

4. Sampling and Test Methods

4.1 Determine the sampling and properties enumerated in this specification in accordance with the following ASTM methods:

4.1.1 *Sampling*—Methods D 270.

4.1.2 *Specific Gravity*—Test Method D 1298.

4.1.3 *Water and Sediment*—Test Methods D 96.

4.1.4 *Flash Point*—Test Methods D 93.

4.1.5 *Viscosity*—Test Method D 88, and Test Method D 445.

5. Keywords

5.1 blending; creosote; petroleum

¹ This specification is under the jurisdiction of ASTM Committee D-7 on Wood and is the direct responsibility of Subcommittee D07.06 on Treatments for Wood Products.

Current edition effective Feb. 24, 1971. Originally issued 1961. Replaces D1859 – 63.

² This specification is essentially the same as the American Wood-Preservers' Assn. Standard for Petroleum for Blending with Creosote (P4-86). Acknowledgment is made to the American Wood-Preservers' Association for its development of the subject matter covered in this standard.

³ *Annual Book of ASTM Standards*, Vol 04.04.

⁴ *Annual Book of ASTM Standards*, Vol 05.01.

⁵ Discontinued; see 1983 *Annual Book of ASTM Standards*, Vol 05.01.

⁶ Available from American Wood-Preservers' Assn., 3246 Fall Creek Highway, Suite 190, Granbury, TX 76049.

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).