

This document is not an ASTM standard and is intended only to provide the user of an ASTM standard an indication of what changes have been made to the previous version. Because it may not be technically possible to adequately depict all changes accurately, ASTM recommends that users consult prior editions as appropriate. In all cases only the current version of the standard as published by ASTM is to be considered the official document.



Designation: D 1640 – 95 (Reapproved 1999)



Designation: D 1640 – 03

Standard Test Methods for Drying, Curing, or Film Formation of Organic Coatings at Room Temperature¹

This standard is issued under the fixed designation D 1640; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

¹ These test methods are under the jurisdiction of ASTM Committee D1 D01 on Paint and Related Coatings, Materials, and Applications and are the direct responsibility of Subcommittee D01.23 on Physical Properties of Applied Paint Film.

Current edition approved Feb. 15, 1995; Dec. 1, 2003. Published April 1995. Originally published as D 1640 – 59 T, approved in 1959. Last previous edition D 1640 – 83 (1989) ϵ 1, approved in 1995 as D 1640 – 95 (1999).

1. Scope

1.1 These test methods cover the determination of the various stages and rates of film formation in the drying or curing of organic coatings normally used under conditions of ambient room temperature.

1.2 The values stated in ~~inch-pound~~ SI units are to be regarded as the standard. The values given in parentheses are for information only.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 *ASTM Standards:*²

D-202 Test Methods of Sampling and Testing Untreated Paper Used 823 Practices for Electrical Insulation²

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards*, Vol 10.01, volume information, refer to the standard's Document Summary page on the ASTM website.

~~D 823 Practices for Producing Films of Uniform Thickness of Paint, Varnish, and Related Products on Test Panels~~

~~D 1005 Test Methods for Measurement of Dry-Film Thickness of Organic Coatings Using Micrometers~~

~~D 2091 Test Method for Print Resistance of Lacquers³~~

~~2.2 U.S. Government Standards:~~

Annual Book

³ See Prane, J. W., "A Latin Square Drying Time Study," *Paint Industry Magazine* (August 1961), for a study of ASTM Standards, Vol 06.02, precision of drying time measurements.

Fed. Spec. No. CCC-C-440, Cheesecloth⁴

Fed. Spec. No. CCC-C-419b, Type III, Army Duck⁵

2.3 TAPPI Standards⁴

F 402 Standard Conditioning and Testing Atmospheres for Paper, Board, Pulp Handsheets, and Related Products

3. Significance and Use

3.1 These test methods are used to determine the various stages and rates of drying, curing, and film formation of organic coatings for the purpose of comparing types of coatings or ingredient changes, or both. This is significant in the development of organic coatings for various end uses and also for production quality control.

4. Coatings and Recommended Film Thicknesses

4.1 Whenever tests are to be performed on coatings not listed in Table 1, there should be a prior agreement between the purchaser and seller as to the substrate, film thickness, and application method for testing the specific coating involved.

5. Test Conditions

5.1 Conduct all drying tests in a well-ventilated room or chamber, free from direct drafts (Note 1), drafts, dust, products of combustion, laboratory fumes and under diffused light (see 5.4). Make all measurements at a temperature of $23 \pm 2^\circ\text{C}$ and $50 \pm 5\%$ relative humidity with the coated panels in a horizontal position while drying. ~~NOTE 1—A device to equalize air change conditions has been developed by F. Seofield.⁴ Relative humidity should be controlled for moisture-cured and two-package urethane coatings, since their cure is greatly affected by the existing moisture conditions.~~

5.2 Tests should be carried out at practical viscosities at which films can be applied to the proper film thickness with resultant good flow and leveling properties. In the absence of any specific material specification, instructions for preparation of the film should be determined and agreed upon between the purchaser and the seller.

5.3 Films to be tested should have practical thicknesses commensurate with performance characteristics expected under actual usage for the type under test. All testing should be done within an area, any point of which is not less than 15 mm (1/2 in. (15 mm) in.) from the film edge.

5.4 *Light Conditions*—Illumination of the films during the entire drying test period ~~should be about 25 ft-candles (270 lx)~~ from normal laboratory or sky sources, never from direct sunlight or other sources high in nonvisible radiant energy.

6. Preparation of Test Specimens

6.1 Carry out all tests as described in 6.1.1, 6.1.2 and 6.1.3, unless otherwise noted.

6.1.1 All test specimens shall be prepared and tested by one operator properly skilled in the methods to be used. Apply the specimens in duplicate at a time arranged so that examination intervals will fall within the normal working hours of the operator.

6.1.2 Apply the materials to be tested on clean glass panels or other specific substrate of suitable dimensions agreed upon between the purchaser and the seller. Ground-glass plates are more suitable for certain types of coatings that tend to crawl, such as low-viscosity drying oils. Suitable plates can be prepared by roughening the surface of polished glass by grinding a paste of silicon carbide (grit 1-F) and water between two glass plates.

6.1.3 The test films preferably shall be cast with a doctor blade having a clearance sufficient to give the recommended dry film thickness indicated in Table 1. When a suitable doctor blade is not available, or it has been agreed upon to apply the film in some other manner, the various conventional and automatic methods of spray, dip, flow, and brush application may be used, provided dry film thicknesses conform to the requirements given in Table 1. See Practices D 823 for a description of the spray and dip methods of application.

6.1.4 Measure the dry film thickness of test films with the proper film thickness gage. This shall be a micrometer, dial comparator, or dial indicator as described in Test Methods D 1005. When plates of small area are used, measurement of dry film thickness can be made by weighing plates before and after coating and calculating from plate area and coating solids.

TABLE 1 Recommended Film Thickness of Materials to be Tested^A

Material	Dry Film Thickness
Drying oils	1.25 ± 0.25 mil (32 ± 6 μm) ^B
Varnishes	1 ± 0.1 mil (25 ± 2 μm) (See 7.4.2)
Varnishes	1 ± 0.1 mil (25 ± 2 μm)
Lacquers	0.5 ± 0.1 mil (12.5 ± 2 μm) (See 7.5.2)
Resin solutions	0.5 ± 0.1 mil (12.5 ± 2 μm)
Enamels	1.5 ± 0.25 mil (36.5 ± 6 μm)
Oil paints	1.8 ± 0.2 mil (45 ± 2.5 μm) (See 6.1.2)
Water paints	1 ± 0.1 mil (25 ± 2 μm)

^AThis table is a general guide to be used when nothing more specific is agreed upon between the purchaser and the seller.

^BSee 6.1.2 and 7.5.1. Add driers a minimum of 24 h before test.

7. Procedure

7.1 When test methods or end points other than those listed in 7.2-7.9~~8~~ are used, there shall be a prior agreement between the purchaser and the seller.

7.2 *Set-To-Touch Time*—To determine set-to-touch time, lightly touch the test film with the tip of a clean finger and immediately place the fingertip against a piece of clean, clear glass. Observe if any of the coating is transferred to the glass. For the purpose of this test, the pressure of the fingertip against the coating shall not be greater than that required to transfer a spot of the coating from 3 to 5 mm ($\frac{1}{8}$ to $\frac{3}{16}$ in. ~~(3 to 5 mm)~~ in.) in cross section. The film is set-to-touch when it still shows a tacky condition, but none of it adheres to the finger.

7.3 *Dust-Free Times:*

7.3.1 *Cotton Fiber Test Method*—Separate a number of individual fibers from a mass of absorbent cotton with the aid of tweezers. At regular drying intervals, drop several of the cotton fibers from a height of ~~1 in. (25 mm)~~ 25 mm (1 in.) onto a marked section of the film. The film is considered to have dried dust free when the cotton fibers can be removed by blowing lightly over the surface of the film.

7.4 *Tack-Free Times:*

7.4.1 *Paper Test Method:*

7.4.1.1 *Test Paper*—The test paper shall be K-4 Power Cable Paper⁴ that when conditioned in accordance with the TAPPI Standard Method T 402, conforms to the following requirements:

Basis weight (24 by 36/500), lb	90 ± 5
Thickness, mils (µm)	6.65 (17)
Air resistance (s/100 cm ² /in. ²)	350
Coefficient of static friction ⁴	0.5
Friction angle, °	22
Tensile strength, machine direction/cross direction	449/32
Tear, machine direction/cross direction	180/250
Elongation, machine direction/cross direction, %	3.0/7.0
pH of water extract	7-4
Ash content, max, %	0.6

⁴All tests except this one shall be run in accordance with Test Method D 202.

All values for properties are typical values and not specification limits.

7.4.1.2 Lay a 2 by 3 in. (50 by 75 mm) piece of the special test paper on the film and place upon it a steel cylinder 2 in. in diameter, and of such weight 6.28 lb, (2.85 kg), as to produce a pressure of 2 psi (13.8 kPa). At the end of 5 s, remove the cylinder and invert the test panel. The film is considered free from after-tack when the paper drops off of the test film within 10 s.

7.4.2 A variation of the test method described in 7.4.1 using the same test paper can be used to test the tack-free time of insulating varnishes. In this method the piece of paper shall be 1½ in. (40 mm) in width and 6 in. (150 mm) in length. The varnish is considered tack-free when this strip of paper does not adhere to it when it is pressed on the surface of the varnish for 1 min by a cylindrical 1-lb (450-g) weight, 1 in. (25 mm) in diameter. In this test, apply the paper in the vicinity of the center of the specimen at right angles to the length of the coated specimen.

7.4.3 *Mechanical Test Method (Tack Tester)*—The⁴—The tack tester to be used in this method comprises essentially a base or surface-contacting portion 1 in. (25 mm) 25-mm (1-in.) square and a counter-balancing portion 1 25 by 2 in. (25 by 50 mm (1 by 2 in.) in area. Both portions are made up from a continuous metal strip 0.016 0.41 to 0.018 in. (0.41 to 0.46 mm (0.016 to 0.018 in.) in thickness. To prepare the apparatus for use (see 7.4.31.1), fit the base with several thicknesses of masking tape and paper strips to provide a means of attaching the aluminum foil and so adjust the angle of the 1 by 2-in. counter-balancing strip so that a weight of 5 g placed in the geometric center of the base portion is just sufficient to overcome the unbalanced force.

7.4.31.1 The tester is prepared for use by carrying out the following steps in sequence:

- (1) Wrap the metal base with three thicknesses of masking tape, sticky side out,
- (2) Cover the outer layer with a good grade of paper, except for two exposed strips, equally spaced, about ¼ by 1 in. (6.4 by 25 mm) in area on the top of the tester, and
- (3) Cover the paper on the contact side of the base with one thickness of pressure-sensitive cellulose tape previously fixed to the metal base of the tester. The cellulose tape serves two purposes:

First, to pull the layers of masking tape firmly against the front of the metal base, and

Second, to provide a smooth surface for the foil. Attach the aluminum foil to the base of the tester by pressing gently but firmly a 1 25 by 2 in. (25 50-mm (1 by 50-mm) 2-in.) piece of foil, 0.0005 in. (13 µm) 13 µm (0.0005 in.) in thickness against one of the 6.4 by 25-mm (¼ by 1-in. (6.4 by 25-mm) 1-in.) exposed strips of masking tape on the top surface of the base. Wrap the foil tightly and smoothly around the base, exposing the shiny side, and finally press the outer end gently against the remaining exposed strip of masking tape. When it finally becomes necessary to replace wrinkled or soiled aluminum foil, the ends are easily removed from the masking tape by exerting a slow, even, upward pull sufficient to overcome the tack of the tape without tearing the foil.

7.4.31.2 A film is considered to have dried tack-free when the tack tester tips over immediately on removing a 300-g weight allowed to act for 5 s on the counter-weighted metal square base fitted with masking tape and aluminum foil.

Annual Book of ASTM Standards, Vol 06.01.

⁴ The standard tack tester is fully described in the U.S. Patent 2,406,989, Sept. 3, 1946.

7.5 *Dry-To-Touch Time:*

7.5.1 *Drying Oils*—Continue testing after the set-to-touch time has been observed. The film is considered dry when it no longer adheres to the finger and does not rub up appreciably when the finger is lightly rubbed across the surface.

7.5.2 *Lacquers (and Sealers)*—Touch the film lightly at varying intervals of time. The film is considered dry when no pronounced marks are left by the finger touching the film in the same area on each observation. Test sealers on wood or other porous substrates as agreed upon between the purchaser and the seller.

7.6 *Dry-Hard Time:*

7.6.1 With the end of the thumb resting on the test film and the forefinger supporting the test panel, exert a maximum downward pressure (without twisting) of the thumb on the film. Lightly polish the contacted area with a soft cloth. The film is considered dry-hard when any mark left by the thumb is completely removed by the polishing operation.

7.7 *Dry-Through (or Dry-To-Handle) Time:*

7.7.1 Place the test panel in a horizontal position at a height such that when the thumb is placed on the film, the arm of the operator is in a vertical line from the wrist to the shoulder. Bear down on the film with the thumb, exerting the maximum pressure of the arm, at the same time turning the thumb through an angle of 90° in the plane of the film. The film is considered dry-through or dry-to-handle when there is no loosening, detachment, wrinkling, or other evidence of distortion of the film.

7.8 *Dry-To-Recoat:*

7.8.1 A film is considered dry for recoating when a second coat or specified topcoat can be applied without the development of any film irregularities such as lifting or loss of adhesion of the first coat, and the dry time of the second coat does not exceed the maximum specified (if any) for the first coat.

7.9 *Print-Free Time:*

NOTE 2—This procedure is similar to Test Method D 2091, except that the time to reach the print-free condition is determined, while Test Method D 2091 is used to evaluate whether a film is print free at a specified time.

7.9.1 *Test Panels*—Apply the material under test to clean plane panels, at least 3 by 6 in. (75 by 150 mm) in size, made of wood, metal, glass, plastic or other material as agreed upon between the purchaser and the seller.

7.9.2 *Imprinting Fabric*—Eight-ounce Army duck conforming to Type III of U.S. Fed. Spec. No. CCC-C-419b or cheesecloth conforming to Fed. Spec. No. CCC-C-440.

7.9.2.1 A pad should be used with the cheesecloth only, made of nonwoven felt cloth at least 0.05 in. (1.3 mm) thick, weighing 7 oz/yd² (0.24 kg/m²) and larger than the plane end of the weight.

7.9.3 *Weights*—Consisting of metal cylinders not less than 2 in. (50 mm) in diameter with plane ends perpendicular to the axis and of a length to give a pressure of ½ or 1 lb/in.² (3.5 or 6.9 kPa).

7.9.4 *Procedure:*

7.9.4.1 Apply the test material to several of the specified or agreed upon panels by a film applicator, or other specified method, as described in Practices D 823 in either single or multiple coats, as agreed upon between the purchaser and the seller. In the absence of a specified dry film thickness, the values listed in Table 1 should be used.

7.9.4.2 Allow the coated panels to dry under the conditions specified in Section 5, unless otherwise agreed. At appropriate intervals, starting shortly before the coating is expected to be print-free, carry out the print-free test as described in Test Method D 2091, comparing the appearance with the photographic standards appearing therein, until the test shows the coating to be print-free.

8. Frequency of Testing

8.1 It is suggested that test intervals be set at periods of approximately 10 % of the total test time. If frequency varies considerably from the 10 % interval or such time interval is impractical, the intervals used shall be reported.

9. Report

9.1 Reports of tests shall include all applicable conditions that deviated from the standards as outlined or special conditions or tests used and the results of the test.

10. Precision and Bias

10.1 Because of the subjective nature of the drying time tests, the agreement to be expected between laboratories depends upon their understanding of the terms used, and is difficult to establish with certainty. Within any laboratory, the agreement depends upon the material being tested, some coatings being much sharper in their end point than others, but duplicate determinations should agree within 10 % of the time of drying.³

10.2 *Bias*—These test methods have no bias because the value for dry times are defined only in terms of these test methods.

11. Keywords

11.1 drying time

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).