



Designation: D 2119 – 96

Standard Test Method for Aldehydes in Styrene Monomer¹

This standard is issued under the fixed designation D 2119; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method covers the determination of aldehydes in styrene monomer. Aldehydes are calculated and reported as benzaldehyde.

1.2 The following applies to all specified limits in this test method: for purposes of determining conformance with this test method, an observed value or a calculated value shall be rounded off “to the nearest unit” in the last right-hand digit used in expressing the specification limit, in accordance with the rounding-off method of Practice E 29.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.* For specific hazard statements, see Section 7.

2. Referenced Documents

2.1 ASTM Standards:

D 1193 Specification for Reagent Water²

D 3437 Practice for Sampling and Handling Liquid Cyclic Products³


E 29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications⁴

2.2 Other Documents:

OSHA Regulations, 29 CFR, paragraphs 1910.1000 and 1910.1200⁵

3. Summary of Test Method

3.1 An alcoholic solution of hydroxylamine hydrochloride is added to a specimen of styrene monomer. Active aldehydes present react in accordance with the following equation:



The hydrochloric acid, which is equivalent to the aldehyde

present in the sample, is titrated with standard sodium hydroxide solution. Ketones, if present, interfere by partially reacting with the reagent.

4. Significance and Use

4.1 This test method is suitable for determining the quantity of aldehydes, both for quality control and quality assurance of the product.

5. Apparatus

5.1 *Erlenmeyer Flasks*, glass-stoppered, 250-mL.

5.2 *Pipets*, 25-mL.

5.3 *Volumetric Flasks*, 100-mL.

5.4 *Burets*, 10-mL. (Microburets are preferred.)

5.5 *Thermometers*, capable of differentiating 1°C at ambient.

6. Reagents

6.1 *Purity of Reagents*—Reagent grade chemicals shall be used in all tests. Unless otherwise indicated, it is intended that all reagents conform to the specifications of the Committee on Analytical Reagents of the American Chemical Society where such specifications are available.⁶ Other grades may be used, provided it is first ascertained that the reagent is of sufficiently high purity to permit its use without lessening the accuracy of the determination.

6.2 *Purity of Water*—Unless otherwise indicated, references to water shall be understood to mean reagent water as defined by Type III of Specification D 1193.

6.3 *Hydrochloric Acid, Standard (0.05 N)*—Prepare a 0.05 N solution of hydrochloric acid (HCl) by diluting 4.15 mL of concentrated HCl (density 1.19 g/mL) to 1 L with water.

6.4 *Hydroxylamine Hydrochloride Solution*—Dissolve 20 g of hydroxylamine hydrochloride (NH₂OH·HCl) in 1 L of methanol and neutralize to the red-yellow end point of thymol blue indicator.

6.5 *Methanol*.

6.6 *Sodium Hydroxide, Standard Solution (0.05 N)*—Dissolve 2.00 g of low-carbonate sodium hydroxide (NaOH) in

¹ This test method is under the jurisdiction of ASTM Committee D16 on Aromatic Hydrocarbons and Related Chemicals and is the direct responsibility of Subcommittee D16.07 on Styrene, Ethylbenzene, and C₉ and C₁₀ Aromatic Hydrocarbons.

Current edition approved June 10, 1996. Published August 1996. Originally published as D 2119 – 62 T. Last previous edition D 2119 – 87 (1992) ^ε1.

² *Annual Book of ASTM Standards*, Vol 11.01.

³ *Annual Book of ASTM Standards*, Vol 06.04.

⁴ *Annual Book of ASTM Standards*, Vol 14.02.

⁵ Available from Superintendent of Documents, U.S. Government Printing Office, Washington, DC 20402.

⁶ *Reagent Chemicals, American Chemical Society Specifications*, American Chemical Society, Washington, DC. For suggestions on the testing of reagents not listed by the American Chemical Society, see *Analar Standards for Laboratory Chemicals*, BDH Ltd., Poole, Dorset, U.K., and the *United States Pharmacopeia and National Formulary*, U.S. Pharmaceutical Convention, Inc. (USPC), Rockville, MD.



D 2119

water and dilute to 1 L. Standardize against primary standard benzoic acid.

6.7 *Thymol Blue Indicator Solution*— Dissolve 0.1 g of thymol sulfonphthalein, sodium salt, in water and dilute to 100 mL.

7. Hazards

7.1 Consult the latest OSHA regulations, supplier's Material Safety Data Sheets, and local regulations regarding all materials used in this test method.

7.2 Styrene monomer is flammable and polymerizes exothermally on contact with peroxides, mineral acids, and AlCl_3 .

8. Sampling

8.1 Collect the sample as directed in Practice D 3437.

9. Procedure

9.1 Pipet 25.0 mL of the sample (**Warning**—see 7.2) into a 250-mL glass-stoppered Erlenmeyer flask containing 25 mL of methanol. Record the temperature of the sample. Add 0.2 mL of thymol blue indicator and, if necessary, neutralize with 0.05 N NaOH solution or 0.05 N HCl to the red-yellow end point (do not record). Add 25 mL of the neutralized hydroxylamine hydrochloride solution and allow to stand 1 h, shaking the flask occasionally. Titrate to the original red-yellow end point with 0.05 N NaOH solution, dispensed from a 10-mL buret, and record the volume used. Let stand 1 h and again titrate any acid that may have been liberated. Record the total volume of NaOH used.

9.2 Since methanol may contain aldehydes, run a blank determination on 25 mL of methanol.

10. Calculation

10.1 Calculate the percentage of aldehydes as benzaldehyde as follows:

$$\text{Aldehydes, \%} = [(A - B)N \times 0.106] / 25C \times 100$$

where:

A = NaOH solution required for titration of the specimen, mL,

B = NaOH solution required for titration of the methanol blank, mL,

N = normality of NaOH solution used, and

C = density of styrene monomer.

11. Report

11.1 Report the aldehydes content to the nearest 0.001 %.

12. Precision

12.1 *Intermediate Precision (formerly called Repeatability)*—Duplicate results by the same operator should not be considered suspect (95 % confidence limit) unless they differ by more than the following:

Aldehyde Content, %	Repeatability, %
0.004	0.0006

12.2 *Reproducibility*—The averages of duplicate results submitted by each of two laboratories should not be considered suspect (95 % confidence limit) unless they differ by more than the following:

Aldehyde Content, %	Reproducibility, %
0.004	0.0016

13. Keywords

13.1 aldehyde content; aldehydes in styrene; styrene

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).