



## Standard Specification for Glacial Methacrylic Acid<sup>1</sup>

This standard is issued under the fixed designation D 3845; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

### 1. Scope

1.1 This specification covers glacial methacrylic acid (98.5 % grade) for use in paint, varnish, lacquer, and related products.

1.2 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

1.3 For hazard information and guidance, see the supplier's Material Safety Data Sheet.

### 2. Referenced Documents

#### 2.1 ASTM Standards:

D 1209 Test Method for Color of Clear Liquids (Platinum-Cobalt Scale)<sup>2</sup>

D 1364 Test Method for Water in Volatile Solvents (Karl Fischer Reagent Titration Method)<sup>2</sup>

D 3125 Test Method for Monomethyl Ether of Hydroquinone in Colorless Monomeric Acrylate Esters and Acrylic Acid<sup>2</sup>

E 300 Practice for Sampling Industrial Chemicals<sup>3</sup>

E 301 Test Method for Total Acidity of Organic Acids<sup>3</sup>

#### 2.2 U.S. Federal Specification:

PPP-C-2020 Chemicals, Liquid, Dry, and Paste: Packaging of<sup>4</sup>

### 3. Properties

3.1 Glacial methacrylic acid shall conform to the following requirements.

Assay, from total acidity by titration, weight %, min	98.5
Water, weight %, max	0.30
Color, Pt-Co scale, max	25
Inhibitor, methyl ether of hydroquinone	<sup>A</sup>

<sup>A</sup> As agreed upon between the purchaser and the manufacturer.

### 4. Sampling

4.1 Sample the material in accordance with Practice E 300. Use brown glass sample bottles and protect samples from light and heat at all times.

### 5. Test Methods

5.1 The properties enumerated in this specification shall be determined in accordance with the following ASTM methods:

5.1.1 *Assay, from Total Acidity by Titration*—Test Method E 301. The molecular weight of methacrylic acid is 86.09 and it has one reacting group.

5.1.2 *Water*—Test Method D 1364.

5.1.3 *Color*—Test Method D 1209.

5.1.4 *Inhibitor*—Test Method D 3125.

### 6. Packaging and Package Marking

6.1 Package size shall be agreed upon between the purchaser and the supplier.

6.2 Packaging shall conform to applicable carrier rules and regulations or when specified shall conform to Fed. Spec. PPP-C-2020.

### 7. Keywords

7.1 glacial methacrylic acid

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee D-1 on Paint and Related Coatings, Materials, and Applications and is the direct responsibility of Subcommittee D01.35 on Solvents, Plasticizers, and Chemical Intermediates.

Current edition approved May 10, 1996. Published July 1996. Originally published as D 3845 – 79. Last previous edition D 3845 – 89.

<sup>2</sup> *Annual Book of ASTM Standards*, Vol 06.04.

<sup>3</sup> *Annual Book of ASTM Standards*, Vol 15.05.

<sup>4</sup> Available from Standardization Documents Order Desk, Bldg. 4 Section D, 700 Robbins Ave., Philadelphia, PA 19111-5094.

*The American Society for Testing and Materials takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.*

*This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, 100 Barr Harbor Drive, West Conshohocken, PA 19428.*