



Designation: D 608 – 90 (Reapproved 1996)

AMERICAN SOCIETY FOR TESTING AND MATERIALS  
100 Barr Harbor Dr., West Conshohocken, PA 19428  
Reprinted from the Annual Book of ASTM Standards. Copyright ASTM

## Standard Specification for Dibutyl Phthalate<sup>1</sup>

This standard is issued under the fixed designation D 608; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

### 1. Scope

1.1 This specification covers dibutyl phthalate (99 % grade).

1.2 For specific hazard information and guidance, see the supplier's Material Safety Data Sheet for materials listed in this specification.

### 2. Referenced Documents

2.1 *ASTM Standards:*

D 268 Guide for Sampling and Testing Volatile Solvents and Chemical Intermediates for Use in Paint and Related Coatings and Materials<sup>2</sup>

D 1209 Test Method for Color of Clear Liquids (Platinum-Cobalt Scale)<sup>2</sup>

D 1296 Test Method for Odor of Volatile Solvents and Diluents<sup>2</sup>

D 1364 Test Method for Water in Volatile Solvents (Fischer Reagent Titration Method)<sup>2</sup>

D 1476 Test Method for Heptane Miscibility of Lacquer Solvents<sup>2</sup>

D 1613 Test Method for Acidity in Volatile Solvents and Chemical Intermediates Used in Paint, Varnish, Lacquer, and Related Products<sup>2</sup>

D 1617 Test Method for Ester Value of Lacquer Solvents and Thinners<sup>2</sup>

D 4052 Test Method for Density and Relative Density of Liquids by Digital Density Meter<sup>3</sup>

E 300 Practice for Sampling Industrial Chemicals<sup>4</sup>

2.2 *U.S. Federal Specification:*

PPP-C-2020 Chemicals, Liquid, Dry, and Paste: Packaging of<sup>5</sup>

### 3. Properties

3.1 Dibutyl phthalate (99 % grade) shall conform to the following requirements:

Apparent specific gravity:	
20/20°C	1.046 to 1.050
25/25°C	1.043 to 1.047
Color, Pt-Co scale, max	20
Odor	nonresidual
Water, max, weight %	0.2 <sup>A</sup>
Acidity (free acid as phthalic acid), max, weight %	0.01 <sup>B</sup>
Ester value, max, weight %	not less than 99.0

<sup>A</sup> This quantitative limit ensures that the material is miscible without turbidity with 19 volumes of 99 % heptane at 20°C.

<sup>B</sup> Equivalent to 0.067 mg of KOH per gram of sample.

### 4. Sampling

4.1 The material shall be sampled in accordance with Practice E 300.

### 5. Test Methods

5.1 The properties enumerated in this specification shall be determined in accordance with the following ASTM methods:

5.1.1 *Apparent Specific Gravity*—Determine the apparent specific gravity at 20 or 25°C by a convenient method that is accurate to the third decimal place. See Guide D 268 or Test Method D 4052.

5.1.2 *Color*—Test Method D 1209.

5.1.3 *Odor*—Test Method D 1296.

5.1.4 *Water*—Test Methods D 1364 and D 1476.

5.1.5 *Acidity*—Test Method D 1613.

5.1.6 *Ester Value*—Test Method D 1617.

### 6. Packaging and Package Marking

6.1 Package size shall be agreed upon between the purchaser and the supplier.

6.2 Packaging shall conform to applicable carrier rules and regulations or when specified shall conform to Fed. Spec. PPP-C-2020.

### 7. Keywords

7.1 dibutyl phthalate

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee D-1 on Paint and Related Coatings, Materials, and Applications and is the direct responsibility of Subcommittee D01.35 on Solvents, Plasticizers, and Chemical Intermediates.

Current edition approved May 25, 1990. Published July 1990. Originally published as D 608 – 41 T. Previous edition D 608 – 90.

<sup>2</sup> *Annual Book of ASTM Standards*, Vol 06.04.

<sup>3</sup> *Annual Book of ASTM Standards*, Vol 05.02.

<sup>4</sup> *Annual Book of ASTM Standards*, Vol 15.05.

<sup>5</sup> Available from Standardization Documents Order Desk, Bldg. 4 Section D, 700 Robbins Ave., Philadelphia, PA 19111-5094, Attn: NPODS.

 **D 608**

*The American Society for Testing and Materials takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.*

*This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, 100 Barr Harbor Drive, West Conshohocken, PA 19428.*