



Designation: D 6367 – 99

## Standard Specification for AMS ( $\alpha$ -Methylstyrene)<sup>1</sup>

This standard is issued under the fixed designation D 6367; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last approval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

### 1. Scope

1.1 This specification covers AMS ( $\alpha$ -Methylstyrene).

1.2 The following applies to all limits in this specification: for purposes of determining conformance with this specification, an observed value or a calculated value shall be rounded off “to the nearest unit” in the last right-hand digit used in expressing the specification limit, in accordance with the rounding-off method of Practice E 29.

1.3 Consult current OSHA regulations, suppliers’ Material Safety Data Sheets, and local regulations for all materials used in this specification.

### 2. Referenced Documents

#### 2.1 ASTM Standards:

D 1209 Test Method for Color of Clear Liquids (Platinum-Cobalt Scale)<sup>2</sup>

D 2121 Test Method for Polymer Content of Styrene Monomer and  $\alpha$ -Methylstyrene<sup>2</sup>

D 3160 Test Method for Phenol Content of Cumene (Isopropylbenzene) or AMS ( $\alpha$ -Methylstyrene)<sup>2</sup>

D 3437 Practice for Sampling and Handling Liquid Cyclic Products<sup>2</sup>

D 4590 Test Method for Colorimetric Determination of *p*-tert-Butylcatechol in Styrene Monomer or AMS ( $\alpha$ -Methylstyrene) by Spectrophotometry<sup>2</sup>

D 5386 Test Method for Color of Liquids Using Tristimulus Colorimetry<sup>2</sup>

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee D16 on Aromatic Hydrocarbons and Related Chemicals and is the direct responsibility of Subcommittee D16.07 on Styrene, Ethylbenzene, and C<sub>9</sub> and C<sub>10</sub> Aromatic Hydrocarbons.

Current edition approved Jan. 10, 1999. Published March 1999.

<sup>2</sup> Annual Book of ASTM Standards, Vol 06.04.

D 6144 Standard Test Method for Analysis of AMS ( $\alpha$ -Methylstyrene) by Capillary Gas Chromatography<sup>2</sup>

E 29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications<sup>3</sup>

#### 2.2 Other Documents:

OSHA Regulations, 29CFR, paragraphs 1910.1000 and 1910.1200<sup>4</sup>

### 3. Properties

3.1 AMS shall conform to the requirements shown in Table 1.

TABLE 1 Requirements

Property	Specification	ASTM Test Method
AMS, min, weight %	99.00	D 6144
Phenols, max, mg/kg	20	D 3160
Polymer, max, mg/kg	10	D 2121, Test Method A
Inhibitor, mg/kg	10-20 (or as required)	D 4590
Appearance	<sup>A</sup>	
Color, max, Pt-Co	20 <sup>B</sup>	D 1209 or D 5386

<sup>A</sup>Clear liquid free of sediment and haze when observed at 18.3 to 25.6°C (65 to 78°F).

<sup>B</sup>Test Method D 5386 is the referee test method in case of dispute.

### 4. Sampling

4.1 Sample the material in accordance with Practice D 3437.

### 5. Keywords

5.1 AMS; $\alpha$ -Methylstyrene

<sup>3</sup> Annual Book of ASTM Standards, Vol 14.02.

<sup>4</sup> Available from Superintendent of Documents, U.S. Government Printing Office, Washington, DC 20402.

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

*This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or [service@astm.org](mailto:service@astm.org) (e-mail); or through the ASTM website ([www.astm.org](http://www.astm.org)).*