



Designation: D 3784 – 95a

Standard Performance Specification for Men's and Boys' Woven Bathrobe and Dressing Gown Fabrics¹

This standard is issued under the fixed designation D 3784; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This performance specification covers men's and boys' woven bathrobe and dressing gown fabrics composed of any textile fiber or mixture of textile fibers.

1.2 This performance specification is not applicable to woven fabrics used for interlinings.

1.3 These requirements apply to the length and width directions for those properties where fabric direction is pertinent.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:

- D 123 Terminology Relating to Textiles²
- D 434 Test Method for Resistance to Slippage of Yarns in Woven Fabrics Using a Standard Seam²
- D 1424 Test Method for Tear Resistance of Woven Fabrics by Falling-Pendulum (Elmendorf) Apparatus²
- D 2262 Test Method for Tearing Strength of Woven Fabrics by the Tongue (Single Rip) Method (Constant Rate-of-Traversal Tensile Testing Machine)²
- D 2724 Test Methods for Bonded, Fused, and Laminated Apparel Fabrics²
- D 2905 Practice for Statements on Number of Specimens for Textiles²
- D 5034 Test Method for Breaking Force and Elongation of Textile Fabrics (Grab Test)³

2.2 AATCC Test Methods:⁴

- 8 Colorfastness to Crocking: AATCC Crockmeter Methods
- 15 Colorfastness to Perspiration

- 16 Colorfastness to Light
 - 23 Colorfastness to Burnt Gas Fumes
 - 61 Colorfastness to Washing, Domestic, and Laundering, Commercial: Accelerated
 - 96 Dimensional Changes in Laundering of Woven and Knitted Textiles Except Wool
 - 116 Colorfastness to Crocking: Rotary Vertical Crockmeter Method
 - 124 Appearance of Durable Press Fabrics After Repeated Home Launderings
 - 132 Colorfastness to Drycleaning
 - 135 Dimensional Changes in Automatic Home Laundering of Durable Press Woven or Knit Fabrics
 - Evaluation Procedure 1 Gray Scale for Color Change
 - Evaluation Procedure 2 Gray Scale for Staining
 - Evaluation Procedure 3 AATCC Chromatic Transference Scale
- ### 2.3 Federal Standard:⁵
- 16 CFR, Chapter II—Consumer Product Safety Commission, Subchapter D—Flammable Fabric Act Regulations
- ### 2.4 Military Standard:⁶
- MIL-STD-105 D Sampling Procedures and Tables for Inspection by Attributes

NOTE 1—Reference to test methods in this specification give only the permanent part of the designation of ASTM, AATCC, or other test methods. The current editions of each test method shall prevail.

3. Terminology

3.1 Definitions:

3.1.1 For definitions of textile terms used in this specification, refer to Terminology D 123 and the Technical Manual of the American Association of Textile Chemists and Colorists.

3.1.2 Definitions found in a dictionary of common terms are suitable for terms used in this specification.

4. Specification Requirements

4.1 The properties of fabrics for men's and boys' woven

¹ This specification is under the jurisdiction of ASTM Committee D-13 on Textiles and is the direct responsibility of Subcommittee D13.56 on Performance Standards for Textile Fabrics.

Current edition approved Dec. 10, 1995. Published March 1996. Originally published as D 3784 – 79. Last previous edition D 3784 – 95.

² *Annual Book of ASTM Standards*, Vol 07.01.

³ *Annual Book of ASTM Standards*, Vol 07.02.

⁴ Available from the American Association of Textile Chemists and Colorists, P.O. Box 12215, Research Triangle Park, NC 27709.

⁵ Available from Superintendent of Documents, Government Printing Office, Washington, DC 20402.

⁶ Available from Standardization Documents Order Desk, Bldg. 4 Section D, 700 Robbins Ave., Philadelphia, PA 19111-5094, Attn: NPODS.

bathrobes and dressing gowns shall conform to the specification requirements in Table 1.

5. Significance and Use

5.1 Upon mutual agreement between the purchaser and the supplier, woven fabrics intended for this end use should meet all of the requirements listed in Table 1 of this specification.

5.2 It is recognized that for purposes of fashion or aesthetics the ultimate consumer of articles made from these fabrics may find acceptable fabrics that do not conform to all of the requirements in Table 1. Therefore, one or more of the requirements listed in Table 1 may be modified by mutual agreement between the purchaser and the supplier.

5.2.1 In such cases, any references to the specification shall specify that: This fabric meets Specification D 3784 except for the following characteristic(s).

5.3 Where no prepurchase agreement has been reached between the purchaser and the supplier, and in case of controversy, the requirements listed in Table 1 are intended to be used as a guide only. As noted in 5.2, ultimate consumer demands dictate varying performance parameters for any particular style of fabric.

5.4 The significance and use of particular properties and test methods are discussed in the appropriate sections of the specified test methods.

6. Sampling

6.1 *Lot Sample*—As a lot sample for acceptance testing, take at random the number of rolls in an applicable specifica-

tion or other agreement between the purchaser and supplier, such as an agreement to use MIL-STD-105D.

6.2 *Laboratory Sample*—From each roll or piece in the lot sample, cut two laboratory samples the full width of the fabric and at least 375 mm (15 in.) along the selvage.

7. Test Methods (see Note 1)

7.1 *Breaking Force*—Determine the dry breaking force, in the standard atmosphere for testing textiles, as directed in Test Method D 5034 using a constant rate of traverse (CRT) tensile testing machine with the speed of the pulling clamp at 300 ± 10 mm (12 ± 0.5 in.)/min.

NOTE 2—If preferred, the use of a constant-rate-of-extension (CRE) tensile testing machine is permitted. The crosshead speed should be as agreed upon between the purchaser and the supplier. There may be no overall correlation between the results obtained with the CRT machine and with the CRE machine. Consequently, these two breaking load testers cannot be used interchangeably. In case of controversy, the CRT method shall prevail.

7.2 *Resistance to Yarn Slippage*—Determine the resistance to yarn slippage as directed in Test Method D 434.

NOTE 3—The precision of Test Method D 434 is being established, and it may not be suitable for fabrics with low yarn counts (see 5.2) in terms of ends and picks per inch.

7.3 *Tongue Tear Strength*—Determine the tongue tear strength as directed in Test Method D 2262.

NOTE 4—If preferred, use of Test Method D 1424 is permitted with existing requirements as given in this specification. There may be no overall correlation between the results obtained with the tongue tear machine and with the Elmendorf machine. Consequently, these two tongue tear testers cannot be used interchangeably. In case of controversy, Test Method D 2262 shall prevail.

7.4 *Dimensional Change:*

7.4.1 *Laundering*—Determine the maximum dimensional change after five launderings as directed in the applicable procedure in AATCC Test Method 135 (Note 5).

7.4.1.1 The wash conditions and drying procedure shall be as specified by the supplier.

7.4.2 *Dry Cleaning*—Determine the maximum dimensional change after three dry cleanings as directed in 10.1.1 through 10.1.4 of Test Methods D 2724.

NOTE 5—Launderable fabrics are expected to be dry-cleanable unless specifically labeled “Do Not Dry Clean.” “Dry-cleanable” goods are to be dry-cleaned only.

7.5 *Colorfastness:*

7.5.1 *Burnt Gas Fumes*—Determine the colorfastness to burnt gas fumes on the original fabric and after one laundering or one dry cleaning as directed in AATCC Test Method 23.

NOTE 6—Washing conditions shall be the same as those used in 7.4.1.1. Dry-cleaning conditions shall be the same as those used in 7.4.2.

7.5.2 *Laundering*—Determine the colorfastness to laundering as directed in the applicable procedure of AATCC Test Method 61. The test conditions shall be as specified by the supplier (Note 5).

7.5.3 *Dry Cleaning*—Determine colorfastness to drycleaning as directed in AATCC Test Method 132 (Note 5).

7.5.4 *Crocking*—Determine colorfastness to dry and wet crocking as directed in AATCC Test Method 8 for solid shades

TABLE 1 Specification Requirements

NOTE 1—Class in colorfastness and DP requirements is based on a numerical scale of 5 for negligible or no color change, color transfer, or fabric wrinkle to 1 for severe color change, color transfer, or fabric wrinkle.

Characteristic	Requirements	Section
Breaking strength (load) (CRT)	89 N (20 lbf), min	7.1
Yarn slippage	6.3-mm (¼-in.) separation 67 N (at 15 lbf), min	7.2
Tongue tear strength	6.7 N (1.5 lbf), min	7.3
Dimensional change:		
After five launderings	3 % max	7.4.1
After three drycleanings	2 % max	7.4.2
Colorfastness:		
Burnt gas fumes—2 cycles:		7.5.1
Shade change, original fabric	Class 4 ^A min	
Shade change after one laundering or one drycleaning	Class 4 ^A min	
Laundering:		7.5.2
Shade change	Class 4 ^A min	
Staining	Class 3 ^B min	
Drycleaning:		7.5.3
Shade change	Class 4 ^A min	
Crocking:		7.5.4
Dry	Class 4 ^C min	
Wet	Class 3 ^C min	
Perspiration:		7.5.5
Shade change	Class 4 ^A min	
Staining	Class 3 ^B min	
Light (20 AATCC FU) (xenon-arc)	Step 4 ^A	7.5.6
Fabric appearance (see 7.6.1.1)	DP 3.5, ^D min	7.6
Flammability	pass	7.7

^A AATCC Gray Scale for Color Change.
^B AATCC Gray Scale for Staining.
^C AATCC Chromatic Transference Scale.
^D For durable press fabrics only.

and AATCC Test Method 116 for prints or as agreed between the purchaser and the supplier.

7.5.5 *Perspiration*—Determine colorfastness to perspiration as directed in AATCC Test Method 15.

7.5.6 *Light*—Determine colorfastness to light as directed in AATCC Test Method 16.

NOTE 7—There are distinct differences in spectral distribution between the various types of machines listed in AATCC Test Method 16, with no overall correlations between them. Consequently, these machines cannot be used interchangeably. In case of controversy, results obtained with the water-cooled xenon-arc machine listed in Option E shall prevail.

7.6 *Fabric Appearance*—Determine the fabric appearance as directed in AATCC Test Method 124 after laundering using the wash-and-wear cycle or the normal cycle as agreed upon between the purchaser and the supplier as specified in 7.4.1.1 for washable fabrics or after dry cleaning as specified in 7.4.2

for dry-cleanable fabrics (see Note 5).

7.6.1 For fabrics not intended for use in “durable-press” garments, determine the fabric smoothness after pressing as specified in 5.12 of AATCC Test Method 96.

7.6.1.1 The fabric smoothness durable-press (DP) rating of such fabrics, and the DP rating of dry-cleaned fabrics, shall have decreased no more than ½ DP rating from that of the fabric before it is laundered or dry-cleaned.

7.7 *Flammability*—The flammability requirements shall be as agreed upon between the purchaser and the supplier, provided they meet or exceed those of Part 1610 of the Flammable Fabrics Act Regulations.

8. Keywords

8.1 bathrobe; fabric; performance; specification

The American Society for Testing and Materials takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, 100 Barr Harbor Drive, West Conshohocken, PA 19428.

This standard is copyrighted by ASTM, 100 Barr Harbor Drive, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (<http://www.astm.org>).