



Standard Practice for Determining Physical Properties of Fabrics, Yarns, and Sewing Thread Used in Inflatable Restraints¹

This standard is issued under the fixed designation D 5446; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This standard is a listing of the test methods commonly employed in determining the physical properties of fabrics and yarns used in the manufacture of inflatable restraints.

1.2 Fabrics used in the manufacture of inflatable restraints may be coated or uncoated, and may be comprised of spun yarns, continuous filament yarns, or a combination thereof.

1.3 Fabrics used in the manufacture of inflatable restraints may be either flat or one piece woven. For the one-piece woven, follow the sampling section of D 5446 and the individual test method.

1.4 In Section 9, this standard lists in alphabetical order the procedures associated with conducting physical testing of the following fabric or yarn properties of concern to the design and manufacture of inflatable restraints:

Yarn	Section
Denier (Yarn Number)	9.3.1
Fiber Content	9.3.2
Finish (Extractable Material)	9.3.3
Strength and Elongation	9.3.4
Twist	9.3.5
Fabric	
Air Permeability	9.3.6
Abrasion Resistance	9.3.7
Blocking	9.3.8
Bow and Skew	9.3.9
Breaking Force & Elongation	9.3.10
Burst Strength	9.3.11
Coating Adhesion	9.3.12
Coating Weight	9.3.13
Count of Woven Fabric	9.3.14
Dynamic Air Permeability	9.3.28
Edgecomb Resistance	9.3.29
Flammability	9.3.15
Fogging (Volatility)	9.3.16
Length	9.3.17
Mass per Unit Area	9.3.18
Non-Fibrous Material	9.3.19
Odor	9.3.20
Packability	9.3.30
pH	9.3.21
Stiffness	9.3.22
Tear Strength	9.3.23
Thickness	9.3.24
Warp Size Content & Residual Sizing	9.3.25
Width	9.3.26
Thread	
Sewing Thread	9.3.27

1.5 This standard may be used in conjunction with Practice D 5427 which prescribes standard practices for the accelerated aging of inflatable restraint fabrics when comparative results of

physical properties before and after accelerated aging are required.

1.6 Procedures and apparatus other than those stated in this standard may be used by agreement of purchaser and supplier with the specific deviations from the standard practice acknowledged in the report.

1.7 The values stated in either SI units or inch-pound units are to be regarded separately as standard. The values stated in each system are not exact equivalents; therefore, each system must be used independent of the other.

1.8 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use. See Note 3.*

2. Referenced Documents

2.1 ASTM Standards:

- D 123 Terminology Relating to Textiles¹
- D 204 Test Methods for Sewing Thread²
- D 276 Test Methods for Identification of Fibers in Textiles²
- D 737 Test Method for Air Permeability of Textile Fabrics²
- D 751 Test Methods for Testing Coated Fabric¹
- D 1059 Test Method for Yarn Number Based on Short-Length Specimens²
- D 1388 Test Methods for Stiffness of Fabrics²
- D 1422 Test Method for Twist in Yarns by the Untwist Retwist Method²
- D 1423 Test Method for Twist in Yarns by Direct Count Method²
- D 1777 Test Method for Measuring Thickness of Textile Materials²
- D 1907 Test Method for Yarn Number by the Skein Method²
- D 2256 Test Method for Tensile Properties of Yarns by the Single Strand Method²
- D 2257 Test Method for Extractable Matter in Textiles²
- D 2261 Test Method for Tearing Strength of Woven Fabrics by the Tongue (Single Rip) Method (Constant-Rate-of-Extension Tensile Testing Machine)²
- D 3773 Test Method for Length of Woven Fabric¹
- D 3774 Test Method for Width of Woven Fabric⁴
- D 3775 Test Method for Fabric Count of Woven Fabric⁴

D-3776 Test Method for Mass Per Unit Area (Weight) of Woven Fabric⁴

D-3786 Test Method for Hydraulic Bursting Strength of Knitted Goods and Nonwoven Fabrics—Diaphragm Bursting Strength Tester Method⁴

D-3882 Test Method for Bow and Skewness in Woven and Knitted Fabrics⁴

D-3990 Terminology Relating to Fabric Defects⁴

D-4032 Test Method for Stiffness of Fabric by the Circular Bend Procedure⁴

D-4157 Test Method for Abrasion Resistance of Textile Fabrics (Oscillatory Cylinder Method)⁴

D-4851 Test Method for Coated and Laminated Fabrics for Architectural Use⁴

D-5034 Test Method for Breaking Force and Elongation of Textile Fabrics (Grab Test)⁴

D-5427 Practice for Accelerated Aging of Inflatable Restraint Fabric⁴

D-5587 Test Method for Trapezoid Tearing Strength of Textiles⁴

F-778 Methods for Gas Flow Resistance Testing of Filtration Media¹

D-6476 Test Method for Determining Dynamic Air Permeability of Inflatable Restraint Fabric⁴

D-6478 Test Method for Determining Specific Packability of Fabrics Used in Inflatable Restraint⁴

D-6479 Test Method for Determining Edgecomb Resistance of Woven Fabrics Used in Inflatable Restraints⁴

D-6613 Practice for Determining the Presence of Sizing in Nylon and Polyester Fabric Used in Inflatable Restraints⁴

2.2—*Federal Standards*:¹

Motor Vehicle Safety Standard 302—Flammability—2.3—*SAE Standards*:¹

J912-A Resistance to Blocking

J1351 Determination of Odor

2.4—*Ford Motor Company Standards*:¹

FLTM-BO116-03 Fogging Standard

FLTM-BN13-1 Coating Adhesion

2.5—*AATCC Methods*:¹

Method 81 pH of Water—Extract from Wet-Processed Textiles

3. Terminology

3.1 Definitions:

3.1.1 *coated fabric, n*—a flexible material composed of a textile fabric and an adherent polymeric material applied to one or both sides.

3.1.2 *inflatable restraint, n*—a vehicular safety device designed to cushion an occupant or equipment during collision; airbag.

3.1.3 *one-piece woven, adj*—for inflatable restraints, a descriptive related to either 1) a tubularly woven fabric composed of two-layer inflatable sections, visible lines where the two layers initially interlace, and non-inflatable sections, or 2) the cushion cut from such fabric.

3.1.3.1 *Discussion*—a weaving machine is capable of simultaneously weaving two separate layers of fabric, one over the other, with tight interfacing selectively woven between them. Where the layers are not interlaced, the fabric is capable

of being inflated; where they are interlaced, inflation is not possible. Although the pattern in the fabric described by the visible line where the two inflatable layers interlace may be a complex shape other than a tube, the construction is commonly referred to as tubularly woven. Such weaving methods are sometimes used to minimize sewn seams in the manufacture of inflatable restraint cushions.

3.2 For definitions of other terms used in these test methods, refer to Terminology D-123 and Terminology D-3990.

4. Summary of Test Method

4.1 Test specimens are taken from sample rolls of fabric and tested using prescribed laboratory procedures, conditions and equipment by the supplier to determine the physical properties of the fabric in accordance with the requirements of the purchaser.

5. Significance and Use

5.1 Every ASTM test method listed in 2.1 contains a section describing its particular significance and use. Other test methods listed in 2.1 of this standard may contain sections pertaining to their particular significance and use.

5.2 The physical testing procedures in this standard can be used in conjunction with lot sampling procedures as a basis for acceptance testing of commercial shipments of inflatable restraint fabrics. They may be used to establish the criteria by which inflatable restraint fabrics will be tested by the supplier to determine whether a lot of material is acceptable for shipment to the purchaser.

5.3 This standard addresses all the physical properties that describe inflatable restraint fabrics and their commonly used test methods. Unless otherwise specified by agreement of purchaser and supplier, these standard test methods shall constitute the test conditions, procedures, and equipment used to determine the physical properties of fabrics used in inflatable restraints. It is intended to be used as a guideline in establishing a written material specification. The specification or agreement of purchaser and supplier may deviate from the practices described herein when (based on experience) considerations of fabric properties, material handling equipment, or inflatable restraint system design dictate otherwise.

6. Apparatus

6.1 Periodic laboratory certification of test equipment used in accordance with this standard is required to reduce test variability due to precision and bias.

6.2 For inflatable restraints, all test equipment used in accordance with the procedures referenced in this standard shall be certified for calibration annually by an independent agency or equipment manufacturer whose results are traceable to National Institute of Science and Technology (NIST) or other national standards laboratory. The test parameters of the equipment shall be tested within the operating ranges covered in the material specification or equivalent document.

7. Sampling

7.1 Lot Sample:

7.1.1 For the size of an acceptance sampling lot of fabric for inflatable restraints, use the number of fabric rolls in a

shipment of a single fabric style unless otherwise agreed upon between the purchaser and supplier. If the fabrics are one piece woven, use the number of units in the shipment as the acceptance sampling lot.

7.1.2 Unless otherwise agreed upon by purchaser and supplier, take as a lot sample all of the rolls or one piece woven units in a shipment of fabric. Consider rolls of fabric to be the primary sampling units.

7.1.3 For the size of an acceptance lot of yarn, use the lot determination and sample plan agreed upon by purchaser and supplier.

7.2 Laboratory Sample:

7.2.1 An entire roll of fabric or a full-width cut from the end of a roll within a lot sample or one piece woven units constitutes a laboratory sample depending on which physical property is to be tested.

7.2.1.1 For fabric width, fabric bow, and fabric length, the rolls in the lot sample serve as the laboratory sample.

7.2.1.2 For all other physical properties, take as the laboratory sample a full width cut of fabric 2 m (2 yd) long from the end of each roll in the lot sample if there is no evidence that the fabric is distorted; if there is evidence of physical distortion on the outside of the fabric roll, take a sample cut from the resulting end of the roll after removing and discarding the distorted portion of fabric.

7.2.2 An entire yarn package constitutes a laboratory sample for yarn testing.

7.3 Test Specimens:

7.3.1 Test specimens are the pieces of yarn or fabric units that actually undergo testing. The fabric units may be entire fabric rolls, one piece woven units or fabric pieces cut from the laboratory sample in accordance with physical testing requirements of a specific test method.

7.3.2 For fabric width, fabric bow, and fabric length, the rolls in the lot sample serve as the test specimens. For all other physical properties to be tested, the test specimens are the fabric pieces cut from the laboratory sample in accordance with the respective test method.

7.3.3 Take specimens from different positions across the roll width or one piece woven units when testing physical properties oriented in the warp direction; take specimens from different positions along the roll length or one piece woven units when testing physical properties oriented in the filling direction.

7.3.4 Take no test specimen closer to the selvage of the fabric than $\frac{1}{10}$ the width of the fabric or 125 mm (5 in.), whichever is smaller.

8. Conditioning

8.1 Test specimens shall be preconditioned as directed by the particular test method or as agreed upon between the purchaser and supplier.

8.2 Prior to testing a physical property, the test specimens shall be brought to moisture equilibrium at ambient atmospheric pressure, at $21 \pm 1^\circ\text{C}$ ($70 \pm 2^\circ\text{F}$), and at $65\% \pm 2\%$ relative humidity, unless directed to do otherwise by the test procedure or an agreement by purchaser and supplier.

8.3 Equilibrium is considered to have been reached when the increase in mass of the specimen in successive weightings

made at intervals of not less than 2 h does not exceed 0.1 % of the mass of the specimen.

NOTE 1—Certain fibers and coatings may exhibit slow rates of achieving moisture equilibrium. When this occurs, a preconditioning cycle such as described in Practice D 1776 may be agreed upon between contractual parties.

9. Procedures

9.1 Secure test specimens from laboratory samples in accordance with the sampling section (Section 7) of this standard for each test required by the material specification or agreement of purchaser and supplier.

9.2 Precondition and condition the test specimens in accordance with the conditioning section (Section 8) of this standard for each test required by the material specification or agreement of purchaser and supplier.

9.3 Test the specimens in accordance with each test method specified.

9.3.1 Determine the denier or yarn number in accordance with Test Method D 1907 for packaged yarn or Test Method D 1059 for beamed yarn or yarns removed from fabric test specimens.

9.3.1.1 When using Test Method D 1907, make one determination from each package in the laboratory sample.

9.3.1.2 When using Test Method D 1059, use twenty-five (25) specimens selected from each laboratory sample in both the warp and filling directions.

9.3.2 Determine the fiber content of the yarn in accordance with Test Method D 276, making one determination from each yarn package in the laboratory sample.

9.3.3 Determine the finish or extractable material content in yarn in accordance with Test Method D 2257, using one test specimen of ten grams removed from each laboratory sample.

9.3.4 Determine the single-end strength and elongation properties of yarns removed from yarn packages, beams, and fabric specimens in accordance with Test Method D 2256, using ten test specimens from each laboratory sample.

9.3.5 Determine the amount and direction of twist in yarns in accordance with Test Method D 1423.

9.3.5.1 Determine the twist in single spun yarns on packages and yarns removed from beams and fabric samples in accordance with Test Method D 1422, using ten test specimens selected from each laboratory sample.

9.3.5.2 Determine the twist in single, ply and cabled filament yarn or ply and cable twist in spun yarns on packages and yarns removed from beams and fabric samples in accordance with Test Method D 1423, using ten test specimens selected from each laboratory sample.

9.3.6 Determine the fabric air permeability of each unit in the lot sample in accordance with Test Method D 737, using five test specimens selected from each laboratory sample so that no two specimens contain the same warp or filling yarns. For additional information on calibration and use of air permeability test equipment, see Test Method F 778.

9.3.7 Determine the fabric abrasion resistance for each unit in the lot sample in accordance with Test Method D 4157, using five test specimens selected from both the warp and filling directions of the fabric rolls.

9.3.8 Determine the blocking of a coated fabric in accordance with Test Method SAE J912-A using five test specimens selected from each laboratory sample so that no two test specimens contain the same warp or filling yarns.

9.3.9 Determine the fabric bow and skew of each unit in the lot sample in accordance with Test Method D 3882 in three places spaced as widely as possible along the roll length. Make no measurement closer to the ends of the roll than 1 m (1 yd).

9.3.10 Determine the fabric breaking force and elongation in accordance with Test Method D 5034 in five places in both the warp and filling directions.

9.3.10.1 Use a tensile testing machine that exhibits either a constant rate of extension (CRE) or a constant rate of traverse (CRT), that is designed for the tensile forces anticipated, and that is operated at a rate of 300 mm/min (12 in./min). Select the force range of the testing machine such that the break occurs between 10 % and 90 % of full scale load.

9.3.10.2 Coat one side of uncoated specimens in accordance with Test Method D 751. Use jaw and specimen size as agreed upon by purchaser and supplier.

9.3.10.3 Calculate the average tensile force and elongation at break for each testing direction using the five highest peak forces recorded.

9.3.11 Determine the fabric burst strength in accordance with Test Method D 3786, using five specimens selected from each laboratory sample so that no two specimens contain the same warp or filling yarns.

9.3.12 Determine the coating adhesion of a coated fabric in accordance with Test Method D 4851, or Ford Motor Company FLTM BN-13-1, using five specimens selected from the laboratory sample.

NOTE 2—Assessment of adhesion may be subjective. Proper interpretation of adhesion test results shall be agreed upon by purchaser and supplier.

9.3.13 Determine the coating weight of a coated fabric in accordance with Test Method D 3776, Option C, using five specimens selected from each of the laboratory samples. The coating weight is calculated as the difference in weight per unit area before and after the fabric has been coated.

9.3.14 Determine the fabric count for test specimens in accordance with Test Method D 3775, making five determinations each in the warp and filling directions.

9.3.15 Determine the flammability of test specimens in accordance with Federal Motor Vehicle Safety Standard 302, using five test specimens each from the warp and filling directions.

9.3.16 Determine the fogging (volatility) of the fabric in the lot sample in accordance with Ford Test Method BO116-03 using three specimens selected from the laboratory sample.

9.3.17 Determine the length of each roll in the lot sample in accordance with Test Method D 3773 using Option B, Drum Method, or Option C, Clock Method. Total the lengths of the rolls measured.

9.3.18 Determine the mass (weight) per unit area of the fabric in the lot sample in accordance with Test Method D 3776 Option C, in five places from each laboratory sample.

9.3.19 Determine the non-fibrous content of the fabric in the lot sample in accordance with Test Method D 2257, using one

specimen selected from the laboratory sample and chloroform as the solvent.

NOTE 3—**Precaution:** As with all volatile solvents, the use of adequate ventilation under a hood is recommended when using chloroform.

9.3.20 Determine the odor of the fabric in the lot sample in accordance with SAE Practice J1351 using one specimen selected from the laboratory sample.

9.3.21 Determine the fabric pH in accordance with AATCC Method 81 for each unit in the lot sample using one 10 g test specimen taken from each laboratory sample.

9.3.22 Determine the fabric stiffness for each unit in the lot sample using Test Method D 4032, using five specimens each from the warp and filling directions selected from each laboratory sample. Use Test Method D 1388 Option 2, Cantilever Method, if directional stiffness is required.

9.3.23 Determine the fabric tear strength for each unit in the lot sample using Test Methods D 2261 or D 2262 if tongue tear is required, or Test Method 5587 if trapezoid tear is required.

9.3.23.1 From the laboratory sample, take five specimens each from the warp and filling directions. Coat one side of uncoated test specimens in accordance with Test Method D 751.

9.3.23.2 Use a tensile testing machine that exhibits either a constant rate of extension (CRE) or a constant rate of traverse (CRT), that is designed for the tear forces anticipated, and that is operated at a rate of 300 mm/min (12 in./min). Select the force range of the testing machine such that the break occurs between 10 % and 90 % of full scale load.

9.3.23.3 Calculate the average tear strength for each tear direction using the five highest peak forces recorded in each test.

9.3.24 Determine the thickness of the fabric in each roll in the lot sample in accordance with Test Method D 1777 from ten specimen areas in each laboratory sample. Use a gage with a presser foot with a diameter of 9.5 ± 0.025 mm (0.375 ± 0.001 in.) that is weighted to apply a total force of 1.7 ± 0.3 N (6 ± 0.1 oz) equivalent in pressure to 23.4 kPa (3.4 psi), unless otherwise specified.

9.3.25 Determine the presence of sizing in the lot sample using Practice D 6613 using one determination from each lab sample.

9.3.26 Determine the fabric width for each roll in the lot sample in accordance with Test Method D 3774 Option B (Laboratory Sample Removed from Full Roll or Bolt), using five determinations from each laboratory sample.

9.3.27 Evaluate sewing thread in accordance with Test Method D 204.

9.3.28 Determine the dynamic air permeability for each unit in the lot sample in accordance with Test Method D 6476 using five determinations from each laboratory sample.

9.3.29 Determine the edgecomb resistance for each unit in the lot sample in accordance with Test Method D 6479 using five determinations in both the warp and filling directions.

9.3.30 Determine the packability for each unit in the lot sample in accordance with Test Method D 6478 using one determination from each unit.

10. Report

10.1 State that the fabric lot was tested in accordance with Test Method D 5446 for testing the physical properties of fabrics used in inflatable restraints. Describe the material or product sampled and the method of sampling used.

10.2 The purchaser and supplier shall determine the exact form of the laboratory report. Unless otherwise specified, the form shall provide the following information:

10.2.1 applicable specification or reference to agreement between purchaser and supplier describing material requirements;

10.2.2 the description or designation of the test, including option(s) or method(s) used;

10.2.3 fabric designation;

10.2.4 identification of lot and lot samples;

10.2.5 specification of performance parameters;

10.2.6 results of each test;

10.2.7 name of tester;

10.2.8 date of test, and

10.2.9 deviations from standard test method procedures and apparatus.

11. Conformance

11.1 The test results of the fabric physical testing must conform to allowable ranges listed in the applicable material specification or other agreement between purchaser and supplier in order to warrant release of the shipment of material.

11.2 Non-conformity shall be reported by the supplier to the purchaser in writing. A material lot that fails to conform to physical testing requirements as specified or as otherwise

agreed upon may only be released for shipment upon written consent of the purchaser.

12. Precision and Bias

12.1 No statement is made about either the precision or bias of the ASTM test methods referenced in Test Method D 5446, Standard Test Methods for Determining the Physical Properties of Fabrics Used in Inflatable Restraints, since a statement regarding precision and bias is included within each ASTM test method.

12.2 Other test methods referenced in Section 2 do not include precision and bias statements. In case of a dispute arising from differences in reported test results when using these test methods, the purchaser and the supplier shall conduct comparative tests to determine if there is a statistical bias between their laboratories. As a minimum, the two parties shall take a group of test specimens which are as homogeneous as possible and from the same lot of material. The test specimens shall then be randomly assigned in equal numbers to each laboratory for testing. The average results from the two laboratories shall be compared using Student's t-test for unpaired data and an acceptable probability level chosen by the two parties before the testing is begun. If a bias is found, either its cause shall be found and corrected or the purchaser and supplier shall agree to interpret future results in light of the known bias.

13. Keywords

13.1 airbag; fabric physical testing; inflatable restraint; physical properties; one piece woven

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).