



Standard Practice for Preparation of Textiles Prior to Ultraviolet (UV) Transmission Testing¹

This standard is issued under the fixed designation D 6544; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This practice delineates standardized exposures to laundering, simulated sunlight, and chlorinated pool water to which cloth, labeled as ultraviolet-(UV) protective, must be exposed prior to testing for UV transmission.

1.2 This practice leads to measurement of the residual level of UV-protection in fabrics or garments labeled as sun- or UV-protective, after exposure to conditions that relate to about two years of seasonal use. The UV transmission measurements may be done in accordance with AATCC Test Method 183 using fabrics prepared in accordance with this practice. This measurement may be used in support of a label statement regarding UV protection.

1.3 The values stated in either SI units or inch-pound units are to be regarded separately as standard. Within the text, the inch-pound units are shown in parentheses. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in nonconformance with the standard.

1.4 *This standard does not purport to address the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:

D 123 Terminology Related to Textiles²

D 2905 Practice for Statements on Number of Specimens for Textiles²

D 3938 Guide for Determining or Confirming Care Instructions for Apparel and Other Textile Consumer Products³

E 122 Practice for Choice of Sample Size to Estimate a Measure of Quality for a Lot or Process⁴

¹ This practice is under the jurisdiction of ASTM Committee D13 on Textiles and is the direct responsibility of Subcommittee D13.65 on UV Protective Fabrics and Clothing.

Current edition May 10, 2000. Published September 2000.

² *Annual Book of ASTM Standards*, Vol 07.01.

³ *Annual Book of ASTM Standards*, Vol 07.02.

⁴ *Annual Book of ASTM Standards*, Vol 14.02.

2.2 AATCC Test Methods and Documents:⁵

16[E] Colorfastness to Light

135 Dimensional Changes in Automatic Home Laundering of Woven or Knit Fabric

162 Colorfastness to Water: Chlorinated Pool

172 Colorfastness to Non-chlorine Bleach in Home Laundering

183 Transmittance or Blocking of Erythemally Weighted Ultraviolet Radiation through Fabrics

Glossary of AATCC Standard Terminology

3. Terminology

3.1 *Definitions*—For definitions of other textile terms used in this practice, refer to Terminology D 123 and the *Glossary of AATCC Standard Terminology*.

4. Summary of Practice

4.1 This practice directs the exposure of cloth, labeled as UV-protective, to conditions of laundering, simulated sunlight, and chlorinated pool water generally known to affect UV transmittance.

4.2 This practice directs selection and sequencing of exposure conditions for UV-protective fabrics and garments.

5. Significance and Use

5.1 The significance of this practice is that cloth, labeled as UV-protective, which will ultimately be submitted for UV transmittance testing will be in a state that simulates their condition at the end of two years of normal seasonal use. Therefore, the UV-protection level ultimately placed on a label estimates the maximum UV transmittance of the garment fabric during a two-year life cycle.

6. Sampling and Test Specimens

6.1 *Primary Sampling Unit*—Consider rolls or bolts of fabric, or cartons of garments to be the primary sampling unit, as applicable.

6.1.1 Take the number of primary sampling units from each lot, shipment, or production run in accordance with Practice E 122.

⁵ Available from the American Association of Textile Chemists and Colorists, P.O. Box 12215, Research Triangle Park, NC 27709.

6.2 Laboratory Sampling Unit:

6.2.1 Take the number of laboratory sampling units from the primary sampling unit in accordance with Practice E 122.

6.2.2 *Rolls or Bolts of Fabric*—Take from each primary sampling unit one full-width piece of fabric that is about 1 m (1 yd) in length along the selvage (machine direction), after removing a first 1-mm length. For narrow fabrics, a longer sample length may be required to meet the test specimen requirements.

6.2.3 *Garments*—Take from each primary sampling unit one entire garment. For small garments, such as children's, where sufficient material is not available to meet the three test specimens requirement, take a pair of garments and treat as one sampling unit.

6.3 *Laundering*—Unless exempt from laundering, launder the laboratory sampling unit or a section of it that is at least 380 by 380 mm (15 by 15 in.) using exposure conditions as described in 8.1. If the laboratory sampling unit does not have the minimum 380-mm dimension, then take a section that is at least 1450 cm² (225 in.²). For small samples, it may be necessary to seal the edges to prevent raveling during laundering.

6.4 *Test Specimens*—As test specimens, take from each laboratory sampling unit at least three specimens of each fabric type in accordance with Practice D 2905.

6.4.1 For simulated sunlight and chlorinated water testing, cut test specimens 125 by 180 mm (5 by 7 in.).

6.4.2 Cut specimens representing a broad distribution diagonally across the width of the laboratory sampling unit. Ensure specimens are free of folds, creases, or wrinkles. Avoid getting oil water, grease, and so forth on the specimens when handling. For printed fabrics, ensure that all colors in the pattern are contained in the test specimen.

6.4.3 For fabric widths 125 mm (5 in.) or more, take no specimen closer than 25 mm (1 in.) from the selvage edge.

6.4.4 For fabric widths less than 125 mm (5 in.) use the entire width for specimens.

6.4.5 When a garment is the laboratory sampling unit, take test specimens from various areas of the garment. Avoid taking specimens along seams.

6.4.6 When the required minimum of three specimens cannot be taken from one garment as might be the case with children's garments, then take two specimens from each of two garments, the pair of garments constituting a laboratory sampling unit.

6.4.7 When a garment is made from different fabrics, at least three test specimens are required of each fabric that covers 10 % or more of the body surface covered by the garment.

7. Procedure

7.1 For garments other than swimwear and fabrics intended to be made into garments other than swimwear, launder 40 times using the exposure conditions described in 8.1 and then take specimens from these fabrics and expose to 100 AATCC Fading Units of simulated sunlight in accordance with the conditions described in 8.2.

7.2 For swimwear and fabric intended for swimwear, launder 40 times in accordance with the exposure conditions

described in 8.1. Then take specimens from the laundered fabrics or garments and expose those specimens to 100 AATCC Fading Units of simulated sunlight in accordance with the conditions described in 8.2 and then to chlorinated water in accordance with the conditions described in 8.3.

7.3 Garments and fabrics intended for use in garments other than swimsuits that are sold with the expectation they will not be laundered (such as disposable or limited-use garments for pesticide application) need only be exposed to simulated sunlight.

8. Exposure Conditions

8.1 Laundering:

8.1.1 *Conditions of Exposure*—Hand washing or automatic machine washing, wash water temperature, agitation cycle in automatic laundering, drying method and temperature if machine drying, and use of bleach must be those that will be conveyed to the consumer on the care label attached to the fabric/garment. Those conditions should have been determined by following Guide D 3938.

8.1.1.1 Care procedures determined in accordance with Guide D 3938 may be modified when it is established that those procedures increase the UV-transmittance of the fabric.

8.1.1.2 Follow one of the washing and drying procedures in AATCC 135 or AATCC 172 that matches the care instructions of the fabric or garment.

8.1.2 The specimens to be laundered may be garments, one-yard lengths of fabric, or areas of fabric having minimum dimensions of 380 by 380 mm (15 by 15 in.) or when applicable 1450 cm² (225 in.²).

8.2 Simulated Sunlight:

8.2.1 A xenon-arc lamp must be used which limits the test conditions to those described in AATCC 16 Option E.

8.2.2 For directions for preparing the specimens to be exposed to UV radiation, refer to the test preparation section of Test Method AATCC 16[E] noting that only two specimens are required and that the specimens are to be cut from the laundered specimens and omitting the section which refers to the testing of yarns, not fabrics.

8.3 Chlorinated Pool Water:

8.3.1 For preparation of the specimens to be exposed to chlorinated pool water, refer to the procedure section of Test Method AATCC 162. Ignore the reference to colored specimens as white specimens may also be exposed to chlorinated pool water conditions.

8.3.2 The specimens are those previously laundered and exposed to simulated sunlight.

8.3.3 For the exposure procedure, follow the procedure provided in the procedure section of Test Method AATCC 162 with the exception that the chlorine concentration in milligrams per kilogram should be adjusted so it is equal to the unit mass of the fabric specimen.

9. Report

9.1 Report that the specimens were prepared for UV transmission testing as directed in this practice. Describe the material or product samples.

9.2 Specific Conditions of Each Exposure:

9.2.1 Use Table X1.1 to report all applicable information about laundering conditions.

9.2.2 Use Table X1.2 to report all applicable information about simulated sunlight exposure.

9.2.3 Use Table X1.3 to report all applicable chlorinated pool water exposure conditions.

9.3 *Deviations from Specified Conditions:*

9.3.1 Report any deviation from laundering conditions specified in AATCC 135 into Table X1.1.

9.3.2 Report any deviation from AATCC Test Method 16 or the performance of the reference standard used in Table X1.2

9.3.3 Report any deviation from AATCC 162 in Table X1.3.

10. Keywords

10.1 care labeling; chlorinated pool water effects; laundering effects; simulated sunlight exposure effects; sunbathing; swimwear; UV-protective fabrics; UV transmission testing

APPENDIX

(Nonmandatory Information)

X1. EXPOSURE REPORT FORMS

See Table X1.1, Table X1.2, and Table X1.3

TABLE X1.1 Laundering Exposure Report Form

Operator's name _____ Date _____

Sample identification _____

Check exposures used:

Machine Cycle: Normal /cotton/sturdy Delicate Permanent press	Washing temperature, °C (°F) ^A 27 ± 3 (80 ± 5) 41 ± 3 (105 ± 5) 49 ± 3 (120 ± 5) 60 ± 3 (140 ± 5)	Drying procedure: ^B Tumble cotton study Tumble, delicate Tumble, permanent press Line Drip Screen
--	--	--

^ADeviations from washing machine conditions as described in Table II AATCC 135-1995.

^BDeviations from drying settings in Table III AATCC 135-1995.

TABLE X1.2 Chlorinated Pool Water Exposure Form

 Operator's name _____ Date _____
 Sample Identification _____
 Deviations from the procedure in AATCC 162:

TABLE X1.3 Sunlight Exposure Report Form

 Operator's name _____ Date _____
 Sample Identification _____
 Material exposed: Face _____ Back _____
 Reference standard _____
 Exposure Controlled by: AATCC Blue Wool Lightfastness Standards _____
 Radiant energy _____ Other _____
 Total radiant energy _____
 Type of test apparatus _____ Model Number _____
 Serial number _____ Manufacturer's name _____
 Specimen rack: Inclined _____ 2-Tier _____ 3-Tier _____ Horizontal _____
 Type of water supply _____
 Option employed _____ Elapsed exposure time _____
 Mounting procedure: Backed _____ Unbacked: _____
 Sample rotation schedule _____ Percent relative humidity _____
 Deviations from the test procedure:

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).