



Designation: D 1712 – 96

Standard Practice for Resistance of Plastics to Sulfide Staining¹

This standard is issued under the fixed designation D 1712; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This practice covers the determination of the resistance of plastics to staining in the presence of sulfides.

1.2 The values stated in SI units are to be regarded as the standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.* For specific precaution statements, see Section 6.

NOTE 1—There is no equivalent ISO standard.

2. Referenced Documents

2.1 *ASTM Standards:*

D 618 Practice for Conditioning Plastics and Electrical Insulating Materials for Testing²

D 883 Terminology Relating to Plastics²

D 1898 Practice for Sampling of Plastics²

3. Terminology

3.1 *Definitions:* For definitions of terms used in this practice, refer to Terminology D 883.

4. Significance and Use

4.1 Plastic compositions containing salts of lead, cadmium, copper, antimony, and certain other metals (as stabilizers, pigments, driers, or fillers) may stain due to the formation of a metallic sulfide when in contact with external materials that contain sulfide. The external sulfide source may be liquid, solid, or gas. Examples of materials that may cause sulfide stains are rubber, industrial fumes, foods, kraft paper, etc. This practice provides a means of estimating the relative susceptibility of plastic composition to sulfide staining.

5. Reagent

5.1 *Hydrogen Sulfide Solution*—A freshly prepared saturated solution of hydrogen sulfide (**Caution**, see Section 6).

Prepare the solution by rapidly bubbling hydrogen sulfide gas (Note 2) through water. Five minutes of bubbling is sufficient for 100 to 150 mL of water at room temperature (approximately 23°C).

NOTE 2—Hydrogen sulfide gas may be obtained commercially as compressed gas in cylinders.

6. Precautions

6.1 Hydrogen sulfide is a highly toxic gas and must be handled only in a suitably ventilated area such as a hood. Avoid breathing of vapors.

7. Sampling

7.1 Sampling shall be in accordance with the pertinent considerations outlined in Practice D 1898.

8. Test Specimens

8.1 Test specimens shall be representative of the particular plastic composition being tested. Size and shape of test specimens are relatively unimportant. Specimens 100 ± 25 mm (4 ± 1 in.) in length by 13 ± 6 mm (0.5 ± 0.25 in.) in width by the thickness of the composition being tested, have been found suitable for this test.

9. Conditioning

9.1 *Conditioning*—Condition the test specimens at $23 \pm 2^\circ\text{C}$ ($73.4 \pm 3.6^\circ\text{F}$) and $50 \pm 5\%$ relative humidity for not less than 40 h prior to test in accordance with Procedure A of Practice D 618 for those tests where conditioning is required. In cases of disagreement, the tolerances shall be $\pm 1^\circ\text{C}$ ($\pm 1.8^\circ\text{F}$) and $\pm 2\%$ relative humidity.

9.2 *Test Conditions*—Conduct tests in the standard laboratory atmosphere of $23 \pm 2^\circ\text{C}$ ($73.4 \pm 3.6^\circ\text{F}$) and $50 \pm 5\%$ relative humidity, unless otherwise specified in the test methods or in this specification. In cases of disagreements, the tolerances shall be $\pm 1^\circ\text{C}$ ($\pm 1.8^\circ\text{F}$) and $\pm 2\%$ relative humidity.

10. Procedure

10.1 Using a 250-mL beaker or equivalent, immerse approximately half of each specimen (Note 3) in the saturated hydrogen sulfide solution for 15 min (Note 4). Cover the test container with a watch glass or aluminum foil during the test.

NOTE 3—It is recommended that a control material, whose tendency to

¹ This practice is under the jurisdiction of ASTM Committee D-20 on Plastics and is the direct responsibility of Subcommittee D20.50 on Permanence Properties.

Current edition approved Nov. 10, 1996. Published January 1997. Originally published as D 1712 – 60 T. Last previous edition D 1712 – 89.

Sections 1.5, 3, and 13 were added in September 1996.

² *Annual Book of ASTM Standards*, Vol 08.01.



sulfide stain is known, be included with each test series. This provides a reference point from series to series. Staining may be rated as more, less, or equal to that of the control.

NOTE 4—If desired, additional specimens may be tested for different periods of time. Suggested periods of immersion are 5, 15, 30, 60, and 120 min. If immersion times greater than 30 min are desired, remove the specimens from the reagent each 30 min and again bubble hydrogen sulfide gas through the solution for 3 min. Reimmerse the specimens and continue the test. Do not dry the specimens during the time they are removed for reconcentration of the solution. Time compensation will not be necessary for the period the specimens are not immersed.

10.2 After immersion for 15 min, remove the specimens, wipe dry, and examine for discoloration of the immersed section compared to a sample of the identical plastic composition not exposed to hydrogen sulfide solution.

10.3 Compare the relative degree of staining for each material being tested in a series, and establish their relative order of sulfide stain resistance.

11. Report

11.1 The report shall include the following:

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).

11.1.1 Complete identification of the material tested, including type, source, manufacturer's code numbers, form, previous history, and other pertinent information,

11.1.2 Duration of exposure, and

11.1.3 Effects of exposure, including whether or not staining occurred, color of stain, and severity of staining in relation to other materials in the series or in relation to a control material, if included.

12. Precision and Bias

12.1 Since the results of this practice are subjective descriptions, statements of precision and bias are not pertinent to the practice.

13. Keywords

13.1 hydrogen sulfide; staining; sulfide