



Standard Test Method for Apparent Viscosity of Plastisols and Organosols at High Shear Rates by Extrusion Viscometer¹

This standard is issued under the fixed designation D 1823; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method covers the measurement of plastisol and organosol viscosity at high shear rates by means of an extrusion viscometer.

1.2 Apparent viscosity at low shear rates is covered in Test Method D 1824.

1.3 The values stated in SI units are to be regarded as the standard. The values in parentheses are given for information only.

1.4 *This standard does not purport to address the safety concerns associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

NOTE 1—This standard resembles ISO 4575-1985 in title only. The content is significantly different.

2. Referenced Documents

2.1 ASTM Standards:

D 1475 Test Method for Density of Paint, Varnish, Lacquer, and Related Products²

D 1755 Specification for Poly(Vinyl Chloride) Resins³

D 1824 Test Method for Apparent Viscosity of Plastisols and Organosols at Low Shear Rate³

E 1 Specification for ASTM Thermometers⁴

E 691 Practice for Conducting an Interlaboratory Study to Determine the Precision of a Test Method⁵

2.2 ISO Standard:

ISO 4575-1985: Poly Vinyl Chloride Pastes—Determination of Apparent Viscosity Using the Severs Rheometer⁶

3. Summary of Test Method

3.1 The sample is conditioned to the proper temperature, placed into an extrusion chamber, and extruded under standard conditions. The viscosity is calculated from the extrusion pressure and the rate of flow through the orifice.

4. Significance and Use

4.1 The suitability of a dispersion resin for any given application is dependent upon its viscosity characteristics.

4.2 The extrusion viscosity defines the flow behavior of a plastisol or organosol under high shear. This viscosity relates to the conditions encountered in mixing, pumping, knife coating, roller coating, and spraying processes.

5. Apparatus

5.1 *Extrusion Rheometer*.⁷

5.2 *Orifice*, 3.17 \pm 0.13 mm (0.125 \pm 0.005 in.) inside diameter and 50 \pm 1.0 mm (1.97 \pm 0.04 in.) long.

5.3 *Sample Containers, Tin Cans, or Glass Jars*, 1-pt (500-mL) capacity.

5.4 *Paper Cups*, 8-oz (250-mL) capacity.

5.5 *Nitrogen Cylinder*, equipped with pressure regulator and gage.

5.6 *Thermometer*—ASTM Solvents Distillation Thermometer having a range from -2 to $+52^\circ\text{C}$ (28 to 126°F) and conforming to the requirements for Thermometer 37C as prescribed in Specification E 1.

5.7 *Timer*.

6. Conditioning

6.1 Maintain the plastisol or organosol samples at $23 \pm 1^\circ\text{C}$ ($73 \pm 2^\circ\text{F}$) and $50 \pm 5\%$ relative humidity at all times after mixing and throughout the period of viscosity determinations.

7. Procedure

7.1 *Set Up Rheometer*—Attach the pressure regulator to the nitrogen tank. Connect the nitrogen supply to the rheometer by means of the copper tubing. Do not use oxygen or liquid pressure sources (Note 2). Set the three-way quick-acting valve to the IN position. Regulate the tank pressure to give 1.04 MPa

¹ This test method is under the jurisdiction of ASTM Committee D-20 on Plastics and is the direct responsibility of Subcommittee D20.15 on Thermoplastic Materials (Section D20.15.08).

Current edition approved March 15, 1995. Published May 1995. Originally published as D 1823 – 61 T. Last previous edition D 1823 – 90.

This edition contains changes in Sections 1, 2, and 11 to include an ISO equivalency statement, to reference a low shear rate test method, and to include Keywords.

² *Annual Book of ASTM Standards*, Vol 06.01.

³ *Annual Book of ASTM Standards*, Vol 08.01.

⁴ *Annual Book of ASTM Standards*, Vol 14.03.

⁵ *Annual Book of ASTM Standards*, Vol 14.02.

⁶ Available from American National Standards Institute, 11 W. 42nd St., 13th Floor, New York, NY 10036.

⁷ Burrell Severs, Model A-120, or equivalent, has been found satisfactory for this purpose. The Burrell Severs, Model A-120 is available from the Burrell Corp., 2223 Fifth Ave., Pittsburgh, PA 15219.

(150 psi) pressure to the instrument. Do not use input or line pressure over 1.38 MPa (200 psi). Insert the medium-size orifice (approximately 3.2 mm (1/8 in.) inside diameter) in the orifice retaining cap, with the orifice and the barrel, then screw the cap solidly in place. Mount the barrel in the instrument.

NOTE 2—Air may be used instead of nitrogen.

7.2 Weigh four empty paper cups for each sample to be tested. Record tare weight of each cup to the nearest 0.1 g. Fill the barrel with the sample to be tested to within 13 mm (1/2 in.) from the top of the barrel. Measure the sample temperature.

7.3 Insert the top air cap and gasket into the air cap ring, screw it in place on top of the barrel, and connect the air supply quick-connector.

7.4 Set the rheometer regulator gage (on the right side of the instrument) to 0.069 MPa (10 psi) pressure. Open the three-way quick-acting valve to the OUT position and allow the mix to extrude into an unweighed paper cup for 10 s. Adjust the gage pressure back to 0.069 MPa (10 psi).

7.5 Quickly place a preweighed and labeled paper cup under the nozzle and at the same time start the timer. Collect the extrudate until approximately 50 g of sample have entered the cup. Simultaneously remove the cup and stop the timer, again placing the unweighed cup under the nozzle. (Use a maximum flow time of 200 s for extremely viscous samples.)

7.6 Push the three-way quick-acting valve to the IN position to turn off the nitrogen supply to the chamber.

7.7 Record the extrudate weight to the nearest 0.1 g and efflux time to the nearest second.

7.8 Increase the gage pressure to 0.28 MPa (40 psi) and repeat 7.4-7.7. Increase to 0.48 MPa (70 psi) and repeat. Make a fourth determination at 0.69 MPa (100 psi). Report the exact efflux time for each determination. After all tests have been completed, turn off the nitrogen supply at the tank. Release the pressure in the instrument by pulling the three-way valve to the OUT position.

7.9 Clean the orifice between runs using pipe cleaners that have been wetted with mineral spirits. Take care that the inner surface of the orifice does not become scratched. After rinsing with mineral spirits, dry the orifice in air.

8. Calculation

8.1 Calculate the shear stress, shear rate, and viscosity as follows:

$$\text{Shear stress, MPa (or psi)} = PR/2L \quad (1)$$

where:

P = pressure in rheometer, MPa (or psi),
 R = radius of orifice, cm (in.), and
 L = length of orifice, cm (in.)

$$\text{Shear rate, s}^{-1} = 4W/3.1416R^3 DT \quad (2)$$

where:

W = weight of material effluxed, g,
 D = density of the sample, determined in accordance with Test Method D 1475, except convert lb/gal to g/mL, and
 T = efflux time, s.

NOTE 3—The preferred practice is to determine both the density and

efflux time on deaerated material. If the efflux time of undeaerated material is specifically desired, the determination of density on an undeaerated sample may also be desirable.

$$\text{Viscosity, pascal seconds} = (\text{shear stress/shear rate}) \times 10^6 \quad (3)$$

if shear stress is in MPa.

$$\text{Viscosity, poises} = (\text{shear stress/shear rate}) \times 6.895 \times 10^4$$

if shear stress is in psi.

9. Report

9.1 The report shall include the following:

9.1.1 Complete sample identification,

9.1.2 Test temperature as measured in,

9.1.3 Conditioning time, and

9.1.4 Extrusion viscosity, in pascal seconds (or poises); shear rate, in reciprocal seconds; and shear stress, in pascals (or pounds-force per square inch), for each of the four pressures (0.069, 0.28, 0.48, and 0.69 MPa (or 10, 40, 70, and 100 psi)).

NOTE 4—If only one viscosity is to be reported, report the data obtained at 100 psi together with the shear rate and shear stress, for example: “Viscosity at a shear stress of Z psi and a shear rate of $Y \text{ s}^{-1} = X$ poises.” The most information will be gained, however, by a plot of shear rate versus shear stress and would typify a true flow curve. In all cases where only one value is to be reported, the test must be run at each pressure in the order indicated in the procedure.

10. Precision and Bias ⁸

10.1 Tables 1-4 are based on a round robin⁸ conducted in

TABLE 1 Precision of Viscosity Data at 10 psi Extrusion Pressure

Resin	Average Viscosity (Poises)	Values expressed as % of the Average			
		νr^A	νR^B	r^C	R^D
IV	79.95	10.5	18.3	29.4	51.1
V	81.05	7.0	25.8	19.6	72.2
I	87.95	7.1	11.9	19.9	33.4
III	99.90	6.1	8.6	17.1	24.1
II	121.55	12.0	13.7	33.6	38.5
VI	221.25	9.4	9.8	26.3	27.3

^A νr is the within-laboratory coefficient of variation of the average.

^B νR is the between-laboratories coefficient of variation of the average.

^C r is the within-laboratory repeatability Limit ($= 2.8 \nu r$).

^D R is the between-laboratories reproducibility Limit ($= 2.8 \nu R$).

1983 involving six PVC dispersion resins tested by four laboratories at extrusion pressures of 10, 40, 70, and 100 psi. For each resin, all the samples were prepared at one source, but the individual plastisols were prepared according to Method D 1755 at the laboratories which tested them. Each test result consisted of one individual determination at the stated extrusion pressure. Each laboratory obtained 5 test results for each resin at each extrusion pressure.

NOTE 5—**Caution:** The following explanations of r and R (10.2-10.2.3) are only intended to present a meaningful way of considering the approximate precision of this test method. With data from only four laboratories, the between-laboratories results, in particular, should be viewed with extreme caution! The data in Tables 1-4 should not be rigorously applied to acceptance or rejection of material, as those data are

⁸ Supporting data are available from ASTM Headquarters. Request RR: D20-1137.

TABLE 2 Precision of Viscosity Data at 40 psi Extrusion Pressure

Resin	Average Viscosity (Poises)	Values expressed as % of the Average			
		νr^A	νR^B	r^C	R^D
V	86.30	7.3	10.2	20.4	28.6
IV	129.85	11.9	24.2	33.3	67.7
II	130.90	9.9	21.8	27.7	61.2
I	147.00	7.4	9.6	20.7	26.9
III	184.20	5.5	11.1	15.4	31.0
VI	211.80	5.9	8.7	16.5	24.3

^A νr is the within-laboratory coefficient of variation of the average.

^B νR is the between-laboratories coefficient of variation of the average.

^C r is the within-laboratory repeatability Limit (= 2.8 νr).

^D R is the between-laboratories reproducibility Limit (= 2.8 νR).

TABLE 3 Precision of Viscosity Data at 70 psi Extrusion Pressure

Resin	Average Viscosity (Poises)	Values expressed as % of the Average			
		νr^A	νR^B	r^C	R^D
V	79.10	7.6	11.1	21.3	31.2
II	119.50	4.9	6.4	13.7	18.0
IV	139.85	11.9	24.3	33.3	68.1
I	150.50	7.6	16.5	21.3	46.3
VI	182.40	5.9	10.3	16.5	28.7
III	233.95	6.6	13.8	18.5	38.5

^A νr is the within-laboratory coefficient of variation of the average.

^B νR is the between-laboratories coefficient of variation of the average.

^C r is the within-laboratory repeatability Limit (= 2.8 νr).

^D R is the between-laboratories reproducibility Limit (= 2.8 νR).

specific to the round robin and may not be representative of other lots, conditions, materials, or laboratories. Users of this test method should apply the principles outlined in Practice E 691 to generate data specific to their laboratory and materials, or between specific laboratories. The principles of 10.2-10.2.3 would then be valid for such data.

10.2 *Concept of r and R* —If S_r and S_R were calculated from a large enough body of data, and for test results consisting of one determination per test result.

10.2.1 *Repeatability Limit, r* —In comparing two test results for the same material, obtained by the same operator using the same equipment on the same day, the two test results should be judged not equivalent if they differ by more than the r value for that material.

10.2.2 *Reproducibility Limit, R* —In comparing two test results for the same material, obtained by different operators

TABLE 4 Precision of Viscosity Data at 100 psi Extrusion Pressure

Resin	Average Viscosity (Poises)	Values expressed as % of the Average			
		νr^A	νR^B	r^C	R^D
V	70.20	6.6	10.8	18.5	30.3
II	107.50	5.3	7.3	14.8	20.6
IV	130.80	6.3	16.5	17.6	46.2
I	134.35	12.4	24.2	34.7	67.7
VI	153.05	5.0	10.1	14.0	28.4
III	249.05	7.4	14.3	20.7	39.9

^A νr is the within-laboratory coefficient of variation of the average.

^B νR is the between-laboratories coefficient of variation of the average.

^C r is the within-laboratory repeatability Limit (= 2.8 νr).

^D R is the between-laboratories reproducibility Limit (= 2.8 νR).

using different equipment in different laboratories on different days, the two test results should be judged not equivalent if they differ by more than the R value for that material.

10.2.3 Any judgment in accordance with 10.2.1 or 10.2.2 would have an approximate 95 % (0.95) probability of being correct.

10.3 There are no recognized standards by which to estimate bias of this test method.

11. Keywords

11.1 apparent viscosity; extrusion viscometer; high shear rate viscometry; PVC organosol; PVC plastisol

The American Society for Testing and Materials takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, 100 Barr Harbor Drive, West Conshohocken, PA 19428.