



# Standard Practice for Preparing Plastic Film Specimens for a Round-Robin Study<sup>1</sup>

This standard is issued under the fixed designation D 4204; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

## 1. Scope \*

1.1 This practice covers the preparation of test sets of plastic film specimens for subsequent use in an interlaboratory round-robin study to evaluate the precision of a test method.

NOTE 1—There is no similar or equivalent ISO standard.

## 2. Referenced Documents

### 2.1 ASTM Standards:

E 691 Practice for Conducting an Interlaboratory Study to Determine the Precision of a Test Method<sup>2</sup>

## 3. Terminology

### 3.1 Definitions of Terms Specific to This Standard:

3.1.1 *film specimen*—one piece of a sample obtained by cutting across the width of the sample and to a length such that one test specimen can subsequently be prepared.

NOTE 2—For any sample in a laboratory,  $n_1$  test specimens are tested to produce a single test result in a short-time period, while replicate test results are obtained over a longer time period. Thus, there are within-laboratory components of variability for both short-term and long-term testing. This practice calls these within-day and between-day components of variability, inasmuch as round-robin protocols often specify that replicate test results be obtained on different days.

3.1.2 *sample*—a quantity of film of a width appropriate to the test method under study and of a length sufficient to yield the total number of film specimens needed for the planned round-robin study.

3.1.3 *test result*—the value (usually, the arithmetic average) of the property derived from one test unit.

3.1.4 *test set*—a group of several film specimens, in a number greater than that specified for a test unit.

3.1.5 *test specimen*—the unit, usually of specified dimensions, that is to be cut from one film specimen and tested, to produce one value of the property, or properties, by the test method under study.

3.1.6 *test unit*—a specified number of film specimens from which an equal number of test specimens is to be prepared and tested in a short-time span to yield one test result for each property.

### 3.2 Symbols:

- RR = round-robin study,  
 $p_1$  = number of laboratories participating in the RR,  
 $q$  = number of samples to be used in the RR,  
 $r$  = number of replicate test results to be obtained on different days by each laboratory for each sample in the RR (Note 1),  
 $n_1$  = specified number of film specimens in a test unit,  
 $n_2$  = number of additional film specimens in each test set,  
 $p_2$  = number of additional “latent” laboratories provided for in the specimen preparation procedure,  
 $L_1$  = film-specimen length appropriate for preparing one test specimen,  
 $L_2$  = length of film from a sample from which can be obtained  $(p_1 + p_2)$  film specimens;  $L_2 = (p_1 + p_2)(L_1)$ ,  
SD = component standard deviation for a single source of variability for one given sample,  
 $S_1$  = SD for within-laboratory within-day variability of a test value,  
 $S_2$  = SD for within-laboratory between-day variability of a test result,  
 $S_3$  = SD for between-laboratory variability of a test result,  
 $S_4$  = SD for within-sample variability,  
 $S_r$  = within-laboratory standard deviation of a single test result for one given sample on any day, and  
 $S_R$  = between-laboratory standard deviation of a single test result for one given sample on any day.

## 4. Significance and Use

4.1 This practice is intended to assist task groups participating in a round-robin study with the preparation of test sets of film specimens from film samples in the form of rolls on a cardboard core.

4.2 This practice assumes that the essential features of the round-robin protocol have already been established by following the guidance of Practice E 691. In particular, it is assumed

<sup>1</sup> This practice is under the jurisdiction of ASTM Committee D20 on Plastics and is the direct responsibility of Subcommittee D20.19 on Film and Sheeting.

Current edition approved March 10, 2000. Published June 2000. Originally published as D 4204 – 82. Last previous edition D 4204 – 95.

<sup>2</sup> *Annual Book of ASTM Standards*, Vols 06.03 and 14.02.

\*A Summary of Changes section appears at the end of this standard.

that the following are known: (1) the number of film samples to be used, (2) the number of participating laboratories, (3) the number of replicate test results to be generated by each laboratory for each sample, and (4) the number of test specimens required to yield one test result for each sample.

4.3 In accordance with this practice, samples are partitioned into test sets so that real within-sample variability will not unduly distort the conclusions drawn from statistical analyses of the data generated in the round-robin study.

## 5. Sample Selection

5.1 Select  $q$  samples that would be expected to be uniform (for which  $S_4$  would be small). The larger the value of  $S_4$ , the greater will be the adverse effect upon conclusions drawn from round-robin data regarding test method precision.

5.1.1 For any sample, the total observed variability will always contain the component  $S_4$ . In the typical study,  $S_4$  is not estimated separately; the result is an overestimation of one or more of the components of variability ( $S_1$ ,  $S_2$ , and  $S_3$ ) that the study is designed to estimate. Because of this,  $S_4$  is a nuisance factor to be dealt with as conveniently as possible.

5.1.2 It is preferable to confound  $S_4$  with within-laboratory components of variability,  $S_1$  and  $S_2$ , and to obtain an estimate of  $S_3$  that is not inflated by within-sample variability,  $S_4$ . This practice is intended to accomplish this. In most cases, in accordance with this practice,  $S_4$  is confounded only with  $S_1$ , so that the estimate of  $S_2$  is also not inflated by within-sample variability,  $S_4$ . The confounding of  $S_4$  with only  $S_1$  is equivalent to a completely random selection of all film specimens from the film sample.

5.1.3 The best source of samples is from commercial or laboratory extrusion operations that have demonstrated the capability to produce film under conditions that have shown that appreciable systematic trends in the level of the property, or properties, to be measured did not occur as the sample was being fabricated.

5.2 Before preparing test sets as described in Section 6, have one laboratory test  $n_1$  test specimen from each sample. If the range of property levels thus found is narrower than is deemed appropriate for the study, it may be desirable to obtain one or more additional samples, to replace one or more of the  $q$  samples collected initially.

## 6. Procedure

6.1 Select a value of  $n_2$  for the RR. In view of the way test sets are made up, as described subsequently, there will always be two “sacrifice” film specimens in a test set, one on top and one on bottom of the stack, that serve to protect the integrity of the film specimens in between. These two are not to be used; always take test specimens from film specimens between the top and bottom film specimens in the test set. In addition, it is usually advisable to include a minimum of one or two extra film specimens in each test set, in the event a laboratory finds

an occasional film specimen with a defect which, properly, should not be used; then, when a defective film specimen is found, it can be discarded and an additional film specimen, already at hand, can be substituted. Thus,  $n_2$  must be at least 2 and, preferably would be 3 or 4. The total number of film specimens in a test set would then be  $(n_1 + n_2)$ , from which one test result would be obtained.

6.2 Select a value of  $p_2$  for the RR. On a practical basis, it is advisable to set  $p_2$  equal to roughly one half of  $p_1$ . Then, if mailed test sets are lost in transit, if after-the-fact recheck testing is needed in one or more laboratories, or if there are late-entering laboratories into the study, additional test sets will be at hand, as needed. For test set preparation, consider the total number of laboratories to be  $(p_1 + p_2)$ .

6.3 Select a value of  $L_1$  appropriate for the test to be conducted.

6.4 Calculate  $L_2$  as follows:

$$L_2 = (p_1 + p_2) (L_1) \quad (1)$$

6.5 For one of the  $q$  samples:

6.5.1 Unwind and cut off successive lengths of film, each of length  $L_2$ . Lay out the first  $r$  lengths, side by side, on a clean flat surface. Place succeeding cut lengths on top of the first  $r$  cut lengths, to form  $r$  stacks of multilayers of film lengths. Build each of the  $r$  stacks first up to 2 layers each, then up to 3 layers each, etc. Continue until each of the  $r$  stacks contains  $(n_1 + n_2)$  layers of film.

6.5.2 From the first of the  $r$  stacks, prepare  $(p_1 + p_2)$  test sets, each containing  $(n_1 + n_2)$  film specimens. Do this by starting at one end of the stack and making successive cuts through all  $(n_1 + n_2)$  layers at incremental distances of  $L_1$  along  $L_2$ . As each test set is obtained, package and label the test set appropriately and mark the package with a sequential number [1, 2, 3, ...,  $(p_1 + p_2)$ ]. Keep the packaged test sets from the first of the  $r$  stacks segregated. Call this a *collection* of  $(p_1 + p_2)$  test sets.

6.5.3 Repeat 6.5.2 for each of the  $r$  stacks, in turn, to form  $r$  segregated collections.

6.5.4 By use of random numbers, select one packaged test set from the first collection. Repeat for each of the  $r$  collections, to form one *group* of  $r$  replicate test sets for testing the first sample in one laboratory.

6.5.5 Continue the selection process of 6.5.4, to end up, finally, with  $(p_1 + p_2)$  groups, each containing  $r$  replicate test sets, for testing the first sample in  $(p_1 + p_2)$  laboratories.

6.6 Repeat 6.5 for each of the  $q$  samples.

6.7 Make an *assembly* by combining one group from each of the  $q$  samples; repeat this process to obtain  $(p_1 + p_2)$  assemblies for testing all  $q$  samples in  $(p_1 + p_2)$  laboratories.

6.8 Distribute  $p_1$  assemblies to the  $p_1$  participating laboratories. Retain the remaining  $p_2$  assemblies in case they are needed subsequently.

## 7. Precision Estimates

7.1 After the round-robin study has been completed, analyses of variance of the data will provide estimates of component standard deviations,  $S_1$ ,  $S_2$ , and  $S_3$ , for each of the  $q$  samples.

7.2 Estimates of within-laboratory and between-laboratory variability for each sample, consistent with the use of symbols in Practice E 691, are arrived at as follows. In the following equations,  $n$  is the standard number of replicate test specimens required for one test result, as dictated by the test method, which is not necessarily the same as the value of  $n_1$  used in the round-robin study.

$$\begin{aligned} S_r &= (S_1^2/n + S_2^2)^{\frac{1}{2}} \\ S_L &= S_3 \\ S_R &= (S_r^2 + S_L^2)^{\frac{1}{2}} \end{aligned} \quad (2)$$

## 8. Keywords

8.1 film; round robin; testing

## SUMMARY OF CHANGES

This section identifies the location of selected changes to this practice. For the convenience of the user, Committee D20 has highlighted those changes that may impact the use of this practice. This section may include descriptions of the changes, or the reasons for the changes, or both.

*D 4204 – 00:*

(1) Editorial changes in 4.1, 5.1.3, 6.1 and 6.2.

(2) Added Keywords section.

*ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.*

*This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.*

*This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).*