



Standard Specification for Plastic Insert Fittings for Polyethylene (PE) Plastic Pipe¹

This standard is issued under the fixed designation D 2609; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

1. Scope

1.1 This specification covers plastic insert fittings for polyethylene (PE) plastic pipe. Included are requirements for materials, workmanship, dimensions, and burst pressure.

1.2 The text of this specification references notes, footnotes, and appendixes which provide explanatory material. These notes and footnotes (excluding those in tables and figures) shall not be considered as requirements of the specification.

1.3 The values stated in inch-pound units are to be regarded as the standard. The values given in parentheses are provided for information only.

1.4 The following safety hazards caveat pertains only to the test methods portion, Section 8, of this specification: *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:

~~D 618 Practice 256 Test Methods for Conditioning Determining the Izod Pendulum Impact Resistance of Plastics and Electrical Insulating Materials for Testing²~~

~~D 789 Test Methods 618 Practice for Determination of Relative Viscosity, Melting Point, and Moisture Content of Polyamide (PA) Conditioning Plastics for Testing²~~

D 1599 Test 638 Test Method for Tensile Properties of Plastics²

D 648 Test Method for Deflection Temperature of Plastics Under Flexural Load in the Edgewise Position²

~~D 789 Test Methods for Determination of Relative Viscosity and Moisture Content of Polyamide (PA)²~~

D 1599 Test Method for Resistance to Short-Time Hydraulic Failure Pressure of Plastic Pipe, Tubing, and Fittings³

D 1600 Terminology for Abbreviated Terms Relating to Plastics²

D 1784 Specification for Rigid Poly(Vinyl Chloride) (PVC) Compounds and Chlorinated Poly(Vinyl Chloride) (CPVC) Compounds²

D 2104 Specification for Polyethylene (PE) Plastic Pipe, Schedule 40³

~~D 2146 Specification for Propylene Plastic Molding and Extrusion Materials⁴~~

~~D 2239 Specification 2239 Specification for Polyethylene (PE) Plastic Pipe (SIDR-PR) Based on Controlled Inside Diameter³~~

F 412 Terminology Relating to Plastic Piping Systems³

F 1498 Specification for Taper Pipe Threads 60° for Thermoplastic Pipe and Fittings³

2.2 NSF Standards:

Standard No. 14 for Plastic Piping Components and Related Materials⁴

¹ This specification is under the jurisdiction of ASTM Committee F17 on Plastic Piping Systems and is the direct responsibility of Subcommittee F17.10 on Fittings. Current edition approved April 10, 2002. Published June 2002. Originally published as D 2609 – 67. Last previous edition D 2609 – 9700.

² Annual Book of ASTM Standards, Vol 08.01.

³ Annual Book of ASTM Standards, Vol 08.04.

~~Discontinued—see 1984 Annual Book of ASTM Standards, Vol 08.02.~~

⁴ Available from the National Sanitation Foundation, P.O. Box 1468, Ann Arbor, MI 48106.

Standard No. 61 for Drinking Water System Components—Health Effects⁴

3. Terminology

3.1 Definitions are in accordance with Terminology F 412 and abbreviations are in accordance with Terminology D 1600, unless otherwise specified.

4. Classification

4.1 This specification covers one class of fittings suitable for use with PE plastic pipe that meet the requirements of applicable ASTM specifications. At present, these are Specifications D 2104 and D 2239.

5. Materials

5.1 *Types of Plastics*—The fittings shall be made from one of the following plastics: (See Note), plastics:

5.1.1 Nylon plastics (NP) meeting the requirements of either Type I or Type II (except Grade 2A) in Test Methods D 789.

5.1.2 Propylene plastics (PP) meeting the requirements with a minimum tensile strength at yield of Type II, Grade 05207, 24.0 MPa (3410 psi) when tested in accordance with Test Method D 638 at a speed of 51 mm/min (2.0 in./min), an Izod impact resistance at 23°C of at least 30 J/m (0.6 ft-lbf/in.) when tested in accordance with Method A of Test Methods D 2456, and a minimum deflection temperature of 64°C at 455 KPa stress when tested in accordance with Test Method D 648.

5.1.3 Poly(vinyl chloride) plastics (PVC) meeting the requirements of 12454-B, 12454-C, 11443-B, or 14333-D, in Specification D 1784.

5.2 *Rework Material*—The manufacturers shall use only their own clean rework fitting material and the fittings produced shall meet all the requirements of this specification. The types of materials specified in 5.1 shall not be mixed with one another.

6. Requirements

6.1 *Dimensions and Tolerances*—The dimensions and tolerances shall be as shown in Tables 1-3 when measured in accordance with 8.4. The negative tolerance on all minimum dimensions is zero.


6.1.1 *Alignment*—The alignment of all openings of fittings shall be within 1/4in./ft.

6.1.2 *Fittings Not Illustrated*—All fittings, whether illustrated in Tables 1-3 or not, shall have insert ends in accordance with Table 1 or threaded ends in accordance with Table 3. For insert ends, which have more than four barbs, the first four barbs, starting from the open end of the fitting connection, shall meet all requirements of Table 1. The remaining barbs shall also meet Table 1, with the exception that mold marks left as a result of the manufacturing process, such as ejector pin marks, are exempt from the “V” dimension requirement, and the minimum requirement for “Z.” D, Zmax, and F apply in all cases. For designs where the entire fitting end is barbed, such as “F” cannot be readily measured, “F” shall be calculated as $[(Z - 2V) - D] / 2$.

6.1.3 *Threads*—For all fittings having taper pipe threads, threads shall conform to Specification F 1498 and be gaged in accordance with 8.6.

6.2 *Burst Pressure*—The minimum burst pressure for the fittings shall be as shown in Table 4, when determined in accordance with 8.5.

TABLE 1 Dimensions of Insert End,^A in. (mm)




Nominal Pipe Size	Insert Length, P min	Barbs				Depth, V min	Wall Thickness, F min	Inside Diameter of Fitting, D min
		Length, Y min	Outside Diameter, Z ^B		Number			
			max	min	min			
1/2	1 1/4 (31.8)	3/4 (19.0)	0.665 (16.9)	0.635 (16.1)	4	0.015 (0.4)	0.080 (2.0)	0.406 (10.3)
3/4	1 1/4 (31.8)	3/4 (19.0)	0.865 (22.0)	0.835 (21.2)	4	0.015 (0.4)	0.085 (2.2)	0.562 (14.3)
1	1 1/4 (31.8)	3/4 (19.0)	1.095 (27.8)	1.065 (27.0)	4	0.020 (0.5)	0.100 (2.5)	0.750 (19.0)
1 1/4	1 1/4 (31.8)	3/4 (19.0)	1.425 (36.2)	1.395 (35.4)	4	0.025 (0.6)	0.110 (2.8)	0.995 (25.3)
1 1/2	1 1/2 (38.1)	3/4 (19.0)	1.665 (42.3)	1.630 (41.4)	4	0.030 (0.8)	0.110 (2.8)	1.125 (28.6)
2	1 1/2 (38.1)	3/4 (19.0)	2.125 (54.0)	2.085 (53.0)	4	0.030 (0.8)	0.110 (2.8)	1.656 (42.1)
2 1/2	2 (50.8)	1 (25.4)	2.520 (64.0)	2.487 (63.2)	4	0.030 (0.8)	0.120 (3.0)	2.062 (52.4)
3	2 1/8 (54.0)	1 1/8 (28.6)	3.125 (79.4)	3.086 (78.4)	4	0.030 (0.8)	0.125 (3.2)	2.600 (66.0)
4	3 (76.2)	1 1/4 (31.8)	4.090 (103.9)	4.044 (102.7)	4	0.030 (0.8)	0.130 (3.3)	3.525 (89.5)

^A The sketches and designs of fittings shown are illustrative only. The dimensions specified shall govern in all cases.

^B Outside diameter maximum and minimum apply to each individual measurement, not the average of the four (see 8.4).

TABLE 2 Dimensions^A of Insert Elbow and Tee, in. (mm)




Nominal Pipe Size ^B	Laying Length Tee and Elbow, min G
1/2	0.344 (8.7)
3/4	0.453 (11.5)
1	0.625 (15.9)
1 1/4	0.781 (19.8)
1 1/2	0.875 (22.2)
2	1.125 (28.6)
2 1/2	1.625 (41.3)
3	1.875 (47.6)
4	2.438 (61.9)

^A The sketches and designs of fittings shown are illustrative only.

^B For dimensions not given in this table, see Table 1.

TABLE 3 Dimensions^A of Insert Adapters with Pipe Thread End, in. (mm)



Nominal Pipe Size, ^B Insert End and Pipe Thread ^C	Length of Thread, min	
	Male, S	Female, T
1/2	0.53 (13.5)	0.64 (16.2)
3/4	0.55 (14.0)	0.65 (16.5)
1	0.68 (17.3)	0.81 (20.6)
1 1/4	0.71 (18.0)	0.85 (21.6)
1 1/2	0.72 (18.3)	0.85 (21.6)
2	0.76 (19.3)	0.90 (22.9)
2 1/2	1.14 (28.9)	1.21 (30.7)
3	1.20 (30.5)	1.30 (33.0)
4	1.30 (33.0)	1.38 (35.0)

^A The sketches and designs of fittings shown are illustrative only.

^B For dimensions of insert ends, see Table 1.

^C For threads on threaded end, see 6.1.3.

7. Workmanship, Finish, and Appearance

7.1 The fittings shall be homogeneous throughout and free of cracks, holes, foreign inclusions, or other defects. The fittings shall be as uniform as commercially practicable in color, opacity, density, and other physical properties.

8. Test Methods

8.1 *Conditioning*—Condition the specimens at $73.4 \pm 3.6^\circ\text{F}$ ($23 \pm 2^\circ\text{C}$) and $50 \pm 5\%$ relative humidity for not less than 40 h prior to test in accordance with Procedure A of Practice D 618, for those tests where conditioning is required. In all cases of disagreement, the tolerances shall be $\pm 1.8^\circ\text{F}$ ($\pm 1^\circ\text{C}$) and $\pm 2\%$ relative humidity.

8.2 *Test Conditions*—Conduct the tests in the standard laboratory atmosphere of $73.4 \pm 3.6^\circ\text{F}$ ($23 \pm 2^\circ\text{C}$) and $50 \pm 5\%$ relative humidity, unless otherwise specified in the test methods or in this specification. In cases of disagreement, the tolerances shall be $\pm 1.8^\circ\text{F}$ (1°C) and $\pm 2\%$ relative humidity.

TABLE 4 Burst Pressure Requirements for Water at 73.4°F (23°C) for Plastic Insert Fittings for PE Plastic Pipe

Nominal Pipe Size, in.	Minimum Burst Strength, psi (MPa)
	NP, PP, and PVC Materials 750 (5.7)
1/2	
3/4	630 (4.34)
1	630 (4.34)
1 1/4	630 (4.34)
1 1/2	500 (3.45)
2	500 (3.45)
2 1/2	400 (2.76)
3	400 (2.76)
4	400 (2.76)
6	250 (1.72)

8.3 *Sampling*—A sample of the fittings sufficient to determine conformance with this specification shall be taken at random.

8.4 *Dimensions*—Fittings used to determine dimensions shall be randomly selected. Measurements shall be made with micrometers, calipers, gages, or other devices accurate to within ± 0.001 in. (± 0.025 mm). Determine the diameters by making measurements at four points spaced at approximately 45° apart around the circumference.

8.5 *Burst Pressure*—Determine the minimum burst pressure with at least three specimens in accordance with Test Method D 1599. Join the fittings as insert fittings to the pipe sufficiently strong and in such a manner that no failure shall occur in the fitting at least than the pressures given in Table 4. The time of testing each assembly shall be between 60 and 70 s.

8.6 *Threads*—All taper pipe threads shall be gaged in accordance with Specification F 1498.

9. Retest and Rejection

9.1 If the results of any test(s) do not meet the requirements of this specification, the tests(s) shall be conducted again only by agreement between the purchaser and seller. Under such agreement, minimum requirements shall not be lowered, changed, or modified, nor shall specification limits be changed. If upon retest, failure occurs, the quantity of product represented by the test(s) does not meet the requirements of this specification.

10. Marking

10.1 Fittings shall be marked with the following:

10.1.1 Manufacturers' name or trademark,

10.1.2 Material designation: NP, PP, or PVC,

10.1.3 Fittings intended for the transport of potable water shall include the seal or mark of the laboratory making the evaluation for this purpose, and

10.1.4 Size.

10.2 Markings or symbols shall be molded, hot-stamped, or applied by printing methods.

10.3 Where recessed marking is used, care shall be taken to see that in no case shall the marking cause cracks or reduce the wall thicknesses below the minimum specified.

11. Quality Assurance

11.1 When the product is marked with this designation, D 2609, the manufacturer affirms that the product was manufactured, inspected, sampled, and tested in accordance with this specification and has been found to meet the requirements of this specification.

12. Keywords

12.1 barb; fittings; insert; plastic; polyethylene



SUPPLEMENTARY REQUIREMENTS

POTABLE WATER REQUIREMENT

This requirement applies whenever a Regulatory Authority or user calls for the product to be used to convey or to be in contact with potable water.

S1. Products intended for contact with potable water shall be evaluated, tested, and certified for conformance with ANSI/NSF Standard No. 61 or the health effects portion of NSF Standard No. 14 by an acceptable certifying organization when required by the regulatory authority having jurisdiction.

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).