



Designation: D 5685 – 012

An American National Standard

Standard Specification for “Fiberglass” (Glass-Fiber-Reinforced Thermosetting-Resin) Pressure Pipe Fittings¹

This standard is issued under the fixed designation D 5685; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

1. Scope*

1.1 This specification covers “fiberglass” (glass-fiber-reinforced thermosetting-resin) fittings for use with filament wound or centrifugally cast fiberglass pipe, or both, in sizes 1 in. through ~~16~~ 24 in. for pipe manufactured to Specification D 2996 or D 2997, or both.

1.2 The following safety hazard caveat pertains only to the test method portion, Section ~~8~~, 7, of this specification:

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

NOTE 1—The term “fiberglass pipe” as described in Section 3 of this specification applies to both reinforced thermosetting resin pipe (RTRP) and reinforced polymer mortar pipe (RPMP).

NOTE 2—For the purposes of this standard, ploymer does not include natural polymers.

NOTE 3—There is no similar or equivalent ISO standard.

2. Referenced Documents

2.1 *ASTM Standards:*

¹ This specification is under the jurisdiction of ASTM Committee D20 on Plastics and is the direct responsibility of Subcommittee D20.23 on Reinforced Plastic Piping System and Chemical Equipment.

Current edition approved ~~June~~ March 10, 2001. ~~Published August~~ 2001, 2002. ~~Published~~ May 2002. Originally published as D5685–95. Last previous edition D5685–9501.

*A Summary of Changes section appears at the end of this standard.

- D 618 Practice for Conditioning Plastics and Electrical Insulating Materials for Testing²
- D 883 Terminology Relating to Plastics²
- D 1598 Test Method for Time-To-Failure of Plastic Pipe Under Constant Internal Pressure³
- D 1599 Test Method for Resistance to Short-Time Hydraulic Failure Pressure of Plastic Pipe, Tubing, and Fittings³
- D 1600 Terminology for Abbreviated Terms Relating to Plastics²
- ~~D 1898 Practice for Sampling of Plastics⁴~~
- ~~D 2143 Test~~ 2143 Test Method for Cyclic Pressure Strength of Reinforced, Thermosetting Plastic Pipe³
- D 2992 Practice for Obtaining Hydrostatic or Pressure Design Basis for “Fiberglass” (Glass-Fiber-Reinforced Thermosetting-Resin) Pipe and Fittings³
- D 2996 Specification for Filament Wound “Fiberglass” (Glass-Fiber-Reinforced-Thermosetting Resin) Pipe³
- D 2997 Specification for Centrifugally Cast “Fiberglass” (Glass-Fiber-Reinforced-Thermosetting Resin) Pipe³
- D 3567 Practice for Determining Dimensions of “Fiberglass” (Glass-Fiber-Reinforced Thermosetting Resin) Pipe and Fittings³
- D 4024 Specification for Machine Made “Fiberglass” (Glass-Fiber-Reinforced Thermosetting Resin) Flanges³
- F 412 Terminology Relating to Plastic Piping Systems³
- F 477 Specification for Elastomeric Seals (Gaskets) for Joining Plastic Pipe³
- 2.2 *ANSI Standard:*
- B16.5 Steel Pipe Flanges, Flanged Valves and Fittings⁴

² *Annual Book of ASTM Standards*, Vol 08.01.

³ *Annual Book of ASTM Standards*, Vol 08.04.

⁴ ~~Discontinued. See 1998 Annual Book of ASTM~~

⁴ Available from American National Standards Institute, 25 W. 43rd St., 4th Floor, New York, NY 10036 .

2.3 *API Standard:*
15LR Low Pressure Fiberglass Line Pipe⁵

3. Terminology

3.1 Definitions:

3.1.1 *General*—Definitions are in accordance with Terminology D 883 or F 412. Abbreviations are in accordance with Terminology D 1600, unless otherwise indicated. The abbreviation for fiberglass pipe is RTRP and the abbreviation for fiberglass fittings is RTRF.

3.1.2 *“fiberglass” pipe*—tubular product containing glass fiber reinforcements embedded in or surrounded by cured thermosetting resin. The composite structure may contain aggregate, granular or platelet fillers, thixotropic agents, pigments, or dyes. Thermoplastic or thermosetting liners or coatings may be included.

3.1.3 *reinforced thermosetting resin pipe*—fiberglass pipe without aggregate (RTRP).

3.1.4 *reinforced polymer mortar pipe*—fiberglass pipe with aggregate (RPMP).

3.1.5 *reinforced thermosetting resin fitting*—fiberglass fitting without aggregate (RTRF).

3.1.6 *reinforced polymer mortar fitting*—fiberglass fitting with aggregate (RPMF).

4. Classification

4.1 This specification covers fiberglass fittings defined by type (method of manufacture), grade (general type of resin), resin type, class (general liner type), category (configuration of joining system), and pressure rating (a single letter designating the pressure class and method of manufacture).

4.2 Types:

4.2.1 *Type 1*—Filament-wound fittings manufactured by winding continuous fibrous-glass strand roving or roving tape, either preimpregnated or impregnated during winding, onto a mandrel, or a liner corresponding to the fitting shape.

4.2.2 *Type 2*—Compression molded fittings made by applying external pressure and heat to a molding compound that is confined within a closed mold.

4.2.3 *Type 3*—Resin transfer molded fittings manufactured by pumping a thermosetting resin into glass reinforcements that have been cut to size and clamped between matched molds.

4.2.4 *Type 4*—Centrifugally cast fittings made by applying resin and reinforcement to the inside of a mold that is rotating and heated, subsequently polymerizing the resin system.

4.2.5 *Type 5*—Contact molded fittings made by applying resin and reinforcement to a mold or to mitered filamentwound stock or centrifugally cast pipe stock. This procedure shall also cover “spray-up” fittings which are made by spraying resin and reinforcement on a mold or over mitered pipe wound stock. “Contact molding” includes both hand lay-up and spray-up manufacturing processes.

4.2.6 Type 6—Fittings

4.2.6 Fittings of Type 1 through Type 5 that which require thrust blocking or external axial restraint when installed shall have the letter “R” appended to the type of designation. (For instance, a contact molded fitting requiring thrust blocking when installed would be designated a type “5R”.)

4.3 Grades:

4.3.1 *Grade 1*—Epoxy-resin.

4.3.2 *Grade 2*—Polyester-resin (see Note 4).

4.3.3 *Grade 3*—Furan-resin.

NOTE 4—For purpose of this specification, polyester-resins include vinyl-ester-resins.

4.4 Classes:

4.4.1 *Class A*—No liner.

4.4.2 *Class B*—Polyester-resin liner (nonreinforced).

4.4.3 *Class C*—Epoxy-resin liner (nonreinforced).

4.4.4 *Class E*—Polyester-resin liner (reinforced).

4.4.5 *Class F*—Epoxy-resin liner (reinforced).

4.4.6 *Class H*—Thermoplastic-resin liner (specify).

4.4.7 *Class I*—Furan-resin liner (reinforced).

4.5 Joint Categories (Method of Joining):

4.5.1 *Category 1*—Taper-to-taper adhesive-bonded joint fittings manufactured with a tapered socket to be used in conjunction with a pipe or fitting with a matching spigot section and a suitable adhesive. This joining method provides an interference fit over the entire length of the bond line.

4.5.2 *Category 2*—Straight-taper adhesive-bonded joint fitting manufactured with a tapered socket to be used with a pipe or fitting with an untapered spigot section and a suitable adhesive. This joining method provides an interference fit at the bottom of the socket.

⁵ Available from American National Standards Petroleum Institute, 11 West 42nd 1220 L St., 13th Floor, New York, NY 10036, NW, Washington, DC 20005.

4.5.3 *Category 3*—Straight adhesive bonded joint fitting manufactured with an untapered socket for use with a pipe or fitting with an untapered spigot and a suitable adhesive. This joining provides no interference fit.

4.5.4 *Category 4*—Butt and strap joint made by a contact molding process which involves hand lay-up with glass-woven roving or chopped strand mat, or both, which is saturated with resin.

4.5.5 *Category 5*—Flanged fittings are available as all outlets flanged or as flange-by-joint specified in this specification. Flanges are in compliance with Specification D 4024.

4.5.6 *Category 6*—Elastomeric (gasket) sealed joints with sealant manufactured in compliance with Specification F 477 for joints which have integral longitudinal restraint and do not require thrust blocking or external longitudinal restraint.

4.5.7 *Category 7*—Elastomeric (gasket) sealed joints with seals manufactured in compliance with Specification F 477 for joints which require thrust blocking or external longitudinal restraint.

4.6 *Pressure Rating*—Pressure rating shall be categorized by a single letter designation. Pressure designations are shown in Table 1. The pressure ratings are applicable for the temperature at which the fittings were tested and for lower temperatures down to -50°F (-46°C). When agreed upon between purchaser and manufacturer, pressure ratings determined by tests conducted following Practice D 2992 are acceptable.

4.7 *Designation Code*—The fitting designation code shall consist of the abbreviation RTRF or RPFM followed by the type, grade, and class in Arabic numerals and the pressure rating category as a capital letter.

NOTE 5—An example is RTRF 21A2E. This designation describes a (Type 2) compression molded fitting with a (Grade 1) epoxy-resin without a liner (Class A), which is joined with a (Category 2) taper-to-taper adhesive joining system and has a 200 psig (1380 kPa) pressure rating.

NOTE 6—Fittings with identical classification from different manufacturers may not be interchangeable due to non-standardization of pipe or socket diameter, socket length, taper angle, or combination thereof.

5. Materials

5.1 Fittings manufactured in accordance with this specification shall be composed of reinforcement embedded in or surrounded by cured thermosetting-resin. The composite structure may contain granular or platelet fillers, thixotropic agents, pigments, or dyes.

5.2 The resins, fiberglass reinforcements, and other materials, when combined into a composite structure, shall produce a fitting that will meet the performance requirements of this specification.

6. Requirements

6.1 *Workmanship*—The fittings shall be free of all defects including indentations, delaminations, bubbles, pin holes, foreign inclusions, and resin starved areas, which, due to their nature, degree, or extent, detrimentally affect the strength and serviceability of the fitting. The fitting shall be as uniform as commercially practicable in color, opacity, and other physical properties.

6.2 *Dimensions and Tolerances*—All flanged fittings shall conform to the center line to flange face dimensions, hole size and hole pattern, and tolerances of ANSI B16.5 short or long radius type, or otherwise as agreed upon between the manufacturer and purchaser. Fitting center line to end dimensions, taper angles, taper length, or combinations thereof, will vary for non-flanged joining systems and the individual manufacturers shall be consulted for dimensions. Dimensions shall be measured in accordance with 7.3.

NOTE 7—Fittings with short radii which are not in compliance with ANSI B16.5 radius tolerances may be available.

6.3 *Fittings and Connections Pressure Test Requirements*—Fittings, couplings, and connections shall meet the following qualification requirements when tested with restrained ends for Type 6 fittings, and unrestrained ends for other type fittings, in accordance with 7.4.1 for short term hydrostatic strength tests, and 7.4.2 for cyclic or static tests.

6.3.1 Each type of component and its field-jointed configuration shall be capable of sustaining a short-time hydrostatic pressure, of at least four times its cyclic-rated pressure or three times its static-rated pressure for 1 min without visible weeping or leakage.

6.3.2 Each component shall meet or exceed the cyclic or static-test requirements of 7.4.2.

TABLE 1 Pressure Categories

Designation	Pressure Rating ^A , psig (kPa)
A	25 (172)
B	50 (345)
C	100 (690)
D	150 (1034)
E	200 (1380)
F	250 (1724)
G	300 (2068)
H	400 (2759)
I	500 (3448)
J	1000 (6896)

^A Pressure ratings are applicable only for the temperature at which the fittings were tested and for lower temperatures.

6.4 *Degree of Cure*—The limits and methods of determining degree of cure shall be in accordance with 6.4.1 or 6.4.2, as agreed upon between purchaser and manufacturer.

6.4.1 *Percent Extractable Material*—Fittings shall have no more than 3 % extractable material when tested in accordance with 7.5.

6.4.2 *Glass Transition Temperature (T_g)*—The T_g for each resin used, as determined by some thermal analysis method, shall be no less than a minimum statistically significant value established by the manufacturer. Samples shall be taken from manufactured fittings when thermal analysis testing is accomplished by differential-scanning-calorimeter (DSC). Test in accordance with 7.6.

6.5 Factory leak tests shall be conducted at a pressure of 1.5 times pressure rating and at a frequency—s determined by an agreement between the purchaser and the seller.

6.6 For individual orders, only those addition—Sal test and number of tests specifically agreed upon—8 between the purchaser and the seller need be conducted.

7. Test Methods

7.1 *Conditioning*—When conditioning is required, and in all cases of disagreement, condition the test specimens at 73.4 ± 3.6°F (23 ± 2°C) and 50 ± 5 % relative humidity for not less than 40 h prior to test, in accordance with Procedure A of Practice D 618.

7.2 *Test Conditions*—The tests may be conducted at ambient temperature and humidity conditions. When controlled environment testing is specified, tests shall be conducted in the Standard Laboratory Atmosphere of 73.4 ± 3.6°F (23 ± 2°C) and 50 ± 5 % relative humidity. When elevated temperature testing is specified, conduct the tests at the design temperature ± 5.4°F (3°C).

7.3 *Dimensions and Tolerances*—Measure fitting dimensions in accordance with applicable documents and Practice D 3567. Measure flange dimensions with a micrometer or vernier calipers, or other suitable measuring devices accurate to within ±0.001 in. (0.02 mm). Diameters shall be determined by averaging a minimum of four measurements, equally spaced circumferentially.

7.4 Pressure Tests:

7.4.1 *Short-Term Hydrostatic Strength Test*—Short-term hydrostatic failure pressure tests to determine compliance with 6.3 performed at ambient temperature in accordance with Test Method D 1599 using specimens and sizes as described in 7.4.3. Leaking past the gasket interface of flanged fittings and elastomeric sealed fittings is permissible during this test, provided the pressure is at least two times the rating when the leak occurs. The bolt torquing sequence of Specification D 4024, Fig. 2 shall be used when testing flanged fittings. Fittings without flanges shall be tested with the pipe they are to be used with joined to the fitting. Bending or shape restraint during the test is permitted to the extent applicable to its anticipated installed conditions. This information shall be contained in the test report.

7.4.2 Cyclic or Static Pressure Test:

7.4.2.1 Using the cyclic test data or static test data and regression analysis as developed for the pipe, following Practice D 2992, Procedure A or B, construct a regression line converting the stress (or strain) versus cycle data or stress (or strain) versus time data to pressure versus cycle or time data for pipe of the intended pressure class.

7.4.2.2 For cyclic pressure tests, the gage pressure at the peak pressure of the cycle shall be not less than 1½ nor more than 2 times the pressure rating of the fitting. The cycle amplitude pressure shall be at least 80 % of the selected peak pressure.

7.4.2.3 For static pressure tests, the gage pressure shall be no less than 2½ times and no more than 2¾ times the fitting static pressure rating.

7.4.2.4 Test each component specimen as required above with unrestrained ends or restrained ends as applicable for the particular type of fitting in accordance with Test Methods D 2143 for cyclic tests and D 1598 for static tests at the components temperature rating.

7.4.2.5 The number of cycles or hours to failure for the component must be no less than that predicted by the HDB line lower 95Q~ prediction limits of the corresponding pipe.

7.4.3 *Test Specimens and Sample Size Requirements for Pressure Tests*—Test specimens shall include at least one fitting in each configuration, for example, 45° and 90° elbow, tee, flange, coupling (includes integral coupling) etc., joined to pipe sections at least 18 in. (0.5 m) long or 2 diameters, whichever is longer, using the joining method, design, and adhesive intended for field assembly. Specimen diameters for test in each configuration shall include the maximum product size in each pressure class and for each method of manufacture. In addition, smaller sizes in the pressure rating shall be tested as follows:

Product Size Range Nominal, in. ⁴	Test Size, Nominal, in.
1, 1½, 2, 2½, 3	3
4, 6	6
8, 10, 12	12
14, 16	16

⁴ In each range of size, the manufacturer may elect to test a smaller product size to qualify only the smaller size.

7.4.4 *Requalification Tests for Fittings, Couplings, Connections, and Adhesives*—The qualification tests in 6.3 shall be repeated after any change in manufacturing process, construction, or type of materials.

NOTE 8—Fiberglass fittings short-term hydrostatic strength at ambient temperature is not necessarily greater than its short-term hydrostatic strength at all higher temperatures.

7.5 *Percent Extractable Material*—Determine by using the procedure in Annex A1 of Specification D 4024.

7.6 *Glass Transition Temperature*—Determine by using the procedure in Annex A1.

8. Sampling

~~8.1 The rate of sampling of fittings for factory leak testing shall be in accordance with Annex A2.~~

~~8.2 For individual orders, only those additional tests and number of tests specifically agreed upon between the purchaser and seller need be conducted.~~

9. Marking

98.1 Mark each fitting with the following information:

98.1.1 The designation “ASTM D 5685” with which the fitting complies,

98.1.2 Identification of the fitting in accordance with the designation code in 4.2,

98.1.3 Nominal fitting size,

98.1.4 Manufacturer’s name (or trademark) and product designation, and

98.1.5 Pressure rating (cyclic or static), psig.

98.2 All required markings shall be legible and applied so as to remain legible under normal handling and installation practices.

~~10.~~

9. Keywords

~~10.1~~ centrifugally cast; compression molded; contact molded; degree of cure; epoxy-resin; filament-wound; furan-resin; glass transition temperature; percent extractable material; polyester-resin; pressure-rating; transfer molded

ANNEXES

(Mandatory Information)

A1. METHOD OF TEST FOR THE DETERMINATION OF DEGREE OF CURE BY DIFFERENTIAL SCANNING CALORIMETRY (DSC)

A1.1 Scope

A1.1.1 This test determines whether the degree of cure of a fiberglass fitting test specimen meets the quality control requirements determined by statistical analysis of typical production products.

A1.2. Terminology

A1.2.1 *Definition:*

A1.2.1.1 *glass transition temperature*—the midpoint of the inflection temperature at the DSC curve (heat flow versus temperature).

A1.3 Apparatus

A1.3.1 *Differential Scanning Calorimeter (DSC).*

A1.4 Test Specimens

A1.4.1 *Size*—The size of the specimen is limited by the size of the DSC sample pan. All specimens can be a chip or filed into a fine powder to provide easy weighing and uniform contact with the pan.

A1.4.2 *Location*—For any given fitting, a sample should be taken 0 to 10 mils (0 to 0.025 m) from the outer surface, as well as 0 to 10 mils from the inner surface. If the fitting has a liner, a specimen should be taken from the liner, as well as the inner and outer edges of the overwrap.

A1.5 Procedure

A1.5.1 The maximum heating rate is ~~72°F~~ 41°F (23°C)/min. The T_g is dependent upon heating rate, therefore a consistent heating rate must be used for all testing.

A1.5.2 Run the scan from room temperature to at least ~~54°F~~ 22°F (12°C) above the expected glass transition temperature and no more than 482°F (250°C).

A1.5.3 Obtain the T_{g1} (midpoint of the inflection in the DSC curve).

A1.5.4 If the T_g is not within 9°F (~~-13°C~~) (16°C) of statistically significant value, cool down the DSC and run another sample

again from room temperature to 54°F (12°C) (30°C) above T_{g1} to obtain T_{g2} .

A1.5.5 The values T_{g1} and T_{g2} obtained with the test sample should be compared to those statistically significant values obtained from typical production product. The measured and typical values should be within 9°F (–136°C).

A1.6 Report

A1.6.1 Report the following information:

A1.6.1.1 Complete identification of the specimens, including material, manufacturer's name, and lot number.

A1.6.1.2 Fitting dimensions, including nominal size, minimum reinforced wall thickness, and average outside diameter of reinforced wall. Unreinforced thickness (that is, liner) shall also be reported.

A1.6.1.3 Number of specimens tested and where the specimens were taken from the fitting.

A1.6.1.4 Heat-up rate for DSC initial temperature and final temperature for both scans.

A1.6.1.5 Record glass transition temperature (inflection value) for the first scan as T_{g1} .

A1.6.1.6 Record glass transition temperature (inflection value) for the second scan as T_{g2} , if applicable.

A1.6.1.7 Date of test.

A2. METHOD

SUMMARY OF SAMPLING FOR PRESSURE-RATING VERIFICATION

A2.1 Scope

~~A2.1.1 This method describes the sampling procedure, which shall be used in determining the acceptance of a given lot of fittings at the pressure rating specified in 4.6 and Table 1.~~

A2.2 Sample

~~A2.2.1 Sample size and selection shall be in accordance with Practice D 1898, except as modified herein.~~

A2.3 Procedure

~~A2.3.1 Sample size shall be determined in accordance with Practice D 1898. The acceptable quality level (AQL) shall be 1.50. Inspection Level 1 shall be used in determining the sample size and acceptance constant.~~

~~A2.3.2 The specification limit value (L) shall be in accordance with 6.3.1 for burst test qualification and shall be the pressure rating times 1.5 for factory leak test.~~

A2.4 Results

~~A2.4.1 *Acceptance*—If the quality level of the sample is greater than or equal to the acceptance constant for both burst and leak testing, the lot shall be accepted at the specified pressure rating category.~~

~~A2.4.2 *Rejection*—If the quality level is less than the acceptance constant for either burst or leak testing, the lot shall be rejected unless rectification is provided as follows:~~

~~A2.4.2.1 The lot shall be resampled at a higher inspection level. The original test results shall be considered a part of the resampled lot. If the lot meets the requirements of A2.4.1 after resampling, the lot shall be accepted at the pressure category specified.~~

~~A2.4.2.2 Alternatively, the lot may be derated to a pressure rating that will bring the quality level of the sample to a value equal to or greater than the acceptance constant. The lot of fittings shall be reclassified at the lower pressure rating category and appropriately marked in accordance with the designation code in 4.7.~~

SUMMARY OF CHANGES

Committee D20 has identified the location of selected changes to this standard since the last issue, D 5685-9501, that may impact the use of this standard.

- (1) Changes acronym, RPMP, definition from reinforced plastic Modified scope section 1.1 to call out current sizes.
- (2) mortar pipe Corrected 4.1 to reinforced polymer reflect 4.2-4.6. requirements.
- (3) 4.2.6 modified to include nomenclature for fittings that require external axial restraint.
- (4) Deleted the Sampling Section, (formerly Section 8).
- (5) Deleted Annex A2 due to discontinuance of D 1898. Method of sampling to be determined by an agreement between purchaser and seller.

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).